Corrections

The paper

Preferred orientation of the internal structure of carbon layers in carbon fibers

by R. Plaetschke and W. Ruland

which appeared in Progr Coll & Polym Sci 71:140–144 (1985)

has been printed with mistakes in Table 2, which we should like to correct as follows:

Table 2. *a*-axis and *c*-axis orientation parameters and type of orientation

Sample	q_a	$ q_c $	Type of orientation
M1	0	0.49	—
M2	0.30	0.90	○
M3	0.33	0.92	○
M4	0.41	0.93	○
P1	−0.30	0.82	○
P2	−0.27	0.83	○
P3	−0.19	0.87	○
P4	0	0.62	—
P5	−0.27	0.82	○
C1	0	0.85	—
C2	0	0.86	—
C3	0.30	0.89	○
C4	0.31	0.91	○