Erratum

P. E. D. MORGAN and M. S. KOUTSOUTIS, *J. Mater. Sci. Lett.* **4** (1985) 321.

On p. 322, Fig. 1 should be:

The Table I, cited on p. 321, was omitted and is reproduced here in condensed form. (A full version of the table is available on request from the authors.)

TABLE I Principal features of the indexed powder patterns for LTA, STA and CTA, including unit cell data

LaTi ₂ Al ₉ O ₁₉					SrTi ₃ Al ₈ O ₁₉					CaTi ₃ Al ₈ O ₁₉				
<i>a</i> = 2.2609	<i>b</i> = 1.1054	<i>c</i> = 0.9756	<i>β</i> = 98.78		<i>a</i> = 2.2553	<i>b</i> = 1.0991	<i>c</i> = 0.9722	<i>β</i> = 98.63		<i>a</i> = 2.2651	<i>b</i> = 1.1046	<i>c</i> = 0.9759	<i>β</i> = 98.72	
<i>d</i> _{obs} (nm)	<i>d</i> _{calc} (nm)	<i>h k l</i>	<i>I</i> / <i>I</i> ₀		<i>d</i> _{obs} (nm)	<i>d</i> _{calc} (nm)	<i>h k l</i>	<i>I</i> / <i>I</i> ₀		<i>d</i> _{obs} (nm)	<i>d</i> _{calc} (nm)	<i>h k l</i>	<i>I</i> / <i>I</i> ₀	
1.123 91	1.116 06	200	297		1.123 13	1.121 95	200	21		1.126 42	1.117 93	200	8	
0.988 79	0.986 55	110	331		0.986 26	0.992 36	110	42		0.996 35	0.990 69	110	3	
0.715 17	0.712 62	111	45							0.718 88	0.715 70	111	12	
0.668 94	0.666 82	111	6		0.667 69	0.670 17	111	4		0.669 42	0.668 58	111	10	
0.618 34	0.616 26	310	29		0.620 00	0.619 66	310	1		0.619 59	0.617 90	310	1	
0.552 01	0.550 90	311	24		0.553 14	0.553 95	311	3		0.554 72	0.553 20	311	78	
0.493 47	0.493 27	220	25		0.493 73	0.494 25	311	2						
0.481 45	0.480 77	002	42							0.483 30	0.482 06	002	1	
0.478 71	0.477 35	021	50		0.480 30	0.480 05	021	4						
0.451 96	0.451 22	221	349		0.452 69	0.453 82	221	75		0.454 06	0.453 31	221	24	
					0.428 69	0.429 85	221	7		0.429 78	0.428 89	221	31	
0.421 42	0.421 31	112	107		0.422 03	0.421 12	202	15						
0.414 15	0.413 65	510	5		0.414 64	0.415 87	510	6		0.415 26	0.414 52	510	14	
0.400 34	0.400 75	511	73		0.402 12	0.402 97	511	11						
0.394 70	0.394 71	402	46		0.395 78	0.396 76	402	12		0.396 33	0.396 40	402	8	
					0.378 06	0.379 04	421	36		0.379 06	0.378 45	421	245	
0.372 62	0.372 02	600	18		0.372 86	0.373 98	600	3						
0.362 36	0.363 30	022	205		0.363 45	0.363 81	022	31		0.363 61	0.363 25	022	10	
	0.361 75	130				0.363 93	130				0.363 46	130		
	0.362 50	511				0.363 95	511				0.362 55	511		
					0.359 25	0.359 75	312	4		0.358 55	0.358 58	312	58	
0.350 20	0.350 08	421	65		0.351 24	0.351 94	421	10		0.343 24	0.342 94	131	27	
										0.340 06	0.340 14	402	31	
0.337 20	0.335 90	131	48		0.337 16	0.337 84	131	22		0.337 55	0.337 33	131	33	
0.329 06	0.328 85	330	36		0.330 67	0.330 79	330	13		0.329 69	0.330 23	330	17	
0.318 11	0.317 68	331	159		0.319 58	0.319 54	331	46		0.319 51	0.319 14	331	16	
	0.318 25	602				0.319 96	602				0.319 52	602		
0.311 48	0.310 95	113	262		0.311 72	0.312 41	113	156		0.312 16	0.311 99	113	169	
0.305 24	0.305 02	331	174		0.306 34	0.306 74	331	80		0.306 30	0.306 09	331	65	
	0.306 26	710								0.306 85	0.306 85	710		
0.300 19	0.300 03	313	135		0.300 94	0.301 52	313	55		0.301 33	0.301 25	313	29	
0.293 95	0.293 99	512	17		0.295 15	0.295 38	512	6		0.293 69	0.294 28	512	4	
0.292 52	0.292 50	132	14		0.293 91	0.294 12	132	5		0.290 98	0.293 76	132	4	
0.283 68	0.283 31	530	1000		0.284 61	0.284 94	530	1000		0.284 42	0.284 32	530	1000	
	0.283 37	621				0.284 86	621				0.283 90	621		
0.280 40	0.280 36	711	189		0.280 92	0.281 78	711	111		0.280 84	0.280 68	711	177	
0.277 43	0.277 30	223	541		0.278 24	0.278 70	223	251		0.278 36	0.278 39	223	239	
0.274 73	0.274 92	602	338		0.276 08	0.276 21	602	142						
0.272 55	0.272 36	513	140		0.273 37	0.273 77	513	85		0.273 52	0.273 54	513	126	
										0.270 77	0.271 33	313	111	
0.267 00	0.266 97	240	111		0.268 06	0.268 57	240	41						

TABLE I Continued

LaTi ₂ Al ₉ O ₁₉				SrTi ₃ Al ₈ O ₁₉				CaTi ₃ Al ₈ O ₁₉			
$a = 2.2609$	$b = 1.1054$	$c = 0.9756$	$\beta = 98.78$	$a = 2.2553$	$b = 1.0991$	$c = 0.9722$	$\beta = 98.63$	$a = 2.2651$	$b = 1.1046$	$c = 0.9759$	$\beta = 98.72$
d_{obs} (nm)	d_{calc} (nm)	hkl	I/I_0	d_{obs} (nm)	d_{calc} (nm)	hkl	I/I_0	d_{obs} (nm)	d_{calc} (nm)	hkl	I/I_0
0.26546	0.26501	531	116	0.26608	0.26646	531	70	0.26588	0.26576	531	57
0.26350	0.26341	332	121	0.26459	0.26480	332	88	0.26450	0.26419	332	71
				0.26299	0.26266	403	28	0.26165	0.26178	403	9
0.25879	0.25877	802	30	0.26015	0.26018	802	12	0.26066	0.26089	241	5
0.25506	0.25489	241	23	0.25595	0.25637	241	9	0.25940	0.25971	802	2
0.24913	0.24911	821	70	0.25019	0.25049	821	65	0.25532	0.25597	241	42
0.24673	0.24664	440	25	0.24778	0.24809	440	22	0.25003	0.24989	821	82
0.24314	0.24321	911	149	0.24386	0.24374	204	96	0.24778	0.24767	440	19
0.24036	0.24039	004	42	0.24139	0.24146	004	38	0.24384	0.24386	911	122
0.23889	0.23868	042	44					0.24114	0.24103	004	71
0.23728	0.23720	114	272	0.23795	0.23830	114	214	0.23846	0.23795	114	273
	0.23704	242			0.23840	242			0.23813	242	
0.23385	0.23390	404	27	0.23490	0.23503	404	4	0.23686	0.23657	423	145
0.22996	0.23007	114	73	0.23098	0.23110	114	26	0.23058	0.23062	114	25
0.22704	0.22690	911	23	0.22792	0.22805	911	22	0.22720	0.22716	911	32
0.22555	0.22561	442	18								
0.22321	0.22321	1000	83	0.22413	0.22439	1000	25	0.22323	0.22359	1000	23
0.22182	0.22197	224	35								
0.21857	0.21890	150	15					0.21988	0.21995	150	7
0.21710	0.21732	604	125	0.21836	0.21842	604	78	0.21812	0.21824	604	61
0.21376	0.21376	442	230	0.21459	0.21493	442	182	0.21461	0.21445	442	234