Failure Diagrams for Unidirectional Fiber Metal/Matrix Composites
By K.S. Chan

Page 1532:

The caption for Figure 2 should read:

Fig. 2—Delamination diagram calculated by He and Hutchinson^[19] on the basis of the ratio of interface toughness (G_i) to fiber toughness (G_f) and the Dundur's parameter, $\alpha = \bar{E}_1 - \bar{E}_2 / (\bar{E}_1 + \bar{E}_2)$.

Page 1533:

B₄c on the third row of Table I should have been B₄C:

Table I. Summary of Matrix Yield Stress (σ_y), Fiber Strength (σ_f), Interface Debonding Strength (τ_d), Interface Friction Stress (τ_f), Dundurs' α Parameter, Interface Toughness (G_i), Fiber Toughness (G_f), Fiber Diameter (D), and the Failure Modes Observed within the Stress Intensity Range, ΔK

Composite	$D, \mu\text{m}$	σ_y, MPa	σ_f, MPa	τ_d, MPa	τ_f, MPa	α	$G_i, \text{J/m}^2$	$G_f, \text{J/m}^2$	G_i/G_f	$\Delta K, \text{MPa} \sqrt{\text{m}}$	Observed Fracture Mode within the ΔK Range
FP/ZE41A	20	190 ^[5]	1380 ^[5]	>275	—	0.78	54.2	57.3	0.95	5 to 10 ^[5]	matrix yielding/fiber fracture ^[5]
B ₄ C-B/Ti-6Al-4V (As-received)	140	827	1940 ^[7]	275.4 ^[22]	135.5 ^[22]	0.53	26.1	65.4	0.41	20 to 30 ^[7]	limited interface cracking/fiber fracture ^[6,7]
B ₄ C-B/Ti-6Al-4V (Heat-treated)	140	827	1630 ^[7]	80.0 ^[7]	—	0.53	8.50	43.9	0.19	26 to 40 ^[7]	extensive interface cracking/fiber fracture ^[7]
SCS-6/Ti-6Al-4V	140	827 ^[11]	3500 ^[11]	138.0 ^[23]	87.5 ^[12,23]	0.55	3.93	43.8	0.09	19 to 35 ^[11]	fiber bridging ^[10,11]
SCS-6/Ti-15-3	140	750 ^[24]	3500	112.4 ^[23]	81.5 ^[23]	0.55	1.45	43.8	0.03	20 to 40 ^[15]	fiber bridging ^[13-15,24]
SCS6-Ti-24-11	140	650 ^[25]	3500	101.9 ^[23]	47.8 ^[23]	0.55	4.46	43.8	0.10	26 to 65 ^[15]	fiber bridging ^[15,16,17]
SCS-6/Ti-25-10	140	650 ^[17]	3500	108.4 ^[23]	56.6 ^[23]	0.55	4.09	43.8	0.09	—	—

Page 1540:

The caption for Figure 12 should read:

Fig. 12—Transition of fracture mechanisms in fiber composite resulting from (1) increasing K levels (path 1); (2) decreasing interface debonding strength, τ_d (path 2); and (3) decreasing fiber strength, σ_f (path 3).