Harper-Dorn Creep in Al, Pb, and Sn, by F. A. Mohamed, K. L. Murty, and J. W. Morris, Jr., pp. 935-40

In private communication, Frost¹ brought to our attention that a discrepancy exists between his estimated values of $\dot{\gamma}kT/DGb$ and our normalized data of Fig. 5 for Pb.² His estimated values are considerably higher than the values plotted in Fig. 5 and Fig. 6.

The normalized Pb data were reviewed and the source of the discrepancy was found. A factor of $10^2/3.5$ was missed in our calculation which resulted in reporting the low values of $\dot{\gamma}kT/DGb$ of Pb in Fig. 5. When the numerical error is corrected, the new values of A and n become respectively:

$$\left(6.6^{+10.9}_{-4.7}\right) \times 10^{-10} \text{ and } 0.97 \pm 0.08 \text{ for region I}$$

$$\left(7.4^{+252}_{-7.19}\right) \times 10^9 \text{ and } 4.99 \pm 0.35 \text{ for region II.}$$

Therefore, it is seen that the correction of the normalized data for Pb does not affect our principal conclusion concerning the Harper-Dorn creep in this metal, *i.e.*, the new value of A (6×10^{-10}) is almost three orders of magnitude above the predicted on basis of Nabarro-Herring model ($A = 8 \times 10^{-13}$ for $d = 1.5$ mm).

REFERENCES

1. H. J. Frost, Harvard University, Division of Engineering and Applied Physics, Cambridge, Mass.
2. F. A. Mohamed, K. L. Murty, and J. W. Morris, *Met. Trans.*, 1973, vol. 4, p. 935.

Farghalli A. Mohamed
J. W. Morris, Jr.

Discussion by J. Bruce See of "Homogeneous Nucleation of CO Bubbles in Fe-C-O Melts," pp. 2000-01.

Page 2001

A negative sign was omitted in Eq. [2]. The equation should read

$$P = -\frac{T^2\rho}{8\pi^2r^2} + \frac{2\sigma}{r}$$