not changed. However, one notices that the shoulder at ≈ 346.0 eV has developed in the spectra for the ex-situ annealed film and thus would imply that this feature is due to a reaction with atmospheric contaminants (*e.g.* O or OH) causing the formation of Ca oxides or hydroxides. Absorption of these gases also hinders solid phase epitaxial growth and thus is responsible for the inferior morphology which was observed.

The Si 2p core level spectra acquired at the CaF_2/Si interface as presented in Fig. 4(b) also supports these conclusions. The Si 2p binding energy at the interface of the as deposited film is 99.0 eV. The shoulder toward the high binding energy side of this peak indicates the presence of SiO_x complexes. In the case of the ex-situ annealed film, one notes the shift of the main Si 2p peak to 99.6 eV which is again indicative of more developed SiO_x phases with an additional feature at 103.7 eV which represents SiO_2 . Clearly the ex-situ anneal causes the formation of these oxides due to the fact that the CaF_2 film is free to react with atmospheric gases (*e.g.* O, H_2O). In the case of the in-situ annealed film, one notes that the major Si 2p line has not shifted from the energy indicative of clean Si. Also, the peak is not as broad as in the case of the as deposited film. The small feature at ≈ 101.8 eV indicates the presence of SiO_x phases although in significantly reduced amounts. Certainly the presence of oxide phases due to absorption of atmospheric gases dur-

ing ex-situ annealing is responsible for the inferior morphology observed for that CaF_2 film.

ERRATUM

Dislocation Filtering: Why it Works, When it Doesn't [J. Electron. Mater. 19, 503 (1990)]

Brian W. Dodson,
Sandia National Laboratories,
Albuquerque, NM 87185

The (*invited*) designation for the above paper was inadvertently omitted during the publication process.

ERRATUM

Theory and Experiment of Capacitance-Voltage Profiling on Semiconductors with Quantum-Confinement [J. Electron. Mater. 19, 521 (1990)]

E. F. Schubert, J. M. Kuo and R. F. Kopf,
AT&T Bell Laboratories, 600 Mountain Avenue,
Murray Hill, New Jersey 07974

The (*invited*) designation for the above paper was inadvertently omitted during the publication process.