of thermodynamic equilibrium and balance of interfacial tensions (energies) can be applied to the twin-grain boundary intersection, I(T) in Fig. 3; and the influence of the twin interface on the grain boundary is clearly evident in the geometric displacement of the grain boundary. It is to be noted, however, that an equilibrium equation which balances the interfacial energies is not applicable to the grain boundary-stacking fault intersection, I(SF) in Fig. 3; and consistent with this feature no geometric displacement of the grain boundary is evident in Fig. 3.

It is also to be noted that the application of a condition of equilibrium of interfacial energies in the work of Peterson and Queeney⁹ involves a temperature $T = 875^{\circ}\text{C}$. Their estimated value was 46 ± 3 ergs per sq cm for γ_{SF} in copper; and they quote for comparison values of γ_{SF} which are normally associated with $T < 100^{\circ}\text{C}$. Let us consider the characteristic temperature dependence of a general interface in a single homogeneous phase in reversible equilibrium to be given by

$$-d\gamma_s = S_s dT$$

where γ_s is the interfacial free energy, S_s is the associated interfacial entropy, and T is the equilibrium temperature. In the absence of actual measurements in copper, $d\gamma_s/dT$ might have a value for copper stacking faults commensurate with the temperature coefficient for stacking faults in silver,¹² i.e., $d\gamma_{\text{SF}}/dT \cong -0.04$ erg per sq cm per $^{\circ}\text{C}$; we observe that the value of γ_{SF} obtained by Peterson and Queeney⁹ adjusted to 100°C becomes approximately 75 ergs per sq cm. This value is of course compatible with the "room temperature" node measurements.^{10,11}

This work was supported by the Office of Naval Research under Contract No. N00014-67-A-0269-0010, NR 031-735.

Authors' Reply

LANCE G. PETERSON AND RICHARD A. QUEENEY

Messrs. Murr and Foltz are correct in their cautions on extrapolating high temperature results to room temperature situations.

The comparison between parameters (free energies) which are explicitly temperature dependent, and measured at different temperatures, is not clearly facilitated by the correction cited by Murr and Foltz. Not only is the factor cited for another metal, but the temperature dependence of the interfacial entropy is ignored.

However, should the temperature dependence of stacking fault free energy actually be accurately accounted for by the above writers, their conclusions are of dubious value. First, although we have not examined the Ref. 11 cited by them, the Ref. 10 presents no direct measurement of stacking fault free

Fig. 3—Nonequilibrium stacking fault-grain boundary intersection, I(SF), and equilibrium twin-grain boundary intersection, I(T), in copper. Bright-field electron transmission image. Electron accelerating potential—125 kv.

energy in copper. The value cited is an extrapolation of alloy data whose exactness (with respect to extrapolated values) has not been established. The Ref. 12 cited in our original paper offers a better estimate than that of 10 or 11 in Murr and Foltz's letter, at any rate.

Finally, it would appear that an intelligent interpretation of our paper would be that it offers an opportunity and a method for characterizing the stacking fault free energy in metals and alloys where mode measurements are impossible. The attempted use of our data by Murr and Foltz to establish a value for the stacking fault free energy of copper is poorly conceived. This is so due to the possible variations in the grain boundary free energy of copper used to arrive at the stacking fault free energy of copper. A larger sampling of such situations would, of course, make this a viable technique.

9. L. G. Peterson and R. A. Queeney: *Trans. TMS-AIME*, 1969, vol. 245, p. 2098.

10. P. R. Thornton, T. E. Mitchell, and P. B. Hirsch: *Phil. Mag.*, 1962, vol. 7, p. 1349.

11. L. E. Murr: *Electron Optical Applications in Materials Science*, Chap. 7, McGraw-Hill Book Co., New York, 1970.

12. S. E. Bühler, K. Lücke, and F. W. Rosenbaum: *Phys. Stat. Sol.*, 1963, vol. 3, p. 886.