Bartholomaeus Anglicus on Gold

THE MODERN VIEWS OF A MEDIAEVAL ENCYCLOPAEDIST

L. B. Hunt

Johnson Matthey & Co Limited, London

“And when a plate of golde shall be bonded with a plate of silver, or joyned thereto, it needeth to beware of three things, of dust, of winde, and of moysture, for if any hereof come betweene golde and silver, they may not be joyned together the one with the other; and therefore it needeth to bond these two mettals together in a full cleane place and quiet.”

These words might very well describe the precautions necessary to the production of the sophisticated types of gold-faced or gold-inlaid contact materials nowadays so much in use in the electronics industry, a technique requiring not only careful control of the bonding process and subsequent rolling but also an exceptional degree of cleanliness, often achieved only by conducting operations in a specially designed area that is air-conditioned and entirely free from contamination.

In fact, they were written, in Latin, well over 700 years ago by a Franciscan friar, and the version given here is only very slightly modernised from the English translation made in the year 1398.

They come from a massive encyclopaedia, *De Proprietatibus Rerum*—“The Properties of Things”—compiled around the year 1250 by Bartholomew the Englishman, or Bartholomaeus Anglicus as he was known to his contemporaries, to provide a compendium of knowledge, largely for the use of the preaching friars; the chapter on gold includes some further perceptive comments on this metal which we shall come to later.

The author of this work, born in Suffolk in about 1205, went up to Oxford at an early age to study under the famous Robert Grosseteste, the first chancellor of the newly founded University and afterwards Bishop of Lincoln. To Grosseteste, who greatly influenced the young Bartholomaeus, we owe a great deal, in that he was the first to interrelate the old methods of logical argument, as used by Aristotle, to scientific experiment, thus really taking the first steps towards the creation of modern science as well as founding a distinguished school of scientific thought.

Grosseteste also had an affection for the Franciscans, who had arrived in Oxford in 1224, two years before the death of St Francis, and he not only lectured to them but provided a house for their studies. At this time there was also a strong link and

an interchange of both men and ideas between the new Universities of Oxford and of Paris, and in 1219 Bartholomaeus himself moved to Paris to take up a teaching post, and a little later, no doubt again influenced by Grosseteste, joined the Franciscans. Here he remained until, in 1230, he was called to become lecturer to the newly founded Franciscan “studium” at Magdeburg in Saxony.

The material for the great encyclopaedia was probably planned during his days at Oxford, assembled mainly during his period in Paris, and the work was completed in Magdeburg. Its date can be established fairly closely as around 1250, and it rapidly became a standard work, the manuscript being copied widely and used as an authority for very many years, in fact for centuries.

Before considering the nature of the encyclopaedia, and in particular its section on gold, it is necessary to appreciate the state of scientific and technical knowledge in the early part of the thirteenth century. Europe at this period knew little of medicine,

Many copies of the *De Proprietatibus Rerum* of Bartholomaeus still survive. This page is from an illuminated manuscript dating from 1323 and now in the Vatican Library. It shows the major part of Book XVI, Chapter 4, “De Auro”. The passage quoted above in mediaeval English can be identified in the Latin original, with some abbreviations, beginning fourteen lines up from the bottom of the left hand column: q(ua)n(do) aut(em) lamina braeha aurea cum argentea s(u)ducta debet malleando incorporari nece(ss)e e(st) actib(us) maxime precau(er)-i sed apulu(er)e uento et hu(m)ore quia si aliq(uid) horum int(er) aurum et argentum se p(er)miscuerit, nequaqua(m) unum cum altero se tenebit. Et ideo oportet ut in loco ualde mundo et quieto hec duo metalla ad inuicem uniantur

nich enim inter metalla e ductilius qz tate
e ductiliteris qz inter eadem et malleum si
ne ruptone. si dicitur parcum in bracteo
i. tenuissimas laminas dilataatur. nec qz
etiam inter metalla quo ad forma et spem
e pulcherris et iteo mcom picturabiles
formas sine spes primum et precipuum
locum aut optinet pulentitudo. En forma
e et rector cum colorum quam tenui me
tallorum. Item nich inter metalla quo
ad uirtutem inuenitur deservit plateam
dicens aurum in quo tempus e omi
metallo et purius et iteo uirtutem habi
confortatam et sup fluitatem quo ad u
natum in corpore exessuam et ito uali
ce lepram et elephanc passionem utilit
emendatur limatura autem aurum in cibo
ul' importu sine in medicina ad presuato
nem alepra ul' saltem ad eius occultatione
qua eius frequens usus ab ea preseruat
ul' recitat aut saltem ipam palliat et oc
cultat ut dicit aue. Item eadem limam
cum sicco bouaginis et o sse te corte ceum
ualet et sintopim et caroiacum passioem
Item lamme aure exentes in uino et ite
te uinum facit utile et uina splenis et
alias passioes multas ul' melancomias
Item usua facta cum in fructu aucto
melior e quam ex alia matia ul' metallo
locum enim usuius custodit inuicem
a ferore. Item puluis carmie auree oc
lis impositus maculas oculorum sanat
fortit aut aur menbra quamuis eis no
in corpore nec ea nutritat de puritate
exa spitate sua sup fluitates que menbr
lecebat. et ite gentio sicut dicit item plac.
Item aur calefactum tollit pilos ame
bis qz ite exstam sunt aut scutum et i
temit crescere no p mictit constan. Et
aurum purissimum no resonat sic es l' auge
tium nec crepat nec finditur. s; pous ex
tium et equalit dilataatur nisi e fuit alio
metallum ad uicem in mo aliquo ito
positum. o iam quam diu es ul' auct
cum cum aur sba e puritatem semp sub
malleo scinditur et semp ad suscepcone
debite forme sub malleo ita in obediens
inuenitur. et ito necesse e omne sup flum
ab eo p excoctionem auferatur. ut efficiat
ductiliter aliquid uas cum optata forma ex
inte producat ut dicit g. qz aur lami
nat bractea aurea cum argentea sba uenit
rebet malleato in corpora necesse e actib
maxime precam. sapuluer uento et buore
quia si aliqz horum inter aurum et argentum
se p mictit. nequa qz unum cum altero se
tenebit. Et ito oportet ut in loco ualde in
to et quieto hoc duo metalla qz ad inuice
inueniuntur. An aut mo debito sic iungut
in separabilis sit unio ita qz ab inuicem no
possint utremis separ.

In calum ut dicit ysto e dictum qz
cum sit es sine capum ut respici
ter superficialit. sicut aurum. ed. eni

greco simone calco uocatur aurum calum ut
qz habet et duntiam lenis sui capu et mix
tione auctens et stringit et quibzdam ali
medicaminibus producat ungue ad colo
rem aur ut dicit ysto. color enim itaqz habi
aut et similitudinem s; si ualorem uas
quis genens artificialia et pulchra in su
uouitate aur spem pteritencia et aurum
calco prepatut. s; paulatim a fulgore p
bebetur et qz in biginatur et sic tam
colore quam otore cupro suam materia
lem originem protestantur. In isto uas
cibana et uino diutius resuata saporem
bonibilem contrahunt et ens uito et otore
colluam tam que oculorum sunt medicina
meis utilit. reseruantur et etens for
matur. ut dicit plac.

Aurpignitum est uena terre sine lap
idis seu silis et fragilis aur spem pte
rentens in colore. et uocatur alio
in me lapis arseuicus e duplex rubens et
cinnus et habet securitatis dias in sul
phuris calefactis. et desiccatis. qui si p
ponatur in ipam malbum transmutat
omnia corpora metallina pter aurum ex
unt et te uasat. ut dicit. o. in plane. aur
aurpignitum calidum e et sic cum unum
gratu et e uena terre et dupla spes ruben
tis et cinnus aut conpetit medicina.

Habet aut uirtutem dissoluentis acta
bent. et mundificandi. En ualeat a sinaj
cis et malum banelicum habentibus et hu
militate. si in melinatio capite fumus em
recipiat. Et aurpimento sit p siloc
linguentum repulatum ut pili facit
ammoneant qui recoquatur cum calce
uina. Sicut etiam contra serpignit et in
pignitum leuit inungatur. s; statim locus
inunctus abluatur quia si unguentum
tale ibi maneret bonam carnem fac
et malam corrodere et ex coriaree mae
nam. enim habet in salina et corosua
ungues etiam de turpatos et de formos
facit catere. ut crescant meliores. ut dic
plac.

Argentum a greca appellatone. ut d
cit ysto e dem. nam argus arg uoi
centur cui inuim in modum accide
qz cum sit caridum in pressum corpori
lineas. nigras. ut dicit ysto. redat. in eius
compositioe sunt argentum inuim et sil
phur album plus aut e ibi te aere qz que
et argenti inuim quam sulphuris et ito no e
tam pntens. sicut aurum ut dicit. y. nisi.
Est aut argentum duplex. s. simplex. et cor
positum simplex aut liquidum et uocatur
argentum inuim. Compositum aut argen
tum solidum compositum et argero inuoi
puro et sulphure albo no inuenit. ut dicit. az.
argentum aut inuim e sba aqua micti
cum sba terre no fort inuicet et inuio
lubili et hoc habet ex magna siccitate ter
rea que no liquefat in superficie plana et ito

chemistry, physics, mathematics, or astronomy, the only works available being a few collections of practical recipes for such processes as dyeing, the colouring of metals and the making of pigments which had come down via the libraries of Constantinople from Greek sources in Alexandria. By the second half of the twelfth century the attention of learned men in Europe had been drawn to the large number of Greek and Arabic manuscripts that were becoming available to them, greatly superior to their own sources in the knowledge of nature and of practical skills.

The Transmission of Greek Learning to Europe

Greek science returned to Europe through the Muslim world. The great conquests of the seventh and eighth centuries—ranging from Persia and Mesopotamia to Spain—had given the Arabs access to a wealth of Greek learning among the civilised peoples they had overrun, and the manuscripts they found were eagerly translated in the ninth century into Arabic in the schools established in Baghdad, Damascus and Cairo, and in some of the cities of Spain. This store of knowledge, supplemented by the work of Arab scientists, was then transmitted to mediaeval scholars in Europe in a great wave of travel and translation. Spain was the principal legatee of Arabic learning, and by the twelfth century, when Europe had become more settled and established, a number of distinguished translators, including Adelard of Bath, Gerard of Cremona and Robert of Chester (who completed the translation of the first book on alchemy to be given to the west in 1144) were hard at work in Toledo, Segovia, Seville, Barcelona, and other Spanish centres. Another major source of translations was the famous court of Friedrich II—“Stupor Mundi”—in Norman Sicily, where a band of scholars—Christian, Jewish and Muslim working together—was maintained and encouraged by the Emperor, while to a lesser extent Greek texts were also received directly into Europe and put into Latin.

Thus by somewhere around 1200 a great body of early scientific and technical knowledge had been absorbed into Western Europe, and—although scholarly works on this subject tend to overlook it—a great interest was being taken in some of the more practical scientific problems; in fact one of the motives for the great interest in Arabic learning was the practical knowledge to be gained.

The Age of the Encyclopaedia

This stimulation of the desire for learning began to make it impossible for students to acquire at first hand a knowledge of all that was becoming available, while the collection of a substantial library of manuscripts was also a near impossibility. So began the

period of the encyclopaedia, and Bartholomew was not alone in seeking to provide a more convenient means of instruction and education, although it was to the Franciscans that fell the main burden of spreading both secular and religious knowledge. It was they, with a few others from the rival Dominican order, who undertook much of the invaluable work of selecting and arranging the new material for general use by both the laity and the clergy.

Alexander Nequam, for instance, an Englishman from St Albans, and a foster-brother of Richard I, had lectured in Paris but had returned to England by 1182 and there compiled his *Liber de Naturis Rerum* “On the Nature of Things”—a mass of scattered information of a scientific nature and the forerunner of Bartholomew’s work—in about 1200.

Alexander of Hales, another Englishman from Gloucestershire and a Franciscan, also working in Paris, produced his *Summa* in about 1230, a work described scathingly by Roger Bacon as “weighing about as much as one horse could carry”. Albertus Magnus, a Dominican, was yet another encyclopaedist, as was his pupil Thomas Aquinas. Roger Bacon, also an Englishman and a Franciscan who was a student under Grosseteste and who went on from Oxford to Paris, compiled his *Opus Majus* in 1268. Another contemporary of Bartholomew’s, the French Dominican Vincent of Beauvais, who was librarian and chaplain to Louis IX, was the author of a vast work, also written in about 1250, in eighty books and nearly 10,000 chapters, the *Speculum Majus*, which he claimed “included whatever has been made or done or said in the visible and invisible world from the beginning until the end”. It has been described as “a popular patchwork”, but like Bartholomew’s work although much larger and less methodical, it was read and quoted for several centuries, although it was not made accessible in English.

All these works were written in mediaeval Latin, as of course was the great encyclopaedia of Bartholomaeus Anglicus, the most popular work of the kind in the thirteenth century.

Although he occasionally gave his own commentaries, Bartholomeus was not an original writer, and took care to quote all his authorities, including contemporaries such as Robert Grosseteste and Albertus Magnus. The list of his authorities given at the beginning runs to 105 names, including St Augustine, St Gregory, Galen, Hippocrates, Avicenna, Pliny, Virgil, Cicero, Plato, Dioscorides, Ptolemy, Herodotus, Isidore of Seville, and Bede. The style of writing is clear, concise and methodical, as one would expect from a pupil of Grosseteste, while the wealth of information displays not only a very wide reading on the author’s part but an originality of treatment and a breadth of view. A great number of manu-

The translation of *De Proprietatibus Rerum* made by John Trevisa at Berkeley Castle, finished in 1398, is one of the earliest examples of English prose. It was printed in 1495 by Wynkyn de Worde and the concluding passage from the chapter on gold is reproduced here. To relate this to the quotation given at the head of this article and to the manuscript version in Latin a little explanation is perhaps necessary. The verb to meddle at this time had the meaning of mixing, mingling or blending and has been interpreted in the present context as bonding, although the Latin *malleando* could simply mean hammered. Trevisa renders the Latine *pulvere* as powder, but this would be better translated as dust. The term "wind" is still in use by older workmen to describe the occasional blister of air that causes rejections in the production of gold-clad silver or other metals

script copies were made and circulated among the universities and monasteries, and something over 100 copies still survive in the great libraries of the world. Roger Bacon referred to it in 1267 as "a well known work of reference", and by 1286 a copy was available on loan to students in the Sorbonne. Copies were sent to England as well as to other European countries, and one surviving manuscript in the Bodleian Library at Oxford dates from 1296.

The Translations of Bartholomaeus

The first translation into a modern language was made in 1372 for Charles V of France, a great collector of books and the founder of the Royal Library at the Louvre, by his chaplain Jean Corbichon. In 1398 an English translation was made by John Trevisa, a Cornishman, an Oxford graduate and chaplain to Sir Thomas Berkeley of Berkeley Castle in Gloucestershire. Trevisa, at a time when Latin and Norman French were only just disappearing as the common tongues of England, played a great part in the early development of English prose (English was first used in the law courts only in 1362 and a year later for the first time in the opening of Parliament). His translation—contemporary with Chaucer's *Canterbury Tales*—was begun shortly after he had completed the translation of the *Polychronicon*, the then standard work on general history written by the Chester monk Ranulph Higden, and was finished on 6th February, 1398, as the following rather delightful last paragraph shows. One can almost hear the sigh of relief mixed with pleasure at the completion of the great task he had undertaken:

Also gold smyten sowmyth not as bras doth & syluer: nor breketh ne cleuyth but stretchich euyn abrode: but yf ocher stronge metall be medled therwth in some wyse. for as longe as bras or laton is medlyd with þe substance of gold: it cleueth alway vnder þe hamour & is inobedyent to take due shape by betyng of þe hamour. And therfore it nedeth þe all supfluite be put away: & the golde clenyd by meleyng & made pure. þe it maye be able to be shape wth a hamour to make the of some vessel wyth couenable shape as Gregor sayth. And whan a plate of golde shalbe medlid wth a plate of syluer or Joyned therto: it nedeth to bewax namely of thre thynges. of powdre/ of wynde. & of moysture. for yf ony herof com betwene golde & syluer they may not be Joyned togyð: ne the one wyth þe other. And therfore it nedeth to medle thyle. ij metals togyð in a full clene place & quite. & whan thei be Joyned in due maner þe onyng is inleparable: so þe they may not afterwarde be departed asondre.

Endless grace, blysse, thankyns and prayings unto our lorde god Omnipotent be gyven, by whose ayde and helpe this translation was ended at Berkeley the vii daye of Feuerer, the year of our lorde MCCCxxxviii, the yere of the reyn of King Rycharde the seconde after the Conqueste of England xxii. The year of my lordes age, Syre Thomas lorde of Berkeley, that made me to make this Translation xlvii.

In the fifteenth century translations were made into German, Italian, Spanish, Dutch, and even into the Provençal language.

Trevisa's English translation circulated in manuscript form, and a few copies survive, but in 1495 a printed version appeared. This was produced at Westminster by Wynkyn de Worde, the assistant and successor to William Caxton, and is a most beautifully produced book.

Printed versions now began to appear in Latin, French and German, while a further English edition was published in London by Thomas Berthelet in 1535.

An extract from the Wynkyn de Worde edition of Trevisa's translation, the last paragraphs from the book on gold, is illustrated here, but for the modern

Among the many manuscript versions of Bartholomaeus Anglicus was a beautifully illustrated and bound copy written in French by Jean du Ries in Bruges in 1482 for presentation to King Edward IV of England and now in the British Museum. This miniature heads the chapter on gold and is intended to illustrate mining operations

reader it is preferable to draw upon a later edition, published during the reign of Queen Elizabeth I.

This was the work of Dr Stephen Batman, a Cambridge man who had the reputation of being “a learned man and an excellent preacher”, and was printed in London in 1582 under the title:

BATMAN VPPON BARTHOLOME
His Booke De Proprietatibus Rerum,

Newly corrected, enlarged and amended:
with such Additions as are requisite, unto
every severall Booke.

Batman made use of Trevisa’s translation and although he made his own additions, particularly on theological subjects, he did not interfere with the scientific matter. It was this edition of Bartholomaeus that was well known to Shakespeare, who drew upon it quite extensively in his allusions to the stars and to plants and animals. By now over 300 years old, Bartholomew’s massive work was still very much alive and sought after.

The encyclopaedia was organised in nineteen books, each of numerous chapters, and covered virtually everything that was known or imagined, from God and the angels to fire, water, air, earth and all its contents—animal, vegetable and mineral—as well as the best methods of bringing up children.

It is Book XVI which is of interest to us: this carries the heading:

The sixteenth book declareth and sheweth the nature and properties of alle stones and the generatyon of all mannre metalles.

Chapter 4, “Of Golde”, opens with some general statements:

Golde is called Aurum, and hath that name of Aura, still whether, as Isidore saith. For it shineth with bright beams and is of best colour.

After some alchemical references of little value today, and a number of quotations from Aristotle, the chapter goes on:

Then among metals nothing is more sad in substance, or more better compact, than golde; and therefore though it bee put in fire, it wasteth not by smoaking or vapours, neither lesseth the waight, and so it is not wasted in fire; but if it be melted with strong heate, then if any filth be therein, it is cleaned thereof, and that maketh the golde more pure and shining. No metall stretcheth more with hammer worke, than golde, for it stretcheth so, that betweene the anfield and the hammer without breaking and renting into pieces, it stretcheth to leaf golde.

The next section extols the virtues of gold in a medicinal sense, even for the treatment of leprosy and “cardiac passion”, “evils of the spleen and other evils”, while there is a foreshadowing of the use of gold in treating rheumatoid diseases—“golde comforteth lymmes . . . it doth away with the sharpness of superfluites that growe in members and cleanseth them in that wise, as Plato saith”.

Although it is nearly 300 years later than the time of Bartholomaeus, this illustration from Vanoccio Biringuccio's *Pirotechnia*, published in Venice in 1540, shows the method of bonding gold to silver practised in the middle ages

A later passage has this to say about the fabrication of gold:

Also gold smitten soundeth not as brasse doth and silver, nor cracketh nor cleaveth, but stretcheth even abroad, except other strong metall be medled therewith in some wise. For as long as brasse or Latton is medled with the substance of gold it cleaveth alway under the hammer and is inobedient to take out shape by beating of the hammer: and therefore it needeth that all superfluitie be put awaye, and the golde cleansed by melting and made pure, that it may be able to be shapen with a hammer, to make thereof some vessell with covenable shape as Gregory sayth.

For the latter part of this paragraph Bartholomaeus was perhaps a little unfortunate in his choice of authority, St Gregory of Nazianzus, one of the early Fathers of the Church and Bishop of Constantinople around the year 380. Gregory was a prolific writer and orator, with a highly developed sense of imagery, and his comments on the effects of brass ("auricalco", which was more likely to be a tin-copper bronze at this time) were of more metaphorical than metallurgical significance, to emphasise the importance of purifying the soul!

The final paragraph, which includes the passage quoted at the head of this article, runs as follows:

And when a plate of golde shall be medled with a plate of silver, or joynd thereto, it needeth to beware namely of three things, of powder, of winde, and of moysture: for if any hereof come betweene golde and silver, they may not be joynd together, the one with the other: and therefore it needeth to meddle these two mettals together, in a full cleane place and quiet, and when they be joynd in due maner, the joyning is inseparable, so that they may not afterward be departed asunder.

Now at the end of this last passage Bartholomaeus does not quote any authority; it must therefore have

been the product of his own knowledge. Bartholomaeus was certainly a man of keen observation, and he had travelled in Flanders and Holland and commented on their industries and agriculture before undertaking his journey to Magdeburg. Where then did he acquire this remarkable understanding of the bonding of gold to another metal? The most likely source was among the goldsmiths working on the Pont au Change and the Quai des Orfèvres in Paris; in 1292 no less than 116 goldsmiths and jewellers were recorded in this area.

The bonding of gold to silver or to other metals, although a procedure nowadays well established and relied upon in modern industry, was obviously open to fraudulent practices. Ordinances were made in Paris in the thirteenth century, not long after Bartholomaeus completed his encyclopedia, forbidding the cladding of silver with gold but were apparently repeatedly ignored by the goldsmiths, while in London in 1238, in the reign of Henry III, it was ordained that, in consequence of the frauds that had been practised by the goldsmiths it had become necessary to prescribe some regulations for their trade; these included an item "that no one shall put gold on brass or copper".

The bonding of a thin layer of gold to a backing material such as copper, bronze or silver is of course nowadays accepted as it has the obvious advantage of providing the desirable properties of gold where they are needed with an economy in cost. The later development, during the eighteenth century, of the bonding of carat gold alloys to base metals led in fact to the large-scale production of the "rolled gold" used so widely in costume jewellery, watch cases, fountain pens and spectacle frames. This perhaps Bartholomaeus could have foreseen; what he certainly could not have imagined was the advent of gold-clad electrical contact materials for the electronic and telecommunications industry, produced "in a full cleane place and quiet".