that a face-centered-cubic metal must always be stronger than a body-centered-cubic metal. It is suggested, however, that for those metals that exhibit allotropic forms, alloys based on the stronger lattice will have an initial advantage over those based on the weaker lattice. This factor may explain why face-centered-cubic "austenitic" alloys of iron tend to have better high temperature strength than body-centered-cubic "ferritic" alloys of iron.

These experiments show that the symmetry of the lattice is an important factor in the strength of metals at elevated temperatures. Conversely, symmetry is related to the ease of deformation of the lattice. These observations tend to support the theory that one mechanism of deformation at elevated temperatures involves glide or slip along crystallographic planes.

Acknowledgments

The author is indebted to C. A. Anderson for aid in the design and construction of the hot hardness machine used in these experiments. The work was performed under AEC Contract W-7405-eng-92.

References

- ¹ W. Rosenhain and J. C. W. Humfrey: The Crystal-line Structure of Iron at High Temperatures. *Proceedings Royal Society, London* (1909) **83**, p. 200.
- ² A. Sauveur: *The Metallography and Heat Treatment*

of Iron and Steel. (1935) p. 123, Fig. 94. The University Press.

³ F. Sauerwald and K. Knehan: The Temperature Dependence of the Hardness of Metals with Relation to Hot Working. *Ztsch. für Anorg. Allgem. Chemie* (1924) **140**, p. 227.

⁴ A. Sauveur: Steel at Elevated Temperatures. *Trans. American Society for Steel Treating* (1930) **17**, p. 410.

⁵ W. Schischokin: The Hardness and Extrusion Pressure of Metals at Various Temperatures. *Ztsch. für Anorg. Allgem. Chemie* (1930) **189**, p. 263.

⁶ A. Nadai and M. J. Manjoine: High Speed Tension Tests at Elevated Temperatures. *Trans. ASME* (1941) **63**; *Journal of Applied Mechanics* (1941) p. A-77.

⁷ J. H. Westbrook: Temperature Dependence of the Hardness of Pure Metals. *Trans. ASM* (1953) **45**, p. 221.

⁸ E. Fetz: Dynamic Hardness Testing of Metals and Alloys at Elevated Temperatures. *Trans. ASM* (1942) **30**, p. 1419.

⁹ E. Fetz: Dynamic Hardness Testing at Elevated Temperatures. *Iron Age* (Dec. 23, 1943) **152**, No. 27, p. 42; (Dec. 30, 1943) p. 40.

¹⁰ H. Cornelius and W. Trossen: Dynamic Hardness Testing. *Stahl und Eisen* (1940) **60**, p. 293.

¹¹ T. Matsuda: On the Dynamic Hardness of Bronze and Brass at Elevated Temperatures. *Science Reports Tohoku Imperial University, Japan* (1925) **13**, p. 401.

¹² G. M. Enos, G. T. Peer, and J. C. Holzwarth: Dynamic Hot Hardness Testing with Special Reference to Isothermal Transformations. *Metal Progress ASM* (1948) **54**, p. 51.

Technical Note

Thermal Conductivity of Uranium and Several Uranium Alloys

by James L. Weeks

THERMAL conductivities of several samples of uranium and uranium alloys were determined using an apparatus previously described.¹ The value previously reported for uranium,¹ 0.035 cal per sec per cm per °C at 70°C, is in error due to the failure of a thermocouple during the determination on uranium. The defective thermocouple was detected after a reanalysis of the data obtained during the run and since has been replaced. Subsequently, runs on several samples of uranium show the thermal conductivity of uranium to be 0.069 cal per sec per cm per °C at 70°C.

The accuracy of the determinations was checked by measuring a sample of synthetic sapphire whose thermal conductivity was previously reported^{1,2} and found to be in agreement with other values.³⁻⁵

The values given in Table I are believed correct to ± 3 pct or 0.003 cal per sec per cm per °C, whichever is larger. The samples were provided by J. H. Kittel of the Argonne National Laboratory, Metallurgy Div.

References

- ¹ J. L. Weeks and R. L. Seifert: Apparatus for the Measurement of the Thermal Conductivity of Solids. *Review of Scientific Instruments* (1953) **24**, pp. 1054-1057.
- ² J. L. Weeks and R. L. Seifert: Note Regarding the Thermal Conductivity of Synthetic Sapphire. *Journal American Ceramic Society* (1952) **35**, p. 15.

J. L. WEEKS is associated with the Chemistry Div., Argonne National Laboratory, Lemont, Ill.
TN 240E. Manuscript, Aug. 5, 1954.

Table I. Thermal Conductivity of Uranium and Several Uranium Alloys

Specimen	Alloying Element, (Pct)*	Remarks	Thermal Conductivity at 70°C, Cal per Sec per Cm per °C
1B2	0.03 C	As-rolled rod	0.070 ₂
2B3	0.08 C	As-rolled rod	0.070 ₂
3B1	1.1 Zr	As-rolled rod	0.059 ₅
4B4	2.2 Zr	As-rolled rod	0.057 ₁
5A3	0.1 Cr	As-rolled rod	0.064 ₅
7B1	0.5 Cr	As-rolled rod	0.066 ₈
A-6	none	High purity, quenched from 1000°C	0.071 ₀
A-8	none	High purity, quenched from 900°C	0.071 ₈
35	none	Prepared from hot-pressed UH ₃	0.064 ₉

* Balance uranium.

³ J. Francel and W. D. Kingery: Thermal Conductivity: IV, Apparatus for Determining Thermal Conductivity by a Comparative Method; Data for Pb, Al₂O₃, BeO, and MgO. *Journal American Ceramic Society* (1954) **37**, No. 2, Part II, pp. 80-84. (Part II: special issue on thermal conductivity.)

⁴ W. D. Kingery, J. Francel, R. L. Coble, and T. Vasilos: Thermal Conductivity: X, Data for Several Pure Oxide Materials Corrected to Zero Porosity. *Journal American Ceramic Society* (1954) **37**, No. 2, Part II, pp. 107-110. (Part II: special issue on thermal conductivity.)

⁵ Edwin Ruh: New Jersey Ceramic Research Station, Rutgers University. Private communication.