Reladling

to obtain uniform bath composition

by J. J. Green

THE matter of uniform bath composition has always been of great concern to makers of electric-furnace steels. This problem is considerably accentuated in the manufacture of steels containing high chromium contents, because of the processes involved. In melting high chromium steels by using a process involving high percentages of chromium-bearing scrap and chrome ore, with a subsequent chromium reduction from slag to metal at high temperatures, or by a practice involving large ferrochrome additions, the stratification of chromium has been regarded as a matter of vital importance.

Obtaining a bath of uniform chemical com-

J. J. Green is Melting Dept. Metallurgist for Universal-Cyclops Steel Corp., Bridgeville, Pa.

This was a paper presented before the Seventh Annual Electric Furnace Steel Conference, Iron and Steel Div., AIME, Dec. 8-10, Pittsburgh.

position by the usual method of stirring with steel rabblers has not always proved satisfactory. It is particularly difficult to stir the bath properly by the use of steel rabblers when excessively high temperatures are obtained after slag reduction because of the consequent rapid melting of the rabblers. A number of companies have made mechanical mixers for stirring the bath, but these devices are usually quite large and could not be readily adapted to our practices.

In an attempt to obtain a more uniform bath, the idea of tapping out a portion of the metal was conceived, and then pouring it back into the furnace over the lip of the ladle, thus duplicating to some extent, the type of mechanical mixing that occurs during the tapping of a heat.

This plan could easily be fitted into practice in the Universal-Cyclops plant, since on all of the furnaces the roofs can be lifted and the furnace shells proper can be moved out from under the electrodes, thus making the return of the metal to the furnace a simple operation.

This process, which is now a standard practice for all straight-chrome stainless iron alloys and chrome-nickel stainless grades, is termed "reladling". The mechanical mixing of the bath thus obtained has resulted in the complete elimination of discrepant results due to an insufficiently mixed bath.

Before the reladling practice was started, 4.7 pct of off-analysis heats could be attributed directly to stratification of chromium in the fluid bath. Since the reladling practice has been in effect, this figure has been reduced to under 2 pct, the over-all improvement from this cause being approximately 70 pct. The other elements, such as manganese, silicon and nickel, have not given as much trouble as chromium. However, after reladling, it has been possible to control bath composition of all elements more closely.

In taking a preliminary test to check bath composition, two samples are taken from differ-

ent parts of the furnace. An examination of the chromium results on the last 600 stainless heats made has disclosed that on 80.5 pct of the heats the variation in chromium on the two tests was less than 0.10 pct, and on only 1.3 pct of the heats was the variation over 0.25 pct. The high percentage of heats showing such good agreement in analysis has saved much furnace time otherwise lost while waiting for a second preliminary determination when the first two samples were not in agreement. It has also reduced the number of determinations required of the chemical laboratory, and only on very rare occasions is it felt necessary to send a second preliminary test to check the first test.

In using the reladling process, other advantages have been found that were not anticipated when it was put into general practice. One advantage of this procedure is that it cools the bath considerably. This is a distinct help, since the reladling operation takes place after reduction of chromium from the slag, and the bath is quite hot. A temperature drop in the bath of from 100° F to 200° F is found, depending on the length of time in the ladle, the rate of tap, and the rate at which the metal is poured back into the furnace. This is a matter of furnace control, and the operator is trained to regulate the reladling process so that he is able to control the bath temperature during the final stage of the heat.

Another advantage of reladling has been that it has eliminated an objectionable job performed by the furnace crews. Standing in front of a hot furnace rabbling a heat with a heavy steel bar is not a very desirable job. This is one case when there is no need for insisting that a furnace operator perform an undesirable job, as it can be done so easily by reladling. Needless to say, the furnace crews are sold 100 pct on reladling.

Since the reladling operation has been in regular use, a much closer control of our analyses has been obtained, and it has been possible to melt to relatively narrow aims within any given specification. Before reladling, the chemical specification to which Type 301 stainless was melted included a 1½ pct chromium range, and a 1 pct nickel range. With the institution of the reladling practice, these ranges have been substantially narrowed, and it is of interest to know that on the last 300 heats of this grade that have been made, 87 pct of such heats have finished within a plus or minus range of 0.35 pct for chromium, and 95 pct of the heats have finished within a plus or minus range of 0.25 pct for nickel.

Steelmakers have always been faced with the necessity of making heats within a desired specification, and today the limits to which heats must be melted are becoming closer and closer. By using the reladling operation it is possible to melt heats to close chemical analysis by having a uniform bath composition before making final alloy additions.