Erratum to: Biogenic Synthesis and Structural Characterization of Polyshaped Gold Nanoparticles Using Leaf Extract of *Swertia chirata* Along with Process Optimization by Response Surface Methodology (RSM)

Nirlipta Saha¹ · S. Dutta Gupta¹

Published online: 17 October 2016
© Springer Science+Business Media New York 2016

**Erratum to: J Clust Sci (2016) 27:1419–1437
DOI 10.1007/s10876-016-1009-8**

The original version of this article unfortunately contained a mistake. The presentation of Table 2 was incorrect. The corrected Table 2 is given in this erratum

The online version of the original article can be found under doi:[10.1007/s10876-016-1009-8](https://doi.org/10.1007/s10876-016-1009-8).

✉ Nirlipta Saha
nirlipta@agfe.iitkgp.ernet.in

¹ Department of Agricultural and Food Engineering, Indian Institute of Technology Kharagpur, Kharagpur, West Bengal 721302, India

Table 2 Results of full factorial central composite design matrix of four variables and mean responses for the biosynthesis of AuNP

Run	Variables in uncoded levels				Responses	
	X ₁ : leaf extract (%)	X ₂ : pH	X ₃ : gold chloride (mM)	X ₄ : temperature (°C)	Y: absorbance at 540 nm	
					Observed	Predicted
1	17.50	2.00	2.75	45.00	1.56	1.56
2	10.00	4.00	1.50	65.00	1.34	1.42
3	25.00	8.00	4.00	65.00	1.83	1.79
4	17.50	6.00	2.75	45.00	1.71	1.70
5	17.50	6.00	2.75	45.00	1.61	1.70
6	17.50	6.00	2.75	5.00	0.44	0.52
7	32.50	6.00	2.75	45.00	1.32	1.36
8	25.00	4.00	4.00	25.00	1.52	1.40
9	17.50	6.00	0.25	45.00	1.15	1.10
10	25.00	8.00	1.50	25.00	1.10	0.99
11	10.00	8.00	1.50	65.00	1.50	1.49
12	25.00	4.00	1.50	25.00	0.51	0.62
13	25.00	4.00	1.50	65.00	1.12	1.10
14	10.00	4.00	4.00	25.00	1.46	1.47
15	10.00	4.00	1.50	25.00	1.18	1.10
16	10.00	4.00	4.00	65.00	1.80	1.78
17	17.50	6.00	2.75	45.00	1.81	1.70
18	10.00	8.00	4.00	25.00	1.50	1.43
19	10.00	8.00	1.50	25.00	1.26	1.31
20	17.50	6.00	2.75	45.00	1.70	1.70
21	25.00	8.00	4.00	25.00	1.51	1.51
22	2.50	6.00	2.75	45.00	1.62	1.64
23	10.00	8.00	4.00	65.00	1.63	1.58
24	17.50	6.00	2.75	45.00	1.72	1.70
25	17.50	10.00	2.75	45.00	1.67	1.73
26	25.00	4.00	4.00	65.00	1.81	1.83
27	25.00	8.00	1.50	65.00	1.22	1.28
28	17.50	6.00	2.75	85.00	1.13	1.12
29	17.50	6.00	2.75	45.00	1.61	1.70
30	17.50	6.00	5.25	45.00	1.87	1.99