Erratum to: Light alkane aromatization over modified Zn-ZSM-5 catalysts: characterization of the catalysts by hydrogen/deuterium isotope exchange

**Krisztina Frey · Louis M. Lubango ·
Mike S. Scurrell · László Guzzi**

Published online: 4 November 2011
© Akadémiai Kiadó, Budapest, Hungary 2011

Erratum to: React Kinet Mech Cat DOI 10.1007/s11144-011-0382-4

Due to an unfortunate mistake in the production process, the column heading of Table 2 is displayed incorrect in the above mentioned publication. The correct representation of Table 2 is published below and should be treated as definitive by the reader.

The online version of the original article can be found under doi:[10.1007/s11144-011-0382-4](https://doi.org/10.1007/s11144-011-0382-4).

K. Frey (✉) · L. Guzzi
Department of Surface Chemistry and Catalysis, Institute of Isotopes, P.O. Box 77, Budapest 1525,
Hungary
e-mail: frey@mail.kfki.hu

L. M. Lubango · M. S. Scurrell
School of Chemistry, Molecular Sciences Institute, University of the Witwatersrand Johannesburg,
P O WITS, Johannesburg 2050, South Africa

Table 2 Propane conversion over Me-Zn/ZSM-5-based catalysts^a

Nature of Me	–	Cr	Co	Mn	Fe
Conversion (%)	24	35	42	35	46
Exit stream					
Composition (%C)					
Methane	1.8	3.7	3.5	2.6	3.1
C ₂	1.6	2.4	4.6	2.3	2.0
C ₄ + C ₅	0.7	0.2	–	–	0.1
Benzene	6.3	10.0	14.1	11.8	15.1
Toluene	6.8	10.8	14.9	12.6	17.8
Xylenes	3.4	5.0	6.0	5.9	8.6
C ₉₊	0.1	–	–	–	–
BTX selectivity (%C)	69	81	74	87	91

^a 0.5 mass% Zn and 1.0 mass% Me