Thermoelectric Properties of the Clathrate I $\text{Ba}_8\text{Ge}_{43}\square_3$

C. CANDOLFI,^{1,2} U. AYDEMIR,¹ M. BAITINGER,¹ N. OESCHLER,¹
F. STEGLICH,¹ and YU. GRIN¹

1.—Max-Planck-Institut für Chemische Physik fester Stoffe, Nöthnitzer Str. 40, 01187 Dresden, Germany. 2.—e-mail: christophe.candolfi@cpfs.mpg.de

The clathrate I $\text{Ba}_8\text{Ge}_{43}\square_3$ [space group $Ia\bar{3}d$, no. 230, $a = 21.307(1)$ Å] has been synthesized as a single phase and characterized by x-ray powder diffraction and metallographic analysis. Electrical and thermal transport measurements have been performed in the temperature range of 5 K to 673 K. $\text{Ba}_8\text{Ge}_{43}\square_3$ displays the electrical resistivity of a poor metal at low temperatures, with semiconducting-like behavior appearing above 300 K.

Key words: $\text{Ba}_8\text{Ge}_{43}$, clathrate I, defects, transport properties

INTRODUCTION

Intermetallic clathrates are considered promising candidates for thermoelectric applications at high temperatures.¹ The crystal structure of the most common clathrate I type can be described as a three-dimensional host framework of four-connected, covalently bonded atoms (e.g., Ga, Si, Ge, Sn) forming 20- and 24-atom cages encapsulating electropositive atoms (e.g., Na, K, Rb, Cs, Sr, Ba, Eu). The interaction between cage atoms and the host framework is a key property for understanding the thermoelectric properties of these compounds. So far, the highest thermoelectric figure of merit for a clathrate compound was reported for $\text{Ba}_8\text{Ga}_{16}\text{Ge}_{30}$ with $ZT \approx 1.35$ at 900 K.² In comparison, the binary archetype $\text{Ba}_8\text{Ge}_{43}\square_3$ ^{3,4} displays only very low ZT values, e.g., 0.06 at 693 K.⁵ However, complete characterization of $\text{Ba}_8\text{Ge}_{43}\square_3$ is important to identify the most promising clathrates among the variety of possible compositions.

$\text{Ba}_8\text{Ge}_{43}\square_3$ was originally predicted to show metallic behavior according to the 8- N rule,^{3,4} because only 12 of the 16 valence electrons related to the Ba atoms are necessary to satisfy the electronic requirements of 12 Ge anions surrounding three vacancies. Experimentally, it was found that the compound shows semiconducting behavior.^{5,6} The apparent discrepancy from the simple valence

rules has been tentatively ascribed to an ordering of the framework vacancies resulting in modifications of the electronic band structure near the Fermi level.⁵ On the other hand, investigations on the ternary system $\text{Ba}_{8-x}\text{Eu}_x\text{Ge}_{43}$ ($x < 0.6$) revealed metallic behavior for the whole homogeneity range.⁷ Here we present detailed transport properties measurements of $\text{Ba}_8\text{Ge}_{43}\square_3$ including electrical resistivity, thermopower, and thermal conductivity in the 5 K to 673 K temperature range. In order to exclude the influence of grain boundary and impurity effects on the transport properties, we developed a preparation route for single-phase polycrystalline samples.

EXPERIMENTAL PROCEDURES

Polycrystalline samples were synthesized from stoichiometric amounts of Ba (Chempur, 99.9%) and Ge (Chempur, 99.9999%) in an argon-filled glove box. $\text{Ba}_8\text{Ge}_{43}\square_3$ is thermodynamically stable in the temperature range from 770°C to 810°C and cannot be obtained as a pure phase by quenching of sealed reaction containers.⁴ To avoid the peritectoid decomposition below 770°C, the elements were placed in a glassy carbon crucible, heated to the melt with an induction furnace, and quenched between two steel plates in less than 1 s to room temperature. The reaction product typically consists of a circular plate, ~10 mm in diameter and ~1 mm in thickness. The single-phase character of the samples was confirmed by metallographic analysis (Fig. 1) and x-ray powder diffraction, which shows a

Fig. 1. Optical microscopy image of a splat-cooled specimen of $\text{Ba}_8\text{Ge}_{43}\square_3$ (bright-field contrast).

narrow half-width of the reflections up to $2\theta = 120^\circ$ (Fig. 2). All reflections were indexed within the space group $Ia\bar{3}d$ [$a = 21.307(1) \text{ \AA}$], and no reflections of impurity phases were observed. The sample composition was determined to be $\text{Ba}_{8.0(1)}\text{Ge}_{43.0(1)}$ according to wavelength-dispersive x-ray spectroscopy (WDXS) results. Within the experimental accuracy of the WDXS measurements, the reaction product is homogeneous.

Electrical and thermal transport properties were measured on parallelepipeds ($1 \times 2 \times 8 \text{ mm}^3$) cut from the quenched sample in the range from 5 K to 350 K by means of a four-point and a steady-state method, respectively (Physical Properties Measurement System, Quantum Design). Due to heat losses towards higher temperatures, the thermal

conductivity has only been investigated up to 150 K. High-temperature electrical resistivity and thermopower on a second sample were simultaneously determined in the 300 K to 673 K temperature range by a standard steady-state method (ZEM 3, Ulvac-Riko).

RESULTS AND DISCUSSION

Electrical resistivity and thermopower of $\text{Ba}_8\text{Ge}_{43}\square_3$ at low temperatures are depicted in Fig. 3a, b, respectively. The first essential outcome of these measurements is the observation of metal-like electrical resistivity below 280 K. Resistivity values are two orders of magnitude lower than those previously reported,⁵ corroborating the high quality of the samples. The thermopower exhibits a rather complex behavior with two sign changes: from n -type to p -type near 90 K (Fig. 3b) and from p -type to n -type slightly above 300 K (Fig. 4b). Such behavior might indicate multiband conduction with differing temperature-dependent mobilities of electrons and holes. The low values ranging between $-5 \mu\text{V K}^{-1}$ and $+10 \mu\text{V K}^{-1}$ are consistent with the metallic character of $\text{Ba}_8\text{Ge}_{43}\square_3$ below 280 K.

Above 300 K, the temperature dependences of the electrical resistivity and thermopower differ substantially from those expected in a metallic system (Fig. 4a, b). The electrical resistivity decreases with temperature, indicating semiconducting behavior. The thermopower displays a linear temperature dependence in the whole temperature range to reach a value close to $-40 \mu\text{V K}^{-1}$ at 673 K. Both features suggest that a transition from metal-like to semiconducting-like behavior sets in near room temperature. The absolute values of low- and high-temperature measurements are slightly

Fig. 2. X-ray powder diffraction pattern of $\text{Ba}_8\text{Ge}_{43}\square_3$ ($\lambda = 1.54056 \text{ \AA}$). All reflections can be indexed with the cubic lattice parameter $a = 21.307(1) \text{ \AA}$; no additional reflections are detected. The baseline corresponds to the residuals of a Rietveld refinement based on the reported structure model.⁴

Fig. 3. Electrical resistivity $\rho(T)$ (a) and thermopower $S(T)$ (b) of $\text{Ba}_8\text{Ge}_{43}\square_3$ at low temperatures.

different (approximately 10% to 20%) at this temperature, but in fair agreement considering the different experimental setups (ZEM 3 and PPMS) as well as uncertainties in the geometry factor. Measurements of the Hall effect, which would help to understand the complex temperature behavior of the thermopower, are currently in progress.

The temperature dependence of the thermal conductivity shows a pronounced maximum near 25 K, indicating a crystal-like character of the thermal transport (Fig. 5). This is in contrast to the glass-like temperature dependence observed in p -type $\text{Ba}_8\text{Ga}_{16}\text{Ge}_{30}$,^{8,9} but is consistent with transport properties reported for other ternary clathrate I compounds containing framework vacancies.¹⁰

Fig. 4. Electrical resistivity $\rho(T)$ (a) and thermopower $S(T)$ (b) of $\text{Ba}_8\text{Ge}_{43}\square_3$ above 300 K.

CONCLUSIONS

The clathrate I $\text{Ba}_8\text{Ge}_{43}\square_3$ has been synthesized as single-phase material. The transport properties reflect a metal-like to semiconducting-like transition near room temperature. The observed metal-like conductivity at low temperatures shows the applicability of the valence rules for the prediction of conduction behavior. The observed semiconducting-like behavior above room temperature is in good agreement with the previously reported result.⁵ The origin of the observed transition, however, must await further structure investigations to determine whether or not an intimate link between possible crystal structure modifications and this electronic transition exists.

Fig. 5. Thermal conductivity $\kappa(T)$ of $\text{Ba}_8\text{Ge}_{43}\square_3$ at low temperatures.

ACKNOWLEDGEMENTS

We thank R. Hempel-Weber for ZEM 3 measurements and the competence groups Structure and Metallography at MPI CPfS. C. Candolfi acknowledges financial support from the CNRS-MPG program.

OPEN ACCESS

This article is distributed under the terms of the Creative Commons Attribution Noncommercial License which permits any noncommercial use, distribution, and reproduction in any medium, provided the original author(s) and source are credited.

REFERENCES

1. G.S. Nolas, J. Sharp, and H.J. Goldsmid in *Thermoelectrics*, Vol. 45, Chap. 6. Springer Series in Materials Science (2001).
2. A. Saramat, G. Svensson, A.E.C. Pamqvist, C. Stiewe, E. Mueller, D. Platzek, S.G.K. Williams, and D.M. Rowe, *J. Appl. Phys.* 99, 023708 (2006).
3. W. Carrillo-Cabrera, J. Curda, K. Peters, S. Paschen, M. Baenitz, Yu. Grin, and H.G. von Schnering, *Z. Kristallogr.* 215, 321 (2000).
4. W. Carrillo-Cabrera, S. Budnyk, Y. Prots, and Yu. Grin, *Z. Anorg. Allg. Chem.* 630, 7226 (2004).
5. N.L. Okamoto, M.W. Oh, T. Nishii, K. Tanaka, and H. Inui, *J. Appl. Phys.* 99, 033513 (2006).
6. R.F.W. Herrmann, K. Tanigaki, T. Kawaguchi, S. Kuroshima, and O. Zhou, *Phys. Rev. B* 60, 13245 (1999).
7. U. Köhler (Thesis, Technical University of Dresden, 2007).
8. A. Bentien, M. Christensen, J.D. Bryan, A. Sanchez, S. Paschen, F. Steglich, G.D. Stucky, and B.B. Iversen, *Phys. Rev. B* 69, 045107 (2004).
9. M.A. Avila, K. Suekuni, K. Umeo, and T. Takabatake, *Physica B* 383, 124 (2006).
10. G.S. Nolas, T.J.R. Weakley, and J.L. Cohn, *Chem. Mater.* 11, 2470 (1999).