Al-Hf-Sc (Aluminum-Hafnium-Scandium)

V. Raghavan

Recently, [2010Rok] determined the phase equilibria between 600 and 400 °C in Al-rich alloys of this ternary system.

Binary Systems

The Al-Hf system [1998Mur] depicts a number of intermediate phases: Hf_2Al (C16, CuAl_2 -type tetragonal), Hf_3Al_2 (Zr_3Al_2 -type tetragonal), Hf_4Al_3 (Zr_4Al_3 -type hexagonal), HfAl (B_7 , CrB-type orthorhombic), Hf_2Al_3 (Zr_2Al_3 -type orthorhombic), HfAl_2 (C14, MgZn_2 -type hexagonal), βHfAl_3 ($D0_{23}$, ZrAl_3 -type tetragonal), and αHfAl_3 ($D0_{22}$, TiAl_3 -type tetragonal). The Al-Sc phase diagram [Massalski2] depicts the following intermetallic compounds: ScAl_3 ($L1_2$, AuCu_3 -type cubic), ScAl_2 (C15, MgCu_2 -type cubic), ScAl ($B2$, CsCl-type cubic), and Sc_2Al ($B8_2$, Ni_2In -type hexagonal). In the Hf-Sc system, continuous solid solutions form between βHf and βSc , and between αHf and αSc .

Phase Equilibria in Al-Rich Alloys

With starting metals of 99.99% Al, 99.8% Hf and 99.875% Sc, [2010Rok] melted about 40 binary and ternary alloys in a resistance furnace, by adding Al-Hf and Al-Sc

Fig. 1 Al-Hf-Sc solubility limit in (Al) at 600, 500 and 400 °C [2010Rok]

Fig. 2 Al-Hf-Sc isothermal section at 600 °C near Al corner [2010Rok]

master alloys to an Al melt. The alloys were given a final anneal at 600, 500 and 400 °C for 30, 100 and 100 h respectively, followed by quenching in water. The phase equilibria were studied with electrical resistivity measurements, optical microscopy and scanning electron microscopy with energy dispersive x-ray analysis. The solubility limits of Hf and Sc in (Al) derived from electrical resistivity measurements at 600, 500 and 400 °C are shown in Fig. 1. Figure 2 shows the isothermal section near the Al corner at 600 °C [2010Rok]. The binary compounds αHfAl_3 and ScAl_3 are in equilibrium with (Al). The isothermal sections at 500 and 400 °C were found by [2010Rok] to be similar to the one in Fig. 2.

References

- 1998Mur: J.L. Murray, A.J. McAlister, and D.J. Kahan, The Al-Hf (Aluminum-Hafnium) System, *J. Phase Equilib.*, 1998, 19(4), p 376-379
- 2010Rok: L.L. Rokhlin, N.R. Bochvar, J. Boselli, and T.V. Dobatkina, Investigation of the Phase Relations in the Al-Rich Alloys of the Al-Sc-Hf System in Solid State, *J. Phase Equilib. Diffus.*, 2010, 31(4), p 327-332