

# Al-V (Aluminum-Vanadium)

H. Okamoto

The Al-V phase diagram was reviewed by [2001Oka]. Further investigation was needed because the phase diagram assessed by [1989Mur] disagreed significantly with the experimental result reported later by [2000Ric]. For example, the peritectic melting point of  $\text{Al}_8\text{V}_5$  estimated at 1670 °C by [1989Mur] must be 1408 °C [2000Ric].

Figure 1 shows the Al-V phase diagram assessed by [2004Gon] by taking into account the result of [2000Ric].

The Al-V phase diagram was calculated earlier by [1987Kau] based on old data. [2006Kos] also calculated the phase diagram, but the data of [2000Ric] were overlooked.

The  $\text{AlV}_3$  phase has not been discussed in all thermodynamic models described above. In order to attract attention, boundaries of the  $\text{AlV}_3$  phase has been copied from [1989Mur] in Fig. 1.

## References

- 1987Kau: L. Kaufman, Computer Based Thermochemical Modeling of Multicomponent Phase Diagrams, Alloy Phase Stability, *Proceedings of the Nato Advanced Study Institute on Alloy Phase Stability*, Maleme, Crete, Greece, 1987, p 145-175
- 1989Mur: J.L. Murray, The Al-V (Aluminum-Vanadium) System, *Bull. Alloy Phase Diagr.*, 1989, **10**(4), p 351-357
- 2000Ric: K.W. Richter and H. Ipser, The Al-V Phase Diagram between 0 and 50 Atomic Percent Vanadium, *Z. Metallkd.*, 2000, **91**(5), p 383-388
- 2001Oka: H. Okamoto, Al-V (Aluminum-Vanadium), *J. Phase Equilib.*, 2001, **22**(1), p 86
- 2004Gon: W. Gong, Y. Du, B. Huang, R. Schmid-Fetzer, C. Zhang, and H. Xu, Thermodynamic Reassessment of the Al-V System, *Z. Metallkd.*, 2004, **95**(11), p 978-986
- 2006Kos: A. Kostov, D. Živković, and B. Friedrich, Thermodynamic Study of Ti-V and Al-V Systems Using FACTSAGE, *J. Min. Metall.*, 2006, **42**, p 57-65




Fig. 1 Al-V phase diagram