

J. K. SOLBERG and E. NES	2233
On the micromechanisms of repeated precipitation on edge dislocations	
T. T. WANG and H. M. ZUPKO	2241
Long-term mechanical behaviour of optical fibres coated with a u.v.-curable epoxy acrylate	
A. L. W. COLLINS and D. M. R. TAPLIN	2249
An experimental fracture map for uranium	
H. SCHMID, P. GENEQUAND, H. TIPPMANN, G. POUILLY and H. GUÉDU	2257
Pyroelectricity and related properties in the fresnoite pseudobinary system $Ba_2TiGe_2O_8-Ba_2TiSi_2O_8$	
Letters	
K. WAKASA and T. NAKAMURA	2266
The formation of α' lath martensite in a textured $(\alpha + \gamma)$ Fe-23.19 wt % Cr-4.91 wt % Ni alloy	
L. E. MURR and S. L. LERNER	2268
Explosive-shock deformation of natural chalcopyrite ($CuFeS_2$)	
Y. MIYAZAWA, Y. MORI and S. HONMA	2272
The growth of $Dy_3Al_5O_{12}$	
R. S. DE BIASI and C. A. TAFT	2274
Magnetic resonance in $KFeS_2$ single crystals	
P. J. BURCHILL	2275
Chemical characterization of Kevlar-49	
K. NIIHARA and T. HIRAI	2276
Hardness anisotropy of α - Si_3N_4 single crystal	
P. LONGLAND and A. J. MOULSON	2279
The growth of α - and β - Si_3N_4 accompanying the nitriding of silicon powder compacts	
Y. W. MAI and A. S. VIPOND	2280
On the opening and edge-sliding fracture toughness of aluminium-epoxy adhesive joints	
M. I. HAKEEM and M. G. PHILLIPS	2284
Effect of environment on stability of cracking in brittle polymers	
S. YAMINI and R. J. YOUNG	2287
Comments on "Effect of environment on stability of cracking in brittle polymers"	
W. M. DAWSON and A. J. MOULSON	2289
The combined effects of Fe and H_2 on the kinetics of silicon nitridation	
D. A. MILLER and R. PILKINGTON	2291
Observations of sub-micron cavities in a low alloy ferritic steel	
J. O. WILLIAMS, P. J. WRIGHT, M. A. ELMORSI and S. E. MORSI	2292
Anodic oxidation of InP and the quaternary alloy $Ga_xIn_{1-x}As_yP_{1-y}$	
F. J. GUILD, B. HARRIS and A. G. ATKINS	2295
Cracking in layered composites	

Errata

D. IWANOV and Chr. NANEV, *J. Mater. Sci.* **13** (1978) 1449.

p. 1449, the last two lines of the abstract should read: . . . of 150 to 310°C with sulphur vapour pressures of 6×10^{-4} to 2.5 torr. It was found that $\{0001\}CdS \parallel \{0001\}Cd$ with $\langle 11\bar{2}0 \rangle CdS \parallel \langle 11\bar{2}0 \rangle Cd$.

p. 1450, in the caption to Fig. 2 read $\{0001\}$ for $\langle 11\bar{2}0 \rangle$.

Technical articles of full page length, or over, appearing in *Journal of Materials Science* are indexed in *British Technology Index*, *Current Contents*, *Science Citation Index (USA)*, and *Engineering Index*. *Journal of Materials Science* is also used by *Chemical Abstracts*, *Metal Abstracts*, and *Physics Abstracts*.

© 1978 Chapman and Hall Ltd. Typeset by the Alden Press Ltd., London and Northampton, and printed in Great Britain by Whitstable Litho Ltd., Whitstable, Kent.