

Communications

Temperature-Oxygen Fugacity Tables for Selected Gas Mixtures in the System C-H-O at One Atmosphere Total Pressure

PETER DEINES, RALPH H. NAFZIGER, GENE C. ULMER, AND EDUARD WOERMANN

For at least two decades, many institutions throughout the world have computerized various calculations of the f_{O_2} values produced at various temperatures by gaseous mixtures within the C-H-O system. The f_{O_2} calculations included within this new compilation were first started at the Pennsylvania State University in 1962; an early approximate unpublished version of T - f_{O_2} tables for mixtures of CO-CO₂, H₂-H₂O, and H₂-CO₂ were finished in 1963 by Vern Porter* and

*Now with Texas Instruments, current residence—188 Mariana Drive, Richardson, TX 75080.

G. C. Ulmer. In the ensuing years, the necessary algebraic equations were freed from all their simplifying assumptions, the data-base for the f_{O_2} - T calculation was changed from Coughlin¹ (1954) to JANAF² (1965), and the graphs of Muan and Osborn³ (1965) presenting temperature *vs* the log of the mixing ratio have been corrected and extended. The goals of this new set of tables are directed at mixtures of CO-CO₂, H₂-H₂O, and H₂-CO₂ with a three fold purpose:

1) to provide at one atmosphere total pressure the most unequivocal set of equilibrium f_{O_2} -temperature data mathematically possible from the JANAF (1965) data base.

2) to provide data for the initial mixing of gases expressed in vol pct with sufficient detail to cover a temperature range of 500 to 2000°C in 5°C steps and to cover an oxygen fugacity range of 10⁻⁴ to 10⁻²⁶ atms in 0.10 log-unit steps.

3) to accurately compare calculated f_{O_2} -temperature relationships among five commonly used sources of C-H-O data, *i.e.*, Wagman *et al*⁴ (1954), Coughlin¹ (1954), Elliot and Gleisser⁵ (1960), Wicks and Block⁶ (1963), and JANAF² (1965).

In the twenty eight pages of the introduction to these tables, the algebraic derivations of the necessary equations are presented along with graphs of f_{O_2} - T -vol pct. These graphs index the information to be found within the tables proper. In addition, Δf_{O_2} data are presented in graphic form as contoured plots which allow the comparison of the other data sources with the JANAF data. The final paragraphs of the introduction explain the uses of the tables and very

PETER DEINES is Associate Professor of Geochemistry, Department of Geosciences, The Pennsylvania State University, University Park, PA 16802. RALPH H. NAFZIGER is Research Chemist, Bureau of Mines, P.O. Box 70, Albany, OR 97321. GENE C. ULMER is Professor and Chairman, Department of Geology, Temple University, Philadelphia, PA 19122. EDUARD WOERMANN is Professor, Institute of Crystallography, 51 Aachen, Templergraben, Germany.

Manuscript submitted August 15, 1975.

briefly reference the experimental techniques suitable for the utilization of these data.

The computer programs used were written in Fortran. Detailed printouts of the programs can be obtained from Dr. Peter Deines, 204 Deike Building, The Pennsylvania State University, University Park, PA 16802. The complete publication (129 pages) in paper binding is available at \$2.00 as Bulletin 88 from the Earth and Mineral Sciences Experiment Station, Mineral Sciences Bldg. College of Earth and Mineral Sciences, The Pennsylvania State University, University Park, PA 16802.

1. J. P. Coughlin: *U.S. Bur. of Mines Bull.*, 1954, no. 542, pp. 1-80.
2. JANAF: *Joint Army, Navy, and Air Force Thermochemical Tables*, 2nd ed., pp. 1-1141, reissued by National Bureau of Standards as Ref. Data Ser. 37, Gaithersburg, Md., 1971.
3. A. Muan and E. F. Osborn: *Phase Equilibria Among Oxides in Steelmaking*, pp. 1-236, Addison-Wesley, Reading, Mass., 1965.
4. D. D. Wagman, J. E. Kilpatrick, W. J. Taylor, K. S. Pitzer, and F. D. Rossini: *J. Res. Nat. Bur. Stand.*, 1945, vol. 34, pp. 143-62.
5. J. F. Elliot and M. Gleiser: *Thermochemistry for Steelmaking*, vol. 1, pp. 1-296, Addison-Wesley, Reading, Mass., 1960.
6. C. E. Wicks and F. E. Block: *U.S. Bur. of Mines Bull.*, 1963, no. 605, pp. 1-147.

Cooling Effect of Iron-Selenium Briquets Added to Liquid Steel

ROBERT H. ABORN

In the processing of liquid steel for casting in a mold, it is necessary to control the temperature to avoid excessive cooling, which could cause inferior ingot characteristics. Consequently it is important to know the temperature change that results from the addition of cold, solid additives to the teeming stream. A recent paper has calculated the cooling effect of alloy additives and reviewed the prior literature,¹ but nothing has been written on the addition of volatile elements which are only partially recovered.

This work is based on the addition of blended and compressed iron and selenium powders, in the shape of 1/4 × 1/2 in. (0.00635 × 0.0127 m) diam. briquets, each containing 85 pct iron and 15 pct selenium, added in sixteen 2 lb (0.91 kg) bags during the filling of a 5 ton (4.535 tonne) ingot mold with low alloy steel. Since the average recovery of selenium in top-poured ingots in air is two-thirds of the amount added, it is assumed that two thirds of the selenium added forms iron selenide (FeSe) at 960°C (1233 K), the eutectic temperature of FeSe and iron saturated with selenium.² The remaining one-third of the selenium is lost by volatilization between its boiling point 685°C (958 K) and 1600°C (1873 K), the temperature of the liquid steel. 32 lbs (14.53 kg) of additive in a 5 ton (4.535 tonne) ingot is equivalent to 6.4 lbs (2.906 kg) per ton of steel or 3200 gms. (3.200 kg) per metric ton. The cooling calculation follows:

Gram atoms of components in 3200 gm. (3.200 kg) of briquets

ROBERT H. ABORN is Metallurgical Consultant to ASARCO, Inc., Millington, NJ 07946.

Manuscript submitted June 24, 1975.