

Table II should read as follows:

**Table II. Measured Steady-State Strain Rates for Al-8.8Fe-3.7Ce Alloy**

| Temperature (K) | Stress (MPa) | Strain Rate ( $\times 10^6$ ) (per h) |
|-----------------|--------------|---------------------------------------|
| 523             | 46.6         | 1.7                                   |
|                 | 52.8         | 2.0                                   |
|                 | 66.0         | 2.4                                   |
|                 | 73.0         | 3.2                                   |
|                 | 79.2         | 3.8                                   |
|                 | 93.2         | 7.5                                   |
|                 | 99.4         | 7.9                                   |
|                 | 106.4        | 8.6                                   |
|                 | 112.6        | 11.3                                  |
|                 | 119.6        | 18.8                                  |
|                 | 125.8        | 23.2                                  |
|                 | 132.8        | 28.2                                  |
|                 | 139.0        | 34.9                                  |
|                 | 146.0        | 68.7                                  |
| 152.1           | 75.2         |                                       |
| 548             | 46.6         | 6.3                                   |
|                 | 59.8         | 7.3                                   |
|                 | 66.0         | 7.6                                   |
|                 | 73.0         | 9.4                                   |
|                 | 79.2         | 9.9                                   |
|                 | 86.2         | 10.4                                  |
|                 | 86.2         | 16.5                                  |
|                 | 92.3         | 18.0                                  |
|                 | 99.4         | 26.3                                  |
|                 | 105.5        | 39.5                                  |
|                 | 112.6        | 70.5                                  |
|                 | 119.6        | 164.6                                 |
|                 | 125.8        | 179.5                                 |
|                 | 131.9        | 219.4                                 |
| 573             | 33.4         | 5.6                                   |
|                 | 39.6         | 7.1                                   |
|                 | 59.8         | 8.9                                   |
|                 | 66.0         | 9.9                                   |
|                 | 73.0         | 11.6                                  |
|                 | 79.2         | 21.9                                  |
|                 | 86.2         | 26.3                                  |
|                 | 93.2         | 54.9                                  |
|                 | 99.4         | 98.8                                  |
|                 | 106.4        | 164.6                                 |
|                 | 112.6        | 359.0                                 |
| 598             | 39.6         | 5.3                                   |
|                 | 52.8         | 8.6                                   |
|                 | 59.8         | 10.4                                  |
|                 | 66.0         | 17.2                                  |
|                 | 73.0         | 30.4                                  |
|                 | 73.0         | 43.9                                  |
|                 | 79.2         | 41.1                                  |
|                 | 79.2         | 67.6                                  |
|                 | 86.2         | 93.6                                  |
|                 | 86.2         | 118.5                                 |
|                 | 93.2         | 212.7                                 |
|                 | 93.2         | 232.0                                 |

**Table II. Cont. Measured Steady-State Strain Rates for Al-8.8Fe-3.7Ce Alloy**

| Temperature (K) | Stress (MPa) | Strain Rate ( $\times 10^6$ ) (per h) |
|-----------------|--------------|---------------------------------------|
| 623             | 99.4         | 534.4                                 |
|                 | 99.4         | 624.0                                 |
|                 | 26.4         | 6.6                                   |
|                 | 33.4         | 9.0                                   |
|                 | 33.4         | 8.7                                   |
|                 | 39.6         | 12.3                                  |
|                 | 46.6         | 18.0                                  |
|                 | 46.6         | 12.3                                  |
|                 | 52.8         | 21.9                                  |
|                 | 52.8         | 20.5                                  |
|                 | 59.8         | 46.5                                  |
|                 | 59.8         | 32.9                                  |
|                 | 66.0         | 76.8                                  |
|                 | 66.0         | 58.1                                  |
| 73.0            | 175.6        |                                       |
| 73.0            | 156.8        |                                       |
| 79.2            | 658.0        |                                       |
| 79.2            | 311.8        |                                       |

Table IV should read as follows:

**Table IV. Results of Linear Regression for Temperature Dependence for Al-8.8Fe-3.7Ce Alloy**

| Stress (MPa) | Activation Energy ( $-\text{Slope} \times 8.314$ ) (J/Mol) | Correlation Coefficient |
|--------------|--|-------------------------|
| 52.8         | 61,050   | 0.98                    |
| 66.0         | 64,999   | 0.97                    |
| 73.0         | 83,190   | 0.97                    |
| 99.4         | 149,261  | 0.99                    |
| 112.6        | 172,390  | 0.99                    |