

which indicates that this phase is energetically favorable. Such a procedure may be named a valence model for metallic phases. An example of such a model has been proposed⁹ and applied to several alloy systems.¹⁶

Summary

A crystal-structure type may be characterized by the phase first found to belong to this type (prototype designation). Several symbol kinds have been developed to give a partial type description; they have a mnemotechnical function supplementary to the prototype designation. The merits of the different symbol kinds are apparent, so that a standardization of one of them would appear premature. The main problem of classification of metallic phases and structures lies in the search for a procedure to attribute to each phase a bonding type which indicates that the phase is energetically favorable.

References

1. C. R. Hubbard and L. D. Calvert, *Bull. Alloy Phase Diagrams*, 2(2), 153-157 (1981).
2. W. B. Pearson, *Bull. Alloy Phase Diagrams*, 4(3), 237-238 (1983).
3. ASTM Standard E, 157-77.
4. ASTM Book of Standards, 11, 286 (1975).
5. ASTM Bulletin TP 215, 27 (1957).
6. W. B. Pearson, *A Handbook of Lattice Spacings and Structures of Metals and Alloys*, Vol 2, Pergamon Press, Oxford (1967).
7. K. Schubert, *Kristallstrukturen zwei Komponentiger Phasen*, Springer Verlag, Berlin (1964).
8. K. Schubert, *Chem. Script.*, 19, 224-233 (1982).
9. B. Aronsson, T. Lundström, and S. T. Rundqvist, *Borides, Silicides, and Phosphides*, Methuen, London (1965).
10. F. Hulliger, in *Structure and Bonding in Crystals*, M. O'Keefe and A. Navrotsky, Ed., Academic Press, New York (1981).
11. E. I. Gladyshevskii, *Kristallochimia Silicidov i Germanidov*, Isd. Metallurgia, Moscow (1971).
12. P. I. Kripiakevich, *Strukturnye Tipy Intermetallicheskikh Soed.*, Isd. Nauka, Moscow (1977).
13. *Structure Reports for 1913-1980*, 47 volumes.
14. IUPAC, *Nomenclature of Inorganic Chemistry, 1970*, Butterworths, London (1971).
15. L. H. Bennett, T. B. Massalski, and B. C. Giessen, *Alloy Phase Diagrams*, New York, 423 (1983).
16. K. Schubert, *Commun. Math. Chem.*, 13, 113-127 (1982); *Monatsh. Chem.*, 113, 651-667 (1982); *Cryst. Res. Technol.*, 17,

553-564 (1982); *Commun. Math. Chem.*, 13, 75-111, (1982); and *I. Solid State Chem.*, 43, 97-105 (1982).

Above remarks by

K. Schubert

Max-Planck-Institut für Metallforschung, F R Germany

Standard-State Pressure

We would like to add the following comment to the note by Dr. L. H. Bennett [*Bull. Alloy Phase Diagrams*, 5(2), 132 (1984)], which is concerned with the selection of a standard-state pressure in thermodynamic calculations.

The *Bulletin of Alloy Phase Diagrams* has adopted the bar (10⁵Pa) as the unit for the presentation of pressure data, but no decision has yet been made with respect to the choice of the standard-state pressure, that is, either 1 bar or 1 atm.

As pointed out by R. D. Freeman, whose paper has appeared in the meantime [*J. Chem. Eng. Data*, 29, 105-111 (1984)], the standard-state pressure should be selected such that it is unity in terms of the pressure units employed. If the pressure is expressed in bar, but the standard-state pressure is defined as 1 atm (1.01325 bar), the simple relationship between pressure values and equilibrium constants will be lost, and the required conversions might be a continuous source of numerical errors.

It appears that, in the long run, the IUPAC recommendation to define 1 bar as the standard-state pressure is the only sensible solution.

Above remarks by

J. P. Neumann and M. Venkatraman

University of Alabama

Editor's response: I agree. Unless there are serious objections raised, it is my intention to adopt the IUPAC recommendation in future *Bulletin* assessments.

We invite your comments on these or any other topics.

—Editor

Addenda

Melting Point of Vanadium

The value for the melting point of V, 1910 °C (2183 K) [81Smi], supersedes the earlier value listed in the chart on "Melting Points of the Elements," *Bull. Alloy Phase Diagrams*, 2(1), 145-146 (1981). (See the Editor's Corner, *Bull. Alloy Phase Diagrams*, 3(2), 133 (1982) for details.)

Reference

81Smi: J. F. Smith, "The V (Vanadium) System", *Bull. Alloy Phase Diagrams*, 2(1), 40-41 (1981).

Melting Point of Iron

The value for the melting point of Fe, 1538 °C (1811 K) [82Swa], supersedes the earlier value listed in the chart on "Melting Points of the Elements", *Bull. Alloy Phase Diagrams*, 2(1), 145-146 (1981). (See the Editor's Corner, *Bull. Alloy Phase Diagrams*, 3(2), 133 (1982) for details.)

Reference

82Swa: L. J. Swartzendruber, "The Fe (Iron) System", *Bull. Alloy Phase Diagrams*, 3(2), 161-165 (1982).