Correction to: Creep and solvent squeeze behavior of κ -carrageenan gels under compression

Takuma Tanigawa¹ · Koichi Yao¹ · Ryosuke Shimizu¹ · Jun-ichi Horinaka¹ · Toshikazu Takigawa¹

Published online: 20 July 2019

© Springer-Verlag GmbH Germany, part of Springer Nature 2019

Correction to: Colloid and Polymer Science

<https://doi.org/10.1007/s00396-019-04526-1>

The author noticed that the published paper contained error. Unfortunately, Table 2 was incorrectly presented. Given in this paper is the correct table.

The original article has been corrected.

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

The online version of the original article can be found at <https://doi.org/10.1007/s00396-019-04526-1>

✉ Toshikazu Takigawa
takigawa.toshikazu.7u@kyoto-u.ac.jp

¹ Department of Material Chemistry, Kyoto University, Nishikyo-ku, Kyoto 615-8510, Japan

Table 2 Initial diameter (D_{ini}), equilibrium strain of the i th spring ($\varepsilon_{i,\text{eq}}$; $i = 1, 2, 3$), sum of $\varepsilon_{i,\text{eq}}$ ($\Sigma\varepsilon_{i,\text{eq}}$), spring constant of the i th spring (E_i ; $i = 1, 2, 3$), and re-defined permeability of the i th cylinder (k'_i ; $i = 1, 2, 3$)

D_{ini} (mm)	$\varepsilon_{1,\text{eq}}$	$\varepsilon_{2,\text{eq}}$	$\varepsilon_{3,\text{eq}}$	$\Sigma\varepsilon_{i,\text{eq}}$	ε_{eq}	E_1 (kPa)	E_2 (kPa)	E_3 (kPa)	k'_1 ($10^{-12}\text{m}^2\text{Pas}$)	k'_2 ($10^{-12}\text{m}^2\text{Pas}$)	k'_3 ($10^{-12}\text{m}^2\text{Pas}$)
10	0.15	0.37	0.18	0.70	0.74	51	21	43	0.086	0.85	1.7
15	0.16	0.32	0.24	0.72	0.75	50	25	33	0.080	0.75	2.4
20	0.17	0.44	0.12	0.73	0.74	47	18	67	0.10	1.5	2.7
25	0.083	0.33	0.25	0.66	0.75	96	24	32	0.053	0.71	2.4