Treatment of environmental contamination using sepiolite: current approaches and future potential

Na Song · Andrew Hursthouse · Iain McLellan · Zhenghua Wang

Received: 15 December 2019 / Accepted: 25 August 2020 / Published online: 11 September 2020
© The Author(s) 2020

Abstract To evaluate the potential of sepiolite-based materials to resolve environmental pollution problems, a study is needed which looks at the whole life cycle of material application, including the residual value of material classified as waste from the exploitation of sepiolite deposits in the region or from its processing and purification. This would also maximize value from the exploitation process and provide new potential for local waste management. We review the geographical distribution of sepiolite, its application in the treatment of potentially toxic elements in soil and across the wider landscape, an assessment of modification and compositional variation of sepiolite-based applications within site remediation and wastewater treatment. The potential of sepiolite-based technologies is widespread and a number of processes utilize sepiolite-derived materials. Along with its intrinsic characteristics, both the long-term durability and the cost-effectiveness of the application need to be considered, making it possible to design ready-to-use products with good market acceptance. From a critical analysis of the literature,

the most frequently associated terms associated with sepiolite powder are the use of lime and bentonite, while fly ash ranked in the top ten of the most frequently used material with sepiolite. These add improved performance for the inclusion as a soil or wastewater treatment options, alone or applied in combination with other treatment methods. This approach needs an integrated assessment to establish economic viability and environmental performance. Applications are not commonly evaluated from a cost–benefit perspective, in particular in relation to case studies within geographical regions hosting primary sepiolite deposits and wastes that have the potential for beneficial reuse.

Keywords Modified sepiolite · Adsorption · Potentially toxic elements · Remediation material composition · Economic analysis

Introduction

Environmental contamination is a persistent issue bringing more challenges to the health and development of the world (Uddin 2017). Pollution caused by the excessive presence of potentially toxic elements (PTEs) is one of the common environmental issues and relates to soil, water, sediment, and air. The magnitude of the total release is difficult to accurately

---

N. Song (✉) · A. Hursthouse · I. McLellan
School of Computing, Engineering and Physical Sciences,
University of the West of Scotland, Paisley PA1 2BE, UK
e-mail: na.song@uws.ac.uk

A. Hursthouse · Z. Wang
Hunan Provincial Key Laboratory of Shale Gas Resource
Utilization, Hunan University of Science and Technology,
Xiangtan 411201, China

estimate given the diverse point and diffuse sources associated with human activity. However, it is reported that an estimated 8.2% of investigated arable land (7.59 million ha) in China is contaminated with PTEs due to (i) high natural concentrations (local geology), (ii) secondary enrichment in soil-forming process and (iii) human activities (China Geological Survey 2015). The environmental problems caused by PTEs are not only affected by their concentrations but also by the different chemical species present under varying environmental conditions. The persistence of PTEs in the environment is prolonged because of resuspension and circulation in the atmosphere and transfer between terrestrial and aquatic systems (Shotyk et al. 2003). This is particularly true in areas of mining, ore exploitation, and metallurgical activity where in addition to direct soil deposition, rivers and wetlands have been contaminated by the PTEs. In addition to the PTEs content, hazards from PTEs are also affected by environmental conditions. In areas where soil PTEs exceed regulatory standards due to high geological background without human activity, the impact from soil PTEs is relatively low and transfer in the food chain is not significant. It is easier for crops to absorb and accumulate PTEs in soils that have been introduced through human activity, making these sources, in general, more accessible to wider dispersal due to chemical reactivity and bioavailability (China Geological Survey 2015). With the changes of soil environmental conditions, a high pollution level of soils with PTEs may lead to migration of contaminants into adjacent areas, which consequently generate hazard to the environment and living organisms (Twaróg et al. 2020). High quantities of PTEs existed in the wastewater from mining, chemical processing plants. The contamination was discharged into the environment as stable forms. Where PTE ions are stable in wastewater or other contaminated aqueous environments, they can be ingested and accumulated easily by aquatic and terrestrial organisms as they are not biodegradable, with the potential to threaten human health through transfer in the food chain (Ajao et al. 2020).

In the management of industrial wastewater, attention has been paid to the treatment of PTEs, such as Cu, Zn, Pb, Cd, Hg, As, Cr and Ni (Ihsanullah et al. 2016) as these are the PTEs more strongly influenced by human activity. Many physical, chemical and biological techniques have been applied to remove

PTEs from wastewater including chemical precipitation, physical adsorption, electrolysis, biological accumulation, reverse osmosis and ion exchange (Ihsanullah et al. 2016). Adsorption is one of the most viable methods for pollution treatment, owing to its relatively straightforward application, high efficiency and insensitivity to the toxicities of contaminants. Activated carbon is probably one of the most widely applied adsorbents with many examples of application to remediate contaminated soil (Söregård et al. 2019), sediment (Rakowska et al. 2014), atmosphere (Huang et al. 2019) and water (Hadi et al. 2015). More novel carbonaceous materials have also been studied for application in land/soil/sediment treatment, including a wide range of nanomaterials (Shahamirifard et al. 2016), such as graphene oxide (Isari et al. 2018; Zhao et al. 2011) and carbon nanotubes (Tofighy and Mohammadi 2015). However, these systems often require extensive synthesis, purification, and as viable treatment technologies still require further optimization. In pursuit of solutions within the life cycle approach to reduce the environmental impact of technologies, more inexpensive and low-cost materials still need to be sought.

Currently, clay minerals are a matter of much attention because they have been utilized as effective amendments for soil contaminated with PTEs and low-cost adsorbents for removing PTEs ions in aqueous solution (Uddin 2017; Xu et al. 2017). As a commonly used industrial material, sepiolite has been used as a therapeutic, functional, inert and bulk agent in the pharmaceutical and cosmetic industries (Carretero and Pozo 2010) and as an adsorbent to reduce the bitterness of cold-pressed grapefruit seed oil (Guneser and Yilmaz 2017). It has also been applied in the sorption of PTEs to improve environmental conditions (Álvarez-Ayuso and García-Sánchez 2003; Kocaoba 2009; Lazarević et al. 2007).

Sepiolite [$\text{Mg}_8\text{Si}_{12}\text{O}_{30}(\text{OH})_4 \cdot 8\text{H}_2\text{O}$] is a complex hydrated magnesium silicate with a porous fibrous structure composed of two blocks of tetrahedral silica sheets and a sandwich octahedral sheet of magnesium hydroxide or oxide (Xu et al. 2017). Sepiolite is widespread and abundant in the earth and most research focuses on the application of natural sepiolite or purified products to remove pollutants from the environment. In addition, applications of purified, or modified, sepiolite are found in improving mechanical properties of materials, improvement of

environmental quality (e.g. air) and in craftwork. There is also an increased interest in modified sepiolite materials for environmental treatment, exploiting higher performance characteristics that can be obtained (Padilla-Ortega et al. 2013).

The extraction and purification of sepiolite require energy input and with the current focus on the climate emergency, the process alone does not meet full circular economy objectives. To address these, the potential of resolving pollution problems and maintaining a low carbon footprint, a study is required that considers the whole life cycle including maximizing the residual value of material classified as waste materials from the extraction and the purification of sepiolite to provide more environmentally friendly and energy-saving methods for contamination treatment. We have previously considered the context of sepiolite as a potential technology to treat localized contamination in China (Wang et al. 2018), highlighting capacity and treatment opportunities for PTEs in aquatic systems, modification and regeneration issues. This review provides a perspective on the life cycle of technology considering the potential application of the raw material, exploitation of residues, properties, and possible risk with the application of sepiolite in projects for the treatment of contaminated soil or land.

Geographical distribution of sepiolite

Suitability of structural features and properties of sepiolite make them very versatile materials that can be applied in many industries and thereby essential and crucial for the world economy as a whole. Spain is the world's largest producer of sepiolite. In Europe, 90% of sepiolite comes from Spain, and the rest of the sepiolite comes mainly from Turkey. Tblsa SA is the largest producer of sepiolite in Spain with a production capacity of 700,000 tons/year, providing 515,000 tons of sepiolite products: of which about 353,000 tons are used in cat and pet litters, and about 162,000 tons are consumed as industrial adsorbents, carriers for chemicals (e.g. pesticides), animal feedstuffs (Yi 2003). The price of sepiolite products depends on particle size, degree of modification, taste, additives, treatment methods. Sepiolite prices vary depending on the degree of processing, as a guide, typical examples from the Spanish markets give low-grade processed sepiolite products ~ \$32/t, industrial

products ~ \$112/t, rheology modifier products ~ \$934/t, and specialized modified sepiolite products ~ \$1871/t (Yi 2003). Raw sepiolite prices from China and Turkey are \$180–300/t and \$500–800/t, respectively, on Alibaba website: (https://www.alibaba.com/trade/search?fsb=y&IndexArea=product_en&CatId=&SearchText=raw+sepiolite&SearchScene=exhibition&spm=a27aq.14827689).

China hosts one of the world's major sepiolite reserves (Yin et al. 2011). The wide applicability and utility of sepiolite in the industry for rheological and catalytic purposes is well known and has driven effort for industrial exploitation for over 200 years (Martin Vivaldi and Robertson 1971). There is a potential in sepiolite-based coating material that helps with arresting heat transmission to reduce energy consumption in daily lives (Wang et al. 2009). Deposits of Hunan province comprise weathered Marine-sedimentary formations, consisting of sepiolite-palygorskite beds in the upper layer of the Permian Qixia (Chihsia) formation and have provided raw materials for purification of high-quality sepiolite products for industrial application. Information on the global distribution of sepiolite deposits is given in Table 1. The chemical composition of the range of sepiolite sources is given in Table 2.

Sepiolite-based material single application

Polymer nanocomposite sepiolite

Application in machinery

Sepiolite has remarkable adsorptive properties as a result of high surface area, and therefore it has been widely used in the preparation of polymer nanocomposites preparation as it increases dimensional stability, processability, thermal resistance and mechanical strength. The influence of different nanofillers, such as sepiolite, has been studied on the properties and characteristics of natural rubber nanocomposites, which showed the maximum improvement in modulus because of the high surface energy of sepiolite which is 38 mJ/m² (Bhattacharya et al. 2009).

The effect of sepiolite nanoclay on the tack strength of brominated isobutylene-*co-p*-methyl styrene loaded rubber was studied (Kumar et al. 2010). It was revealed that tack strength increased by around

Table 1 Global sepiolite distribution

Distribution	Country	Deposit	Deposition type	Estimated reserve (ton)	Approximately annual output (ton)	Study
1 North America	USA	Amargosa, Nevada	–	–	10000 (in Georgia)	(Eberl et al. 1982; Khoury et al. 1982; Liang 2008)
2 Europe	Spain	Vallecas-Vicálvaro-Yuncillos, Battallones and Mara	–	–	700,000	(Mayayo et al. 1998; Yi 2003)
3 Western Asia	Turkey	Eskişehir	Marine sepiolite-palygorskite	17,000 (nodular sepiolite) for Eskişehir	20,000–60,000 (in 1990s) for Turkey	(DPT 2001; Hüseyin and Bozkaya 2011; Yalçın and Bozkaya 1995)
			Lacustrine sepiolite-palygorskite			(Yalçın and Bozkaya 1995)
			Hydrothermal sepiolite			(Irkeç and Ünlü 1993)
			Hydrothermal sepiolite			(Yalçın and Bozkaya 2011)
4 East Asia	China	Anatolia	–	8.5 million for central Anatolia	–	(Hüseyin and Bozkaya 2011)
		Hunan, Henan	–	20 million for Hunan	–	(Wang et al. 2018; Zhang and Yang 1986)
5 East Africa	Kenya-Tanzania	Amboseli	–	–	320	(Liang 2008; Stoessel and Hay 1978)
6 Africa	Somalia	El-Bur	–	–	Hundreds	(Liang 2008; Singer et al. 1998)
7 The whole world				–	850,000	(Galán and Pozo 2015)

Table 2 Sepiolite composition across the world

	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	FeO	MnO	CaO	MgO	K ₂ O	Na ₂ O	H ₂ O ⁺	H ₂ O [−]	LOI	Total	Study
1	59.41	0.02	0.42	0.76	0.02	0.08	1.47	24.03	0.17	0.05	9.22	9.68		105.33	(Zhang and Yang 1986)
2	60.88	0.002	0.45	0.48	0.12	0.004	0.08	25.68	0	0.03	11.68	9.5*		99.41	(IGGCMBMI 1980)
3	58.71	0.02	0.9	1.07	0.09	0.06	1.86	25.06	0.1	0.35	9.75			99.43	(Zhang and Yang 1986)
4	61.4	–	0.38	0.19	0.07	–	0.79	26.51	< 0.01	0.03	11.17	9.45*		100.55	(IGGCMBMI 1980)
5	52.69	0.03	0.41	0.44	0.2	0.1	7.2	24.29	–	–	8.35		14.51	99.8	(Zhang and Yang 1986)
6	55.10	0.05	3.13	0.04	0.01	0.04	0.23	22.37	0.16	0.08	7.40	11.40		100.01	(Peng 2017)
7	54.44	–	0.4	0.15	0	–	0.11	24.59	0	0.05	9.12	11.5		100.39	(Zhang and Yang 1986)
8	54.75	–	0.8	4.1	–	–	1.68	18.3			20				(Liu and Xu 1984)
9	55.21	0.05	0.43	0.15		0.02	0.2	24.26	0.15	0.1	–	–	19.21	99.78	(Lopez Galindo et al. 1996)
10	63.10	–	1.08	0.27	–	–	0.49	23.80	0.21	0.09	10.88	–	–	99.92	(Galan and Castillo 1984)
11	53.17	0.17	1.76	0.99	0.04	–	0.23	24.70	0.97	0.45	8.29	8.79	–	99.57	(Hay and Stoessell 1984)
12	56.46	0.08	1.17	0.37	–	–	0.19	22.67	0.18	0.06	–	–	18.57		(Pozo et al. 2014)
13	56.95	0.15	1.05	0.93	–	–	2.45	23.35	0.41	0.11	–	–	14.60		(Ece and Çoban 1994)

*The total amount does not include H₂O[−]

Fibers sepiolite (α -type): (1) Henan Neixiang; (2) Henan Lushi; (3) Anhui Quanjiao; (4) Hubei Guangji; (5) Zhejiang Lin'an; (6) Hunan Yonghe; (7) Sichuan Shimian; (8) Guangxi Du'an; (13) Turkey Eskişehir

Clay sepiolite (β -type): (9) Spain Madrid; (10) Spain Vallecas; (11) Kenia Amboseli; (12) Spain Battallones; (13) Turkey Eskişehir

300% over that of neat BIMS (brominated isobutylene-*co-p*-methyl styrene) rubber. The molecular diffusion across the interface of BIMS rubber was lowered upon the addition of sepiolite nanoclay due to its reinforcing effect. However, the average penetration depth of the diffused chains of BIMS in the composites was still sufficient to form entanglements at either side of the interfaces, leading to greater resistance to separation due to an increase in cohesive strength of the corresponding nanocomposites (Kumar et al. 2010).

Sepiolite was modified by Tartaglione et al. (2008) in two different processes of functionalization: surface adsorption of quaternary ammonium salts/amines or grafting of silane reagents to surface silanols by covalent bonding. The grafted sepiolite-based nanocomposites of poly (butylene terephthalate) (PBT) and polypropylene (PP) are performed higher thermal stability compared to those of adsorbed sepiolite. There is no effect of sepiolite on thermal characters of PBT, whereas there is a polymer crystalline structure revealed on PP nanocomposites. Sepiolite was modified with cetyltrimethyl ammonium bromide (CTAB) by ion exchange and further was used to prepare polypropylene and polypropylene grafted with maleic anhydride composites by melting extrusion. The properties of modified sepiolite were compared with those of unmodified sepiolite-based nanocomposites. It is sepiolite that was modified by polypropylene/polypropylene grafted maleic anhydride/CTAB, showing the best interaction and resulting in increased elastic modulus and thermal resistance. There is a lower maximum heat release rate for the composite than those of neat polymer.

Application in wastewater

In wastewater treatment, sepiolite has been applied as a denser core anchoring chain for a polyelectrolyte, such as a polycationic polymer, with charge opposed to the colloidal charges, which leads to the fast formation of neutralized flocs with a higher density than organic colloids (Rytwo 2014, 2017). Sepiolite polymer nanocomposites offer effective clarification of water with a reduction of turbidity and suspended solids by more than 90% in effluents (Rytwo 2014, 2017). It is a technology that could be developed for wide ranges of applications. The properties of the polymer will be combined with that of the fillers,

which means the significance of modification is obvious.

A novel amidoxime based chelating nanohybrid adsorbent was synthesized with poly (acrylonitrile) grafted sepiolite nanohybrid material (RGS) with simultaneous radiation grafting technique (Taimur et al. 2017). Batch adsorption studies were carried out for Cu adsorbed on amidoximated nanohybrid adsorbents to study the effects of pH, contact time, adsorbent dose and initial concentration. Removal of Cu ion attained equilibrium follows pseudo-second-order kinetics within 30 min. There is a good description of the equilibrium process by the Langmuir isotherm model, and adsorption capacity reached its maximum at 278 mg/g for irradiated samples (Taimur et al. 2017).

Polyaniline/sepiolite (PANI/sepiolite) nanofibers were synthesized by chemical oxidation polymerization to remove Cr^{6+} from aqueous solution (Chen et al. 2014). The adsorption of Cr^{6+} to the PANI/sepiolite nanofibers was strongly influenced by pH within a range of 2–10, and adsorption efficiency of Cr^{6+} to the PANI/sepiolite reached the highest at pH 2. The maximum adsorption capacity of the nanofibers for Cr^{6+} was utmost at 206.6 mg/g at 25 °C, and it increased with the increase in temperature. Experiments of desorption revealed that PANI/sepiolite can be reused and regenerated for 2 continuous cycles without loss of its removal efficiency (100% in the first cycle and removal efficiency remained almost the same in the second cycle), which indicated that the nanofibers can be used as an economical and efficient adsorbent for Cr^{6+} (Chen et al. 2014).

Modified sepiolite combines with other fillers has been a subject of research and the work has been started. The opportunities for sepiolite applications are vast and hence there are numerous opportunities to utilize sepiolite. Along with its specific characteristics, both the long-term durability and the cost-effectiveness of the application need to be considered, making it possible to design ready-to-use products with good market acceptance. Sepiolite polymer nanocomposite has not been applied in the treatment of polluted soil or land so far because it is difficult and expensive to retrieve the polymer nanocomposite for reprocessing/reuse.

Other modified sepiolite materials for treatment

Application in water

To improve PTEs adsorption to sepiolite, there are a number of modification methods, including acid treatment, thermal treatment, magnetic modification, organic-modification and acid-thermal treatment (Wang et al. 2018). A method for removal of PTEs using nanoscale-zero-valent iron material loaded with sepiolite in aquaculture water involves microwave-assisted acid modification of sepiolite powder in hydrochloric acid solution. Therefore, it can quickly adsorb and remove PTEs from the aquaculture water body, help to adjust the pH to meet the requirements for good aquaculture conditions. The reaction conditions required are relatively easily achieved, the raw materials are low cost and easy to obtain, and this method is overall less time-consuming compared with traditional chemical precipitation of PTEs. The reaction is mild and the method is suitable for wider operation (Liu et al. 2018). In addition, to treat Cu in aquaculture wastewater, negatively magnetically modified sepiolite has been used to adsorb the Cu ions followed by filtering the sepiolite adsorbent and post-treatment processing (Zhang et al. 2018). A comparison of the adsorption capacity of waste sepiolite, modified sepiolite, natural sepiolite and other materials is given in Table 3.

Studies have been carried out on the structural effect of cationic surfactant to treatment capacity of PTEs (Kalpakli and Cansev 2018). The organo-clays were synthesized with smectite and hexadecyltrimethylammonium bromide (HDTMAB) which is a cationic surfactant. Moreover, the characteristics of prepared organoclay to remove Cd^{2+} , Cu^{2+} and Pb^{2+} ions from solution have been studied and the results demonstrated that organoclay increased their adsorption capacity for the Pb, Cu and Cd from aqueous solution (Kalpakli and Cansev 2018). A sepiolite modified material was prepared by microwave reaction of the mixture of sepiolite and kaolin and the mixture of ferric salt of cellulose, ferrous chloride and ferric chloride and then applied to remove Cd^{2+} , Cu^{2+} , Cr^{6+} and Pb^{2+} ions from solution with the benefit of a lower cost, higher adsorption efficiency and stability of the material (Huang 2017).

Composites of natural sepiolite (SEP) and partially acid-activated (AAS) were prepared at different ratios

and nanoscale zero-valent iron (nZVI) to obtain the best nZVI dispersibility and best performance of adsorption of Cd^{2+} (Habish et al. 2017). Though there is a higher surface area and pore volume of nZVI composed with AAS, the dispersibility of nZVI was better when SEP was used as the support. However, a lower degree of oxidation was attained during the synthesis by AAS. X-ray photoelectron spectroscopy (XPS) analysis of the composite with the best dispersibility for nZVI before and after adsorption of Cd^{2+} , indicated that the surface of the nZVI particles was composed of oxidized iron species. The adsorption isotherms of Cd^{2+} revealed that the existence of SEP and AAS reduced the agglomeration of nZVI particles when being compared to the pure nZVI, which showed higher adsorption capacity (Habish et al. 2017). A study was carried out by Bahabadi et al. (2017) on the application of natural sepiolite and Fe^{3+} modified sepiolite for the treatment of Cu, Zn and Cd in aqueous solutions. The concentration of iron chloride applied for modification was 1 M. Zn removal by sepiolite remained the same before and after the surface modification, while removal of Cu and Cd were increased by 13.6% and 21.2%, respectively.

A modified sepiolite was prepared with magnetite by chemical co-precipitation, and the magnetite/sepiolite (M/SEP) composite was characterized by X-ray diffraction (XRD), scanning electron microscopy (SEM), Fourier transform infrared spectroscopy (FT-IR), vibrating sample magnetometer (VSM) and X-ray photoelectron spectroscopy (XPS). The results revealed the composition of M/SEP is magnetite and sepiolite, having a superparamagnetic property. The results of the application of M/SEP to adsorb Co^{2+} and Cd^{2+} from aqueous solutions showed that sorption processes were endothermic and spontaneous processes on the basis of thermodynamic parameters, which indicates that M/SEP composite can be used on the preconcentration of Co^{2+} and Cd^{2+} in wastewater treatment (Yu et al. 2016).

Furthermore, sepiolite was also modified by *N*-1-[3-(trimethoxysilyl)propyl]] and the interaction with PTEs was studied systematically as a function of ionic strength, pH and temperature using ASS. The results revealed that the amount of adsorbed PTEs increased with an increase in equilibrium pH and temperature of the solution, while it decreased generally with the increase in ionic strength. The adsorption mechanism

Table 3 The adsorption capacity of sepiolite, modified sepiolite and other materials

Material	Treatment	PTE (s)	Capacity	Reference
Waste sepiolite	–	Boron	96.15 mg/g	(Öztürk and Kavak 2004)
Activated waste sepiolite	HCl activated	Boron	178.57 mg/g	(Öztürk and Kavak 2004)
Natural sepiolite		U	34.61 mg/g	(Donat 2009)
Modified sepiolite	Modified by 3-(trimethoxysilyl) propyl methacrylate (monolayer maximum adsorption capacity)	Cu, Mn, Zn, Fe, Co, Cd	12.3×10^{-5} mol/L, 11.7×10^{-5} mol/L, 9.0×10^{-5} mol/L, 8.2×10^{-5} mol/L, 5.7×10^{-5} mol/L, 1.8×10^{-5} mol/L	(Beyli et al. 2016a)
Modified sepiolite	Modified by N-1-[3-(trimethoxysilylpropyl)]	Co, Cd, Mn, Fe, Cu, Zn	30 mol/g, 37 mol/g, 80 mol/g, 110 mol/g, 118 mol/g, 118 mol/g	(Beyli et al. 2016b)
Activated carbon		Cd, Cr, Cu, Pb	0.19 mg/g, 0.16 mg/g, 0.21 mg/g, 0.18 mg/g	(Sajjad et al. 2017)
Silver birch (<i>B. pendula</i>) biochar		Cu, Pb	0.13 mg/g, 1.29×10^{-3} – 3.77×10^{-3} mg/g	(Komkine and Baltrenaite 2016)
Scots pine (<i>P. sylvestris</i> L.) biochar		Zn, Pb	0.11 mg/g, 2.37×10^{-3} – 4.49×10^{-3} mg/g	(Komkine and Baltrenaite 2016)
Chitosan		As	50.0 mg/g	(Brion-roby et al. 2018)
Rice straw		Cr	34.90 mg/g	(Lin et al. 2018)
Chinese loess		Ni	15.61 mg/g	(Wang et al. 2015)
Modified agricultural wastes		Cd	195.5 mg/g	(Al Othman et al. 2011)

of metal ions to modified sepiolite was identified by analyzing the experimental data on the basis of Langmuir and Freundlich isotherms, which indicated that the isotherm data were correlated to Langmuir isotherm. The monolayer adsorption capacities of modified sepiolite were estimated as 30, 37, 80, 110, 118 and 118 mol/g for Co^{2+} , Cd^{2+} , Mn^{2+} , Fe^{3+} , Cu^{2+} and Zn^{2+} , respectively. The affinity of adsorption was in the order of $\text{Co}^{2+} < \text{Cd}^{2+} < \text{Mn}^{2+} < \text{Fe}^{3+} < \text{Cu}^{2+} = \text{Zn}^{2+}$. The results demonstrated that Co^{2+} and Cd^{2+} were less efficiently adsorbed than Fe^{3+} , Cu^{2+} and Zn^{2+} by modified sepiolite. In conclusion, modified sepiolite can be applied as an alternative low-cost adsorbent in adsorption process in nanocomposite synthesis and chromatographic purification process (Beyli et al. 2016b).

Sepiolite was synthesized by nanoscale zero-valent iron particles (S-NZVI) for the adsorption and reduction of Cr^{6+} and Pb^{2+} ions from groundwater and results showed that S-NZVI had the potential for in situ remediation of heavy metal-contaminated groundwater (Fu et al. 2015). Acid-activated sepiolites and natural sepiolites were functionalized with covalent grafting [3-(2-aminoethylamino) propyl] trimethoxy-silane on the sepiolite surface, and their adsorption capacities of amine-functionalized sepiolites to Cr^{6+} from aqueous solution were investigated (Marjanović et al. 2013). The adsorption isotherms showed that the adsorption capacities of the modified acid activated sepiolite were higher than those of modified natural sepiolite for all of the researched initial pH values. The maximum concentrations of Cr^{6+} removal were 60 mg/g of functionalized acid-activated sepiolites and 37 mg/g of functionalized sepiolites, respectively, achieved at an initial pH of 2.0 (Marjanović et al. 2013).

Application in soil

A mercapto functionalized sepiolite material (MSEP) was prepared as an immobilization agent for treatment of Cd-polluted paddy soil (Liang et al. 2017). The Cd content of husked rice (*Oryza sativa* L.) was reduced by 65.4–77.9% at the trace dosages of 0.1–0.3% for MSEP. Single and sequential procedures showed that MSEP could boost the sorption or fixation of Cd on soil and decrease the bioavailability of Cd (Liang et al. 2017). MSEP had negligible effects on the point of zero charge of the paddy soil and pH values. There is

no obvious effect on extractable Zn, available phosphorus and hydrolysable nitrogen in the soil, which indicated that MSEP is environment friendly and compatible to use (Liang et al. 2017).

All of the sepiolite-based material might have a good effect on soil remediation; however, reuse or recycle of products is a problem. Furthermore, it might be a potential threat that some chemicals of the products could enter into groundwater.

Sepiolite combined with other additives in treatment

Raw sepiolite, modified sepiolite and sepiolite tailings have been applied as an additive combined with other additives together, which is adsorbent for water treatment, amendment agent, conditioner agent and inactivator for soil remediation. For instance, for PTEs polluted soil application of sepiolite-based material has included adding 10–385 wt% modified sepiolite tailings, 1–80 wt% modified zeolite, 1–5 wt% hyposulfite, 10–20 wt% nano iron powder and 45–60 wt% quicklime (Wang et al. 2017).

We identified 150 sepiolite-based literature reports and patents from databases (Web of Science, United States Patent and Trademark Office (<https://www.uspto.gov>), Chinese Patent database (<http://www.sooopat.com/>) for application in the treatment of water or soil contaminated by PTEs. The word cloud picture (Fig. 1) is produced by software Nvivo12 with an analysis of key content of combinations of materials. Figures 2, 3 and 4 are produced from Microsoft Office 2010 Excel by frequencies analysis to all additives of combinations of materials. All of them get checked if they (natural sepiolite, modified sepiolite, sepiolite tailings) are used as an additive to combine other additives for PTEs treatment in water, soil, land, sludge. There are published papers and patents (English abstract from different countries) in the database Web of Science. Only published patents and licensed patents are shown in the US patent office (in English) and Chinese patent database (in Chinese). A patent is only counted as one though this one might be published and licensed in more than one document.

To synthesize a large amount of literature and patents published on sepiolite, a word cloud picture has been prepared (Fig. 1). Figures 2, 3 and 4 describe the results in more detail.

Fig. 2 Variation of additives in sepiolite-based composites (in literature reports 1864–2018)

Fig. 3 Variation of additives in sepiolite-based composites (in literature reports 1864–2018)

Fig. 4 Variation of additives in sepiolite-based composites (in literature reports 1864–2018)

environment and poses a disposal challenge (Ochedi et al. 2020). However, fly ash is also a resource that can be widely applied in the fields of construction

materials, road sub-base, mine backfill etc. (Ahmaruz-zaman 2010), and fly ash also shows a promising ability as a heterogeneous catalyst to oxidize aqueous

Na₂S solution (Mallik and Chaudhuri 1999) or sorbent to remove various air pollution (Ahmaruzzaman and Gupta 2012; Ochedi et al. 2020). Fly ash is utilized as a constituent of mixtures for solidification/stabilization technologies because of its low-cost, good pozzolanic properties, which helps with solid waste disposal and coping with potential stress of its large generation and accumulation in an economically beneficial way (Terzano et al. 2005).

The influence of fly ash on properties of sepiolite is carried out by adding fly ash to the sepiolite with 2%, 4% and 6% by weight (Joseph and Angel 2020). The results showed that the pH of the mixture is decreased with a content increase in fly ash. The specific gravity and the Atterberg limit of the mixture showed a negative trend with an additional increase in fly ash. The mechanical standard compaction test results revealed a slight increase in the maximum dry density and a decrease in the optimum moisture content with an increase percentage of fly ash in the mixture. The strength and permeability of the mixture were improved up to 4% of the fly ash content, after that they showed a decrease in trend. The maximum values of strength and permeability of the sepiolite were reached at 4% addition of fly ash (Joseph and Angel 2020).

All of the sepiolite-based material additives might have a good effect on water treatment which is recyclable and low cost. They are much safer and cheaper to be added in soil but could still be more difficult to control the amount of sepiolite-based material and combined ratio because of various soil background comparing with other soil remediation methods.

Economic constraints for the application of sepiolite in remediation

Direct project cost and period of treatment

In the research of potential for ensuring the safety of production of rice planted in Cd-polluted soil by using sepiolite and humic acid, the production was studied using *Oryza sativa* L. (Jia-33) in which the accumulation of Cd with different weights of additives (including humic acid at 0.750, 2.250, 3.750, 5.250, 7.500 t/ha; or sepiolite at 2.250, 6.750, 11.250, 15.750, 22.500 t/ha, or combination of humic acid and

sepiolite at 0.375 + 1.125, 1.125 + 3.375, 1.875 + 5.625, 2.625 + 7.875, 3.750 + 11.250 t/ha) was assessed (Xie et al. 2018). Results showed that applications of humic acid are at 5.250 t/ha, or sepiolite at 6.750 t/ha or a combination of humic acid at 1.125 t/ha and sepiolite at 3.375 t/ha leads to that Cd content of polished rice were 0.171 ± 0.01 mg/kg, 0.184 ± 0.01 mg/kg, and 0.181 ± 0.01 mg/kg, respectively, lowering than the Cd limit defined in the National Food Safety Standard (GB 2762-2012, 0.2 mg/kg) of the PRC. The material purchase prices were 197.59 \$/t of humic acid, 112.91 \$/t of sepiolite, which means that the corresponding cost of applications of 5.250 t/ha humic acid, 6.750 t/ha sepiolite, the combination of 1.125 t/ha humic acid and 3.375 t/ha sepiolite were 1037.34, 762.13 and 433.99 \$/ha, respectively (Xie et al. 2018).

Research has shown that Cd passivated by the soil amendment calcium–magnesium phosphate and lime starts to re-release from the fourth year, which revealed that the passivation effect could last for 3 years (Jiang et al. 2017). This is much better than more intrusive stabilization methods such as lime/cement as soil function is preserved to some extent. Regardless of human resource and in terms of the cost of the materials, the lowest cost for the combination of humic acid at 1.125 t/ha and sepiolite at 3.375 t/ha with the average annual cost is about 144.66 \$/ha. This further illustrates the potential of low accumulation strains of rice combined with the application of the sepiolite to meet agricultural safety standards (Xie et al. 2018).

Remediation potential for contaminated land

Sepiolite is applied as amendments or immobilizers for remediation of soils contaminated with PTEs. The remediation efficiency and function of sepiolite on the remediation Pb and Cd-polluted farmland have been verified with field studies by Zhan et al. (2019). The pH value of soils increased by 1.67 after the application of sepiolite, whereas the CaCl₂-extractable concentration of Cd and the exchangeable concentration of Pb in soils decreased by 63.4% and 21.5%, respectively. The results indicated that immobilization mechanisms for the sepiolite may be complex, which not only involved with surface adsorption due to high specific surface but also involved with a high ion-exchange capacity of sepiolite (Zhan et al. 2019).

Sepiolite materials alone or in a combination with other materials such as limestone/bentonite/calcium carbonate can significantly cut down the content of Cd in brown rice, regardless of its application in a field study or pot trials (Sun et al. 2016a, b; Wu et al. 2016; Li et al. 2020). For instance, when sepiolite combined with low Cd-accumulating cultivar rice (*Oryza sativa* L.) in field experiment, the concentration of Cd in brown rice of low Cd-accumulating cultivar rice (*Oryza sativa* L.) from the control group was $0.72 \text{ mg} \cdot \text{kg}^{-1}$, while the concentration of Cd in brown rice of the cultivar rice from the experimental group was 0.18 mg/kg , which is lower than that of the maximum amount level proposed as “Maximum Levels of Pollutants in Foods” standard (GB 2762-2012) in the Chinese national standard and the Codex Alimentarius Commission (CAC 153-1995) requirement in the World Health Organization (WHO) (Liang et al. 2014).

However, there are differences in remediation effects of sepiolite-based amendment on soil polluted with Cd, Pb. For example, a 3-year in situ experiment was carried out in a paddy soil around a mine of southern Hunan, China (Wu et al. 2016). The combined amendment (LS, limestone and sepiolite) was applied in order of 0, 2, 4 and 8 g/kg (w/w) and rice were subsequently planted in 2012 (first season), 2013 (second season) and 2014 (third season). The results showed that the pH values of soils increased significantly in all three seasons and the ranking of enhancement was as follows: the first season > the second season > the third season. Experiment results indicated that the effect of the LS on reducing exchangeable Pb and Cd content of soil ranked as follows: the first season (97.6–99.8%) > the second season (80.7–97.7%) > the third season (32.6–97.7%) for Pb and the first season (88.3–98.9%) > the second season (28.3–88.0%) > the third season (8.3–71.4%) for Cd, respectively. It showed that the effects were persistent on soil exchangeable Cd concentration but gradually decreased with time on soil exchangeable Pb concentration, which implied that LS was more suitable for Cd than Pb contaminated soil in long-term remediation (Wu et al. 2016). Furthermore, a 2-year consecutive experiment was conducted on immobilization effect of sepiolite alone by Liang et al. (2016), which revealed that immobilization effect is maintained seen in the decrease in Cd content of the rice, 0.025 M HCl extractable Cd content of

paddy soil and the soil exchangeable Cd in the second year without any additional amendment.

Economic impacts and project risk

In China, contaminated land is identified by the government or local authority. Typically, several contamination treatment enterprises will compete via tender to secure a pollution treatment project. Once a firm is appointed, a feasibility report for soil remediation is required for the company to obtain final approval from the relevant authority. The specific details of the project are then decided; this involves a comparison of remediation technologies and methods. The project would be carried out after the approval is granted; then immediate or long-term monitoring of contamination treatment results would be arranged based on the design.

To use sepiolite for the treatment of land contamination by PTEs will increase the value or quality of the land and its potential possibility for reuse commercial purpose, create more space for residential development in the area, increasing employment in land remediation and redevelopment, which bring more local tax revenues (Song et al. 2019). With the development of society and new knowledge gained by individuals, the choice of methodology for soil remediation could be combined with positive interactions with neighborhoods, for example through community center development as part of the remediation, which can satisfy the social and economic needs of different stakeholders. This would support the harmonious integration of new solutions for contamination treatment within surrounding communities and lead to a more sustainable local economy (Dagenhart et al. 2006).

When remediation projects involved some related risk, the regular lifestyle might be impacted, affecting local traffic movement, environmental degradation during project implementation, or for workers' safety during the remediation period and even neighbor nuisance complaints. Recent studies of a farmland remediation project (Xu et al. 2019) showed that by adopting species sensitivity distribution models with joint probability curves, a different conclusion was reached related to ecological risk assessment results compared to that of the traditional methods. The conclusion revealed that Cr indicated the highest risk at 84.3% that presents an 84.3% probability for 5% of

the species to exceed NOEC/LOECs (maximum no-effect concentration and the lowest effective concentration) in Zhuzhou City (Xu et al. 2019). This study showed that the soil ecological risk of exposure to PTEs is underestimated by traditional methods and prioritizing ecosystem protection could be considered for PTEs contaminated land treatment (Xu et al. 2019). However, in the site where sepiolite-based material is applied, microbial community diversity and soil enzymatic activities showed that soil metabolic function is a certain degree recovered and sepiolite application is environmentally friendly (Sun et al. 2016b).

Ultimately sepiolite, its modified forms and components of the recovered waste provides remediation capability by immobilizing contaminants and restricting migration in the aqueous phase. This reduces food chain transfer and may be enhanced by combining with various additives. However, when considering the complex characteristics of the soil, the effectiveness and durability of sepiolite-based materials could be decreased with low pH (Chen et al. 2020), releasing pollution and making PTEs bio-accessible to crops and even increase the risk to humans. Constant changes in soil environment and soil quality will continue to present new challenges to application amount control of products and monitoring by environmental laboratories. The use of sepiolite as an additive for soil remediation may require additional testing that has not included within regulatory methods.

Summary, conclusion and future perspectives

This review highlighted the geographical distribution of sepiolite, its application for PTEs treatment in soil and land, assessing approaches to modification and composition on the application of sepiolite-based systems within site remediation and wastewater treatment. The considerable potential is highlighted for modified sepiolite or natural sepiolite to be applied in combination with other treatment methods. These should not be viewed in isolation, and an integrated assessment is needed to identify the future influence on the economic feasibility and if true environmental control is obtained.

A life cycle approach to sepiolite-based technologies needs to be developed. Commencing with natural

sepiolite mining and exploitation, the pretreatment, purification and modification coupled with the waste generated at each stage. Modified and activated sepiolites are products that are utilized as soil conditioners, soil amendments or pesticide carriers that reside in the soil and become integrated part of the soil. Waste materials from mining exploitation and purification could be potentially used alone or combined with other additives in the treatment of locally slightly contaminated soil or to be soil fertilizers.

Sepiolite applications can have economic advantages relative to other contamination treatment methods, such as smaller project costs, more environmentally friendly impact on contaminated land, and reduced project risks. The treatment period of sepiolite applications also compares favorably with other treatment methods, such as phytoremediation and constructed wetlands. Sepiolite application combined with other low PTEs accumulating plants has the potential for cost effective solutions. However, more investigation is needed to clarify the appropriate scale of land application, development of technology to meet that and the potential for regulation change to allow stabilization and immobilization of the environmental hazard.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

- Ahmaruzzaman, M. (2010). A review on the utilization of fly ash. *Progress in Energy and Combustion Science*, 36(3), 327–363. <https://doi.org/10.1016/j.peccs.2009.11.003>.
- Ahmaruzzaman, M., & Gupta, V. K. (2012). Application of coal fly ash in air quality management. *Industrial and Engineering Chemistry Research*, 51(47), 15299–15314. <https://doi.org/10.1021/ie301336m>.
- Ajao, V., Nam, K., Chatzopoulos, P., Spruijt, E., Bruning, H., Rijnaarts, H., et al. (2020). Regeneration and reuse of

- microbial extracellular polymers immobilised on a bed column for heavy metal recovery. *Water Research*, 171, 115472. <https://doi.org/10.1016/j.watres.2020.115472>.
- Al Othman, Z. A., Hashem, A., & Habila, M. A. (2011). Kinetic, equilibrium and thermodynamic studies of cadmium (II) adsorption by modified agricultural wastes. *Molecules*, 16(12), 10443–10456. <https://doi.org/10.3390/molecules161210443>.
- Álvarez-Ayuso, E., & García-Sánchez, A. (2003). Sepiolite as a feasible soil additive for the immobilization of cadmium and zinc. *The Science of the Total Environment*, 305, 1–12. [https://doi.org/10.1016/S0048-9697\(02\)00468-0](https://doi.org/10.1016/S0048-9697(02)00468-0).
- Bahabadi, F. N., Farpoor, M. H., & Mehri, M. H. (2017). Removal of Cd, Cu and Zn ions from aqueous solutions using natural and Fe modified sepiolite, zeolite and palygorskite clay minerals. *Water Science and Technology*, 75(2), 340–349. <https://doi.org/10.2166/wst.2016.522>.
- Beyli, P. T., Doğan, M., Alkan, M., Türkyilmaz, A., Turhan, Y., Demirbaş, Ö., et al. (2016a). Characterization, adsorption, and electrokinetic properties of modified sepiolite. *Desalination and Water Treatment*, 57(41), 19248–19261. <https://doi.org/10.1080/19443994.2015.1102773>.
- Beyli, P. T., Doğan, M., Alkan, M., Türkyilmaz, A., Turhan, Y., Demirbaş, Ö., et al. (2016b). Synthesis characterization electrokinetic and adsorption properties of an organo-modified adsorbent for selective. *Fresenius Environmental Bulletin*, 25(4), 991–1006.
- Bhattacharya, M., Maiti, M., & Bhowmick, A. K. (2009). Tailoring properties of styrene butadiene rubber nanocomposite by various nanofillers and their dispersion. *Polymer Engineering & Science*, 49(1), 81–98. <https://doi.org/10.1002/pen.21224>.
- Brion-roby, R., Gagnon, J., Deschênes, J., & Chabot, B. (2018). Investigation of fixed bed adsorption column operation parameters using a chitosan material for treatment of arsenate contaminated water. *Journal of Environmental Chemical Engineering*, 6(1), 505–511. <https://doi.org/10.1016/j.jece.2017.12.032>.
- Carretero, M. I., & Pozo, M. (2010). Clay and non-clay minerals in the pharmaceutical and cosmetic industries Part II. Active ingredients. *Applied Clay Science*, 47(3–4), 171–181. <https://doi.org/10.1016/j.clay.2009.10.016>.
- Chen, J., Hong, X., Xie, Q., Li, D., & Zhang, Q. (2014). Highly efficient removal of chromium (VI) from aqueous solution using polyaniline/sepiolite nanofibers. *Water Science and Technology*, 70(7), 1236–1243. <https://doi.org/10.2166/wst.2014.361>.
- Chen, D., Ye, X., Zhang, Q., Xiao, W., Ni, Z., Yang, L., et al. (2020). The effect of sepiolite application on rice Cd uptake—A two-year field study in Southern China. *Journal of Environmental Management*, 254, 109–788. <https://doi.org/10.1016/j.jenvman.2019.109788>.
- China Geological Survey. (2015). *China arable land geochemistry survey report* (pp. 1–11). Beijing: Ministry of Land and Resources of the People's Republic of China. (in Chinese).
- Dagenhart, R., Leigh, N. G., & Skach, J. (2006). Brownfields and urban design: Learning from Atlantic Station. *WIT Transactions on Ecology and the Environment*, 94, 185–194. <https://doi.org/10.2495/BF060181>.
- Donat, R. (2009). The removal of uranium (VI) from aqueous solutions onto natural sepiolite. *The Journal of Chemical Thermodynamics*, 41(7), 829–835. <https://doi.org/10.1016/j.jct.2009.01.009>.
- DPT (State Planning Organization). (2001). *Mining. 8th Five-Year Development Plan* (pp. 1–32). Ankara: Republic of Turkey, State Plan Organization.
- Eberl, D. D., Jones, B. F., & Khoury, H. N. (1982). Mixed-layer kerolite/stevensite from the Amargosa desert, Nevada. *Clays and Clay Minerals*, 30(5), 321–326. <https://doi.org/10.1346/CCMN.1982.0300501>.
- Ece, Ö. I., & Çoban, F. (1994). Geology, occurrence, and genesis of Eskişehir sepiolites, Turkey. *Clays and Clay Minerals*, 42(1), 81–92. <https://doi.org/10.1346/CCMN.1994.0420111>.
- Fu, R., Yang, Y., Xu, Z., Zhang, X., Guo, X., & Bi, D. (2015). The removal of chromium (VI) and lead (II) from groundwater using sepiolite-supported nanoscale zero-valent iron (S-NZVI). *Chemosphere*, 138, 726–734. <https://doi.org/10.1016/j.chemosphere.2015.07.051>.
- Galan, E., & Castillo, A. (1984). Sepiolite-palygorskite in Spanish Tertiary basins: Genetical patterns in continental environments. *Developments in Sedimentology*, 37, 87–124. [https://doi.org/10.1016/S0070-4571\(08\)70031-1](https://doi.org/10.1016/S0070-4571(08)70031-1).
- Galán, E., & Pozo, M. (2015). The mineralogy, geology, and main occurrences of sepiolite and palygorskite clays. In P. Pasbakhsh & G. J. Churchman (Eds.), *Natural Mineral Nanotubes* (pp. 117–130). New York, USA: Apple Academic Press. <https://doi.org/10.1201/b18107>.
- GB 2762-2012 (2012). National food safety standard maximum levels of contaminants in foods. (in Chinese).
- Guneser, B. A., & Yilmaz, E. (2017). Bioactives, aromatics and sensory properties of cold-pressed and hexane-extracted lemon (*Citrus limon* L.) seed oils. *Journal of the American Oil Chemists' Society*, 94(5), 723–731. <https://doi.org/10.1007/s11746-017-2977-z>.
- Habish, A. J., Lazarević, S., Janković-Častvan, I., Jokić, B., Kovač, J., Rogan, J., et al. (2017). Nanoscale zerovalent iron (nZVI) supported by natural and acid-activated sepiolites: The effect of the nZVI/support ratio on the composite properties and Cd²⁺ adsorption. *Environmental Science and Pollution Research*, 24(1), 628–643. <https://doi.org/10.1007/s11356-016-7802-y>.
- Hadi, P., To, M. H., Hui, C. W., Lin, C. S. K., & McKay, G. (2015). Aqueous mercury adsorption by activated carbons. *Water Research*, 73, 37–55. <https://doi.org/10.1016/j.watres.2015.01.018>.
- Hay, R. L., & Stoessell, R. K. (1984). Sepiolite in the Amboseli Basin of Kenya: A new interpretation. *Developments in Sedimentology*, 37, 125–136. [https://doi.org/10.1016/S0070-4571\(08\)70032-3](https://doi.org/10.1016/S0070-4571(08)70032-3).
- Huang, J. (2017). *Preparing sepiolite modified material comprises microwave reaction of a mixture of sepiolite and kaolin with mixed ferric salt of cellulose, ferric chloride and ferrous chloride*. P.R.C. Patent CN107262049 A, 20 October 2017 (in Chinese).
- Huang, X., Lu, Q., Hao, H., Wei, Q., Shi, B., Yu, J., et al. (2019). Evaluation of the treatability of various odor compounds by powdered activated carbon. *Water Research*, 156, 414–424. <https://doi.org/10.1016/j.watres.2019.03.043>.

- Hüseyin, Y., & Bozkaya, Ö. (2011). Sepiolite—palygorskite occurrences in Turkey. *Developments in clay science* (pp. 175–200). Amsterdam: Elsevier. <https://doi.org/10.1016/b978-0-444-53607-5.00007-4>.
- IGGCMBMI (Institute of Geology of Geological Company of Ministry of Building Materials Industry). (1980). Sepiolite asbestos of Lushi county of Henan Province and Guangji county of Hubei Province. *Journal of the Chinese Ceramic Society*, 8(2), 194–201. (in Chinese).
- Ihsanullah Abbas, A., Al-Amer, A. M., Laoui, T., Al-Marri, M. J., Nasser, M. S., et al. (2016). Heavy metal removal from aqueous solution by advanced carbon nanotubes: Critical review of adsorption applications. *Separation and Purification Technology*, 157, 141–161. <https://doi.org/10.1016/j.seppur.2015.11.039>.
- İrkeç, T., & Ünlü, T. (1993). An example to sepiolite formation in volcanic belts by hydrothermal alteration: Kibriscik (Bolu) sepiolite occurrence. *Bulletin of the Mineral Research and Exploration*, 115, 49–68.
- Isari, A. A., Payan, A., Fattahi, M., Jorfi, S., & Kakavandi, B. (2018). Photocatalytic degradation of rhodamine B and real textile wastewater using Fe-doped TiO₂/rGO: Characterization and feasibility, mechanism and pathway studies. *Applied Surface Science*, 462, 549–564. <https://doi.org/10.1016/j.apsusc.2018.08.133>.
- Jiang, Y., Luo, Y., & Gu, X. (2017). In situ immobilization of cadmium in soil and persistence study. *Journal of Nanjing University (Natural Sciences)*, 53(2), 265–274. <https://doi.org/10.13232/j.cnki.jnju.2017.02.007>. (in Chinese).
- Joseph, J., & Angel, P. R. A. (2020). Influence of fly ash on sepiolite. *International Journal of Research in Engineering, Science and Management*, 3(2), 379–381.
- Kalpakli, Y., & Cansev, H. (2018). Strutural effect of cationic surfactant on heavy metal removal capacity of raw sepiolite. *Indian Journal of Chemical Technology*, 25(1), 61–67.
- Khoury, H. N., Eberl, D. D., & Jones, B. F. (1982). Origin of magnesium clays from the Amargosa Desert, Nevada. *Clays and Clay Minerals*, 30(5), 327–336. <https://doi.org/10.1346/CCMN.1982.0300502>.
- Kocaoba, S. (2009). Adsorption of Cd (II), Cr(III) and Mn(II) on natural sepiolite. *Desalination*, 244(1–3), 24–30. <https://doi.org/10.1016/j.desal.2008.04.033>.
- Komkiene, J., & Baltreinaite, E. (2016). Biochar as adsorbent for removal of heavy metal ions [Cadmium (II), Copper (II), Lead (II), Zinc (II)] from aqueous phase. *International Journal of Environmental Science and Technology*, 13, 471–482. <https://doi.org/10.1007/s13762-015-0873-3>.
- Kumar, K. D., Tsou, A. H., & Bhowmick, A. K. (2010). Unique tackification behavior of needle-like sepiolite nanoclay in brominated isobutylene-co-*p*-methylstyrene (BIMS) rubber. *Macromolecules*, 43(9), 4184–4193. <https://doi.org/10.1021/ma100472r>.
- Lazarević, S., Janković-Častvan, I., Jovanović, D., Milonjić, S., Janačković, D., & Petrović, R. (2007). Adsorption of Pb²⁺, Cd²⁺ and Sr²⁺ ions onto natural and acid-activated sepiolites. *Applied Clay Science*, 37(1–2), 47–57. <https://doi.org/10.1016/j.clay.2006.11.008>.
- Li, Q., Zhang, P., Zhou, H., Peng, P., Zhang, K., Mei, J., et al. (2020). Effects of Cd-resistant bacteria and calcium carbonate and sepiolite on Cd availability in contaminated paddy soil and on Cd accumulation in brown rice grains. *Ecotoxicology and Environmental Safety*, 195, 110–492. <https://doi.org/10.1016/j.ecoenv.2020.110492>.
- Liang, K. (2008). *The mineralogy research of the sepiolite and its application in environment conservation (Doctoral dissertation)*. Changsha, China: Central South University. (in Chinese).
- Liang, X., Han, J., Xu, Y., Sun, Y., Wang, L., & Tan, X. (2014). In situ field-scale remediation of Cd polluted paddy soil using sepiolite and palygorskite. *Geoderma*, 235–236, 9–18. <https://doi.org/10.1016/j.geoderma.2014.06.029>.
- Liang, X., Qin, X., Huang, Q., Huang, R., Yin, X., Wang, L., et al. (2017). Mercapto functionalized sepiolite: A novel and efficient immobilization agent for cadmium polluted soil. *The Royal Society of Chemistry Advances*, 7, 39955–39961. <https://doi.org/10.1039/C7RA07893E>.
- Liang, X., Xu, Y., Xu, Y., Wang, P., Wang, L., Sun, Y., et al. (2016). Two-year stability of immobilization effect of sepiolite on Cd contaminants in paddy soil. *Environmental Science and Pollution Research*, 23, 12922–12931. <https://doi.org/10.1007/s11356-016-6466-y>.
- Lin, C., Luo, W., Luo, T., Zhou, Q., Li, H., & Jing, L. (2018). A study on adsorption of Cr(VI) by modified rice straw: Characteristics, performances and mechanism. *Journal of Cleaner Production*, 196, 626–634. <https://doi.org/10.1016/j.jclepro.2018.05.279>.
- Liu, X., Liu, X., Cao, J., Zeng, X., Gao, M., & Wei, B. (2018). Preparation of sepiolite-loaded nano zero-valent iron material used for removing e.g. copper in aquaculture water, involves adding ferrous sulfate heptahydrate to suspension, stirring, dripping weakly basic solution, enriching with magnet. P.R.C. Patent CN108187609 A, 22 June 2018 (in Chinese).
- Liu, G., & Xu, T. (1984). Sepiolite in olivine-basalt from Duan, Guangxi. *Bulletin Yichang Institute of Geology and Mineral Resources, Chinese Academy of Geological Sciences*, 8, 63–69. (in Chinese).
- Lopez Galindo, A., Torres Ruiz, J., & Gonzalez Lopez, J. M. (1996). Mineral quantification in sepiolite-palygorskite deposits using X-ray diffraction and chemical data. *Clay Minerals*, 31(2), 217–224. <https://doi.org/10.1180/claymin.1996.031.2.07>.
- Mallik, D., & Chaudhuri, S. K. (1999). Air oxidation of aqueous sodium sulfide solutions with coal fly ash. *Water Research*, 33(2), 585–590. [https://doi.org/10.1016/S0043-1354\(98\)00205-X](https://doi.org/10.1016/S0043-1354(98)00205-X).
- Marjanović, V., Lazarević, S., Janković-Častvan, I., Jokić, B., Janačković, D., & Petrović, R. (2013). Adsorption of chromium (VI) from aqueous solutions onto amine-functionalized natural and acid-activated sepiolites. *Applied Clay Science*, 80–81, 202–210. <https://doi.org/10.1016/j.clay.2013.04.008>.
- Martin Vivaldi, J. L., & Robertson, R. H. S. (1971). Palygorskite and sepiolite (the hormites). *Electron-optical investigation of clays, monograph (Mineralogical Society (Great Britain))* (3rd ed., pp. 255–275). London: Mineralogical Society (Clay Minerals Group).
- Mayayo, M. J., Torres-Ruiz, J., González-López, J. M., López-Galindo, A., & Bauluz, B. (1998). Mineralogical and chemical characterization of the sepiolite/Mg-smectite deposit at Mara (Calatayud basin, Spain). *European*

- Journal of Mineralogy*, 10(2), 367–384. <https://doi.org/10.1127/ejm/10/2/0367>.
- Ochedi, F. O., Liu, Y., & Hussain, A. (2020). A review on coal fly ash-based adsorbents for mercury and arsenic removal. *Journal of Cleaner Production*, 267, 122143. <https://doi.org/10.1016/j.jclepro.2020.122143>.
- Öztürk, N., & Kavak, D. (2004). Boron removal from aqueous solutions by adsorption on waste sepiolite and activated waste sepiolite using full factorial design. *Adsorption*, 10(3), 245–257. <https://doi.org/10.1023/B:ADSO.0000046361.62180.c6>.
- Padilla-Ortega, E., Leyva-Ramos, R., & Flores-Cano, J. V. (2013). Binary adsorption of heavy metals from aqueous solution onto natural clays. *Chemical Engineering Journal*, 225, 535–546. <https://doi.org/10.1016/j.cej.2013.04.011>.
- Peng, L. (2017). Study of sepiolite in Yonghe, Liuyang. *Hunan Province. Resource Information and Engineering*, 32(3), 38–41. (in Chinese).
- Pozo, M., Calvo, J. P., Pozo, E., & Moreno, Á. (2014). Genetic constraints on crystallinity, thermal behaviour and surface area of sepiolite from the Cerro de los Batallones deposit (Madrid Basin, Spain). *Applied Clay Science*, 91–92, 30–45. <https://doi.org/10.1016/j.clay.2014.02.005>.
- Rakowska, M. I., Kupryianchyk, D., Koelmans, A. A., Grotenhuis, T., & Rijnaarts, H. H. M. (2014). Equilibrium and kinetic modeling of contaminant immobilization by activated carbon amended to sediments in the field. *Water Research*, 67, 96–104. <https://doi.org/10.1016/j.watres.2014.07.046>.
- Rytwo, G. (2014). *Method for pretreatment of wastewater and recreational water with nanocomposites*. U.S. Patent 9546102, 13 February 2014.
- Rytwo, G. (2017). Hybrid clay-polymer nanocomposites for the clarification of water and effluents. *Recent Patents on Nanotechnology*, 11(3), 181–193. <https://doi.org/10.2174/1872210511666170125125928>.
- Sajjad, M., Khan, S., Baig, S. A., Munir, S., Naz, A., Ahmad, S. S., et al. (2017). Removal of potentially toxic elements from aqueous solutions and industrial wastewater using activated carbon. *Water Science and Technology*, 75(11), 2571–2579. <https://doi.org/10.2166/wst.2017.130>.
- Shahamirifard, S. A. R., Ghaedi, M., Rahimi, M. R., Hajati, S., Montazerzohori, M., & Soylak, M. (2016). Simultaneous extraction and preconcentration of Cu^{2+} , Ni^{2+} and Zn^{2+} ions using Ag nanoparticle-loaded activated carbon: Response surface methodology. *Advanced Powder Technology*, 27(2), 426–435. <https://doi.org/10.1016/j.appt.2016.01.023>.
- Shotyk, W., Goodsite, M. E. E., Roos-Barracough, F., Frei, R., Heinemeier, J., Asmund, G., et al. (2003). Anthropogenic contributions to atmospheric Hg, Pb and As accumulation recorded by peat cores from southern Greenland and Denmark dated using the ^{14}C “bomb pulse curve”. *Geochimica et Cosmochimica Acta*, 67(21), 3991–4011. [https://doi.org/10.1016/S0016-7037\(03\)00409-5](https://doi.org/10.1016/S0016-7037(03)00409-5).
- Singer, A., Stahr, K., & Zarei, M. (1998). Characteristics and origin of sepiolite (Meerschaum) from Central Somalia. *Clay Minerals*, 33(2), 349–362. <https://doi.org/10.1180/000985598545525>.
- Song, Y., Kirkwood, N., Maksimović, Č., Zhen, X., O'Connor, D., Jin, Y., et al. (2019). Nature based solutions for contaminated land remediation and brownfield redevelopment in cities: A review. *Science of the Total Environment*, 663, 568–579. <https://doi.org/10.1016/j.scitotenv.2019.01.347>.
- Söregård, M., Kleja, D. B., & Ahrens, L. (2019). Stabilization and solidification remediation of soil contaminated with poly- and perfluoroalkyl substances (PFASs). *Journal of Hazardous Materials*, 367, 639–646. <https://doi.org/10.1016/j.jhazmat.2019.01.005>.
- Stoessel, R. K., & Hay, R. L. (1978). The geochemical origin of sepiolite and kerolite at Amboseli, Kenya. *Contributions to Mineralogy and Petrology*, 65(3), 255–267. <https://doi.org/10.1007/BF00375511>.
- Sun, Y., Sun, G., Xu, Y., Liu, W., Liang, X., & Wang, L. (2016a). Evaluation of the effectiveness of sepiolite, bentonite, and phosphate amendments on the stabilization remediation of cadmium-contaminated soils. *Journal of Environmental Management*, 166, 204–210. <https://doi.org/10.1016/j.jenvman.2015.10.017>.
- Sun, Y., Xu, Y., Xu, Y., Wang, L., Liang, X., & Li, Y. (2016b). Reliability and stability of immobilization remediation of Cd polluted soils using sepiolite under pot and field trials. *Environmental Pollution*, 208, 739–746. <https://doi.org/10.1016/j.envpol.2015.10.054>.
- Taimur, S., Hassan, M. I., & Yasin, T. (2017). Removal of copper using novel amidoxime based chelating nanohybrid adsorbent. *European Polymer Journal*, 95, 93–104. <https://doi.org/10.1016/j.eurpolymj.2017.08.004>.
- Tartaglione, G., Tabuani, D., & Camino, G. (2008). PP and PBT composites filled with sepiolite: Morphology and thermal behaviour. *Composites Science and Technology*, 68(2), 451–460. <https://doi.org/10.1016/j.compscitech.2007.06.023>.
- Terzano, R., Spagnuolo, M., Medici, L., Vekemans, B., Vincze, L., Janssens, K., et al. (2005). Copper stabilization by zeolite synthesis in polluted soils treated with coal fly ash. *Environmental Science and Technology*, 39(16), 6280–6287. <https://doi.org/10.1021/es050079d>.
- Tofighy, M. A., & Mohammadi, T. (2015). Copper ions removal from water using functionalized carbon nanotubes-mullite composite as adsorbent. *Materials Research Bulletin*, 68, 54–59. <https://doi.org/10.1016/j.materresbull.2015.03.017>.
- Twaróg, A., Mamak, M., Sechman, H., Rusiniak, P., Kasprzak, E., & Stanek, K. (2020). Impact of the landfill of ashes from the smelter on the soil environment: Case study from the South Poland, Europe. *Environmental Geochemistry and Health*, 42, 1453–1467. <https://doi.org/10.1007/s10653-019-00435-y>.
- Uddin, M. K. (2017). A review on the adsorption of heavy metals by clay minerals, with special focus on the past decade. *Chemical Engineering Journal*, 308, 438–462. <https://doi.org/10.1016/j.cej.2016.09.029>.
- Vassilev, S. (1992). Phase mineralogy studies of solid waste products from coal burning at some Bulgarian thermoelectric power plants. *Fuel*, 71(6), 625–633. [https://doi.org/10.1016/0016-2361\(92\)90164-J](https://doi.org/10.1016/0016-2361(92)90164-J).
- Wang, X., Chen, M., Zhang, J., Liu, G., Li, X., & Yu, G. (2017). Heavy metal contaminated soil repair material for paddy fields, comprises modified zeolite, modified sepiolite

- tailings, nano iron powder, hyposulfite and quicklime. P.R.C. Patent CN106903150 A, 30 June 2017 (**in Chinese**).
- Wang, F., Liang, J., Tang, Q., Wang, N., & Li, L. (2009). Preparation and properties of thermal insulation latex paint for exterior wall based on defibred sepiolite and hollow glass microspheres. *Advanced Materials Research*, 58, 103–108. <https://doi.org/10.4028/www.scientific.net/AMR.58.103>.
- Wang, Z., Liao, L., Hursthouse, A., Song, N., & Ren, B. (2018). Sepiolite-based adsorbents for the removal of potentially toxic elements from water: A strategic review for the case of environmental contamination in Hunan, China. *International Journal of Environmental Research and Public Health*, 15(8), 1653. <https://doi.org/10.3390/ijerph15081653>.
- Wang, N., Sun, X., Zhao, Q., Yang, Y., & Wang, P. (2020). Leachability and adverse effects of coal fly ash: A review. *Journal of Hazardous Materials journal*, 396, 122725. <https://doi.org/10.1016/j.jhazmat.2020.122725>.
- Wang, Y., Tang, X., & Wang, H. (2015). Characteristics and mechanisms of Ni (II) removal from aqueous solution by Chinese loess. *Journal of Central South University*, 22, 4184–4192. <https://doi.org/10.1007/s11771-015-2966-z>.
- Wu, Y. J., Zhou, H., Zou, Z. J., Zhu, W., Yang, W. T., Peng, P. Q., et al. (2016). A three-year in situ study on the persistence of a combined amendment (limestone + sepiolite) for remedying paddy soil polluted with heavy metals. *Ecotoxicology and Environmental Safety*, 130, 163–170. <https://doi.org/10.1016/j.ecoenv.2016.04.018>.
- Xie, X., Fang, Z., Liao, M., Huang, Y., & Huang, X. (2018). Potential to ensure safe production from rice fields polluted with heavy cadmium by combining a rice variety with low cadmium accumulation, humic acid, and sepiolite. *Environmental Science*, 39(9), 4348–4358. <https://doi.org/10.13227/j.hjxx.201801030>. (**in Chinese**).
- Xu, Y., Liang, X., Xu, Y., Qin, X., Huang, Q., Wang, L., et al. (2017). Remediation of heavy metal-polluted agricultural soils using clay minerals: A review. *Pedosphere*, 27(2), 193–204. [https://doi.org/10.1016/S1002-0160\(17\)60310-2](https://doi.org/10.1016/S1002-0160(17)60310-2).
- Xu, X., Wang, T., Sun, M., Bai, Y., Fu, C., Zhang, L., et al. (2019). Management principles for heavy metal contaminated farmland based on ecological risk—A case study in the pilot area of Hunan province, China. *Science of the Total Environment*, 684, 537–547. <https://doi.org/10.1016/j.scitotenv.2019.05.015>.
- Yalçın, H., & Bozkaya, Ö. (1995). Sepiolite-palygorskite from the Hekimhan region (Turkey). *Clays and Clay Minerals*, 43(6), 705–717. <https://doi.org/10.1346/CCMN.1995.0430607>.
- Yalçın, H., & Bozkaya, Ö. (2011). Sepiolite-palygorskite occurrences in Turkey. *Developments in Clay Science* (Vol. 3, pp. 175–200). Amsterdam: Elsevier. <https://doi.org/10.1016/b978-0-444-53607-5.00007-4>.
- Yi, Y. (2003). Foreign sepiolite production and market. *Industrial Minerals & Processing*, 3, 43. (**in Chinese**).
- Yin, H., Yun, Y., Zhang, Y., & Fan, C. (2011). Phosphate removal from wastewaters by a naturally occurring, calcium-rich sepiolite. *Journal of Hazardous Materials*, 198, 362–369. <https://doi.org/10.1016/j.jhazmat.2011.10.072>.
- Yu, S., Zhai, L., Zhong, S., Qiu, Y., Cheng, L., & Ren, X. (2016). Synthesis and structural characterization of magnetite/sepiolite composite and its sorptive properties for Co (II) and Cd (II). *Journal of the Taiwan Institute of Chemical Engineers*, 59, 221–228. <https://doi.org/10.1016/j.jtice.2015.07.025>.
- Zhan, F., Zeng, W., Yuan, X., Li, B., Li, T., Zu, Y., et al. (2019). Field experiment on the effects of sepiolite and biochar on the remediation of Cd- and Pb-polluted farmlands around a Pb–Zn mine in Yunnan Province, China. *Environmental Science and Pollution Research*, 26, 7743–7751. <https://doi.org/10.1007/s11356-018-04079-w>.
- Zhang, R., & Yang, Z. (1986). Occurrence and distribution of sepiolite in China. *Bulletin of the Chinese Academy of Geological Sciences*, 15, 45–51. (**in Chinese**).
- Zhang, W., Yuan, Y., & Zhong, C. (2018). *Treating heavy metal copper in aquaculture wastewater comprises e.g. pre-processing aquaculture wastewater, then adding pre-treated wastewater into adsorption reaction tank and adsorbing heavy metal copper*. P.R.C. Patent CN 107686146 A, 13 February 2018 (**in Chinese**).
- Zhao, G., Li, J., Ren, X., Chen, C., & Wang, X. (2011). Few-layered graphene oxide nanosheets as superior sorbents for heavy metal ion pollution management. *Environmental Science and Technology*, 45(24), 10454–10462. <https://doi.org/10.1021/es203439v>.

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.