



## Correction to: Physicochemical Properties of Sb, Sn, Zn, and Sb–Sn System

Tomasz Gancarz<sup>1</sup> · Władysław Gąsior<sup>1</sup> · Hani Henein<sup>2</sup>

Published online: 26 April 2019

© The Author(s) 2019

### Correction to: Int J Thermophys (2013) 34:250–266 <https://doi.org/10.1007/s10765-013-1407-1>

The original version of the article unfortunately contained an error in Table 3. Value of ‘E’ for the material ‘Sb’ 16938.1 (J·mol<sup>-1</sup>) should be replaced with 17229.1 (J·mol<sup>-1</sup>). Revised version of Table 3 is given below.

**Table 3** Parameters of Arrhenius equation  $Ae^{E/(RT)}$ , with errors (mPa·s). Viscosity for Sb, Sn, Zn, and Sb–Sn alloys

Materials	$\eta = A e^{E/(RT)}$ (mPa·s)			
	$A$	$\delta A$	$E$	$\delta E$
Sn	0.315	0.029	8488.6	57.1
SnSb10	0.280	0.012	9334.1	61.4
SnSb20	0.272	0.017	9710.8	87.8
SnSb25	0.262	0.020	10301.0	119.5
SnSb50	0.259	0.017	11619.6	115.0
SnSb75	0.171	0.017	15480.7	263.4
Sb	0.160	0.014	17229.1	151.8
Zn	0.394	0.031	13497.3	124.6

**Publisher's Note** Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

The original article can be found online at <https://doi.org/10.1007/s10765-013-1407-1>.

✉ Tomasz Gancarz  
nmgancar@imim.pan.krakow.pl

<sup>1</sup> Institute of Metallurgy and Materials Science, Polish Academy of Science, Kraków, Poland

<sup>2</sup> Department of Chemical and Materials Engineering, University of Alberta, Edmonton, AB, Canada