Correction to: Transparent conductive organic-inorganic hybrid composites based on Ag nanowires

Katharina Lang¹ · Matthias Klein¹ · Gerhard Domann¹ · Peer Löbmann¹

Published online: 25 July 2020

© Springer Science+Business Media, LLC, part of Springer Nature 2020

Correction to: Journal of Sol-Gel Science and Technology
<https://doi.org/10.1007/s10971-020-05330-y>

The author would like to correct the errors in the publication of the original article. The corrected details are given below.

(a). The units for specific resistance has been corrected as “[Ω cm]” in line 3 of Table 1.

(b). The units for specific resistance has been corrected as “[Ω cm]” in line 6 of 17th paragraph of section “Results and discussion”.

The above data show excellent results regarding processing parameters and optoelectronic properties. While TCOs require high posttreatment temperatures exceeding 300 °C the silver nanowire composites can be cured and activated at lower temperatures. Furthermore, a comparison of the specific resistances ($\sim 1 \times 10^{-4} \Omega \text{ cm}$) with the commonly used conductive oxides illustrates good electrical properties for technical performances and are in no way inferior to them [37].

The original article has been corrected.

Table 1 Properties of different AgNW composite films

Matrix system	Silicone	Nonpolar hybrid	Polar hybrid
Treatment temperature [°C]	220	230	250
Film thickness [μm]	330	290	225
Sheet resistance [Ω□]	4.58	4.84	7.23
Specific resistance [Ω cm]	1.51E−04	1.40E−04	1.63E−04
Transmittance at 550 nm [%]	79	76	63

The original article can be found online at <https://doi.org/10.1007/s10971-020-05330-y>.

✉ Peer Löbmann
peer.loebmann@isc.fraunhofer.de

¹ Fraunhofer-Institut für Silicatforschung, Neunerplatz 2, 97082 Würzburg, Germany