Correction to: Multistage thermal decomposition in films of cadmium chloride-doped PVA–PVP polymeric blend

Basavarajeshwari M. Baraker¹ · Blaise Lobo¹

Published online: 12 May 2018
 © Akadémiai Kiadó, Budapest, Hungary 2018

Correction to: Journal of Thermal Analysis and Calorimetry
<https://doi.org/10.1007/s10973-018-7289-5>

There is an error in position of a multiplication factor in Table 2 of the article. The multiplication factor should come directly under the symbol A . The corrected table is given as follows (Table 2).

Table 2 Estimated kinetic parameters from the FWO, KAS and Kissinger models at four thermal decomposition stages

α	Second stage		Third stage		Fourth stage		Fifth stage	
	$E_a/\text{kJ mol}^{-1}$	A/min^{-1}	$E_a/\text{kJ mol}^{-1}$	A/min^{-1}	$E_a/\text{kJ mol}^{-1}$	A/min^{-1}	$E_a/\text{kJ mol}^{-1}$	A/min^{-1}
FWO model								
		$\times 10^4$		$\times 10^{14}$		$\times 10^8$		$\times 10^7$
0.1	59.58 ± 0.17	3.01	216.68 ± 0.11	27.06	151.46 ± 0.07	2.648	87.83 ± 0.05	3.029
0.3	69.31 ± 0.16	43.88	206.81 ± 0.07	10.03	162.29 ± 0.05	18.492	91.57 ± 0.07	15.96
0.5	79.17 ± 0.15	162.1	196.26 ± 0.04	1.969	187.54 ± 0.05	535.55	93.90 ± 0.10	34.94
0.7	86.11 ± 0.14	1284	188.19 ± 0.02	0.524	203.09 ± 0.05	2950.3	95.04 ± 0.15	50.07
0.9	88.15 ± 0.16	1608	179.40 ± 0.03	0.112	210.83 ± 0.09	4528.1	95.07 ± 0.19	52.58
Average	76.47	620.2	197.46	7.94	183.04	1607.0	92.68	31.32
KAS model								
		$\times 10^4$		$\times 10^{14}$		$\times 10^8$		$\times 10^7$
0.1	53.19 ± 0.19	0.640	216.40 ± 0.12	24.86	139.68 ± 0.09	0.3254	83.31 ± 0.05	0.700
0.3	63.15 ± 0.18	5.261	205.92 ± 0.07	8.234	150.70 ± 0.07	1.7032	87.11 ± 0.08	3.905
0.5	73.28 ± 0.17	52.99	194.73 ± 0.04	1.429	176.29 ± 0.04	53.622	89.43 ± 0.11	8.770
0.7	80.34 ± 0.16	220.7	186.16 ± 0.02	0.344	192.15 ± 0.06	557.26	90.52 ± 0.15	12.56
0.9	82.24 ± 0.18	290.4	176.81 ± 0.03	0.065	200.55 ± 0.11	985.13	90.44 ± 0.19	12.87
Average	70.44	114.0	196.00	6.986	171.88	319.61	88.16	7.76
Kissinger model								
		$\times 10^{14}$		$\times 10^{10}$		$\times 10^4$		$\times 10^7$
	165.12 ± 0.04	3.22	175.26 ± 0.019	2.000	78.27 ± 0.303	1.19	78.52 ± 0.088	3.36

The symbols E_a and A are used for activation energy and pre-exponential factor, respectively, whereas E_x and A_x are used (for denoting activation energy and pre-exponential factor) in FWO, KAS and Kissinger equations, respectively

The original article can be found online at <https://doi.org/10.1007/s10973-018-7289-5>.

✉ Blaise Lobo
 blaise.loblo@gmail.com

¹ Department of Physics, Karnatak University's Karnatak Science College, Dharwad, Karnataka 580001, India