Stoichiometry and disorder influence over electronic structure in nanostructured VO_x films

A. D'Elia · S. J. Rezvani · N. Zema · F. Zuccaro ·
M. Fanetti · B. Belec · B. W. Li · C. W. Zou ·
C. Spezzani · M. Sacchi · A. Marcelli · M. Coreno

Received: 28 July 2020 / Accepted: 21 December 2020 / Published online: 30 January 2021
© The Author(s) 2021

Abstract We present and discuss the role of nanoparticles size and stoichiometry over the local atomic environment of nanostructured VO_x films. The samples have been characterized in situ using X-ray absorption near-edge structure (XANES) spectroscopy identifying the stoichiometry-dependent fingerprints of disordered atomic arrangement. In vanadium oxides, the ligand atoms arrange according to a distorted octahedral geometry depending on the oxidation state, e.g. trigonal distortion in V₂O₃ and tetragonal distortion in bulk VO₂. We demonstrate, taking VO₂ as a case study, that as a

consequence of the nanometric size of the nanoparticles, the original ligands symmetry of the bulk is broken resulting in the coexistence of a continuum of distorted atomic conformations. The resulting modulation of the electronic structure of the nanostructured VO_x as a function of the oxygen content reveals a stoichiometry-dependent increase of disorder in the ligands matrix. This work shows the possibility to produce VO_x nanostructured films accessing new disordered phases and provides a unique tool to investigate the complex matter.

A. D'Elia (✉)
II Physikalisches Institut, Universität zu Köln, Zùlpicher StraÙe
77, 50937 Köln, Germany
e-mail: delia@ph2.uni-koeln.de

A. D'Elia · S. J. Rezvani
Laboratorio TASC, IOM-CNR, Basovizza SS-14, km 163.5,
34149 Trieste, Italy

S. J. Rezvani · A. Marcelli
Laboratori Nazionale di Frascati, INFN, Via Enrico Fermi 54,
Frascati, Italy

N. Zema
ISM-CNR, Istituto Struttura della Materia, Area della Ricerca di
Tor Vergata, Via del Fosso del Cavaliere, Rome, Italy

F. Zuccaro · A. Marcelli · M. Coreno
ISM-CNR, Istituto Struttura della Materia, LD2 Unit, Basovizza
Area Science Park, 34149 Trieste, Italy

M. Fanetti · B. Belec
Materials Research Laboratory, University of Nova Gorica,
Vipavska 11c, SI-5270 AjdovÙina, Slovenia

B. W. Li · C. W. Zou
National Synchrotron Radiation Laboratory, University of Science
and Technology of China, Hefei 230029, People's Republic of
China

C. Spezzani
Elettra-Sincrotrone Trieste, I-34149 Basovizza, Italy

M. Sacchi
Synchrotron SOLEIL, L'Orme des Merisiers, Saint-Aubin, BP 48,
91192 Gif-sur-Yvette Cedex, France

M. Sacchi
Institut des NanoSciences de Paris, Sorbonne UniversitÙ, CNRS
UMR 7588, 4 Place Jussieu, 75005 Paris, France

A. Marcelli
Rome International Centre for Material Science Superstripes,
RICMASS, Via dei Sabelli 119A, 00185 Rome, Italy

Keywords Disordered materials · Nanostructured vanadium oxides · Distorted ligand environment · XANES · VO_x

Introduction

Vanadium oxides have been studied extensively due to their various possible stoichiometric phases characterized by different oxidation states, from V^{+2} to V^{+5} as well as mixed-valence oxides (Magneli and Wadsley series) (Schwingenschlögl and Eyert 2004; Chen et al. 2019) which provides an equally large variety of electronic and physico-chemical properties. For instance, V_2O_5 and V_6O_{13} have been investigated for possible applications as cathode material in Li-ion batteries (Chan et al. 2007; Xu et al. 2016; Shi et al. 2018; Xiao and Zhang 2018; Tan et al. 2018). Vanadium oxides also bear the seed of a strong electronic correlation. VO_2 , V_2O_3 and the mixed-valence $\text{V}_n\text{O}_{2n-1}$ ($n = 3-6, 8$ and 9) systems all exhibit first-order metal-insulator transitions (MIT) characterized by a nanoscale phase separation (Marcelli et al. 2017; McLeod et al. 2017), which can be exploited in the emerging field of Mottronics (Brahlek et al. 2017). Nevertheless, tuning the properties of vanadium oxides during the early synthesis stages is a difficult task, due to the complex interplay among stoichiometry, lattice order and size of the sample.

The control of the lattice order is one of the most used tools to modulate the electronic structure of matter (Fan et al. 2014; Pinto et al. 2018a; Rezvani et al. 2016a; Rezvani et al. 2018; D'Elia et al. 2020a). However, while methods to slightly modify the inter-atomic distances, e.g. application of epitaxial strain, are widely used, the development of a technique able to produce disordered samples with controllable stoichiometry is in its early stage despite its potential.

It has been shown that the amorphous VO_x exhibits superior intercalation properties with respect to the crystalline counterpart due to the large number of the dangling bond within the defective structure revealing their technological appeal (Uchaker et al. 2014; Chae et al. 2014; Wu et al. 2018).

Disordered VO_x could benefit from reducing their size to the nanoscale (Jagiello et al. 2017; Pasqualini et al. 2017; Sartale et al. 2013) because of confinement effects over the electronic structure, e.g. quantum confinement enhancement of the work function (D'Elia

et al. 2020b; Zhou and Zachariah 2012), and because of a large effective surface area (Rezvani et al. 2016b; Pinto et al. 2016; Pinto et al. 2018b).

The possibility to produce disordered nanostructured (NS), i.e. assembled by nanoparticles, VO_x films and to monitor in situ their local atomic arrangement is therefore of great interest.

In the present work, we present an in situ X-ray absorption near-edge structure (XANES) spectroscopy investigation of NS VO_x with tunable stoichiometry.

XANES is associated with the electronic transitions from core shells to unoccupied states following a photo-absorption process, possessing the unique capability to probe concurrently the stoichiometry and local structure of the sample (Bachrach 1992; Bianconi 1982). The fabricated films have been characterized at distinct oxygen concentration stages monitoring the evolution of the electronic structure as a function of stoichiometry.

The fingerprints of a disordered ligands arrangement have been observed and are discussed comparing our data with those of a crystalline samples and with several simulations linking the coexistence of multiple randomly distributed atomic dislocations, with surface area and nanoparticle size.

Experimental

The NS VO_x films were deposited using a combination of the Pulsed Micro-plasma Cluster Source (PMCS) and the Supersonic Cluster Beam Deposition (SCBD) method. SCBD is a well-known synthesis method able to produce cluster assembled NS materials (D'Elia et al. 2020b; Borghi et al. 2018; Barborini et al. 2011). This method offers considerable advantages for neutral cluster manipulation based on effusive beams making the seeded supersonic beam approach very powerful for the deposition of NS films. PMCS is a cluster source characterized by high deposition rate, control over cluster growth and landing energy of the cluster beam (Wegner et al. 2006; Piseri et al. 2004; Barborini et al. 1999). Combining SCBD and PMCS is an original approach to the preparation of disordered NS vanadium oxide films, which facilitated their in situ characterization by XANES spectroscopy.

The PMCS is a pulsed-cluster source driven by a high-power pulsed electric discharge. A vanadium cathode (6 mm diam. rod, purity 99.9%, EvoChem GmbH) was used to generate a seeded supersonic beam of

vanadium oxide clusters. To oxidize the nanoparticles in the early synthesis stage, an Ar-O₂ gas mixture (high purity Ar: 99.9995%, SIAD) with a controlled quantity of oxygen was used. In the experimental layout, the supersonic cluster beam produced by the PMCS is deposited in situ on a copper substrate, which is electrically isolated from the rest of the experimental chamber. The base pressure of the experimental chamber was 1×10^{-9} mbar, while operating the PMCS, raised it to $\sim 5 \times 10^{-9}$ mbar due to the carrier gas injected by the cluster source.

To synthesize samples with different stoichiometry, we fed the PMCS with an Ar-O₂ gas mixture with an O₂ molar percentage in the range of 0–1.25%. The working parameters of the PMCS have been adjusted to maximize the deposition rate. The delay between the gas injection and the discharge firing was 0.51–0.64 ms; the discharge operating voltage was 0.9 kV, and the discharge duration was 60 μ s; the pulsed-valve aperture was between 196 and 220 μ s; and the pulse repetition rate was 3 Hz, and the Ar-O₂ pressure feeding the Parker valve was 60 bar. All the samples have been synthesized using Ar or Ar-O₂ gas mixture as specified elsewhere (D’Elia et al. 2020b). The substrate was kept at ~ 300 K during the deposition, and the deposited films have been studied in situ using XANES spectroscopy. The UHV chamber has been coupled to the PMCS, available at the TASC laboratory (De Simone et al. 2012) and equipped with an XYZ manipulator as depicted in Fig. 1. The XANES measurements have been performed at the Circular Polarization beamline of the Elettra synchrotron radiation facility using the CryoAlp UHV experimental chamber (Marcelli et al. 2018). Total electron yield (TEY) spectra have been acquired measuring the drain current, connecting the sample to ground through a Keithley 486 picoammeter (see Fig. 1). The sample was kept normal to the cluster beam, while the angle between the incident photons and the sample surface was 45°.

Furthermore, ex situ XANES measurements on crystalline sample, synthesized by molecular beam epitaxy (Fan et al. 2014), were performed using the IRMA experimental chamber (Sacchi et al. 2003) and used as a reference in our experiment. All the XANES spectra have been normalized to the incident photon flux and keeping the substrate temperature at ~ 300 K. The morphology and the size of the clusters have been analysed also by transmission electron microscopy (TEM) using a 200 kV field-emission microscope (JEM2100F-UHR, JEOL).

Results and discussion

The morphology and size of nanoparticles deposited by SCBD have been investigated using TEM. A deposition of 1 s has been performed on a TEM grid with an amorphous C supporting film. Figure 2 shows the TEM image of the VO_{2.5} sample. Although the individual nanoparticles form large agglomerates, they remain distinctly visible in the magnified image. Despite the aggregation that hampers the size distribution assessment, the size of the nanoparticles can be estimated to be in the range 3–6 nm with an average value of ~ 4.4 nm.

No clear differences in the particle size distribution have been observed as a function of carrier gas and oxidation state.

The different NS VO_x films have been deposited and investigated in situ using XANES spectroscopy at V L_{2,3} and O K edges. All the deposited films have a thickness of at least 15 nm in order to avoid probing the Cu substrate. We identify the different VO_x samples using the stoichiometric ratio defined as $x = [\text{No. O atoms}/\text{No. V atoms}]$, in the range $0 \leq x \leq 2.5$. The XANES spectra for different VO_x samples are shown in Fig. 3.

The vanadium L-edges spectra show two major components at ~ 515.2 eV (a) and ~ 522.3 eV (b) (see left panel of Fig. 3). We observe a chemical shift towards the higher photon energies with the introduction of the oxygen into the structure for values as low as $x = 0.3$.

The O K-edge spectra of the VO_x samples (Fig. 3 right panel), reveal a significant evolution of the electronic structure with stoichiometry which can be understood in terms of crystal field splitting and metal-ligand hybridization. In VO_x, O atoms arrange in an octahedral geometry generating a cubic crystal field (Hermann and Witko 2001; De Groot et al. 1989), which splits the degenerate 3d manifold into t_{2g} and e_g levels. As shown in Fig. 3, the O K edge XANES exhibits two main contributions at ~ 530 and ~ 532.5 eV, which can be associated with t_{2g}^* and e_g^* states, respectively (De Groot et al. 1989). Their relative intensity shows a marked dependence on the oxidation state.

Since XANES probes the empty density of states (DOS), t_{2g}^* and e_g^* signals can be observed at the O K edge only when t_{2g} and e_g electrons are bound with the O 2p electrons. The presence of t_{2g}^* in VO_{0.6} samples (the weak component around 530 eV) can be attributed to the hybridization of V-3d and O-2p electrons in agreement with a previous Auger investigation, which

Fig. 1 Layout of the experimental setup including the cluster beam and the TEY acquisition scheme. A copper substrate is positioned normal to the cluster beam and at 45° with respect to the incident X-ray beam. The X-ray induced electron yield is measured by collecting the drain current via the copper substrate

predicts a mixed $4s - 3d$ valence band for this sub-oxide (D'Elia et al. 2020b). e_g^* and t_{2g}^* features are observable on the whole VO_x set, even though they are broad and not well separated.

The origin of e_g^* and t_{2g}^* width and energy separation can be interpreted by comparison with a reference single crystal (SC) sample. We investigated

VO_2 as a case study. The comparison of the SC- VO_2 and NS- VO_2 is reported in Fig. 4.

In the SC sample spectra, the e_g^* and t_{2g}^* features are well separated pointing to a strong and homogeneous crystal field and therefore to a locally ordered atomic environment. The e_g^* and t_{2g}^* features of the NS film, on the other hand, are broadened and less resolved. The t_{2g}^*

Fig. 2 TEM image of the nanoparticle aggregates for $VO_{2.5}$ along with the size distribution of the particles. The particles show a size distribution between ~ 3 and ~ 6 nm with an average value of $d = 4.4$ nm

Fig. 3 Left: XANES spectra of different VO_x films at the V $L_{2,3}$ edges and the O K-edge. Right: Comparison of the O K-edge XANES spectra of VO_x samples

energy position seems unaffected within our experimental resolution, while the e_g^* component is red-shifted of about 0.4 eV. Coherently, a red-shift of the L_3 energy position is observed in the NS sample with respect to the SC since V L edges are particularly sensitive to the e_g^* contribution to the empty DOS (Zaanen et al. 1985; Abbate et al. 1991).

The observed e_g^* red-shift in the NS- VO_2 is possibly due to the presence of Jahn-Teller-like distortions of the oxygen octahedron matrix which directly influences the electronic structure of the NS sample (Kasatnikov et al. 2019; Ruzmetov et al. 2007). In the extreme case, a high number (ideally infinite) of different ligand distortions coexist within

a disordered material. The disorder considered here is of geometric nature; around each metal site, the local symmetry of the ligands arrangement is broken because of random atomic dislocations, i.e. displacements from their symmetry site. In this picture, each vanadium site is surrounded by a different distorted ligand conformation which leads to an overall disordered structure.

In order to confirm this observation, and since the e_g^* orbitals are the most involved, we investigated V L edges line shape of the NS VO_2 sample (Zaanen et al. 1985; Kasatnikov et al. 2019). Several simulations were carried out within the charge transfer multiplet framework to investigate possible distortions effect on the VO_2 electronic structures. The calculations were performed by the configuration interaction cluster for octahedral and distorted VO_2 structures (see Fig. 5). The refinement of the analysis of the distorted structures was performed, employing the CTM4XAS (Stavitski and de Groot 2010) simulation code.

According to previously published work (Ikeno et al. 2011), the calculations were based on a crystal field $10Dq=2.35$ eV with 80% reduction of the Slater integrals and an average Coulomb interaction $U_{dd} - U_{pd}$ of 0.88 eV. Finally, an overall broadening of 0.35 eV full width was applied.

In VO_2 the oxygen atoms are arranged according to a tetragonally distorted octahedral geometry (D'Elia et al. 2020a, c). The tetragonal distortion leads to a further splitting of the t_{2g}^* and e_g^* orbitals resulting in the four levels e_g^* , b_{2g}^* , a_{1g}^* and b_{1g}^* (see Fig. 5 right panel). The e_g , b_{2g} , separation is called Q_1 , while the a_{1g} and b_{1g} are splitted by Q_2 . To mimic the ligand atomic

Fig. 4 Comparison between the O K edge of the NS VO_2 film and that of a single crystalline (SC) film

Fig. 5 Left: simulated V L edges spectra of VO₂ for different Q₂ energy splitting values and NS VO₂ measured spectrum (black). Right: schematic representation of the energy levels splitting passing from O_h to D_{4h} symmetry

dislocations, e.g. the bending of two opposite octahedron vertices which red-shift the e_g^* , the calculations were performed for increasing values of $Q_2 = 0.2, 0.5, 0.8$ and 1.0 eV while keeping $Q_1 = 0.2$ eV. The choice to keep the Q_1 constant is justified by considering the prominent sensitivity of V L edges to the e_g^* orbitals which hide small spectral changes in the t_{2g}^* energy region (Zaanan et al. 1985). We compare the simulated spectra with the V L₂₃ spectrum of NS VO₂ sample in Fig. 5.

The results demonstrate that the observed e_g^* red-shift in our sample is mainly due to the presence of distorted ligand environment and that simulations with $Q_2 = 0.2$ eV and 0.5 eV match better the experimental data.

However, the experimental spectrum shows features of distinct distorted states. Since the geometrical distortion of the oxygen octahedron matrix reflects atomic disloca-

tions, i.e. displacements, from the ordered atomic arrangement, the results displayed in Fig. 5 point to the coexistence of a multitude of distorted ligand conformations.

The cause of the disordered nature of our samples can be identified in the small size of the nanoparticles. The finite dimensions of the NS films constituents and their irregular shape (see Fig. 2) provide a higher surface area with respect to bulk materials, naturally leading to symmetry breaking and to the creations of random atomic dislocations.

The disorder-induced L₃ red-shift with respect to the bulk samples reported for VO₂ can be observed for the whole set of VO_x films.

The L₃ maximum position as a function of the oxidation state is depicted in Fig. 6. The comparison with crystalline bulk samples found in literature (Chen et al. 1994) evidences a stoichiometry-dependent L₃ red-shift for the whole oxygen concentration range.

This implies that the degree of disorder increases with stoichiometry which can be understood considering that to a high number of oxygen atoms corresponds a high number of achievable distorted atomic conformations. As a consequence, the highest oxidation states are most likely to assume a severely distorted atomic arrangement with respect to the samples with less oxygen.

The evidence of the disordered ligand environment for all the oxygen concentration is linked to the synthesis method and to the nucleation conditions of the nanoparticles. During the supersonic expansion of the seeded cluster beam, the thermal energy acquired during the nucleation process is converted in kinetic energy quenching the atoms in disordered conformations. This process is particularly efficient in small nanoparticles whose high surface area favours the symmetry breaking of ligand conformations.

Fig. 6 Comparison between the V L₃ energy position as a function of stoichiometry for the NS VO_x film (black) and crystalline samples data (blue) found in literature (Chen et al. 1994)

This demonstrates that there is a complex influence of stoichiometry and disorder in VO_x NS films with respect to the bulk analogue that suggest a way to tailor the electronic structure of these materials.

Conclusion

We investigated in situ NS VO_x NS films using XANES spectroscopy demonstrating that nanoparticle size and stoichiometry contribute to determine the symmetry of ligands arrangement.

We demonstrated that broad t_{2g}^* and e_g^* features and reduced $t_{2g}^* - e_g^*$ splitting with respect to crystalline samples represent the fingerprints of disordered ligand matrix. This is confirmed by XANES simulations that show the coexistence of multiple distorted local environments. Our results point towards a stoichiometry-dependent red-shift of the V L₃ edge with respect to the bulk counterpart. This transfer of spectral weight towards lower photon energy is induced by the disordered structure of our samples which can be directly connected to the reduced dimension of the nanoparticles composing the films. Our study shows the complex interplay among stoichiometry, sample size and disorder in vanadium oxides and provides a tool to monitor and control the disorder in NS VO_x films. Our results are of potential interest in different research area, such as Li-ion insertion devices, where the use of a disordered and NS material may be beneficial.

Acknowledgments The authors would like to thank D. Catone (ISM-CNR) for writing the acquisition software.

Funding Open Access funding enabled and organized by Projekt DEAL.

Compliance with ethical standards

Conflict of interest The authors declare that they have no conflict of interest.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party

material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

- Abbate M, De Groot FMF, Fuggle JC et al (1991) Soft-x-ray-absorption studies of the electronic-structure changes through the VO₂ phase transition. *Phys Rev B* 43:7263–7266. <https://doi.org/10.1103/PhysRevB.43.7263>
- Bachrach RZ (1992) Synchrotron radiation research advances in surface and interface science. Springer US, Boston, MA
- Barborini E, Piseri P, Milani P (1999) Pulsed microplasma source of high intensity supersonic carbon cluster beams. *J Phys D Appl Phys* 32:L105–L109. <https://doi.org/10.1088/0022-3727/32/21/102>
- Barborini E, Ducati C, Leccardi M, et al (2011) Nanostructured refractory metal oxide films produced by a pulsed microplasma cluster source as active layers in microfabricated gas sensors. *Jpn J Appl Phys* 50 01AK01. <https://doi.org/10.1143/JJAP.50.01AK01>
- Bianconi A (1982) Multiplet splitting of final-state configurations in x-ray-absorption spectrum of metal VO₂: effect of core-hole-screening, electron correlation, and metal-insulator transition. *Phys Rev B* 26:2741–2747. <https://doi.org/10.1103/PhysRevB.26.2741>
- Borghi F, Podestà A, Piazzoni C, Milani P (2018) Growth mechanism of cluster-assembled surfaces: from submonolayer to thin-film regime. *Phys Rev Appl* 9:044016. <https://doi.org/10.1103/PhysRevApplied.9.044016>
- Brahlek M, Zhang L, Lapano J, Zhang HT, Engel-Herbert R, Shukla N, Datta S, Paik H, Schlom DG (2017) Opportunities in vanadium-based strongly correlated electron systems. *MRS Commun* 7:27–52. <https://doi.org/10.1557/mrc.2017.2>
- Chae OB, Kim J, Park I, Jeong H, Ku JH, Ryu JH, Kang K, Oh SM (2014) Reversible lithium storage at highly populated vacant sites in an amorphous vanadium pentoxide electrode. *Chem Mater* 26:5874–5881. <https://doi.org/10.1021/cm502268u>
- Chan CK, Peng H, Twisten RD, Jarausch K, Zhang XF, Cui Y (2007) Fast, completely reversible Li insertion in vanadium pentoxide nanoribbons. *Nano Lett* 7:490–495. <https://doi.org/10.1021/nl062883j>
- Chen JG, Kim CM, Frühberger B et al (1994) A NEXAFS determination of the oxidation state of vanadium carbide on V(110): observation of charge transfer from vanadium to carbon. *Surf Sci* 321:145–155. [https://doi.org/10.1016/0039-6028\(94\)90035-3](https://doi.org/10.1016/0039-6028(94)90035-3)
- Chen L, Ruan Y, Zhang G, Wei Q, Jiang Y, Xiong T, He P, Yang W, Yan M, An Q, Mai L (2019) Ultrastable and high-performance Zn/VO₂ battery based on a reversible single-phase reaction. *Chem Mater* 31:699–706. <https://doi.org/10.1021/acs.chemmater.8b03409>
- D'Elia A, Grazioli C, Cossaro A, et al (2020a) Strain mediated filling control nature of the metal-insulator transition of VO₂

- and electron correlation effects in nanostructured films. *Appl Surf Sci* 148341. <https://doi.org/10.1016/j.apsusc.2020.148341>
- D'Elia A, Cepek C, de Simone M, Macis S, Belec B, Fanetti M, Piseri P, Marcelli A, Coreno M (2020b) Interplay among work function, electronic structure and stoichiometry in nanostructured VO_x films. *Phys Chem Chem Phys* 22: 6282–6290. <https://doi.org/10.1039/d0cp00216j>
- D'Elia A, Rezvani SJ, Cossaro A et al (2020c) Strain induced orbital dynamics across the metal insulator transition in thin VO_2/TiO_2 (001) films. *J Supercond Nov Magn* 33:2383–2388. <https://doi.org/10.1007/s10948-019-05378-0>
- De Groot FMF, Griener M, Fuggle JC et al (1989) Oxygen 1s X-ray-absorption edges of transition-metal oxides. *Phys Rev B* 40:5715–5723. <https://doi.org/10.1103/PhysRevB.40.5715>
- De Simone M, Snidero E, Coreno M et al (2012) Oxidation of nanostructured Ti films produced by low energy cluster beam deposition: an X-ray photoelectron spectroscopy characterization. *Thin Solid Films* 520:4803–4807. <https://doi.org/10.1016/j.tsf.2011.10.075>
- Fan LL, Chen S, Luo ZL, Liu QH, Wu YF, Song L, Ji DX, Wang P, Chu WS, Gao C, Zou CW, Wu ZY (2014) Strain dynamics of ultrathin VO_2 film grown on TiO_2 (001) and the associated phase transition modulation. *Nano Lett* 14:4036–4043. <https://doi.org/10.1021/nl501480f>
- Hermann K, Witko M (2001) Chapter 4 Theory of physical and chemical behavior of transition metal oxides: vanadium and molybdenum oxides *The Chemical Physics of Solid Surfaces* 9(2001):136–198. [https://doi.org/10.1016/S1571-0785\(01\)80024-9](https://doi.org/10.1016/S1571-0785(01)80024-9)
- Ikeno H, Mizoguchi T, Tanaka I (2011) Ab initio charge transfer multiplet calculations on the L2,3 XANES and ELNES of 3d transition metal oxides. *Phys Rev B - Condens Matter Mater Phys* 83:155107. <https://doi.org/10.1103/PhysRevB.83.155107>
- Jagiello K, Chomicz B, Avramopoulos A, Gajewicz A, Mikolajczyk A, Bonifassi P, Papadopoulos MG, Leszczynski J, Puzyn T (2017) Size-dependent electronic properties of nanomaterials: how this novel class of nanodescriptors supposed to be calculated? *Struct Chem* 28: 635–643. <https://doi.org/10.1007/s11224-016-0838-2>
- Kasatkov S, Filatova E, Sakhonenkov S et al (2019) Relationship between Ta oxidation state and its local atomic coordination symmetry in a wide range of oxygen nonstoichiometry extent of TaO_x . *J Phys Chem C* 123:6849–6860. <https://doi.org/10.1021/acs.jpcc.8b12053>
- Marcelli A, Coreno M, Stredansky M, Xu W, Zou C, Fan L, Chu W, Wei S, Cossaro A, Ricci A, Bianconi A, D'Elia A (2017) Nanoscale phase separation and lattice complexity in VO_2 : the metal–insulator transition investigated by XANES via auger electron yield at the vanadium L23-edge and resonant photoemission. *Condens Matter* 2:38. <https://doi.org/10.3390/condmat2040038>
- Marcelli A, Mazuritskiy MI, Dabagov SB et al (2018) A new XUV optical end-station to characterize compact and flexible photonic devices using synchrotron radiation. *J Instrum* 13: C03035–C03035. <https://doi.org/10.1088/1748-0221/13/03/C03035>
- McLeod AS, Van Heumen E, Ramirez JG et al (2017) Nanotextured phase coexistence in the correlated insulator V_2O_3 . *Nat Phys* 13:80–86. <https://doi.org/10.1038/nphys3882>
- Pasqualini M, Calcaterra S, Maroni F, Rezvani SJ, di Cicco A, Alexander S, Rajantie H, Tossici R, Nobili F (2017) Electrochemical and spectroscopic characterization of an alumina-coated LiMn_2O_4 cathode with enhanced interfacial stability. *Electrochim Acta* 258:175–181. <https://doi.org/10.1016/j.electacta.2017.10.115>
- Pinto N, Rezvani SJ, Favre L, Berbezier I, Fretto M, Boarino L (2016) Geometrically induced electron–electron interaction in semiconductor nanowires. *Appl Phys Lett* 109:109. <https://doi.org/10.1063/1.4962893>
- Pinto N, Caproli F, Maggioni G, Carturan S, Napoli DR (2018a) Thermally induced irreversibility in the conductivity of germanium nitride and oxynitride films. *Mater Sci Semicond Process* 74:57–63. <https://doi.org/10.1016/j.mssp.2017.10.006>
- Pinto N, Rezvani SJ, Perali A, Flammia L, Milošević MV, Fretto M, Cassiogo C, de Leo N (2018b) Dimensional crossover and incipient quantum size effects in superconducting niobium nanofilms. *Sci Rep* 8:4710. <https://doi.org/10.1038/s41598-018-22983-6>
- Piseri P, Tafreshi HV, Milani P (2004) Manipulation of nanoparticles in supersonic beams for the production of nanostructured materials. *Curr Opin Solid State Mater Sci* 8:195–202. <https://doi.org/10.1016/j.cossms.2004.08.002>
- Rezvani SJ, Pinto N, Boarino L (2018) Rapid formation of single crystalline Ge nanowires by anodic metal assisted etching. *Cryst Eng Comm* 18(40):7843–7848. <https://doi.org/10.1039/C6CE01598K>
- Rezvani SJ, Pinto N, Enrico E, D'Ortenzi L, Chiodoni A, Boarino L (2016a) Thermally activated tunneling in porous silicon nanowires with embedded Si quantum dots. *J Phys D Appl Phys* 49:49. <https://doi.org/10.1088/0022-3727/49/10/105104>
- Rezvani SJ, Gunnella R, Neilson D, Boarino L, Croin L, Aprile G, Fretto M, Rizzi P, Antonioli D, Pinto N (2016b) Effect of carrier tunneling on the structure of Si nanowires fabricated by metal assisted etching. *Nanotechnology* 27:27. <https://doi.org/10.1088/0957-4484/27/34/345301>
- Rezvani SJ, Pasqualini M, Witkowska A, Gunnella R, Birrozzi A, Minicucci M, Rajantie H, Copley M, Nobili F, di Cicco A (2018) Binder-induced surface structure evolution effects on Li-ion battery performance. *Appl Surf Sci* 435:1029–1036. <https://doi.org/10.1016/j.apsusc.2017.10.195>
- Ruzmetov D, Senanayake SD, Ramanathan S (2007) X-ray absorption spectroscopy of vanadium dioxide thin films across the phase-transition boundary. *Phys Rev B - Condens Matter Mater Phys* 75:. <https://doi.org/10.1103/PhysRevB.75.195102>
- Sacchi M, Spezzani C, Torelli P et al (2003) Ultrahigh-vacuum soft x-ray reflectometer. *Rev Sci Instrum* 74:2791–2795. <https://doi.org/10.1063/1.1568552>
- Sartale SD, Ansari AA, Rezvani SJ (2013) Influence of Ti film thickness and oxidation temperature on TiO_2 thin film formation via thermal oxidation of sputtered Ti film. *Mater Sci Semicond Process* 16:2005–2012. <https://doi.org/10.1016/j.mssp.2013.07.006>
- Schwingenschlögl U, Eyert V (2004) The vanadium Magnéli phases $\text{V}_n\text{O}_{2n-1}$. *Ann Phys* 13:475–510. <https://doi.org/10.1002/andp.200410099>
- Shi X, Du J, Jones TGJ et al (2018) Understanding the mechanism for capacity decay of V_6O_{13} -based lithium-metal polymer

- batteries. *ACS Appl Mater Interfaces* 10:29667–29674. <https://doi.org/10.1021/acsami.8b10629>
- Stavitski E, de Groot FMF (2010) The CTM4XAS program for EELS and XAS spectral shape analysis of transition metal L edges. *Micron* 41:687–694. <https://doi.org/10.1016/j.micron.2010.06.005>
- Tan S, Jiang Y, Wei Q, Huang Q, Dai Y, Xiong F, Li Q, An Q, Xu X, Zhu Z, Bai X, Mai L (2018) Multidimensional synergistic nanoarchitecture exhibiting highly stable and ultrafast sodium-ion storage. *Adv Mater* 30:1707122. <https://doi.org/10.1002/adma.201707122>
- Uchaker E, Zheng YZ, Li S, Candelaria SL, Hu S, Cao GZ (2014) Better than crystalline: amorphous vanadium oxide for sodium-ion batteries. *J Mater Chem A* 2:18208–18214. <https://doi.org/10.1039/c4ta03788j>
- Wegner K, Piseri P, Tafreshi HV, Milani P (2006) Cluster beam deposition: a tool for nanoscale science and technology. *J Phys D Appl Phys* 39:R439–R459. <https://doi.org/10.1088/0022-3727/39/22/R02>
- Wu H, Qin M, Wang W, Cao Z, Liu Z, Yu Q, Lao C, Zhang D, Jia B, He D, Liu T, Volinsky AA, Cao P, Qu X (2018) Ultrafast synthesis of amorphous VO_x embedded into 3D strutted amorphous carbon frameworks-short-range order in dual-amorphous composites boosts lithium storage. *J Mater Chem A* 6:7053–7061. <https://doi.org/10.1039/c8ta00654g>
- Xiao B, Zhang B, Tang L bo, et al (2018) V₂O₃/rGO composite as a potential anode material for lithium ion batteries. *Ceram Int* 44:15044–15049. <https://doi.org/10.1016/j.ceramint.2018.05.134>
- Xu N, Ma X, Wang M, Qian T, Liang J, Yang W, Wang Y, Hu J, Yan C (2016) Stationary full Li-ion batteries with interlayer-expanded V₆O₁₃ cathodes and lithiated graphite anodes. *Electrochim Acta* 203:171–177. <https://doi.org/10.1016/j.electacta.2016.04.044>
- Zaanen J, Sawatzky GA, Fink J et al (1985) L_{2,3} absorption spectra of the lighter 3d transition metals. *Phys Rev B* 32:4905–4913. <https://doi.org/10.1103/PhysRevB.32.4905>
- Zhou L, Zachariah MR (2012) Size resolved particle work function measurement of free nanoparticles: aggregates vs. spheres. *Chem Phys Lett* 525–526:77–81. <https://doi.org/10.1016/j.cplett.2011.11.045>

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.