Erratum to: The Effect of Multivalley Bandstructure on Thermoelectric Properties of $\text{Al}_x\text{Ga}_{1-x}\text{As}$

PAYAM NOROUZZADEH¹ and DARYOOSH VASHAEE^{2,3}

1.—School of Electrical and Computer Engineering, Helmerich Advanced Technology Research Center, Oklahoma State University, Tulsa, OK 74106, USA. 2.—Electrical and Computer Engineering Department, North Carolina State University, 890 Oval Dr., Raleigh, NC 27606, USA. 4.—e-mail: dvashae@ncsu.edu

**Erratum to: Journal of ELECTRONIC
MATERIALS
Vol. 44, No. 2, 2015
DOI: 10.1007/s11664-014-3535-1**

In the original article there were three references that were inadvertently omitted from Tables I and

II and from the reference list, in addition to a few content errors in these tables. The corrected Tables I and II and the three omitted references are presented below:

Table I. $\text{Al}_x\text{Ga}_{1-x}\text{As}$ electronic structure parameters used to calculate electrical properties

Parameter	Value	Reference
Static dielectric constant	$13.18(1-x) + 10.06x$	30
High frequency dielectric constant	$11.6(1-x) + 8.16x$	30
Bulk modulus (N/m^2)	$(7.55 + 0.26x) \times 10^{10}$	31
Energy at Γ at $T = 0$ (eV)- $E_{\Gamma 0}$	$1.519 + 1.155x + 0.37x^2$	32
Temperature dependency of energy at Γ	$E_{\Gamma 0} - 5.41 \times 10^{-4} T^2 / (T + 204)$	32
Energy at L at $T = 0$ (eV)- E_{L0}	$1.815 + 0.69x$	32
Temperature dependency of energy at L	$E_{L0} - 6.05 \times 10^{-4} T^2 / (T + 204) + 0.040$	32
Energy at X at $T = 0$ (eV)- E_{X0}	$1.981 + 0.124x + 0.144x^2$	32
Temperature dependency of energy at X	$E_{X0} - 4.6 \times 10^{-4} T^2 / (T + 204) + 0.1$	32
Conduction band (CB) effective mass at Γ for GaAs	0.063	32
CB longitudinal effective mass at L for GaAs	1.9	32
CB transverse effective mass at L for GaAs	0.075	32
CB longitudinal effective mass at X for GaAs	1.58	This work
CB transverse effective mass at X for GaAs	0.95	This work
CB effective mass at Γ for AlAs	0.15	30
CB longitudinal effective mass at L for AlAs	1.32	30
CB transverse effective mass at L for AlAs	0.15	30
CB longitudinal effective mass at X for AlAs	1.1	This work
CB transverse effective mass at X for AlAs	0.19	This work
Valence band (VB) effective mass	0.51	This work
CB non-parabolicity (eV^{-1}) for L , Γ , X	0.5, 0.5, 0.5	This work
VB non-parabolicity (eV^{-1})	0.83	This work
CB acoustic phonon deformation potential (eV)	$3.6 - 0.7x$	This work
VB acoustic phonon deformation potential (eV)	$2.7 - 0.1x$	This work

Table II. $\text{Al}_x\text{Ga}_{1-x}\text{As}$ lattice parameters used to calculate the thermal conductivity

Parameter	Value	Reference
Debye temperature (K)	$368.57 + 55.941x + 23.487x^2$	32 ^a
Bulk modulus (N/m^2)	$(7.55 + 0.26x) \times 10^{10}$	31
Mass density (kg/m^3)	$(5.32 - 1.56x) \times 10^3$	30
CB acoustic phonon deformation potential (eV)	$3.6 - 0.7x$	This work
VB acoustic phonon deformation potential (eV)	$2.7 - 0.1x$	This work
Strain parameter for point defect scattering	1.3	This work
Grüneisen parameter	$0.12(1-x) + 0.07x + 1.5x(1-x)$	This work
Higher order phonon scattering	2.0	This work
Ratio of normal to Umklapp scattering	1.0	This work

^aPolynomial fit of the experimental data reported in Ref. 32.

REFERENCES

30. Landolt-Börnstein online library, Vol. III, <http://www.springermaterials.com/>. The $\text{Al}_x\text{Ga}_{1-x}\text{As}$ data is the weighted average of those of GaAs and AlAs.
31. S. Adachi, *J. Appl. Phys.* 61, 10 (1987).
32. <http://www.ioffe.ru/SVA/NSM/Semicond/AlGaAs/index.html>.