CORRECTION

Correction to: Parameter Development via In Situ Residual Stress Measurement and Post-deposition Analysis of Cold Spray CuNi Coatings

Robert F. Brown¹ · Gregory M. Smith² · John Potter¹ · Timothy J. Eden¹

Published online: 30 July 2021
© ASM International 2021

Correction to: J Therm Spray Tech (2020) 29:1876–1891
<https://doi.org/10.1007/s11666-020-01109-3>

In the Discussion section, the Table 4 that appeared is a duplicate of Table 5.

Table 4 should read as follows:

Table 4 Coating property data comparison to surface preparation/deposition angle and coating adhesion

Coating	Surface preparation & nozzle angle	Deposition thickness, mm	Surface profile, Ra μm	Hardness, HV0.3	Porosity, %	Adhesion, MPa	Residual stress, MPa
C	Grit-blast & 90°	0.60 (5 passes)	5.8	197 $\pm$ 11	2.4 $\pm$ 0.2	5.8 $\pm$ 1.2	+15 $\pm$ 5
D	Abrasive pad & 40° + 90°	0.46 (5 passes)	0.79	180 $\pm$ 27	2.9 $\pm$ 0.2	44.4 $\pm$ 4.5	−19 $\pm$ 5
E	Grit-blast & 40° + 90°	0.25 (5 passes)	4.4	N/A	2.0 $\pm$ 0.2	20.7 $\pm$ 4.0	+2 $\pm$ 5

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

The original article can be found online at <https://doi.org/10.1007/s11666-020-01109-3>.

✉ Robert F. Brown
rfb74@psu.edu

¹ The Pennsylvania State University, 3075 Research Drive, State College, PA 16801, USA

² Naval Research Laboratory, 4555 Overlook Ave SW, Washington, DC 20375, USA