Molecular diffusion in ternary poly(vinyl alcohol) solutions

Katarzyna Majerczak¹, Ophelie Squillace¹, Zhiwei Shi², Zhanping Zhang², Zhenyu J. Zhang (✉)¹

¹ School of Chemical Engineering, University of Birmingham, Birmingham B15 2TT, UK

² The Procter and Gamble Company, Cincinnati, OH 45040, USA

© The Author(s) 2021. This article is published with open access at link.springer.com and journal.hep.com.cn

Abstract The diffusion kinetics of a molecular probe—rhodamine B—in ternary aqueous solutions containing poly(vinyl alcohol), glycerol, and surfactants was investigated using fluorescence correlation spectroscopy and dynamic light scattering. We show that the diffusion characteristics of rhodamine B in such complex systems is determined by a synergistic effect of molecular crowding and intermolecular interactions between chemical species. The presence of glycerol has no noticeable impact on rhodamine B diffusion at low concentration, but significantly slows down the diffusion of rhodamine B above 3.9% (w/v) due to a dominating steric inhibition effect. Furthermore, introducing surfactants (cationic/nonionic/anionic) to the system results in a decreased diffusion coefficient of the molecular probe. In solutions containing nonionic surfactant, this can be explained by an increased crowding effect. For ternary poly(vinyl alcohol) solutions containing cationic or anionic surfactant, surfactant–polymer and surfactant–rhodamine B interactions alongside the crowding effect of the molecules slow down the overall diffusivity of rhodamine B. The results advance our insight of molecular migration in a broad range of industrial complex formulations that incorporate multiple compounds, and highlight the importance of selecting the appropriate additives and surfactants in formulated products.

Keywords fluorescence correlation spectroscopy, poly(vinyl alcohol), anomalous diffusion, crowding effects, dynamic light scattering, binding effects, rhodamine B

1 Introduction

Poly(vinyl alcohol) (PVA) is widely used in consumer products due to its high degree of water solubility,

exceptional film forming capability [1,2], low toxicity [2], approved biodegradability [3,4], and excellent barrier properties [5]. As a packaging material [6–8], PVA is exposed to additives and surfactants through the life cycle of a formulated product. Migration of additive molecules in such complex matrices has a significant impact on the manufacturing process, as well as product shelf-life and performance, therefore is determined by the molecular interactions between PVA and the small molecules, often in an aqueous environment.

Building upon a well-established theoretical framework [9,10], diffusion is commonly considered as the mean-square displacement of the moving entity, which changes proportionally with its diffusion time [11]. However, molecular diffusion in polymer solutions that contain multiple components [12,13] should be considered by more specific models, such as obstruction effect models [14,15], free volume theory-based models [16,17], and hydrodynamic models [18,19]. Despite the advancements, these mechanisms do not adequately describe diffusion in complex mixtures of polymers and surfactants [20,21], proving the need for further investigations. The size, shape, and flexibility of the molecules were proven to significantly influence the magnitude of the rotational dynamics [22] and translational diffusion coefficient [23–26] due to temporary confinement [25], molecular crowding [27], and reversible binding to ‘traps’ in the system [28]. Furthermore, intermolecular interactions between solutes and solvent are often complex, substantially influencing the anomalous character of diffusion in polymer solutions.

Investigations into the mechanisms that determine the molecular diffusion in PVA solutions are further complicated by the formation of complexes in the presence of charged molecules (e.g., surfactants) [29,30]. For example, surfactants were shown to influence the viscosity of PVA solutions because of the changes in intermolecular interactions [31,32] and formation of molecular aggregates [33].

For polymer solutions, extensive studies had been carried out to investigate the magnitude of the intermolecular interactions and the formation mechanisms of

complexes [29,31,32,34–36], with less attention paid on the effect of the additives on the molecular diffusion characteristics. Furthermore, the majority considers only a binary system that contains the polymer and a particular guest molecule. To understand the molecular interactions in a complex, multi-component polymer solution that is relevant to industrial applications, four components are essential: solvent, polymer, plasticiser, and another additive (i.e., a surfactant of various head group chemistry).

Molecular diffusion in a polymer solution can be measured by a range of techniques, including fluorescence methods such as fluorescence correlation spectroscopy (FCS) [37], dynamic light scattering (DLS) [38,39], pulsed-field gradient spin-echo nuclear magnetic resonance [40], and centrifugation (sedimentation) [41,42]. They can be further divided into techniques measuring self-diffusion coefficient (describing the motion of the molecule due to the thermal motion that is relative to the surrounding molecules) and cooperative diffusion coefficient (transport of a number of molecules due to density gradient), both of which offer critical information about migration behavior of molecules in a controlled environment [43].

Among the techniques measuring self-diffusion coefficient, FCS enables investigation at the single-molecule level, with minimal disruption to the system being investigated. It has been used to characterize the self-diffusion of both polymer [44–47] and probe of various sizes, chemistry and concentration in both dilute and semi-dilute solutions [12,48–53], revealing the binding [43], reaction kinetics [54], and crowding effects [55], and offering the capability to explore an unknown micro-structure [56]. FCS also enables investigations into diffusion mechanisms [57], differentiating anomalous [11,28,58,59], walking-confinement [60], and time-dependent diffusion behaviors [61]. DLS, on the other hand, is used widely to measure the cooperative diffusion coefficient, but is incapable of examining multicomponent systems as all solutes contribute to the scattering signal [12].

In the present study, we investigated the effects of crowding and intermolecular interactions on the molecular diffusion in ternary mixtures that replicate PVA based

chemical products dissolved in water. Rhodamine B (RhB), a well-characterized [62], industrially applied fluorophore [63–65] was selected. Initially, diffusion of RhB in PVA solutions of different polymer concentrations was measured by FCS, and analyzed by a hydrodynamic stretched exponential model, to examine the effects of molecular crowding [66]. Glycerol, a plasticiser commonly used for PVA formulations [67], was subsequently introduced to observe its effect on the diffusion of RhB. Finally, surfactants of various head groups (cationic/nonionic/anionic) were introduced to investigate the effect of detergent on molecular diffusion. By introducing complexity in a stepwise fashion, the contribution of each newly added component was examined independently. The specific interactions between each component could be characterized, revealing three primary effects: the behavior of the polymer itself, the overall molecular crowding in the system, and specific (charged) interactions between individual species, which could enable a prediction of molecular behavior in complex systems.

2 Experimental

2.1 Materials

PVA (Sigma-Aldrich P8136, molecular weight (M_w) = 30–70 kg·mol⁻¹, degree of hydrolysis (DH) = 87%–90%), glycerol (Sigma-Aldrich G9012, ≥99.5%), sodium dodecyl sulfate (SDS, Fisher Scientific S/5200/53), decaethylene glycol monododecyl ether (C₁₂E₁₀, Sigma-Aldrich P9769), cetyltrimethylammonium bromide (CTAB, Sigma-Aldrich H5882, ≥98%), RhB (Sigma-Aldrich R6626, ≥95%, HPLC), and HPLC water (HPLC Plus, Sigma Aldrich 34877-M) were purchased and used as received. Chemical structures of the components used in this study are shown in Fig. 1.

2.2 Sample preparation

PVA stock solution (4% (w/v)) was prepared by adding pure PVA to HPLC water and heating up to 75 °C with

Fig. 1 Chemical structures of the compounds used.

Scheme 1 Preparation method for test solutions of various compositions: (a) PVA solutions of various concentrations, (b) PVA/glycerol solutions of various ratio of components (with changes in PVA concentration), (c) PVA/glycerol solutions of various ratio of components (with almost constant PVA concentration), (d) PVA/surfactant solutions, (e) PVA/glycerol/surfactant solutions, and (f) concentrated PVA/glycerol/surfactant solutions.

continuous stirring for ca. 2 h. Solutions of glycerol, anionic surfactant (SDS), and cationic surfactant (CTAB) were prepared by dissolving required amount of substance and stirring at room temperature for ca. 4 h to prepare solutions of 4% (w/v), 1% (w/v), and 1% (w/v), respectively. When SDS or CTAB solutions were visibly cloudy, they were heated up to 50 °C for 15 min to remove surfactant mesophases [68]. Stock solutions of 1% (w/v) nonionic surfactant ($C_{12}E_{10}$) were prepared by dissolving the compound at 30 °C with continuous mixing for ca. 2 h and stirring at room temperature. All stock solutions prepared were below their solubility limits.

Multiple sets of solutions were prepared by mixing PVA/glycerol/surfactant stock solutions at various volumetric ratios, as presented in Scheme 1, to examine: 1) Effect of PVA concentration in the absence of other additives (Scheme 1(a)); 2) effect of glycerol addition at various concentrations (Schemes 1(b) and 1(c)); 3) effect of surfactant in the absence of glycerol (Scheme 1(d)); 4) synergistic effect of both surfactant and glycerol at a 12:4:1 PVA/glycerol/surfactant mass ratio (Schemes 1(e) and 1(f)). Molecular probe, RhB was introduced to the corresponding test solutions using a $2.5 \text{ mmol} \cdot \text{L}^{-1}$ stock solution to obtain a final concentration of $50 \text{ nmol} \cdot \text{L}^{-1}$. A piranha solution cleaned coverslip [69] with 50 μL of each as prepared solution was used for FCS analysis.

2.3 Fluorescence correlation spectroscopy

FCS measurements were performed on a ZEISS LSM 710 confocal microscope under a $40 \times$ water immersion objective. RhB was excited using the 488 nm line of the Ar laser at 5% of its maximum power, with the 505–610 nm band-pass filter used to collect the fluorescence emission.

Diffusion coefficient of the RhB in water is well documented in the literature ($3.6 \times 10^{-10} \text{ m}^2 \cdot \text{s}^{-1}$ at 21.5 °C) [37], which was used to calibrate the width of the confocal volume, using Einstein's equation [37]:

$$D = \frac{w_{xy}^2}{4\tau_D}, \quad (1)$$

where w_{xy} is the width of the confocal volume, τ_D is the average diffusion time of RhB through the confocal volume, and D is the diffusion coefficient of RhB in given solution. Equation (2) was used to correct the effect of temperature on the diffusion coefficient of RhB:

$$D_{\text{RhB}} = \frac{D_{21.5} T_x \eta_{21.5}}{T \eta_x}, \quad (2)$$

where D_{RhB} and $D_{21.5}$ are diffusion coefficients of RhB in water at the temperature of experiment (T_x) and 21.5 °C ($T_{21.5}$), respectively, while η_x and $\eta_{21.5}$ represent the

corresponding solution viscosity. Using the ZEN 2010 software, the autocorrelation data acquired was analyzed using the free diffusion model that takes into account the possibility of triplet state during measurement, with diffusion coefficient of RhB in given solution calculated using Eq. (1).

2.4 Rheology

A HR-1 Discovery Hybrid Rheometer with double wall geometry was used to quantify the viscosity of the PVA solutions (without RhB) at a constant temperature (25 °C) as a function of shear rate. Prior to each measurement, solutions were sonicated for 20 min at ca. 25 °C, and then allowed to cool to ambient temperature. The rheological data were fit to the Herschel-Bulkley model [70] by the TRIOS software to estimate the viscosity at zero shear rate.

2.5 Dynamic light scattering

DLS measurements were performed using a Zetasizer (Nano-ZS, Malvern Instruments, UK) with a measurement angle of 178° and beam wavelength 632.8 nm at 25 °C. Due to the presence of multiple species in some of the sample solutions, hydrodynamic diameter (d_H) distribution was measured as a function of intensity [71] over three repeats. Hydrodynamic diameter was estimated using the Malvern software.

3 Results and discussion

3.1 Determining the appropriate model for PVA diffusion in solution

Dynamics of polymers in solution is determined by their concentration, with three distinguishable regimes: in the dilute regime, each polymer chain can be treated individually; in the intermediate semi-dilute regime, polymer coils overlap and their diffusion is dominated by a reptation process, with chains moving primarily parallel to their own backbones; while in the concentrated regime, chains are in close proximity to the others, with consequent interactions [45,72]. A polymer solution is in the semi-dilute regime when its concentration is greater than the overlap concentration (c^*) that can be calculated according to Eq. (3) [45]:

$$c^* = \frac{3M_w}{4\pi N_A R_g^3}, \quad (3)$$

where N_A is Avogadro's number, and R_g is the radius of gyration. R_g of the PVA molecules used in the present work is in the region of 6.7–10.3 nm, calculated with Eq. (4) [73]:

$$R_g = 0.0388M_w^{0.5}. \quad (4)$$

Minimum value of c^* (1.1 wt%) suggests that most of the investigated solutions in the present work are in the semi-dilute regime, wherein the thermodynamic behavior is governed by a specific correlation length (ξ)—the average distance between the points of entanglement of different chains.

The difference between ξ and the size of the molecular probe introduces three sub-regimes of semi-dilute regime: for probes whose size is either far greater or smaller than ξ , viscosity of the solution or pure solvent, respectively, determine their diffusion rates [12,58]. However, for molecular size that is of the same order of magnitude as ξ (ca. 1.14 nm for RhB) [75], further investigation into dominating factors controlling the diffusion processes is required [12]. To assess ξ , Eq. (5) was used [75]:

$$\frac{R_g}{\xi} = \left(\frac{c}{c^*}\right)^{0.75}, \quad (5)$$

where c is concentration of polymer solution. The average values of ξ (Table 1) and its minimum in the currently investigated system (2.6 nm) are either lower or of the same magnitude as R_g of PVA, confirming the finding that all samples investigated can be treated as belonging to semi-dilute regime [76]. Moreover, since the value of ξ is in general of the same order of magnitude as d_H of the tracer used, it is appropriate to use the third subregime. Therein, a semi-empirical stretched exponential function (such as in Eq. (6)) [66] has been developed to describe its diffusion behavior:

$$\frac{D}{D_0} = \exp(-\beta c^n), \quad (6)$$

where D_0 is the diffusion coefficient of RhB in pure solvent; n is a scaling parameter related to the polymer chain excluded volume, which reflects the solubility of the polymer ($n = 1$ for theta solvent and $n = 0.75$ for good solvent); and β is a pre-factor related to the probe size that can be described by Eq. (7) [12]:

$$\beta = \frac{R}{r \cdot c^{*n}}, \quad (7)$$

where R is the radius of the probe, and r is the average polymer chain size, signifying that β scales linearly with the size of the probe particle, which was confirmed experimentally [12]. Equation (6) provided a satisfactory fit for changes of diffusion coefficient of particles in semi-dilute PVA solutions [12], and was used in the present work to interpret diffusivity measurements as a function of PVA concentration with or without the addition of glycerol to estimate β and n .

3.2 Molecular diffusion in PVA solutions

Diffusion of the molecular probe, RhB, in PVA solutions was quantified using FCS with three sets of independent

experiments on different days. Figure 2 shows the relationship between the measured diffusion coefficients (D), upon satisfactory fit of the autocorrelation function (Fig. S1, cf. Electronic Supplementary Material, ESM), and the concentrations of PVA (0–4% (w/v)), using Eq. (6). It was found that there is a decrease in RhB diffusion coefficient (from $432.4 \mu\text{m}^2 \cdot \text{s}^{-1}$ to $188.4 \mu\text{m}^2 \cdot \text{s}^{-1}$ for solutions 1 and 6, respectively) with an increased PVA concentration. Using the least squares method, values of $\beta = 0.270 \pm 0.019$ and $n = 0.767 \pm 0.046$ were obtained, which are consistent with the values reported in literature for tracer molecules of similar chemistry and/or size [12], and confirming that water is a good solvent for PVA ($n \approx 0.75$).

The observed reduction in the diffusivity of RhB is likely attributed to the increased crowding density (itself a function of the polymer concentration), which can be directly correlated with the reduced hydrodynamic diameter of PVA (d_H) determined by DLS (Fig. 3(a)) and the corresponding ξ (Table 1). For all of the investigated solutions, a polymodal size distribution was observed, which is inconsistent with a previous report for PVA of similar DH [77], but agrees with the behavior of an almost completely hydrolysed PVA [78]. According to the calculated R_g , peak I in Fig. 3 is assigned to the individual PVA chains, of which the maximum is shifted to lower d_H when there is less room available as the result of an increased number of molecules. This in turn leads to a significantly increased crowding density, impeding the migration of the probe. It is likely that peak II found in the size distribution profiles in Fig. 3 corresponds to polymer aggregates [78], while peak III is a sign of large clusters [79] in the solution. Considering that the scattered light intensity is proportional to diameter of given particle to the sixth power, the signal scattered from aggregates in intensity plot is amplified [80]. Majority of the scattered signal detected contributes to peak I, suggesting that the quantity of polymer aggregates and clusters is rather insignificant in the present work.

Hydrodynamic radius of PVA was estimated to be in the range of 10.3–15.9 nm, following Eq. (8) [81]:

$$\frac{d_H}{R_g} = 1.5. \quad (8)$$

The value calculated from Eq. (8) is greater than the average d_H acquired from samples 2–6 (Table 1), which is likely due to the presence of steric obstructions in discussed system. Since water is a good solvent for PVA, only weak excluded-volume interactions are present, with changes in viscosity directly correlated with the overlapping of the polymer chains [82]. The increased solution viscosity with increasing polymer concentration (Table 1) alongside the crowding density effects proven by DLS measurements confirms the effect of polymer–polymer interactions on molecular migration in the semi-dilute regime.

3.3 Molecular diffusion in PVA/glycerol binary solutions

Glycerol, commonly used as a plasticiser for PVA based products such as water soluble films [83], competes with PVA molecules to form PVA–glycerol hydrogen bonds at the expense of PVA–PVA hydrogen bonds. However, both types of interaction could be hampered when glycerol and PVA molecules are well solvated by an excessive amount of water. Addition of glycerol led to an increased viscosity (Table 2), reducing the diffusivity of the molecular probe due to the additional crowding effects.

To distinguish the effects of the overall solute concentration and the interactions between PVA and glycerol, two additional sets of samples (1a–5a and 2b–5b) were prepared, keeping either the total (PVA + glycerol) or PVA concentration constant, for which the molar ratio between PVA and glycerol was equivalent (i.e., the PVA/glycerol molar ratio in sample 2a is the same as in sample 2b). Compositions of the binary PVA/glycerol solutions investigated are presented in Table 2. As new species are introduced, it is expected that the D of RhB will decrease, either due to PVA–glycerol interactions (leading to increased polymer–plasticiser aggregate size and consequent increase in RhB mean free path) or overall molecular crowding (leading to macroscale increase in viscosity).

3.3.1 Synergistic effect of water and glycerol

The diffusion coefficients of RhB in PVA/glycerol binary mixtures were found to decrease nonlinearly with an

Table 1 Compositions used to investigate the dependence of RhB diffusion coefficient on PVA concentration ^{a)}

Sample	PVA concentration/wt%	Average ξ /nm	Average η /(mPa·s)	Average d_H /nm
1	0.0	0.0	0.890 [74]	–
2	1.0	19.9	1.184 ± 0.016	12.6 ± 0.2
3	2.0	11.9	1.813 ± 0.032	8.2 ± 0.1
4	3.0	8.8	2.669 ± 0.024	6.1 ± 0.1
5	3.3	8.0	2.975 ± 0.024	6.0 ± 0.1
6	4.0	7.1	4.052 ± 0.081	3.8 ± 0.1

a) Average number of repeating units in PVA molecule used in the calculation is 581.

Fig. 2 Normalized diffusion coefficient of RhB as a function of PVA concentration without (samples 2–6) and with glycerol (samples 1a–5a). Solid lines represent fitting based on Eq. (6), with diffusion coefficient calculated using Eq. (1). Closed symbols correspond to PVA solution diluted with water, while open symbols are for PVA solution diluted with glycerol solution. Color code for each PVA concentration corresponds to DLS data (Fig. 3). Standard errors are based on 10 measurements.

increasing PVA concentration (Fig. 2), in a similar trend to that observed for PVA solution without glycerol (samples 2–5). Both sets of FCS experiments (solutions with or without glycerol) were investigated on the same day to minimise the experimental errors due to any potential variations in environmental conditions, laser output, or calibration.

Overall, addition of glycerol solution instead of water led to an increased diffusion time for solutions of the same PVA concentration. Following a stretched exponential fit (Eq. (6)), β and n were estimated as 0.304 ± 0.016 and 0.666 ± 0.036 for samples 2a–5a, accordingly. In here, glycerol stock solution was treated as a new solvent, hence diffusion coefficient of RhB in this solution was used as D_0 (Eq. (6)). Different fitted values both of β and n may arise due to the composition of the solvent, i.e., normalization against D_0 . Statistical t -test result ($\alpha = 0.05$) confirms that there was no significant difference in the measured diffusion coefficients of RhB in PVA solutions with (2a–5a) or without glycerol (2–5), as presented in Table S1 (cf. ESM). It can be concluded that concentration of PVA in the solvent plays a dominant role in determining the diffusivity of PVA at low glycerol concentration (up to 4% (w/v)).

The decreased value of n indicates a reduced solvent quality, while the increased pre-factor β suggests migration of molecule of larger size. These are attributed to the interactions between glycerol and the other species present. RhB-glycerol interactions will slow the tracer diffusion directly due to entrainment of larger molecules in the solvation shell, whereas in the case of PVA, larger glycerol–PVA aggregates will increase the solution molecular crowding hence indirectly slowing tracer diffusion.

The latter is responsible for the changes observed in

PVA size distribution with samples 2a–5a (Fig. 3(b)). Similar to samples 2–5, shift of the size distribution toward larger d_H with increasing dilution of the system is observed. However, increased viscosity and higher number of solute molecules present in samples 2a–5a, in comparison to samples 2–5, lead to the decrease in d_H of the PVA molecules (Tables 1, 2), resulting in a decreased diffusion coefficient of the probe. Upon dilution by either pure water or glycerol solution, changes in the average d_H of PVA show an almost linear dependence on the viscosity of the solution, while the corresponding DLS autocorrelation functions show almost no change in its characteristics (Fig. S2, cf. ESM).

Fig. 3 Distribution of hydrodynamic diameter for solutions of various PVA concentration with the addition of (a) water, (b) glycerol stock solution, and (c) pure glycerol. The percentage of polymer in the graph is given in % (w/v).

Although it is not possible to exclude the likelihood that the solvation shells of RhB molecules are expanded in glycerol solution, the DLS results acquired strongly imply

that the additional crowding effects are responsible for the increased β values. PVA concentration, however, showed a dominating influence. To clarify conclusions about observed mechanisms, further experiments using higher concentrations of glycerol were carried out.

3.3.2 Effect of glycerol addition

A set of PVA/glycerol binary mixtures (samples 2b–5b, Table 2) were prepared by introducing pure glycerol to PVA solutions to distinguish the effects of glycerol and water on RhB diffusivity. The average diffusion coefficients (Fig. 4) show that glycerol has no notable impact on the RhB diffusion coefficient at low concentrations (0%–3.9% (w/v)), but causes it to decrease at high concentrations (> 3.9% (w/v)).

DLS results of this set of samples (Fig. 3(c)) indicate that increasing glycerol concentration causes a barely noticeable increase in d_H (the minimal shift of peak I that corresponds to the individual PVA molecules), as well an increased intensity of peak II. This suggests a formation of glycerol–PVA complexes (leading to the slight increase in d_H of peak I) and a greater number of polymer–polymer clusters (peak II). In contrast, for samples 2a–5a where the solute concentration was constant, the trend with increasing PVA concentration is similar to that of samples 2–5 (containing only PVA). It appears that chains become more compact (accelerated by the presence of other solutes) as PVA concentration increases to 4% (w/v). Conversely, when PVA concentration is constant but overall solute concentration increases, glycerol–PVA complexes form, leading to the slight increase in measured d_H .

Another factor that determines molecular diffusion is the solution viscosity, of which a constant value was observed up to 1:1 polymer to glycerol mass ratio (Table 2). Glycerol is therefore likely to disrupt polymer–polymer entanglements, which results in no viscosity changes. For sample 2b (containing 10.9 wt% glycerol), however, an increased solution viscosity was observed. It might be attributed to

the high viscosity of glycerol itself (ca. 0.945 Pa·s for pure glycerol [84] cf. 0.890 mPa·s for water [74] at 25 °C), which becomes important once 1:1 ratio of components is reached.

It is worth noting that the increased glycerol content in samples 2b and 3b resulted in a broad range of diffusion times and consequent diffusion coefficient (as can be seen by relatively large error bars in Fig. 4 as glycerol concentration increases), with measurements of much slower diffusion time compared to samples 4b and 5b noted, and an overall decrease of RhB diffusivity. It is probable that samples 4b and 5b have a more homogeneous composition, where crowding effects is less important than for samples 2b and 3b. Samples of low glycerol content show smaller changes in d_H (Table 2) compared against solution 6 (4.0 wt% PVA only), which, together with the described viscosity behavior, leads to a similar diffusion coefficient of the tracer to that in PVA stock solution. As for sample 3b, increased amount of solute molecules is likely the more pronounced effect than viscosity values similar to that of PVA stock solution, despite the minor increase in the average d_H . PVA–glycerol clusters therefore influence the migration of the molecular probe: the higher glycerol concentration, the more visible change in tracer's diffusion coefficient.

Generally, adding glycerol to PVA solutions at low concentrations without adjusting the overall water concentration has a minimal effect on the diffusion characteristics of RhB or the aggregation behavior of PVA compared to the results acquired in pure water. Addition of large quantity of pure glycerol, however, caused a reduction in the diffusivity of RhB. It is worth noting that the size of PVA was very similar in these solutions, indicating that the hydrodynamic diameter of PVA is primarily dependent on its concentration, while the addition of glycerol appeared to promote the formation of PVA–glycerol complex. With this characterization of the effects of adding glycerol on the solution behavior, understanding the effect of introducing our model additives to the discussed system is now possible.

Table 2 Composition of PVA-based solutions with the addition of glycerol ^{a)}

Sample		PVA concentration /wt%	Glycerol concentration /wt%	PVA/glycerol molar ratio	Average η /(mPa·s)	Average d_H /nm
Addition of glycerol solution	1a	0.0	4.0	0:1	0.971 ± 0.011	–
	2a	1.0	3.0	1:1629	1.437 ± 0.051	10.4 ± 0.1
	3a	2.0	2.0	1:543	2.136 ± 0.026	7.5 ± 0.1
	4a	3.0	1.0	1:181	3.065 ± 0.060	5.2 ± 0.1
	5a	3.3	0.7	1:109	3.383 ± 0.004	4.7 ± 0.1
Addition of pure glycerol	2b	3.6	10.9	1:1629	4.574 ± 0.020	5.2 ± 0.2
	3b	3.9	3.9	1:543	4.020 ± 0.044	4.9 ± 0.1
	4b	4.0	1.3	1:181	4.009 ± 0.049	4.4 ± 0.1
	5b	4.0	0.8	1:109	4.024 ± 0.097	4.4 ± 0.1

a) Samples of composition 1a did not provide reliable d_H results.

Fig. 4 Diffusion coefficient of RhB in PVA solution with the addition of pure glycerol. Error bars are one standard error around the mean, number of measurements equal to 10.

3.4 Molecular diffusion in PVA/glycerol/surfactant ternary solutions

Diffusion of RhB in ternary aqueous solutions of PVA, glycerol, and surfactant, were studied to quantitatively establish the effects of crowding and binding on the mobility of the probe, as a function of the surfactant chemistry (cationic/nonionic/anionic). Specifically, the samples were prepared from polymer-surfactant mixtures (samples 4c–4e, Table 3), glycerol and surfactant solutions added to PVA solution (samples 4f–4h, Table 3), as well as from polymer solutions with the addition of pure glycerol and surfactant (samples 4i–4k, Table 3). Instead of the effect of an increased molecular crowding, it is expected that strong directional (i.e., charge-matching) interactions between the ionic surfactants and the tracer will lead to the reduced diffusivity in the system. The nonionic surfactant, however, is expected to act similarly to glycerol.

3.4.1 Addition of glycerol and/or surfactant stock solutions

Average diffusion coefficients of RhB in PVA/glycerol/surfactants ternary mixtures are presented in Fig. 5. It

appears that the addition of surfactant led to a decreased diffusion coefficient of RhB: SDS has the most significant reduction (by 86%), followed by CTAB (by 70%), while $C_{12}E_{10}$ shows the least impact (by 31%), compared with the control solution that had no surfactants. Surfactant seemed to change the nature of the molecular interactions via the formation of charge-matching complexes with RhB. Although this behavior would likely cause the ternary mixtures to become less homogeneous [73,83], diffusion coefficients measured here show a monomodal distribution with low standard error, confirming that the average values reported are representative.

No notable difference in RhB diffusivity was found for system composed of PVA/surfactant solutions with the addition of glycerol stock solution (samples 4f–4h, green bars in Fig. 5), in comparison to the ones diluted by water (samples 4c–4e, blue bars in Fig. 5). Indeed, experiments performed on the same day resulted in the average diffusion times and distributions of very similar range with no statistically significant difference ($\alpha = 0.05$). It is clear that the addition of glycerol at low concentration does not influence the diffusion coefficient of RhB in the polymer solutions with the presence of surfactant and therefore that the surfactants are primarily responsible for such a significant change in probe diffusivity. This is consistent with the findings acquired from the PVA/glycerol binary mixtures (solutions 2a–2e, Table 2), where addition of glycerol solution has minimal effects on RhB diffusivity and PVA particle size.

Strong interactions between RhB and charged surfactants have been identified elsewhere as controlling their behavior both below and above the critical micelle concentration (CMC) due surfactant–dye aggregation or entrapment within micelles [85]. In this study, surfactants were above their respective CMC for all formulations studied with the exception of samples 4c and 4f [86]. The aggregation between RhB and surfactants (in its zwitterionic form following dissociation) [87] hinders its diffusion rate. The findings presented here agree with a previous study which showed that the diffusion coefficient of RhB was significantly reduced due to the SDS-RhB

Table 3 Viscosity and average hydrodynamic diameter of PVA solutions with the addition of glycerol and surfactant of various head group chemistry

Sample	Surfactant	PVA/glycerol/surfactant molar ratio	Average η /(mPa·s)	Average d_H /nm
Addition of water	4c SDS (–)	1:0:14.5	2.462 ± 0.200	5.6 ± 0.2
	4d $C_{12}E_{10}$ (0)	1:0:6.7	2.122 ± 0.034	6.9 ± 0.1
	4e CTAB (+)	1:0:11.4	2.877 ± 0.022	5.1 ± 0.1
Addition of glycerol solution	4f SDS (–)	1:181:14.5	2.939 ± 0.043	4.1 ± 0.1
	4g $C_{12}E_{10}$ (0)	1:181:6.7	2.313 ± 0.040	6.0 ± 0.1
	4h CTAB (+)	1:181:11.4	3.060 ± 0.222	4.5 ± 0.1
Addition of pure glycerol and surfactant	4i SDS (–)	1:181:14.5	5.550 ± 0.230	2.4 ± 0.1
	4j $C_{12}E_{10}$ (0)	1:181:6.7	4.315 ± 0.057	3.9 ± 0.1
	4k CTAB (+)	1:181:11.4	5.658 ± 0.456	2.6 ± 0.1

Fig. 5 Average diffusion coefficient of RhB in PVA solutions with the addition of surfactant and water (samples 4c–4e) or glycerol solution (samples 4f–4h), compared against control samples with no surfactants (4, 4a). Error bars are standard error based on 10 repeats.

interactions that is dependent on the pH of the solution [88]. In addition, there is a possible polymer-surfactant attraction, whose magnitude is determined by the counterion effect of surfactant on water [89] and the chemical characteristics of the compounds involved [90].

Similarly to SDS, CTAB is likely to form charged aggregates with RhB, leading to a substantial change in the diffusion coefficient of RhB, with a similar magnitude for SDS and CTAB [85]. Even though the number of possible interaction sites for cationic and anionic surfactant is the same, accessibility is probably sterically hindered to the anionic moiety of RhB, which explains the differences of RhB diffusivity in ternary PVA solutions with cationic and anionic surfactant (Fig. 6).

3.4.1.1 Specific effects of ionic surfactants (SDS and CTAB)

Upon the introduction of charged surfactants, DLS shows a reduction in average d_H of the PVA molecules (Fig. 7, Tables 2 and 3). This effect is consistent in both PVA-

surfactant mixtures diluted by water (Fig. 7(a)) and by glycerol (Fig. 7(b)).

The polymer-surfactant interactions via their hydrophobic parts are believed to be a major driving force in the system (Fig. 6) [91,92]. SDS was shown to disrupt polymer aggregates in aqueous solution [31]. Such effect was more pronounced for PVA of low DH (i.e., 70%) due to an increased fraction of acetate groups in the polymer chains [77]. Moreover, SDS is capable of shifting PVA-glycerol interaction to glycerol-SDS interactions in PVA films [83]. Even though presented measurements are in liquid state, those interactions are also plausible. The combined effect of increased molecular crowding due to the presence of surfactant micelles as well as polymer-surfactant interactions led to more compact molecular packing, hence decreasing d_H of the PVA.

In addition to the polymer-surfactant interaction, it is likely that the dilution itself could play an important role in the ternary PVA solutions by reducing solution viscosity. In PVA-SDS mixtures, hydrophobic interactions between species result in a preferential adsorption of the surfactants on polymer chains [93], and change viscosity depending on the DH of PVA [92] and amount of surfactant added [93]. Accordingly, both decreased [92,93] and increased [94] viscosity values of PVA solutions containing SDS have been reported. In this study the viscosity decreased, primarily due to the reduced PVA concentration in all solutions discussed in this section after the introduction of surfactant solutions.

Previous studies suggest that CTAB would interact with PVA chain in a similar fashion to SDS, and form a polymer-surfactant complex [92,94,95]. Even though the PVA solution was diluted by the surfactant stock solution in the present work, the average d_H of PVA decreased (Tables 2 and 3), while viscosity either increased or remained unchanged compared to samples 4 and 4a (without addition of surfactant). It is therefore likely that CTAB interacts with PVA via hydrophobic interactions, disrupting the PVA-PVA interactions.

To conclude, two main factors hinder the diffusion of the molecular probe in the PVA-based ternary solutions: first, crowding effect that is caused by the increased polymer

Fig. 6 Possible interactions between (a) RhB and both cationic and anionic surfactants; (b) PVA-surfactant tail group interactions, using SDS molecule as an example.

Fig. 7 Particle size distribution for (a) PVA/water/surfactant (compositions 4c–4e), (b) PVA/glycerol/surfactant solutions (compositions 4f–4h), and (c) PVA/pure glycerol/pure surfactant solutions (compositions 4i–4k). The percentages of polymer and glycerol in the graphs are given in %(w/v).

size and the presence of surfactants; secondly, interactions between RhB and surfactants that slow down the diffusion of the probe [85] (Fig. 6(a)).

3.4.1.2 Effects of nonionic surfactant solutions

Although adding surfactant solutions resulted in only a slight dilution of PVA–glycerol mixture compared to sample 4a, the presence of nonionic surfactants appeared to have a noticeable effect on the diffusion of the fluorescent probe (Fig. 5). While charge-matching aggregation between $C_{12}E_{10}$ and RhB cannot occur due to its nonionic nature, it remains possible for $C_{12}E_{10}$ to interact with PVA via hydrophobic interactions between surfactant tail and acetate groups on the polymer. However, such effect

appears to be less pronounced in comparison to CTAB and SDS addition as the ionic strength of the solution remains constant.

Unlike that of SDS and CTAB, stock solution of $C_{12}E_{10}$ showed a monomodal size distribution (Fig. S3, cf. ESM), with a d_H very similar to peak I of the PVA particle-size distribution. Indeed, overall d_H of solutions 4d and 4g increased compared their corresponding surfactant-free solutions (4 and 4a, Tables 1–3). The increased intensity of peak I in sample 4d (Figs. 7(a) and 7(b)) can be related to both individual PVA molecules and micelles of $C_{12}E_{10}$. Therefore, the nonionic surfactant acts in a similar way to glycerol in the system, however with a larger effect due to the much larger molecular weight of $C_{12}E_{10}$.

Building upon the findings of surfactant–PVA and surfactant–RhB interactions at low concentrations, systems with the addition of pure glycerol and surfactant to PVA stock solution were investigated to study their influence in the absence of dilution (additional water being introduced) in the system.

3.4.2 Crowding and binding effects

Adding pure surfactant and glycerol to PVA solutions showed the same trend to that observed with adding their stock solutions. Their effects on the diffusion of RhB were pronounced in PVA solutions with the addition of anionic surfactant, which decreased by 67% for composition 4i compared to composition 4c (90% compared to 4b). For cationic and nonionic surfactants, the diffusion coefficients decreased by 44% and 46% respectively compared to compositions 4d and 4e (Fig. 8), and by 75% and 41%, respectively compared to composition 4b. It is likely that the increased concentration of surfactants led to an additional crowding effect (as seen in the decrease in hydrodynamic diameter in Fig. 7(c)). This is amplified due to the strong interactions between the RhB and surfactant in the now more concentrated solutions. The variation with different head group chemistry provides further evidence for preferential probe–surfactant interactions for charged surfactants, while the relatively weak response of $C_{12}E_{10}$ compared to solution 4b again demonstrates its similar behavior to glycerol.

Addition of surfactant to PVA solutions therefore has a significant retarding effect on the diffusivity of RhB, with the driving force for these changes being largely dependent on head group chemistry: 1) For nonionic surfactant ($C_{12}E_{10}$), a minimal interactions with the fluorescence probe is suspected, with the diffusivity of RhB being determined by the enhanced crowding effects the surfactant places on the PVA molecules. 2) For anionic surfactant (SDS), there are strong interactions between surfactant–PVA and surfactant–probe, leading to a significantly reduced diffusivity compared to the nonionic surfactant. 3) For cationic surfactant (CTAB), although the same type

Fig. 8 Average diffusion coefficients of RhB in PVA solutions with the addition of pure glycerol and surfactant (samples 4i–4k, blue columns), compared against equivalent samples with the addition of glycerol and surfactant solutions (4f–4h, green columns) and corresponding control solutions containing no surfactant (4b and 4a). Error bars are standard error based on 10 repeats.

of interactions is present as in the system with SDS (i.e., hydrophobic interactions between tail group and PVA, and charge-matching interactions between head group and RhB), steric barriers reducing the surfactant–tracer interaction strength cause a slightly lower change in tracer diffusivity.

The explanations above are supported by the viscosity data presented in Table 3. The changes in the viscosity of PVA ternary solutions were negligible when nonionic surfactant was used, but significant when ionic surfactants were interacting with the PVA molecules, in agreement with previous findings [94]. For all investigated solutions, no phase separation was observed (which is in line with results published for PVA–water–SDS system) [83].

4 Conclusions

Diffusion behaviour of a molecular probe (RhB) in a series of aqueous PVA solutions, representing complex formulations involved in industrial processes, was examined in the present work as a function of polymer and plasticiser concentration, as well as the presence of surfactants of various head group chemistry. For the PVA solutions, our results demonstrate a good agreement with the scaling theory of anomalous diffusion in semi-dilute polymer systems, showing a nonlinear increase of diffusion coefficient of the probe with decreasing polymer concentration. PVA solutions diluted by glycerol solutions do not exhibit significant changes in the mobility of RhB, proving the vital role of PVA concentration. For PVA solutions with an increased glycerol concentration, crowding effects play an important role in the system, leading to a decreased

diffusivity of the probe due to the increased diffusion path length.

Crowding effects also provided a plausible explanation for the diffusion kinetics in the PVA solutions with the addition of nonionic surfactant. However, for solutions with the addition of cationic and anionic surfactant, surfactant–PVA and surfactant–RhB interactions play a dominant role, slowing down the migration of the tracer. These interactions are strengthened in the more concentrated PVA solutions with an additional pure glycerol and surfactant (rather than their respective solutions), indicating that the concentration of each individual chemical compound (polymer and additives) present in the PVA ternary solutions has a profound influence on the diffusivity of the molecular probe.

Acknowledgements This research was funded by School of Chemical Engineering, University of Birmingham, and Engineering & Physical Science Research Council (EPSRC) with grant number EP/P007864/1. ZJZ acknowledges an Industrial Fellowship with P&G, funded by the Royal Academy of Engineering (IF2021\100).

Electronic Supplementary Material Supplementary material is available in the online version of this article at <https://dx.doi.org/10.1007/s11705-021-2121-3> and is accessible for authorized users.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

- Moraes I C F, Carvalho R A, Bittante A M Q B, Solorza-Feria J, Sobral P J A. Film forming solutions based on gelatin and poly(vinyl alcohol) blends: thermal and rheological characterizations. *Journal of Food Engineering*, 2009, 95(4): 588–596
- Hasimi A, Stavropoulou A, Papadokostaki K G, Sanopoulou M. Transport of water in polyvinyl alcohol films: effect of thermal treatment and chemical crosslinking. *European Polymer Journal*, 2008, 44(12): 4114–4123
- Kawai F, Hu X. Biochemistry of microbial polyvinyl alcohol degradation. *Applied Microbiology and Biotechnology*, 2009, 84(2): 227–237
- Kim D Y, Rhee Y H. Biodegradation of microbial and synthetic polyesters by fungi. *Applied Microbiology and Biotechnology*, 2003, 61(4): 300–308
- Bergo P, Moraes I C F, Sobral P J A. Effects of different moisture contents on physical properties of PVA–gelatin films. *Food Biophysics*, 2012, 7(4): 354–361
- El-Nasser H M. Effects of methyl red acidity and UV illumination

- on absorption coefficient of MR/PVA thin films. *Physica B, Condensed Matter*, 2011, 406(10): 1940–1943
7. Konidari M V, Papadokostaki K G, Sanopoulou M. Moisture-induced effects on the tensile mechanical properties and glass-transition temperature of poly(vinyl alcohol) films. *Journal of Applied Polymer Science*, 2011, 120(6): 3381–3386
 8. Hodge R M, Bastow T J, Edward G H, Simon G P, Hill A J. Free volume and the mechanism of plasticization in water-swollen poly (vinyl alcohol). *Macromolecules*, 1996, 29(25): 8137–8143
 9. Fick A. On liquid diffusion. *The London, Edinburgh, and Dublin Philosophical Magazine and Journal of Science*, 1855, 10(63): 30–39
 10. Miller C C. The Stokes–Einstein law for diffusion in solution. *Proceedings of the Royal Society of London. Series A, Containing Papers of a Mathematical and Physical Character*, 1924, 106(740): 724–749
 11. Masuda A, Ushida K, Okamoto T. New fluorescence correlation spectroscopy (FCS) suitable for the observation of anomalous diffusion in polymer solution: time and space dependences of diffusion coefficients. *Journal of Photochemistry and Photobiology A Chemistry*, 2006, 183(3): 304–308
 12. Michelman-Ribeiro A, Horkay F, Nossal R, Boukari H. Probe diffusion in aqueous poly(vinyl alcohol) solutions studied by fluorescence correlation spectroscopy. *Biomacromolecules*, 2007, 8(5): 1595–1600
 13. Bu Z, Russo P S. Diffusion of dextran in aqueous (hydroxypropyl) cellulose. *Macromolecules*, 1994, 27(5): 1187–1194
 14. Amsden B. Solute diffusion in hydrogels: an examination of the retardation effect. *Polymer Gels and Networks*, 1998, 6(1): 13–43
 15. Mustafa M B, Tipton D L, Barkley M D, Russo P S, Blum F D. Dye diffusion in isotropic and liquid crystalline aqueous (hydroxypropyl)cellulose. *Macromolecules*, 1993, 26(2): 370–378
 16. Ventas J S, Duda J L. Diffusion in polymer-solvent systems. I. Reexamination of the free-volume theory. *Journal of Polymer Science. Polymer Physics Edition*, 1977, 15(12): 403–416
 17. Ventas J S, Duda J L. Diffusion in polymer-solvent systems. II. A predictive theory for the dependence of diffusion coefficient on temperature, concentration, and molecular weight. *Journal of Polymer Science. Polymer Physics Edition*, 1977, 15(12): 417–439
 18. Phillies G D J. Universal scaling equation for self-diffusion by macromolecules in solution. *Macromolecules*, 1986, 19(9): 2367–2376
 19. Park I H, Johnson C S, Hill C, Carolina N, Gabriel D A. Probe diffusion in polyacrylamide gels as observed by means of holographic relaxation methods: search for a universal equation. *Macromolecules*, 1990, 23(5): 1548–1553
 20. Senanayake K K, Fakhraabadi E A, Liberatore M W, Mukhopadhyay A. Diffusion of nanoparticles in entangled poly(vinyl alcohol) solutions and gels. *Macromolecules*, 2019, 52(3): 787–795
 21. Slim A H, Poling-Skutvik R, Conrad J C. Local confinement controls diffusive nanoparticle dynamics in semidilute polyelectrolyte solutions. *Langmuir*, 2020, 36(31): 9153–9159
 22. Gratz M, Tschöpe A. Size effects in the oscillatory rotation dynamics of Ni nanorods in poly(ethylene oxide) solutions. *Macromolecules*, 2019, 52(17): 6600–6612
 23. Cherdhirankorn T, Harmandaris V, Juhari A, Voudouris P, Fytas G, Kremer K, Koynov K. Fluorescence correlation spectroscopy study of molecular probe diffusion in polymer melts. *Macromolecules*, 2009, 42(13): 4858–4866
 24. Senanayake K K, Shokeen N, Fakhraabadi E A, Liberatore M W, Mukhopadhyay A. Diffusion of nanoparticles within a semidilute polyelectrolyte solution. *Soft Matter*, 2019, 15(38): 7616–7622
 25. Wang W, Barkai E, Burov S. Large deviations for continuous time random walks. *Entropy (Basel, Switzerland)*, 2020, 22(6): 697–719
 26. Xue C, Shi X, Tian Y, Zheng X, Hu G. Diffusion of nanoparticles with activated hopping in crowded polymer solutions. *Nano Letters*, 2020, 20(5): 3895–3904
 27. Jia D, Muthukumar M. Electrostatically driven topological freezing of polymer diffusion at intermediate confinements. *Physical Review Letters*, 2021, 126(5): 057802
 28. Banks D S, Tressler C, Peters R D, Höfling F, Fradin C. Characterizing anomalous diffusion in crowded polymer solutions and gels over five decades in time with variable-lengthscale fluorescence correlation spectroscopy. *Soft Matter*, 2016, 12(18): 4190–4203
 29. Guillemet F, Piculell L. Interactions in aqueous mixtures of hydrophobically modified polyelectrolyte and oppositely charged surfactant: mixed micelle formation and associative phase separation. *Journal of Physical Chemistry*, 1995, 99(22): 9201–9209
 30. Langevin D. Complexation of oppositely charged polyelectrolytes and surfactants in aqueous solutions: a review. *Advances in Colloid and Interface Science*, 2009, 147–148: 170–177
 31. Lewis K E, Robinson C P. The interaction of sodium dodecyl sulfate with methyl cellulose and polyvinyl alcohol. *Journal of Colloid and Interface Science*, 1970, 32(3): 539–546
 32. Qiu L, Cheng M, Xie A, Shen Y. Study on the viscosity of cationic gemini surfactant-nonionic polymer complex in water. *Journal of Colloid and Interface Science*, 2004, 278(1): 40–43
 33. Negm N A, Mohamed A S, Ahmed S M, El-Raouf M A. Polymer-cationic surfactant interaction. I. Surface and physicochemical properties of polyvinyl alcohol (PVA)-S-alkyl isothiuronium bromide surfactant mixed systems. *Journal of Surfactants and Detergents*, 2015, 18(2): 245–250
 34. Trabelsi S, Guillot S, Ritacco H, Boué F, Langevin D. Nanostructures of colloidal complexes formed in oppositely charged polyelectrolyte/surfactant dilute aqueous solutions. *European Physical Journal E*, 2007, 23(3): 305–311
 35. Babak V G, Merkovich E A, Desbrières J, Rinaudo M. Formation of an ordered nanostructure in surfactant-polyelectrolyte complexes formed by interfacial diffusion. *Polymer Bulletin*, 2000, 45(1): 77–81
 36. Zana R, Lianos P, Lang J. Fluorescence probe studies of the interactions between poly(oxyethylene) and surfactant micelles and microemulsion droplets in aqueous solutions. *Journal of Physical Chemistry*, 1985, 89(1): 41–44
 37. Wöll D. Fluorescence correlation spectroscopy in polymer science. *RSC Advances*, 2014, 4(5): 2447–2465
 38. Annunziata O, Buzatu D, Albright J G. Protein diffusion coefficients determined by macroscopic-gradient rayleigh interferometry and dynamic light scattering. *Langmuir*, 2005, 21(26): 12085–12089
 39. Ivanov D A, Grossmann T, Winkelmann J. Comparison of ternary diffusion coefficients obtained from dynamic light scattering and

- Taylor dispersion. *Fluid Phase Equilibria*, 2005, 228–229: 283–291
40. Wang S, Sun P, Zhang R, Lu A, Liu M, Zhang L. Cation/macromolecule interaction in alkaline cellulose solution characterized with pulsed field-gradient spin-echo NMR spectroscopy. *Physical Chemistry Chemical Physics*, 2017, 19(11): 7486–7490
41. Baldwin R L, Ogston A G. The diffusion and sedimentation coefficients of a liquid two-component system in terms of macroscopic properties of the system. *Transactions of the Faraday Society*, 1954, 50: 749–755
42. Ono M, Mashim T. Sedimentation process for atoms in a Bi-Sb system alloy under a strong gravitational field: a new type of diffusion of substitutional solutes. *Philosophical Magazine. A. Physics of Condensed Matter. Structure, Defects and Mechanical Properties*, 2002, 82(3): 591–600
43. Zettl U, Hoffmann S T, Koberling F, Krausch G, Enderlein J, Harnau L, Ballauff M. Self-diffusion and cooperative diffusion in semidilute polymer solutions as measured by fluorescence correlation spectroscopy. *Macromolecules*, 2009, 42(24): 9537–9547
44. Giacin J R. Evaluation of plastics packaging materials for food packaging applications: food safety considerations. *Journal of Food Safety*, 1980, 2(4): 257–276
45. Liu R, Gao X, Adams J, Oppermann W. A fluorescence correlation spectroscopy study on the self-diffusion of polystyrene chains in dilute and semidilute solution. *Macromolecules*, 2005, 38(21): 8845–8849
46. Zettl H, Zettl U, Krausch G, Enderlein J, Ballauff M. Direct observation of single molecule mobility in semidilute polymer solutions. *Physical Review. E*, 2007, 75(6): 194–196
47. Zettl H, Hafner W, Boker A, Schmalz H, Lanzendorfer M, Muller A H E, Krausch G. Fluorescence correlation spectroscopy of single dye-labeled polymers in organic solvents. *Macromolecules*, 2004, 37(5): 1917–1920
48. Cai L, Panyukov S, Rubinstein M. Mobility of nonsticky nanoparticles in polymer liquids. *Macromolecules*, 2011, 44(19): 7853–7863
49. Cherdhirankorn T, Best A, Koynov K, Peneva K, Muellen K, Fytas G. Diffusion in polymer solutions studied by fluorescence correlation spectroscopy. *Journal of Physical Chemistry B*, 2009, 113(11): 3355–3359
50. Boukari H, Nossal R, Sackett D, Schuck P. Hydrodynamics of nanoscopic tubulin rings in dilute solutions. *Physical Review Letters*, 2004, 93(9): 098106
51. Michelman-Ribeiro A, Boukari H, Nossal R, Horkay F. Fluorescence correlation spectroscopy study of probe diffusion in poly(vinyl alcohol) solutions and gels. *Macromolecular Symposia*, 2005, 227(1): 221–230
52. Pristinski D, Kozlovskaya V, Sukhishvili S A. Fluorescence correlation spectroscopy studies of diffusion of a weak polyelectrolyte in aqueous solutions. *Journal of Chemical Physics*, 2005, 122(1): 14907–14910
53. Zhao J J, Bae S C, Xie F, Granick S. Diffusion of polymer-coated nanoparticles studied by fluorescence correlation spectroscopy. *Macromolecules*, 2001, 34(10): 3123–3126
54. Enderlein J, Gregor I, Patra D, Dertinger T, Kaupp U B. Performance of fluorescence correlation spectroscopy for measuring diffusion and concentration. *ChemPhysChem*, 2005, 6(11): 2324–2336
55. Zustiak S P, Nossal R, Sackett D L. Hindered diffusion in polymeric solutions studied by fluorescence correlation spectroscopy. *Biophysical Journal*, 2011, 101(1): 255–264
56. Rusu L, Lumma D, Rädler J O. Charge and size dependence of liposome diffusion in semidilute biopolymer solutions. *Macromolecular Bioscience*, 2010, 10(12): 1465–1472
57. Vagias A, Raccis R, Koynov K, Jonas U, Butt H, Fytas G, Kosovan P, Lenz O, Holm C. Complex tracer diffusion dynamics in polymer solutions. *Physical Review Letters*, 2013, 111(8): 088301
58. Omari R A, Aneese A M, Grabowski C A, Mukhopadhyay A. Diffusion of nanoparticles in semidilute and entangled polymer solutions. *Journal of Physical Chemistry B*, 2009, 113(25): 8449–8452
59. Rashid R, Chee S M L, Raghunath M, Wohland T. Macromolecular crowding gives rise to microviscosity, anomalous diffusion and accelerated actin polymerization. *Physical Biology*, 2015, 12(3): 034001
60. Ochab-Marcinek A, Hołyst R. Scale-dependent diffusion of spheres in solutions of flexible and rigid polymers: mean square displacement and autocorrelation function for FCS and DLS measurements. *Soft Matter*, 2011, 7(16): 7366–7369
61. Dong Y, Feng X, Zhao N, Hou Z. Diffusion of nanoparticles in semidilute polymer solutions: a mode-coupling theory study. *Journal of Chemical Physics*, 2015, 143(2): 024903
62. Mchedlov-Petrosyan N O, Vodolazkaya N A, Doroshenko A O. Ionic equilibria of fluorophores in organized solutions: the Influence of micellar microenvironment on protolytic and photophysical properties of rhodamine B. *Journal of Fluorescence*, 2003, 13(3): 235–248
63. Merouani S, Hamdaoui O, Saoudi F, Chiha M. Sonochemical degradation of rhodamine B in aqueous phase: effects of additives. *Chemical Engineering Journal*, 2010, 158(3): 550–557
64. Arbeloa I L, Ojeda P R. Molecular forms of rhodamine B. *Chemical Physics Letters*, 1981, 79(2): 347–350
65. Soares E T, Lansarin M A, Moro C C. A study of process variables for the photocatalytic degradation of rhodamine B. *Brazilian Journal of Chemical Engineering*, 2007, 24(1): 29–36
66. Goins A B, Sanabria H, Waxham M N. Macromolecular crowding and size effects on probe microviscosity. *Biophysical Journal*, 2008, 95(11): 5362–5373
67. Mohsin M, Hossin A, Haik Y. Thermal and mechanical properties of poly(vinyl alcohol) plasticized with glycerol. *Journal of Applied Polymer Science*, 2011, 122(5): 3102–3109
68. Dix L R, Gilblas R. Lyotropic and interfacial behaviour of an anionic gemini surfactant. *Journal of Colloid and Interface Science*, 2006, 296(2): 762–765
69. Zhang Z, Mosey M, Alswieleh A, Morse A J, Lewis A L, Geoghegan M, Leggett A J. Effect of salt on phosphorylcholine-based zwitterionic polymer brushes. *Langmuir*, 2016, 32(20): 5048–5057
70. Shakouri A, Ahmari H, Hojjat M, Zeinali Heris S. Effect of TiO₂ nanoparticle on rheological behavior of poly(vinyl alcohol) solution. *Journal of Vinyl and Additive Technology*, 2017, 23(3): 234–240
71. Stetefeld J, McKenna S A, Patel T R. Dynamic light scattering: a practical guide and applications in biomedical sciences. *Biophysical*

- Reviews, 2016, 8(4): 409–427
72. Phillies G D J. Dynamics of macromolecules in concentrated solutions: the universal scaling function derived. *Macromolecules*, 1987, 20(3): 558–564
73. Briddick A, Li P, Hughes A, Courchay F, Martinez A, Thompson R L. Surfactant and plasticizer segregation in thin poly(vinyl alcohol) films. *Langmuir*, 2016, 32(3): 864–872
74. Korosi A, Fabuss B M. Viscosity of liquid water from 25 to 150 °C: measurements in pressurized glass capillary viscometer. *Analytical Chemistry*, 1968, 40(1): 157–162
75. Sozański K, Wiśniewska A, Kalwarczyk T, Hołyst R. Activation energy for mobility of dyes and proteins in polymer solutions: from diffusion of single particles to macroscale flow. *Physical Review Letters*, 2013, 111(22): 228301
76. Ohta T, Nakanishi A. Theory of semi-dilute polymer solutions. I. Static property in a good solvent. *Journal of Physics. A, Mathematical and General*, 1983, 16(17): 4155–4170
77. Atanase L I, Riess G. Poly(vinyl alcohol-co-vinyl acetate) complex formation with anionic surfactants particle size of nanogels and their disaggregation with sodium dodecyl sulfate. *Colloids and Surfaces. A, Physicochemical and Engineering Aspects*, 2010, 355(1–3): 29–36
78. Kjøniksen A L, Nyström B. Dynamic light scattering of poly(vinyl alcohol) solutions and their dynamical behavior during the chemical gelation process. *Macromolecules*, 1996, 29(22): 7116–7123
79. Taylor S J, Haw M D, Sefcik J, Fletcher A J. Gelation mechanism of resorcinol-formaldehyde gels investigated by dynamic light scattering. *Langmuir*, 2014, 30(34): 10231–10240
80. Tomaszewska E, Soliwoda K, Kadziola K, Tkacz-Szczesna B, Celichowski G, Cichomski M, Szmaja W, Grobelny J. Detection limits of DLS and UV-Vis spectroscopy in characterization of polydisperse nanoparticles colloids. *Journal of Nanomaterials*, 2013, 2013: 1–10
81. Kok C M, Rudin A. Relationship between the hydrodynamic radius and the radius of gyration of a polymer in solution. *Die Makromolekulare Chemie. Rapid Communications*, 1981, 2(11): 655–659
82. Hong P, Chou C, He C. Solvent effects on aggregation behavior of polyvinyl alcohol solutions. *Polymer*, 2001, 42(14): 6105–6112
83. Briddick A, Fong R J, Sabattie E F D, Li P, Skoda M W A, Courchay F, Thompson R L. Blooming of smectic surfactant/plasticizer layers on spin-cast poly(vinyl alcohol) films. *Langmuir*, 2018, 34(4): 1410–1418
84. Sheely M L. Glycerol viscosity tables. *Industrial & Engineering Chemistry*, 1932, 24(9): 1060–1064
85. Tajalli H, Ghanadzadeh Gilani A, Zakerhamidi M S, Moghadam M. Effects of surfactants on the molecular aggregation of rhodamine dyes in aqueous solutions. *Spectrochimica Acta. Part A: Molecular and Biomolecular Spectroscopy*, 2009, 72(4): 697–702
86. Hansson P, Lindman B. Surfactant-polymer interactions. *Current Opinion in Colloid & Interface Science*, 1996, 1(5): 604–613
87. McHedlov-Petrosyan N O, Kholin Y V. Aggregation of rhodamine B in water. *Russian Journal of Applied Chemistry*, 2004, 77(3): 414–422
88. Haglund B O, Sundelöf L, Upadrashta S M, Wurster D E. Effect of SDS micelles on rhodamine-B diffusion in hydrogels. *Journal of Chemical Education*, 1996, 73(9): 889
89. Saito S, Yukawa M. Interactions of polymers and cationic surfactants with thiocyanate as counterions. *Journal of Colloid and Interface Science*, 1969, 30(2): 211–218
90. Saito S, Kitamura K. Counterion effect of tetraalkylammonium and long-chain alkylammonium salts in the interaction with nonionic polymers. *Journal of Colloid and Interface Science*, 1971, 35(2): 346–353
91. Nakagaki M, Ninomiya Y. Colloid chemical studies of starching materials. VI. Viscometric studies of the interaction between polyvinyl alcohol and sodium dodecyl sulfate. *Bulletin of the Chemical Society of Japan*, 1964, 37(6): 817–821
92. Arai H, Horin S, Goods H. Interaction between polymer and detergent in aqueous solution. *Journal of Colloid and Interface Science*, 1969, 30(3): 372–377
93. Isemura T, Imanishi A. The dissolution of water-insoluble polymers in the surfactant solution: the polyelectrolyte-like behavior of the dissolved polymers. *Journal of Polymer Science*, 1958, 33(126): 337–352
94. Jia L, Qin X. The effect of different surfactants on the electrospinning poly(vinyl alcohol) (PVA) nanofibers. *Journal of Thermal Analysis and Calorimetry*, 2013, 112(2): 595–605
95. Tadros T F. The interaction of cetyltrimethylammonium bromide and sodium dodecylbenzene sulfonate with polyvinyl alcohol: adsorption of the polymer-surfactant complexes on silica. *Journal of Colloid and Interface Science*, 1974, 46(3): 528–540