Alternative Strategies Toward Sustainable Ammonia Synthesis

Chengcheng Li^{1,2,3,4} · Tuo Wang^{1,2,3} · Jinlong Gong^{1,2,3}

Received: 2 January 2020 / Revised: 16 January 2020 / Accepted: 15 February 2020 / Published online: 13 March 2020
© The Author(s) 2020

Abstract

As one of the world's most produced chemicals, ammonia (NH₃) is synthesized by Haber–Bosch process. This century-old industry nourishes billions of people and promotes social and economic development. In the meantime, 3%–5% of the world's natural gas and 1%–2% of the world's energy reserves are consumed, releasing millions of tons of carbon dioxide annually to the atmosphere. The urgency of replacing fossil fuels and mitigating climate change motivates us to progress toward more sustainable methods for N₂ reduction reaction based on clean energy. Herein, we overview the emerging advancement for sustainable N₂ fixation under mild conditions, which include electrochemical, photo-, plasma-enabled and homogeneous molecular NH₃ productions. We focus on NH₃ generation by electrocatalysts and photocatalysts. We clarify the features and progress of each kind of NH₃ synthesis process and provide promising strategies to further promote sustainable ammonia production and construct state-of-the-art catalytic systems.

Keywords Nitrogen fixation · Sustainable ammonia synthesis · Electrocatalyst · Photocatalyst · Ambient conditions

Introduction

Occupying 78% of the atmosphere on the earth in volume and being the fifth most abundant element in solar system, nitrogen is essential for the synthesis of nucleic acids and proteins, which are the most important building blocks of life [1]. This condition is based on the reactive nitrogen that entails dinitrogen (N₂) fixation to its fully hydrogenated product: ammonia (NH₃). However, N₂ fixation is a grand challenge because N₂ molecule is thermodynamically stable with an extremely high triple-bond energy (941 kJ/mol) and insurmountable first-bond cleavage energy (410 kJ/mol) [2]. In nature, only a small group of microorganisms could biologically fix N₂ to NH₃ with the enzyme nitrogenase [3–5]. The most common molybdenum (Mo)-based nitrogenase is a

two-component system, with Fe protein as electron-transfer media and FeMo protein as the N₂-binding and reduction site (Fig. 1a) [6, 7]. During reaction, electrons flow from a pair of adenosine triphosphate (ATP) molecules to the Fe–S cluster within the Fe protein, pass through the P cluster on FeMo protein and finally arrive at the FeMo cofactor (FeMoco), where the reduction of N₂ to NH₃ occurs. The accumulation of 8e[−] results in the reduction of one N₂ molecule along with the reductive elimination of one H₂ molecule [8, 9]:

Figure 1b illustrates the structure of FeMoco, which contains seven Fe atoms and one Mo atom that are bonded to the sulfur bridge with an interstitial carbon atom [10].

Although nitrogenase has long existed in nature, artificial N₂ fixation was invented not until the early twentieth century by Fritz Haber, and Carl Bosch developed the necessary engineering skills [11]. This pioneering work, known as the Haber–Bosch (H–B) process, successfully converts atmospheric N₂ to NH₃ on a large scale by reacting with H₂ using an iron metal-based catalyst under high temperature (400–500 °C) and pressure (100–200 bar):

✉ Tuo Wang
wangtuo@tju.edu.cn

¹ School of Chemical Engineering and Technology, Tianjin University, Tianjin 300072, China

² Key Laboratory for Green Chemical Technology of Ministry of Education, Tianjin 300072, China

³ Collaborative Innovation Center of Chemical Science and Engineering, Tianjin 300072, China

⁴ School of Materials Sciences and Engineering, Nanyang Technological University, Singapore 639798, Singapore

Fig. 1 Biological N_2 fixation. **a** Reaction pathway of N_2 reduction to NH_3 on nitrogenase. Reproduced with permission from Ref. [7]. Copyright 2016, AAAS. **b** Structure of the resting-state FeMoco. Reproduced with permission from Ref. [10]. Copyright 2016, American Chemical Society

To date, the worldwide output of NH_3 by H–B process has exceeded 200 million metric tons per year, which contributes to half of the global nitrogen fixation [12]. A total of 80% of the produced NH_3 is used for fertilizer production [13], whereas the remaining reserves are used in refrigeration, explosives, pharmaceuticals, plastics and other industrial processes [14]. NH_3 is a promising chemical energy carrier candidate, and it could be converted into hydrogen at point of use, showing great application potential in fuel cell technology [15, 16]. Nitrogen fertilizer has supported nearly 4 billion people born since 1908 [17], and more than half of the nitrogen found in the modern human bodies originates from the H–B process [18]. Nonetheless, H–B process consumes 3%–5% of the world's natural gas for H_2 extraction and 1%–2% of the world's energy reserves, belching out millions of tons of carbon dioxide (CO_2), which accounts for 1.5% of all greenhouse gas emissions, annually to the atmosphere [19, 20]. Over the past 150 years, atmospheric CO_2 concentration has increased from 280×10^{-6} to 408×10^{-6} as a result of intensive fossil fuel consumption [21]. The urgency of limiting global warming and fossil energy use has led to intense research on N_2 reduction driven by renewable sources, thus providing effective strategies to close the gap in carbon cycle and address the food supply in the future [22]. On the other hand, H–B process is a highly centralized industry, but fertilizer consumption is distributed throughout agricultural territories [23]. This condition results in elevated transportation costs and emissions, especially for remote and underdeveloped regions.

Therefore, sustainable strategies that would allow NH_3 production under benign conditions at distributed sources must be developed [22].

In addition to enzymatic N_2 fixation in nature, several alternative methods for N_2 reduction reaction (NRR), including electrocatalysis [13, 24–30], photocatalysis [19, 23, 29, 31–33], plasma catalysis [14, 34] and homogeneous molecular catalysis, have been developed [2, 35]. Compared with the H–B process that requires high temperature and pressure, the reactions of these alternative methods are induced under mild conditions, which include partially reduced temperature/pressure [36], high or intermediate temperature with atmospheric pressure [37, 38] and room temperature (RT) with atmospheric pressure (ambient conditions) [39]. On the other hand, the hydrogen of synthesized NH_3 in these alternative methods originates from H_2 (same as in H–B process) or H_2O molecules. From a thermodynamic point of view [22], NH_3 synthesis using N_2 and H_2O at ambient conditions is extremely challenging, but such process will result in profound influence on the sustainable future once achieved.

Electrochemical Ammonia Synthesis

Motivated by the urgent targets of CO_2 emission reduction and decreasing costs of renewable energy such as solar and wind, the electrical grid is rapidly transforming toward a low-carbon system. The necessity of protons/electrons for the completion of natural enzymatic N_2 fixation (reaction 1) indicates that NH_3 could be synthesized via an electrochemical process. Investigating electrochemical N_2 reduction could not only realize distributed NH_3 production but also balance the supply in electrical grids due to the intermittency of renewable sources. Thus far, several kinds of electrolytes [13, 26] are used for electrochemical NH_3 synthesis: (1) solid electrolytes, such as solid polymer or perovskites, which are operated from RT to high temperature ($T > 500^\circ\text{C}$); (2) molten electrolytes which are operated at intermediate temperature ($100^\circ\text{C} < T < 500^\circ\text{C}$); (3) liquid electrolytes which are operated at near RT. In the first decade of this millennium, research was focused on NH_3 synthesis in solid electrolytes or molten salts, and relatively high NH_3 production rate up to the order of $10^{-8} \text{ mol}/(\text{cm}^2 \text{ s})$ has been achieved at elevated temperature [13]; however, these methods remain inapplicable for practical use. Research on N_2 fixation at ambient conditions in liquid electrolytes, especially aqueous media, has experienced an explosive growth in the last 4 or 5 years [40], aiming at harvesting NH_3 from ubiquitous nitrogen and water by renewable electricity.

Solid-State Electrochemical Ammonia Synthesis (SSAS)

The reaction kinetics of NH_3 synthesis is favored at high temperatures. However, general electrolytes could not be operated in the high-temperature region. Highly proton-conductive solid-state materials working at high temperatures were discovered in 1980s [41]. In 1998, Marnellos and Stoukides [37] first demonstrated the electrochemical synthesis of NH_3 from N_2 and H_2 using a solid proton conductor. Typically, the SSAS system is composed of two porous electrodes (anode and cathode) separated by a dense solid electrolyte, which blocks gas diffusion and facilitates ion transport of protons or oxide anions [42] (Fig. 2).

Proton-Conducting SSAS

In Marnellos's work [37], the electrolyte was a solid proton conductor composed of strontia–ceria–ytterbia (SCY) perovskite in the form of $\text{SrCe}_{0.95}\text{Yb}_{0.05}\text{O}_3$, whereas two porous polycrystalline palladium electrodes were deposited on the two sides of the SCY electrolyte as anode and cathode (Fig. 2a). NH_3 was successfully generated from N_2 and H_2 [Eqs. (3), (4)]:

At 570 °C and atmospheric pressure, a current efficiency of 78% was observed, leading to NH_3 production rate of $4.5 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$. Hereafter, dozens of proton-conducting electrolyte materials were tested, including perovskite-type oxides [43, 44], pyrochlore-type oxides [45, 46], fluorite-type oxides [47], polymers [48–50] and composite electrolytes [51, 52].

Fig. 2 Schematic of SSAS systems using **a** solid-state proton-conducting electrolyte and **b** solid-state oxygen anion-conducting electrolyte. Inert carrier gas is omitted. Adapted with permission from Ref. [42]. Copyright 2014, Frontiers Production Office

Liu and coworkers [44] synthesized perovskite-type oxides $\text{BaCe}_{0.90}\text{Sm}_{0.10}\text{O}_{3-\delta}$ and $\text{BaCe}_{0.80}\text{Gd}_{0.10}\text{Sm}_{0.10}\text{O}_{3-\delta}$ by sol–gel method. Both materials showed high proton conductivity for SSAS, leading to a maximum NH_3 production rate of $5.82 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$ at 620 °C. Chen and Ma [53] fabricated perovskite-type $\text{BaCe}_{1-x}\text{Gd}_x\text{O}_{3-\alpha}$ ($0.05 \leq x \leq 0.20$) ceramic by microemulsion method and sintering. This ceramic exhibited proton-conducting properties from 300 to 600 °C in hydrogen atmosphere. When 90 μm thick $\text{BaCe}_{0.85}\text{Gd}_{0.15}\text{O}_{3-\alpha}$ film was used as the electrolyte, a NH_3 formation rate of $4.63 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$ was obtained.

Xie et al. [45] prepared pyrochlore-type oxides of $\text{La}_{1.9}\text{Ca}_{0.1}\text{Zr}_2\text{O}_{6.95}$ via sol–gel method as proton-conducting electrolyte for SSAS. The rate of NH_3 evolution was up to $2.0 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$ at 520 °C. When Zr was replaced by Ce, a rate of $1.3 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$ was observed [46]. The same group also studied proton conduction properties of fluorite-type oxide ceramics $\text{Ce}_{0.8}\text{M}_{0.2}\text{O}_{2-\delta}$ ($\text{M} = \text{La}, \text{Y}, \text{Gd}, \text{Sm}$) from 400 to 800 °C [47]. At 650 °C, the rate of NH_3 evolution varied from $7.2 \text{ mol}/(\text{cm}^2 \text{ s})$ to $8.2 \times 10^{-9} \text{ mol}/(\text{cm}^2 \text{ s})$ depending on various M elements.

The aforementioned perovskite, pyrochlore and fluorite-type electrolytes belong to high-temperature proton conductors for NH_3 synthesis at atmospheric pressure. Nonetheless, high temperature would increase energy consumption and cause NH_3 decomposition. Solid polymers, such as Nafion, are good proton conductors that can be used as electrolytes for SSAS at atmospheric pressure and low temperature. Kyrriacou and coworkers [54] first introduced Nafion membrane to SSAS with Pt and Ru, which were used as anode and cathode, respectively. At -1.02 V and 90 °C, this system achieved an ammonia formation rate of $2.12 \times 10^{-11} \text{ mol}/(\text{cm}^2 \text{ s})$ with a current efficiency of 0.24%. The performance of Nafion-based SSAS was greatly improved when metal electrodes were replaced by composite oxides. Liu's group [48] adopted fluorite-type $\text{Ce}_{0.8}\text{Sm}_{0.2}\text{O}_{2-\delta}$ and perovskite-type $\text{SmFe}_{0.7}\text{Cu}_{0.3-x}\text{Ni}_x\text{O}_3$ as the anode and cathode, respectively, in a Nafion-based SSAS cell. At -2 V and 80 °C, this system yielded NH_3 with a fast rate of $1.13 \times 10^{-8} \text{ mol}/(\text{cm}^2 \text{ s})$ and a high current efficiency of 90.4%. This rate is the highest among SSAS cells to date.

O^{2-} -Conducting SSAS

In addition to proton-conducting electrolytes, O^{2-} -conducting solid electrolyte cells could realize NH_3 production from N_2 and H_2O (Fig. 2b):

Stoukides's group [55] reported yttria-stabilized zirconia (8% $\text{Y}_2\text{O}_3/\text{ZrO}_2$) as O^{2-} -conducting electrolyte for SSAS using N_2 and H_2O as feed gases. At 650 °C and atmospheric pressure, an ammonia rate of $1.50 \times 10^{-13} \text{ mol}/(\text{cm}^2 \text{ s})$ was obtained. Amar et al. [56] presented ammonia synthesis from wet nitrogen (with H_2O) at 375–425 °C in an O^{2-} -conducting composite electrolyte: $\text{Ce}_{0.8}\text{Gd}_{0.18}\text{Ca}_{0.02}\text{O}_{2-\delta}$ – $(\text{Li}/\text{Na}/\text{K})_2\text{CO}_3$. A maximum ammonia formation rate of $4.0 \times 10^{-10} \text{ mol}/(\text{cm}^2 \text{ s})$ with a current efficiency of 3.87% was observed at 375 °C and 1.4 V on a $\text{La}_{0.75}\text{Sr}_{0.25}\text{Cr}_{0.5}\text{Fe}_{0.5}\text{O}_{3-\delta}$ – $\text{Ce}_{0.8}\text{Gd}_{0.18}\text{Ca}_{0.02}\text{O}_{2-\delta}$ composite cathode.

Pros and Cons of SSAS

NH_3 synthesis in solid-state electrolytes is usually conducted at elevated temperatures, because of not only hastened reaction kinetics but also substantially boosted conductivity of electrolytes. An appreciable production rate of up to $10^{-8} \text{ mol}/(\text{cm}^2 \text{ s})$ can be achieved from N_2 and H_2 [Eq. (2)], but this exothermic reaction is not thermodynamically favorable at high temperatures, necessitating a trade-off for maximizing NH_3 yield. H_2 production from natural gas reforming is energy intensive and causes most of CO_2 release. Although NH_3 production from N_2 and H_2O [Eq. (7)] is endothermic and theoretically carbon-free, the weak reducing power and low conductivity of O^{2-} greatly restrict NH_3 yield.

Electrochemical Ammonia Synthesis in Molten Electrolytes

Compared with SSAS, molten electrolytes enhance the ionic conductivity and reduce the operating temperature of the reactions. In molten alkali metal salts, N^{3-} is stabilized and acts as intermediate product from N_2 to NH_3 . Moreover, protic solvents are avoided, which eliminates the competitive hydrogen evolution reaction (HER).

Ito and coworkers [57, 58] discovered that N_2 gas could be electrochemically reduced to N^{3-} in molten LiCl – KCl – Li_3N eutectic melts. Afterward, they used the molten salt system for electrochemical NH_3 synthesis (Fig. 3a) [59]. N^{3-} is the conducting ion in molten LiCl – KCl – Li_3N or LiCl – KCl – CsCl – Li_3N electrolytes. The reactions on the two electrodes are as follows:

In this system, the NH_3 synthesis rate was correlated to hydrogen partial pressure in the gas electrode instead of

electrolysis potential [60]. The rate-determining step was proposed to be the dissolution/diffusion of hydrogen in the molten electrolytes. The highest NH_3 production rate was $3.33 \times 10^{-8} \text{ mol}/(\text{cm}^2 \text{ s})$ with a current efficiency of 72% at 400 °C [60]. In the presence of N^{3-} , however, a portion of NH_3 could dissolve to form imide (NH_2^-) and amide (NH_2^-) anions, which might lower the NH_3 production rate [61]. Apart from H_2 , other hydrogen sources, such as H_2O [62, 63], HCl [64], H_2S [65] and CH_4 [66], were explored for electrochemical NH_3 synthesis in LiCl – KCl – CsCl eutectic melts.

Licht and colleagues [36] illustrated a configuration for electrochemical NH_3 synthesis, where NH_3 was generated by electrolysis of air and water steam in molten 0.5 $\text{NaOH}/0.5 \text{ KOH}$ in the presence of nano- Fe_2O_3 catalysts. At 200 °C and 1.2 V, NH_3 was produced under 2 mA/cm^2 of applied current with a current efficiency of 35%. At the largest current density of 200 mA/cm^2 , the production rate of NH_3 was as high as $1.0 \times 10^{-8} \text{ mol}/(\text{cm}^2 \text{ s})$. The high surface area of the nano- Fe_2O_3 that remained colloidal in electrolysis was critical to the NH_3 synthesis process, whereas macro- Fe_2O_3 descended and accumulated at the cell bottom without discernible NH_3 production. Notably, solar thermal energy could be introduced into the system, resulting in a solar thermal electrochemical process (Fig. 3b) [67].

McEnaney et al. [68] reported an ammonia synthesis system from N_2 and H_2O using a lithium cycling electrification strategy at atmospheric pressure (Fig. 3c). This lithium-mediated cycling process combines three steps:

Step 1: Electrolyzing molten LiOH to metallic Li at 400 °C–450 °C:

Step 2: Nitridation of metallic Li to form Li_3N :

Step 3: Li_3N hydrolysis to release NH_3 and regenerate LiOH :

This stepwise approach circumvents direct N_2 protonation and therefore substantially inhibits undesired HER, leading to a high initial current efficiency of 88.5%. The ease of dissociation of the strong N – N bond over metallic Li and diffusion processes to form Li_3N at RT are keys to the demonstrated cycle. This strategy could be coupled with renewable sources of electricity to facilitate localized sustainable NH_3 synthesis.

Fig. 3 Electrochemical NH_3 synthesis in molten electrolytes. **a** Schematic of the principle of electrolytic synthesis of NH_3 from N_2 and H_2 in molten LiCl-KCl-CsCl salts containing N^{3-} . Adapted with permission from Ref. [59]. Copyright 2003, American Chemical Society. **b** Illustration of electrochemical NH_3 synthesis by electrolysis of air and water steam in a molten hydroxide suspension of nano- Fe_2O_3 catalysts. Reproduced with permission from Ref. [67]. Copyright 2014, American Chemical Society. **c** Schematic of a stepwise lithium-mediated cycling process for the sustainable NH_3 production from N_2 and H_2O driven by renewable energy sources. Reproduced with permission from Ref. [68]. Copyright 2017, The Royal Society of Chemistry

Electrochemical Ammonia Synthesis in Liquid Electrolytes

Low-temperature electrochemical NH_3 synthesis in liquid or aqueous electrolytes has attracted considerable research attention. On the one hand, NH_3 production at low RT could substantially reduce the energy consumption. On the other hand, ubiquitous H_2O is used as the proton source instead of H_2 , which reduces the process cost and inhibits greenhouse gas emission fundamentally. Solid or molten salt electrolyte-mediated N_2 reduction systems contain limited or zero water molecules, resulting in an insignificant hydrogen evolution. Therefore, research on NH_3 synthesis in solid or molten salt media mainly focuses on electrolytes and the system design to reduce operating temperatures and enhance ion conductivity. In liquids, especially aqueous media, however, the abundance of water results in an extremely competitive electrolysis to hydrogen. In theory, given a highly active electrocatalyst, NRR can proceed in a narrow region of negative

potentials without inducing H_2O reduction (line a in Fig. 4) at any pH condition [22]. However, most electrocatalysts have an insufficient activity toward NRR. Therefore, NH_3 could only be generated at more negative potentials than water reduction, where most electrons would favor H_2 generation. Normally, the current efficiency of NH_3 production in aqueous electrolyte hardly exceeds 5%. The selectivity challenge necessitates the delineation of a mechanistic understanding of catalytic dinitrogen reduction to ammonia, based on which efficient heterogeneous electrocatalysts could be reasonably designed.

Reaction Mechanisms

The hydrogenation of N_2 to NH_3 on heterogeneous catalysts can be divided into dissociative and associative mechanisms (Fig. 5) [69, 70]. As for the dissociative mechanism, the $\text{N}\equiv\text{N}$ molecule is cleaved into adsorbed atomic nitrogen, which is subsequently hydrogenated to

Fig. 4 Partial Pourbaix diagram for the N_2 - H_2O system. Red line represents N_2 reduction to NH_4^+ or NH_3 , whereas blue line denotes N_2 oxidation to NO_3^- . Dotted lines a and b represent H_2O reduction to H_2 and oxidation to O_2 , respectively. Reproduced with permission from Ref. [22]. Copyright 2018, AAAS

generate NH_3 (Fig. 5a). Dissociative pathway is assumed to dominate ammonia synthesis in H-B process, where the nitrogen chemisorption/dissociation is considered as the rate-determining step [71]. In the associative pathway, protonation on adsorbed N_2 primarily occurs. The N-N linkage is maintained during the initial reduction steps. Based on the hydrogenation sequences on two nitrogen atoms in

N_2 , the associative mechanism can be specifically assigned to the distal or alternating pathways. In the distal pathway (Fig. 5b), hydrogenation is asymmetric: the distal (relative to the substrate) nitrogen atom is hydrogenated first until one NH_3 molecule is released, followed by subsequent hydrogenation on the proximal nitrogen atom and the second NH_3 release. In the alternating pathway (Fig. 5c), the two N atoms are hydrogenated simultaneously (symmetrically) until NH_3 is released, which is analogous to the mechanism of nitrogenase [6].

In a particular electrocatalytic system of NRR, the explicit pathways (Fig. 5) remain obscure. Density functional theory (DFT) is often used to calculate the free energy changes of possible intermediates and delineate the possible mechanism on specific catalysts. For example, Nørskov's group [72] systematically evaluated the electrocatalytic activity of NH_3 formation on both flat and stepped surfaces of a range of transition metals. Based on the approximate linear relations between the adsorption energies of nitrogen-containing intermediates $\text{NH}_x/\text{N}_2\text{H}_x$ and the chemisorption energy of N-atom, the free energy changes in elementary reactions (ΔG) were calculated, and the rate-limiting ΔG reflected the onset potential (U) for NH_3 synthesis. Combined volcano diagrams were plotted [72, 73] to show the estimated onset potential as a function of the nitrogen-binding energy for dissociative (solid lines)

Fig. 5 Nitrogen reduction pathways on heterogeneous catalysts. **a** Dissociative pathway where $\text{N}\equiv\text{N}$ bond is broken before hydrogenation. Associative pathways including **b** distal or asymmetric hydrogenation and **c** alternating or symmetric hydrogenation. Adapted with permission from Ref. [70]. Copyright 2014, The Royal Society of Chemistry

and associative (dashed lines) mechanisms on either flat (blue) or stepped (red) surfaces (Fig. 6). On the left sides of the volcanoes, the dissociative pathway dominates, and the onset potential for NH_3 formation is slightly more positive on the flat surfaces than that on the stepped ones. This slight difference is attributed to the smaller free energy change from $^*\text{NH}$ to $^*\text{NH}_2$ (rate-limiting step on flat surfaces) than that from $^*\text{NH}_2$ to NH_3 (rate-limiting step on stepped surfaces). On the right sides of the volcanoes, N_2 splitting is the rate-limiting step for dissociative mechanism on either flat or stepped surfaces (overlapped as black solid line) due to the same free energy change from N_2 to $^*2\text{N}$, whereas the first hydrogenation step on adsorbed N_2 determines the onset potential for the associative mechanism (blue and red dashed lines). Different transition metals prefer different reaction pathways. Reactants on early transition metals (Sc to Fe; Y to Ru) follow a dissociative pathway with one of the hydrogenation reactions as the rate-limiting step. Several late transition metals prefer a dissociative mechanism with N_2 splitting as the limiting step (Rh, Ir, Co and Ni), whereas others prefer an associative mechanism at more negative potentials (Pd, Cu, Ag and Au). Notably, the surfaces in most part of the diagrams are dominated by H-atoms, resulting in the rapid formation of H_2 other than N_2 . Ru and Rh with theoretically the highest activity (top of volcano diagrams) exhibit poor selectivity due to strong H adsorption. Only the flat metal surfaces of Sc, Y, Ti and Zr (shaded green area) are assumed to be covered by N instead of H. However, the

strong binding of N might lead to the difficult desorption of reaction intermediates.

Theoretical screening provides limited guidance for catalyst design. The actual surface environment on the catalyst could occasionally be located distantly from that in calculations. For example, surface reconstruction occurs during reactions, and certain metal catalysts would form surface oxide layers under reduction potentials. Nanosized catalysts also have more complexed exposed faces and defects than their bulk counterparts [74–79]. In recent years, various electrocatalysts have been explored for NH_3 synthesis from N_2 and H_2O in liquid or aqueous media [80].

Metal Catalysts

Thus far, limited experimental reports are available regarding electrochemical NRR (ENRR) on metal bulks or films in aqueous media. One chemically deposited Au thin-film electrode produced NH_3 at potentials below 0 V versus reversible hydrogen electrode (V_{RHE}) [81]. The authors used surface-enhanced infrared absorption spectroscopy (SEIRAS) to successfully detect N_2H_x species in the reaction process. The current efficiency was 0.12%, and the NH_3 formation rate reached $3.84 \times 10^{-12} \text{ mol}/(\text{cm}^2 \text{ s})$ at $-0.5 V_{\text{RHE}}$. N_2H_x intermediates indicated an associative mechanism on Au, which is consistent with the calculations in Fig. 6. A parallel experiment on Pt film showed no intermediate absorption bands under the same conditions. Another active metal film reported is a (110) orientation Mo, which achieved a current efficiency of 0.72% for NH_3 generation [82].

Fig. 6 Combined volcano diagrams evaluating onset potential (U) on different transition metals. Solid lines represent dissociative mechanisms, and dashed lines denote associative ones. Blue and red lines represent reactions on flat and stepped surfaces, respectively. Black line indicates an overlap between blue and red lines. The green

shaded area indicates the region where surface is likely to be covered by adsorbed nitrogen, and white area denotes the region where surface is likely to be covered by adsorbed hydrogen. Adapted with permission from Refs. [72] and [73]. Copyright 2012, The Royal Chemical Society. Copyright 2019, Macmillan Publishers Limited

More active results were observed on nanosized metal catalysts. Yan and colleagues [83–85] tested a series of Au electrocatalysts with different nanostructures. Tetrahexahedral (THH) Au nanorods (NRs) by a seeded growth method showed good electrocatalytic N_2 reduction performance in 0.1 mol/L KOH [83]. THH–Au NRs exposed abundant high-index facets of (310) and (210), which facilitated N_2 activation and reduction. The THH–Au achieved the highest ammonia production rate of 2.69×10^{-11} mol/(cm^2 s) at $-0.2 V_{\text{RHE}}$ with a current efficiency of $\sim 4\%$. Although high-index faces on THH–Au play important roles in N_2 reduction, the relatively large size of NRs (~ 50 nm in length) restricts the atomic utilization. Subnanometer Au clusters (0.5 nm) on TiO_2 support showed enhanced electrocatalytic NRR, where the low-coordination sites on small Au clusters are considered crucial. An ammonia production rate of 1.12×10^{-10} mol/(cm^2 s) with a current efficiency of 8.11% was achieved at $-0.2 V_{\text{RHE}}$ [84]. Amorphous nanocatalysts with highly unsaturated coordination sites are occasionally more active than the crystalline ones in catalysis. This condition is illustrated by anchored amorphous Au nanoparticles (a-Au NPs, ~ 5 nm) on a bisubstrate of $\text{CeO}_x/\text{reduced graphene oxide}$ ($\text{CeO}_x\text{-RGO}$), where CeO_x transforms the crystallized Au into its amorphous form, and RGO acts as the substrate to anchor and disperse the Au NPs [85]. The obtained a-Au/ $\text{CeO}_x\text{-RGO}$ exhibited a current efficiency of 10.1%, which was considerably higher than that of crystalline Au on RGO.

On a carbon-supported nano-Pd catalyst, an overpotential as low as 56 mV was reported for N_2 reduction [86]. α -Palladium hydride was assumed to form during reaction and to lower the free energy barrier of N_2 hydrogenation

to $^*\text{N}_2\text{H}$, the rate-limiting step for NH_3 electrosynthesis. A current efficiency of 8.2% was attained at $0.1 V_{\text{RHE}}$.

A record-breaking activity and selectivity for ENRR at ambient conditions were recently realized on a main-group metal bismuth nanocrystals with K^+ promoters in aqueous electrolyte [87]. At the optimum potential of $-0.6 V_{\text{RHE}}$, the NH_3 generation rate reached as high as 1.44×10^{-8} mol/(cm^2 s) with a remarkable current efficiency of 66%. This production rate outperforms other works of ENRR in aqueous media by one to three orders of magnitude and parallels the levels in molten salt electrolyte cells operating at elevated temperature or pressure. During the long-term operation of up to 50 h, the Bi nanocrystal catalyst retained its activity and metallic state. The authors proposed a distal pathway of associative mechanism (Fig. 5b), with the reductive protonation of N_2 to $^*\text{NNH}$ as the rate-limiting step. The projected density of states revealed a remarkable overlap between $2p$ orbitals of adsorbed N and Bi $6p$ bands both below and above the Fermi level. By comparison, Au as a transition metal showed minimal overlap between its $5d$ band and N $2p$ orbital. Therefore, a stronger interaction existed between Bi surface and $^*\text{NNH}$ intermediate, whose formation energy barrier ($\Delta G_{^*\text{NNH}}$) was considerably lower compared with that on Au (Fig. 7a). More importantly, K^+ acted as a strong promoter in this system, boosting the current efficiency from 9.8% to 67%. On the one hand, K^+ shifted the $2p$ orbital of adsorbed N to lower energy and decreased $\Delta G_{^*\text{NNH}}$ (Fig. 7b), leading to a stronger Bi–N bond and a better N–N activation. On the other hand, high-concentration K^+ hindered proton migration from the bulk solution to the Bi electrode surface, suppressing HER and enhancing ENRR selectivity (Fig. 7c, d, respectively).

Fig. 7 Boosting ENRR with Bi metal catalysts and K^+ cations. **a** Free energy changes ($\Delta G_{^*\text{NNH}}$) for the rate-limiting step forming $^*\text{NNH}$ ($^* + \text{N}_2 + \text{H}^+ + \text{e}^- \rightarrow ^*\text{NNH}$) on Bi (012), (110), (104), and Au (111) facets. **b** $\Delta G_{^*\text{NNH}}$ on Bi (012), (110), and (104) facets without (patterned bars) and with (filled bars) K^+ . Mass transfer of H^+ and N_2 to the catalyst surface in electrolytes without **c** and with **d** K^+ . Adapted with permission from Ref. [87]. Copyright 2019, Macmillan Publishers Limited

As illustrated in the “Reaction Mechanisms” section, the electrocatalytic conversion of N_2 to NH_3 on transition metal relies on the linear scaling relationship between $*N_2H$ and $*NH_2$. The overpotentials of ENRR are larger than those of HER, leading to the limited success of NRR on transition metals. Metal alloys might be an approach to meet this challenge because of their synergetic interactions with the absorbed intermediates. Nonetheless, alloys cannot break the scaling relationship for $*N_2H$ and $*NH_2$, as each kind of metal bonds to the intermediates through a single N atom. How to design the active sites to change the intermediates’ binding modes remains an important question.

Metal Compound Catalysts

As mentioned in the “Electrochemical Ammonia Synthesis in Molten Electrolytes” section, nano- Fe_2O_3 shows excellent electrocatalytic performance for NRR in molten base electrolyte, but the possible mechanism was not discussed [36]. A DFT study on hematite (0001) revealed an associative pathway where the potential demanding step is $*NNH$ formation from N_2 [88]. The calculated applied bias needed is -1.1 V, which is consistent with the conducted 1.2 V for nano- Fe_2O_3 [36]. Apart from molten electrolytes, Fe_2O_3 electrocatalyst was also applied either in gas diffusion layer (GDL) electrode [89–91] or directly immersed in aqueous media [92]. Chen et al. [89, 91] studied carbon nanotube-supported iron oxide (Fe_2O_3 -CNT) as N_2 reduction electrocatalyst on GDL electrode in a three-phase cell separated by a proton exchange membrane. The liquid chamber contained

aqueous electrolyte for H_2O electrolysis to produce H^+ and electrons. The protons migrated through proton exchange membrane to the GDL electrode, where N_2 gas was reduced by electrons and hydrogenated to form NH_3 . The current densities were determined by proton concentration in acid electrolyte and by water transport in the base electrolyte. The 30% Fe_2O_3 -CNT was the best electrocatalyst among all Fe_2O_3 -CNT samples [89]. Kong et al. [90] also investigated γ - Fe_2O_3 electrocatalyst for NH_3 synthesis in a three-phase cell separated by an anion-exchange membrane. Using KOH electrolyte, the γ - Fe_2O_3 electrode achieved a current efficiency of 1.9% at 0 V_{RHE}.

Through an electrospinning/calcination method, a hybrid metal oxide $Bi_4V_2O_{11}/CeO_2$ with an amorphous phase (BVC-A) was fabricated and used as the cathode for electrocatalytic nitrogen reduction [93]. The amorphous $Bi_4V_2O_{11}$ contains abundant oxygen vacancies (O_{vac}), which acted as active sites for N_2 reduction. CeO_2 not only induced the amorphous structure but also established suitable band alignment with $Bi_4V_2O_{11}$ to facilitate interfacial charge transfer (Fig. 8a). A high current efficiency of 10.16% was achieved at -0.2 V_{RHE}.

MoS_2 as one hot-spot two-dimensional (2D) material has attractive catalytic properties. The NH_3 formation by MoS_2 was first reported in 0.1 mol/L Na_2SO_4 [94]. Defects on the monolayer of MoS_2 boosted N_2 reduction [95]. A DFT simulation assumed that single Fe atom deposited on MoS_2 would mimic FeMoco and endow inactive MoS_2 the capability to convert N_2 to NH_3 electrocatalytically. Fe center yields electron charge to MoS_2 and turns into an

Fig. 8 ENRR on metal compound catalysts. **a** Interfacial charge transfer in BVC-A for ENRR. Reproduced with permission from Ref. [93]. Copyright 2018, Wiley–VCH. **b** Ru/ MoS_2 catalyzes an ENRR process in which Ru cluster acts as an NRR active site, whereas S-vacancy of MoS_2 acts as a hydrogenation site. Adapted with permission from Ref. [97]. Copyright 2019, American Chemical Society. **c** NRR pathway on the surface of $VN_{0.7}O_{0.45}$ via a Mars–van Krevelen (MvK) mechanism and the catalyst deactivation mechanism. Adapted with permission from Ref. [104]. Copyright 2018, American Chemical Society

extremely rare and reactive Fe^{I} species [96]. Interestingly, Ru instead of Fe on MoS_2 was experimentally discovered as an active catalyst for ENRR [97]. As shown previously in Fig. 6, Ru is near the top of volcano plot but exhibits considerable hydrogen evolution due to dominant H adsorption. In the work on Ru/ MoS_2 [97], dispersed Ru clusters provide N_2 -binding sites, whereas nearby S-vacancies on the 2H- MoS_2 serve as centers for H^+ reduction to adsorbed $^*\text{H}$ (Fig. 8b). These hydrogenated S-vacancies act as the H-provider because the formed $^*\text{H}$ can be transferred directly to nearby N_2 on Ru, forming $^*\text{NNH}$ as an intermediate. The $^*\text{NNH}$ was unstable on Ru/ MoS_2 and spontaneously cleaved into $^*\text{N}$ and $^*\text{NH}$, following which a dissociative pathway was proposed.

M_3C_2 transition metal carbides (M stands for metals from d^2 , d^3 and d^4 series), as a kind of Mxene, have shown capabilities for N_2 capture and reduction in a DFT study [98]. V_3C_2 and Nb_3C_2 exhibited the most promising features for reduction to NH_3 . In another metal carbide system, Mo_2C nanodots embedded in carbon nanosheets were developed for electrochemical nitrogen fixation [99]. At $-0.3 \text{ V}_{\text{RHE}}$, the NH_3 production rate reached $11.3 \mu\text{g}/(\text{h mg})$. Carbon-supported Mo_2C is proposed to be rich in nitrogen adsorption active sites, and the unique electronic structure is favorable to $\text{N}\equiv\text{N}$ bond cleavage and hydrogenation.

Transition metal nitrides draw great attention because they have the potential to activate adsorbed N_2 via the MvK mechanism [100–103]. Specifically, one surface N atom on the nitride is hydrogenated and reduced to one NH_3 molecule, forming a lattice vacancy which is subsequently restored by reductive incorporation of a N_2 molecule. One good example was demonstrated by vanadium nitride (VN) NPs, where surface $\text{VN}_{0.7}\text{O}_{0.45}$ acted as the active phase [104]. The use of $^{15}\text{N}_2$ feed gas produced $^{14}\text{NH}_3$ and $^{15}\text{NH}_3$, indicating a MvK mechanism. In a catalytic cycle, a native surface N atom of VN was extracted by hydrogen atoms and left behind a N vacancy (N_{vac}), which could activate/adsorb a N_2 molecule and be healed after the desorption of one NH_3 molecule. Moreover, only the surface N sites adjacent to a surface O are active toward nitrogen reduction, and the removal of surface O would deactivate the catalyst (Fig. 8c). The 2D MoN material is also a promising candidate for ENRR in theoretical and experimental demonstrations [105, 106].

As illustrated, in metal compound catalysts, introducing anion vacancies, such as oxygen, nitrogen, sulfur and selenium vacancies, plays an important role in ENRR. The anion vacancies could trap metastable electrons, which are transported into an antibonding orbital of adsorbed N_2 molecules, contributing to enhancing nitrogen triple-bond cleavage for subsequent catalytic reaction. The regeneration capability of vacancies during reaction needs further investigation.

Metal-Free Catalysts

Scalable hierarchically structured nitrogen-doped nanoporous carbon membranes with embedded CNTs were developed for ENRR [107]. In this hierarchically porous membrane structure, micropores and small mesopores provided large and accessible surface areas up to $432 \text{ m}^2/\text{g}$. Meanwhile, large mesopores and macropores formed interconnected 3D conductive framework to expedite mass diffusion and enhanced N_2 reduction efficiency on active sites, which are proposed to be pyridinic and pyrrolic N atoms in N-doped carbons [107, 108].

A polymeric carbon nitride (PCN) abundant in N_{vac} was proposed as an electrocatalyst to enable ammonia synthesis under ambient conditions [109]. DFT calculations illustrated that dinitrogen molecule can be chemisorbed on N_{vac} of PCN in a dinuclear end-on bound structure, which dramatically increases N–N bond length and improves spatial electron transfer. A high current efficiency of 11.59% was therefore obtained at $-0.2 \text{ V}_{\text{RHE}}$, leading to an ammonia production rate of $9.64 \times 10^{-10} \text{ mol}/(\text{cm}^2 \text{ s})$.

Black phosphorus (BP) with a few layers of nanosheet structure is a nonmetallic electrocatalyst for nitrogen reduction under ambient conditions [110]. DFT calculations propose an alternating hydrogenation pathway. The zigzag and diff-zigzag edges of BP are active centers for nitrogen adsorption and activation.

Battery Configurations for NRR

In addition to electrolysis, proof-of-concept batteries have led to new directions toward N_2 fixation. Minteer and colleagues [111] combined nitrogenase and hydrogenase into a H_2/N_2 fuel cell, with a 3-morpholinopropane-1-sulfonic acid buffer as the electrolyte (Fig. 9). The electron transfer between cathode/nitrogenase and anode/hydrogenase was realized by using methyl viologen (MV, N,N' -dimethyl-4,4'-bipyridinium) as the sole electron donor. The coupling of this nitrogenase cathode to reduce N_2 with a hydrogenase anode to oxidize H_2 resulted in an enzyme-assisted fuel cell (EFC), generating NH_3 from H_2 and N_2 while simultaneously outputting an electrical current. A current efficiency of 26.4% was obtained on this H_2/N_2 EFC. Ma et al. [112] reported a successful illustration of a reversible nitrogen cycle based on a rechargeable lithium–nitrogen ($\text{Li}-\text{N}_2$) battery with the proposed reversible reaction of $6\text{Li} + \text{N}_2 \rightleftharpoons 2\text{Li}_3\text{N}$. The N_2 fixation battery assembly was composed of a lithium anode, an ether-based electrolyte, and a carbon cloth cathode and exhibited a promising electrochemical current efficiency of 59%.

Fig. 9 Incorporation of hydrogenase and nitrogenase proteins into a H_2/N_2 fuel cell with MV as the electron mediator in both chambers. This fuel cell produces NH_3 and electrical energy from H_2 and N_2 at RT and ambient pressure. Reproduced with permission from Ref. [111]. Copyright 2017, Wiley–VCH

Methods to Suppress HER

In protic (e.g., aqueous) electrolytes, HER is a serious competitive reaction that greatly restricts the selectivity of N_2 reduction to NH_3 in the presence of protons. For example, recent publications [83–86, 93, 109, 113–115] reported electrochemical NH_3 synthesis in aqueous solutions: The highest current efficiency for NH_3 and the highest NH_3 production rate depend on small applied potentials, whereas further enlarged negative potentials result in a significantly reduced current efficiencies and NH_3 production rates (Fig. 10). $-0.2 \text{ V}_{\text{RHE}}$ is the most frequently reported potential [83–85, 93, 109, 113, 114] at which the fastest NH_3 generation is attained (Fig. 10a–c). For a palladium-catalyzed N_2 reduction system, the highest current efficiency of 8.2% was achieved at as high as $0.1 \text{ V}_{\text{RHE}}$ (Fig. 10d) [86]. At such small applied

potentials, the current densities are in the range of several hundred microamperes to several microamperes, which are inapplicable to practical applications. This effect could be amplified when current densities are larger.

Nørskov and colleagues [116] presented in-depth perspectives on the selectivity challenges for electrochemical NH_3 synthesis. They suggested that limiting either proton or electron availability at the surface is a promising way to improve the selectivity of NH_3 . Detailed methods include limiting the proton transfer rates by reducing proton concentration in the electrolyte or increasing proton transfer barriers to the catalyst surface or limiting the electron transfer rates by constructing thin insulators or supplying slow streams of electrons.

By reducing proton concentration using ionic liquids as the electrolytes, MacFarlane and coworkers [117]

Fig. 10 Low selectivity of NH_3 in ENRR compared with H_2 generation, shown by the yield and current efficiency of NH_3 at various potentials on different electrocatalysts. **a** BVC-A. Adapted with permission from Ref. [93]. Copyright 2018, Wiley–VCH. **b** a-Au/ CeO_x -RGO. Adapted with permission from Ref. [85]. Copyright 2017, Wiley–VCH. **c** $\text{Pd}_{0.2}\text{Cu}_{0.8}/\text{rGO}$. Adapted with permission from Ref. [114]. Copyright 2018, Wiley–VCH. **d** Pd/C. Adapted with permission from Ref. [86]. Copyright 2018, Macmillan Publishers Limited

reported a highly selective system for NH_3 electrosynthesis on a nanostructured iron catalyst at ambient temperature and pressure. The solubility of N_2 in $[\text{C}_4\text{mpyr}][\text{eFAP}]$ and $[\text{P}_{6,6,6,14}][\text{eFAP}]$ is notably higher than that in aqueous solutions. In addition, these ionic liquids can serve as aprotic electrolytes where H_2 evolution can be effectively suppressed. Notably, a trace amount of water (20×10^{-6} – 250×10^{-6}) is the only proton source. As a result, an unprecedented current efficiency of 60% for NH_3 synthesis in liquid electrolytes at ambient conditions was achieved.

High current efficiency of ENRR was also realized in a solution of LiClO_4 (0.2 mol/L) in tetrahydrofuran/ethanol (99:1 V/V) on metal electrodes [118]. Lithium in the electrolyte acted as a mediator because Li^+ was reduced on the electrode to deposit metallic Li, which reacted with N_2 to form Li_3N . Li_3N underwent a subsequent ethanolysis to generate NH_3 . Moreover, in this Li-mediated system, the metal electrode can be modified with a functional layer such as superhydrophobic metal–organic framework to suppress the proton availability and accumulate N_2 molecules at the electrode surface [119].

Although reducing proton concentration surrounding the catalyst is an effective way to improve the selectivity of ENRR, the sacrifice of current density or NH_3 generation rate cannot be overlooked. The operating current density

at several microamperes [117, 119] is insufficient. New approaches need to be developed to solve this dilemma.

Summary and Protocols for Electrochemical Ammonia Synthesis

The past three decades have witnessed a flourishing of interest in electrochemical NH_3 synthesis. Table 1 summarizes several representative developments in this realm. For SSAS using N_2 and H_2 as the reactants, NH_3 generation rate could reach the order of 10^{-9} mol/(cm² s) to 10^{-8} mol/(cm² s), and the current efficiency is considerable. However, either the high temperature [37] (usually larger than 500 °C) or the large cell potential [48] limits the energy utilization; furthermore, H_2 production is energy consuming and carbon intensive. Molten electrolytes enhance the ionic conductivity and reduce the operating temperature to 200–400 °C. The current efficiency in molten electrolytes is as high as that in SSAS, whereas the NH_3 generation rate is faster at the order of 10^{-8} mol/(cm² s). Notably, reaction from N_2 and H_2O achieves a NH_3 production rate of 1.0×10^{-8} mol/(cm² s) in molten NaOH/KOH at a moderate temperature of 200 °C [36]. From the perspective of sustainable development, harvesting NH_3 from N_2 and H_2O at ambient conditions is the most tempting goal. Nonetheless, this process is extremely challenging because of the competitive hydrogen evolution and difficult

Table 1 Summary of representative developments in electrochemical NH_3 synthesis

Electrolyte type	Reactants	Electrode/catalyst	Conditions ^a	NH_3 yield [mol/(cm ² s)] ^b	Current efficiency (%)	Applied potential ^c	References
Solid	N_2/H_2	Porous Pd	$\text{SrCe}_{0.95}\text{Yb}_{0.05}\text{O}_3$, 570 °C	4.5×10^{-9}	78.00	N.A. ^d	[37]
	N_2/H_2	Ag–Pd	$\text{BaCe}_{0.80}\text{Gd}_{0.10}\text{Sm}_{0.10}\text{O}_{3-\delta}$, 620 °C	5.82×10^{-9}	N.A.	0.6 V	[44]
	N_2/H_2	Ag–Pd	$\text{Ce}_{0.8}\text{Sm}_{0.2}\text{O}_{2-\delta}$, 650 °C	8.2×10^{-9}	N.A.	0.6 V	[47]
	N_2/H_2	$\text{SmFe}_{0.7}\text{Cu}_{0.3-x}\text{Ni}_x\text{O}_3$	Nafion, 80 °C	1.13×10^{-8}	90.40	2 V	[48]
Molten	N_2/H_2	Porous Ni	Molten LiCl-KCl-CsCl with 0.5 mol% Li_3N , 400 °C	3.33×10^{-8}	72.00	0.7 V versus Li^+/Li	[60]
	$\text{N}_2/\text{H}_2\text{O}$	Ni electrode, nano- Fe_2O_3 catalyst	Molten NaOH/KOH , 200 °C	1.0×10^{-8}	35.00	1.2 V	[36]
Aqueous	$\text{N}_2/\text{H}_2\text{O}$	Au film	0.1 mol/L KOH	3.84×10^{-12}	0.12	–0.5 V versus RHE	[81]
	$\text{N}_2/\text{H}_2\text{O}$	Au nanoclusters	0.1 mol/L HCl	1.12×10^{-10}	8.11	–0.2 V versus RHE	[84]
	$\text{N}_2/\text{H}_2\text{O}$	Pd NP	0.1 mol/L PBS	1.7×10^{-11}	8.20	0.1 V versus RHE	[86]
	$\text{N}_2/\text{H}_2\text{O}$	Bi nanocrystals	0.5 mol/L K_2SO_4 , pH 3.5	1.44×10^{-8}	66.00	–0.6 V versus RHE	[87]
	$\text{N}_2/\text{H}_2\text{O}$	$\text{Bi}_4\text{V}_2\text{O}_{11}/\text{CeO}_2$	0.1 mol/L HCl	7.6×10^{-10}	10.16	–0.2 V versus RHE	[93]
	$\text{N}_2/\text{H}_2\text{O}$	Ru/MoS_2	0.01 mol/L HCl, 50 °C	1.14×10^{-10}	17.60	–0.15 V versus RHE	[97]
	$\text{N}_2/\text{H}_2\text{O}$	VN NP	0.05 mol/L H_2SO_4	3.3×10^{-10}	6.00	–0.1 V versus RHE	[104]
Nonaqueous liquid	$\text{N}_2/\text{H}_2\text{O}$	Nanostructured Fe	$[\text{P}_{6,6,6,14}][\text{eFAP}]$	2.1×10^{-11}	60.00	–0.8 V versus RHE	[117]
	$\text{N}_2/\text{H}_2\text{O}$	Ag–Au@ZIF	LiCF_3SO_3 (0.2 mol/L) in THF/ethanol (99:1 V/V)	9.5×10^{-12}	18.00	2.9 V	[119]

^aConditions indicate electrolyte, temperature, and pressure. Unless otherwise specified, the experiments were conducted under RT and ambient pressure

^bFrom given or calculated data based on reference data in the literature. Normalized based on the geometric areas of the electrodes

^cThe potentials without a reference refer to the cell potentials

^dN.A. stands for not applicable

N₂ activation. The NH₃ yield in aqueous electrolytes ranges from the order of 10⁻¹² mol/(cm² s) to 10⁻¹⁰ mol/(cm² s) with a current efficiency less than 10%. Reducing the proton availability, such as by using aprotic solvents, is an approach to notably boost the current efficiency; however, the operating current density is extremely small, leading to a low NH₃ yield [117, 119]. One Bi nanocrystal catalyst in aqueous media achieves a high NH₃ yield of 1.44 × 10⁻⁸ mol/(cm² s) and a high current efficiency of 60% [87]. This result is exciting, but more study is needed to solve the problems of high overpotential and the narrow operating potential window.

In spite of the reported progress thus far, electrochemical NH₃ production will need to achieve considerable progress toward practical applications that require a minimum NH₃ production rate in the order of 10⁻⁷ mol/(cm² s) [13]. More importantly, electrochemical NH₃ production needs both scientific and engineering design to make the process less energy consuming than the well-developed H-B process.

Another challenge is that the slow NH₃ generation rate of ENRR causes difficulty in attributing the detected NH₃ to real electrochemical N₂ fixation given the existence of numerous exogenous nitrogen contaminants. In addition, N₂ as a robust and nonpolar molecule is extremely difficult to fix under ambient conditions. Although ENRR has achieved great enhancement in ammonia production rates in the past 4 years, limited papers provide rigorous evidence to prove that ammonia truly comes from N₂. In any given experiment, adventitious ammonia can be introduced in the reaction system in various ways, as illustrated by a rigorous protocol by Andersen et al. [120]. Ammonia contamination could be present in air, atmosphere, human breath or Nafion membranes or originate from nitrogen-containing compounds that are normally present in the nitrogen gas supply. Numerous electrocatalysts are also nitrogen-containing compounds or fabricated from nitrogen-containing precursors. Therefore, excluding the interference of exogenous contamination and confirming the source of fixed nitrogen are the prerequisites to reporting a positive result. Fortunately, benchmarking protocols are being progressively established to identify and eliminate contamination sources [40, 73, 120], to prevent false positives and standardize ENRR experiments. Upon successful detection of ammonia after running electrolysis, one must conduct control experiments with Ar gas supply under the exact same conditions and with N₂ gas in the open-circuit condition. Isotope labeling using ¹⁵N₂ is a necessary confirmation procedure. Numerous papers reported the qualitative detection of ¹⁵NH₃ or ¹⁵NH₄⁺ from ¹⁵N₂, thereby alleging the successful fixing of N₂. However, ¹⁵N₂ gas stock normally contains ¹⁵N-labeled nitrate or ammonia, which invalidates the detected results [121]. Therefore, gas-cleaning unit must be applied before bubbling N₂ stream to the electrolyte. Meanwhile, the yield

of ¹⁵NH₃ should be quantitatively consistent with that of ¹⁴NH₃ during identical reduction experiments. Andersen's work demonstrates excellently how to perform quantitative isotope measurements. A copper catalyst trap was used to eliminate N-containing contaminations, and a gas circulation system was used to maximize the use of expensive ¹⁵N₂ gas [120]. The developing rigorous protocols will enable the identification of ENRR results by preventing false positive data and contribute to the development of more efficient processes toward electrochemical NH₃ production.

Photocatalytic Ammonia Synthesis

Effectively capturing solar energy for the production of fertilizers and fuels is an ambitious and challenging goal [122]. Green ammonia from nitrogen photofixation has drawn increasing attention in recent years [19, 123]. Abiotic photofixation of dinitrogen in soils and sands has been suggested to be the third most significant source of natural nitrogen fixation, apart from biological N₂ fixation and lightning discharges [23, 124]. The investigation of solar-driven N₂ fixation is significant for people to comprehend and modulate the nitrogen cycle. Although early studies mainly focused on titania-based catalysts, a sharp increase occurred in recent years regarding photocatalytic N₂ fixation on emerging catalytic systems.

Ammonia Synthesis on Powdered Photocatalysts

Titania-Based Photocatalysts

Rutile TiO₂ in sands or soils is considered to be the N₂ reduction catalyst in the presence of light and water [124]. The first experiment on N₂ photoreduction with water splitting was reported by Schrauzer and Guth [125] on outgassed rutile TiO₂ powders. H₂ evolution was notably inhibited in N₂ atmosphere, whereas iron doping enhanced the photocatalytic reactivity. Since then, titania has been intensively explored as the photocatalyst for N₂ fixation, although other metal oxide semiconductors, such as tungsten oxide [126] and iron oxide [127], were also investigated. Ranjit et al. [128] studied photocatalytic reduction of N₂ to NH₃ on noble-metal-loaded TiO₂. They observed a correlation between NH₃ yield and the M-H bond strength, where a high-bond strength gives rise to a high NH₃ yield. Hoshino et al. [129] reported N₂ photoreduction on needle-like solid ammonium perchlorate (NH₄ClO₄) using a TiO₂/conducting polymer (poly 3-methylthiophene, P3MeT) catalyst. Under illumination, photogenerated carriers at the TiO₂/P3MeT interface contributed to NH₃ synthesis in the presence of water. Meanwhile, ClO₄⁻ was doped from P3MeT driven by electrons, and the acid-base reaction formed mesoscale

NH_4ClO_4 needles. Kisch and colleagues [130] reported nitrogen fixation at nanostructured iron titanate films, where the highest NH_3 generation rate was realized on iron titanate film with Fe:Ti ratio of 1:1. Zhao et al. [131] fabricated Fe-doped TiO_2 NPs with highly exposed (101) facets by a two-step hydrothermal method. Optimal doping of Fe^{3+} is essential to the improvement of photocatalytic activity.

Recently, the introduction of O_{vac} has drawn new insight into N_2 photofixation on TiO_2 catalysts. Hirakawa et al. [132] introduced a large number of O_{vac} in a commercially available TiO_2 by H_2 treatment. Under UV light illumination, N_2 molecules were reduced to NH_3 by Ti^{3+} species on O_{vac} (Fig. 11a), leading to a solar-to-chemical energy conversion efficiency of 0.02%. However, methods such as H_2 reduction do not avoid the introduction of O_{vac} to the bulk to form bulk defects, which potentially act as carrier traps and induce charge recombination [133]. Therefore, the introduction of O_{vac} on the outermost surface is highly desirable for TiO_2 and many other reducible oxides. Gong and coworkers [39] reported the conversion of N_2 to NH_3 in pure water using a plasmon-enhanced rutile TiO_2 NR array modified with surface O_{vac} , which were created by atomic layer deposition (ALD). This method ensures the introduction of O_{vac} on the surface without affecting bulk structure. Compared with the less active rutile TiO_2 surface, the amorphous ALD TiO_2 layer (a- TiO_2) with catalytic centers of surface O_{vac} could promote N_2 adsorption and activation, greatly

enhancing the N_2 photofixation rate. Meanwhile, surface plasmons of Au extended the absorption range of TiO_2 to the visible region and provided high-energy hot electrons for N_2 reduction (Fig. 11b). Accordingly, the $\text{TiO}_2/\text{Au}/\text{a-TiO}_2$ photoelectrode exhibited a notably higher NH_3 production rate than bare TiO_2 , achieving $13.4 \text{ nmol}/(\text{cm}^2 \text{ h})$ under 1 sun illumination [39]. Similarly, Yang et al. [134] illustrated a “working-in-tandem” nitrogen photofixation system, which was realized by assembling plasmonic Au nanocrystals on O_{vac} -rich ultrathin TiO_2 nanosheets (Fig. 11c, d). The O_{vac} on the TiO_2 nanosheets chemisorbed and activated N_2 molecules, which were further reduced to ammonia by hot electrons generated from plasmonic gold nanocrystals. The apparent quantum efficiency for the conversion of incident photons to NH_3 reached 0.82% at 550 nm. The N_2 photofixation rate can be further improved by optimizing the absorption of visible light with the mixture of Au nanospheres and NRs.

2D-Layered Photocatalysts

Layered bismuth oxyhalides for nitrogen photofixation were first reported by Zhang and coworkers [31, 135]. Under visible-light illumination and ambient conditions, efficient NH_3 was generated from N_2 and water on bismuth oxybromide (BiOBr) nanosheets of O_{vac} in the absence of any organic scavengers and precious-metal cocatalysts. O_{vac} on the

Fig. 11 Solar N_2 fixation on TiO_2 photocatalysts. **a** Proposed photocatalytic cycle for N_2 fixation on the Ti^{3+} sites of rutile TiO_2 (110) surface. Reproduced with permission from Ref. [97]. Copyright 2017, American Chemical Society. **b** Illustration of the synergistic effect of surface O_{vac} and plasmonic Au NPs for photocatalytic N_2 reduction on $\text{TiO}_2/\text{Au}/\text{a-TiO}_2$. Reproduced with permission from Ref. [39]. Copyright 2018, Wiley–VCH. **c** Transmission electron microscopy (TEM) image of $\text{Au}/\text{TiO}_2\text{-OV}$ nanosheet. **d** NH_3 concentration on the four catalysts as a function of time. Reproduced with permission from Ref. [134]. Copyright 2018, American Chemical Society

exposed (001) facets provided localized electrons for π -back-donation and activated adsorbed N_2 , which could be reduced to NH_3 by the transferred electrons from the conduction band of excited BiOBr nanosheets (Fig. 12a). The resultant N_2 photofixation rate on BiOBr was $104.2 \mu\text{mol}/(\text{h g})$ [135]. Zhang and coworkers [136] further demonstrated that O_{vac} on BiOCl could act as the catalytic centers and contribute to the solar light driven $N \equiv N$ triple-bond cleavage via a proton-assisted electron-transfer pathway. In addition, different BiOCl facets strongly influence the N_2 reduction pathways by affecting both the adsorption structure and the activation level of N_2 .

Graphitic carbon nitride ($g\text{-C}_3\text{N}_4$) is a burgeoning material for N_2 photofixation, either as a catalytic or a supportive material [137–143]. Dong et al. [137] observed that N_{vac} endowed $g\text{-C}_3\text{N}_4$ with the photocatalytic N_2 fixation capability because N_{vac} could selectively adsorb and activate N_2 given their same shape and size with the nitrogen atom in N_2 . Cao et al. [138] reported a Z-scheme heterojunction-structured photocatalyst: 3,4-dihydroxybenzaldehyde-functionalized Ga_2O_3 /graphitic carbon nitride ($\text{Ga}_2\text{O}_3\text{-DBD}/g\text{-C}_3\text{N}_4$). The interaction between aromatic aldehydes in $\text{Ga}_2\text{O}_3\text{-DBD}$ and the terminal $-\text{NH}_2$ groups in $g\text{-C}_3\text{N}_4$ improved the dispersion of $\text{Ga}_2\text{O}_3\text{-DBD}$ NPs and resulted in the formation of a well-combined interface, which enhanced the charge transfer rates. Aromatic rings with good conductivity acted as electron mediators and promoted the recombination between photogenerated electrons from the conduction band of Ga_2O_3

and photogenerated holes from the valence band of $g\text{-C}_3\text{N}_4$, boosting the overall photovoltage [138]. Hu et al. [139, 140] anchored Fe^{3+} and Cu^{1+} at the interstitial position of $g\text{-C}_3\text{N}_4$, where coordinative $M\text{-N}$ bonds were formed. The metal-doped $g\text{-C}_3\text{N}_4$ exhibited notably higher photoactivity for N_2 reduction compared with bare $g\text{-C}_3\text{N}_4$. DFT simulations showed that a high nitrogen adsorption energy was obtained on anchored metal sites, and $N\text{-N}$ bond could be elongated. DOS results indicate that the electrons of $\sigma_g 2p$ orbital (highest-occupied molecular orbital) in nitrogen atom were substantially delocalized when N_2 adsorbed on metal-doped sites, and the orbital energy almost crossed that of $\pi_g^* 2p$ orbital (LUMO), illustrating that Fe^{3+} or Cu^{1+} sites can activate the N_2 molecule effectively. Jiang and colleagues [142] designed and fabricated a new $\text{TiO}_2@C/g\text{-C}_3\text{N}_4$ photocatalyst through thermal treatment of a mixture of melamine and MXene $\text{Ti}_3\text{C}_2\text{T}_x$. This method endowed carbon nanosheet-supported TiO_2 with abundant Ti^{3+} species that were tightly wrapped by in situ-formed $g\text{-C}_3\text{N}_4$ nanosheets. This heterojunction enhanced light absorption and charge separation, where electrons were injected from $g\text{-C}_3\text{N}_4$ to Ti^{3+} on TiO_2 for N_2 activation and reduction (Fig. 12b).

Graphene could generate a high density of hot electrons well above the Fermi level under visible light [144, 145]. Chen and colleagues [146] noted that light-generated highly energetic hot/free electrons of graphene could act as a promising reducing agent for NH_3 synthesis from N_2 and H_2 under ambient conditions. They fabricated an iron- and

Fig. 12 Solar N_2 fixation on 2D photocatalysts. **a** Schematic of N_2 reduction on O_{vac} of excited BiOBr nanosheets. Reproduced with permission from Ref. [135]. Copyright 2015, American Chemical Society. **b** Schematic of the energy band structure and electron–hole separation of $\text{TiO}_2@C/g\text{-C}_3\text{N}_4$. Adapted with permission from Ref. [142]. Copyright 2018, the Royal Society of Chemistry. **c** Proposed pathway for the NH_3 synthesis using $\text{Fe}@3\text{DG}$ catalyst under light illumination. Adapted with permission from Ref. [146]. Copyright 2016, American Chemical Society

graphene-based catalyst, Fe@3DGraphene, for NH_3 photosynthesis. Hot electrons from graphene induced by visible light were ejected onto the Fe catalytic sites, where N_2 activation and NH_3/H_2 generation occurred directly, without any other agents (Fig. 12c). Alumina as a structural promoter enhanced the stability of Fe@3DGraphene up to 50 h [146]. The same group further proved that nano- Al_2O_3 acting as a barrier among nano- Fe_2O_3 could significantly prevent the aggregation of Fe_2O_3 particles, improving the stability of catalysts [147].

A series of ultrathin layered-double-hydroxide (LDH) nanosheet photocatalysts of the type $\text{M}^{\text{II}}\text{M}^{\text{III}}\text{-LDH}$ (where $\text{M}^{\text{II}} = \text{Mg, Zn, Ni, Cu}$; and $\text{M}^{\text{III}} = \text{Al, Cr}$) were synthesized by simple coprecipitation routes [148]. These LDH nanosheets were engineered with O_{vac} defects to enhance the absorption and activation of N_2 . Especially, the CuCr-LDH photocatalyst exhibited a high activity under visible light for the photoreduction of N_2 to NH_3 . Cu^{2+} ions in the LDH nanosheets were assumed to introduce additional structural distortions and compressive strain, which boosted the interaction between the nanosheets and N_2 and thereby enhanced NH_3 formation.

Other Semiconductor Photocatalysts

Bismuth oxyhalide is susceptible to photocorrosion, where surface O_{vac} is easily oxidized to lose the catalytic sites. Wang et al. [149] resolved this problem using self-assembled 5 nm diameter $\text{Bi}_5\text{O}_7\text{Br}$ nanotubes (NTs) through a low-temperature wet chemical method. The $\text{Bi}_5\text{O}_7\text{Br}$ NTs contained abundant and light-switchable O_{vac} , realizing excellent and stable photosynthesis of NH_3 in pure water. The NH_3 generation rate was as high as 1.38 mmol/(h g), with an apparent quantum efficiency of 2.3% at 420 nm.

Bismuth monoxide (BiO) quantum dot is a low-valence metal oxide semiconductor that has fewer coordination atoms than its high-valence states [150]. This condition endows BiO with high electron-donating power and empty 6*d* orbitals for N_2 adsorption and activation. The N_2 molecule could be stretched and activated by alternately arranged Bi atoms by donating electrons to the empty Bi 6*d* orbitals. Without hole scavengers, BiO quantum dots exhibited a high NH_3 generation rate of 1226 $\mu\text{mol}/(\text{h g})$.

Biohybrid and Biomimetic Photocatalysts

In a bioinorganic system, cadmium sulfide (CdS) nanocrystals were used to photosensitize the nitrogenases molybdenum–iron (MoFe) protein, where light harvesting from CdS replaced ATP hydrolysis on the Fe protein to transfer electrons for enzymatic reduction of N_2 into NH_3 [7]. This CdS:MoFe protein biohybrid system achieved an optimal turnover rate of 75 per minute, which is 63% of

the ATP-coupled reaction for nitrogenase. Kanatzidis and coworkers [151] reported a nitrogenase-inspired biomimetic chalcogel system that exhibited photoactivity for N_2 reduction to NH_3 in aqueous media under ambient pressure and RT. The high-surface-area amorphous chalcogels were composed of $\text{Mo}_2\text{Fe}_6\text{S}_8(\text{SPh})_3$ or Fe_4S_4 with Sn_2S_6 clusters and exhibited strong optical absorption. Compared with chalcogels with $\text{Mo}_2\text{Fe}_6\text{S}_8(\text{SPh})_3$ cluster [151], Mo-free chalcogels containing only Fe_4S_4 clusters are more efficient for N_2 reduction to NH_3 [152]. This result suggests that Fe might be the active site for N_2 binding, similar to that in nitrogenase.

Ammonia Synthesis on Photoelectrodes

Unlike photoelectrochemical (PEC) water splitting [153, 154] or CO_2 reduction [155], N_2 fixation in PEC systems was rarely investigated. Limited studies reported N_2 photo-fixation on photoelectrodes [39, 156–162].

The first trial was realized in a PEC cell that contained a p-GaP cathode and an Al metal anode immersed in a non-aqueous electrolyte. N_2 was reduced to NH_3 on illuminated p-GaP electrode, whereas Al was continually consumed as the reducing agent [156]. Hamers and coworkers [157] used diamond as a solid-state source of solvated electrons for N_2 reduction. The conduction band edge of diamond lay at about 1 eV above the vacuum level, which enabled the electrons to be directly ejected into the inert N_2 molecules with negligible barrier (Fig. 13a). Oshikiri et al. [158, 160] investigated Au-decorated SrTiO_3 photoelectrode with Ru or Zr/ZrO_x as the cocatalysts. Water was oxidized by holes on the Au side, whereas excited hot electrons were conducted through the conduction band of SrTiO_3 to the catalyst side for N_2 reduction (Fig. 13b). MacFarlane and colleagues [159] presented a solar-driven PEC cell based on plasmon-enhanced black silicon nanowires (NWs) for the reduction of N_2 to ammonia. When sulfite was used as a reactant, the process could produce ammonium sulfate, an important fertilizer with high economic value (Fig. 13c). Li et al. [161] fabricated GaN NW array on a silicon substrate by plasma-assisted molecular beam epitaxy. Afterward, finely dispersed sub-nanoclusters of Ru were deposited on GaN with a high load of 5 wt% (Fig. 13d), forming a Schottky barrier junction between Ru and GaN (Fig. 13e), which resulted in partially negatively charged Ru species for elevated N_2 reduction performance under illumination. Zheng et al. [162] designed an aerophilic–hydrophilic heterostructured Si-based composite photocathode for PEC reduction of N_2 to NH_3 . Polytetrafluoroethylene (PTFE) porous framework was used as the N_2 diffusion layer, whereas Au NPs acted as the active sites and the electric contact between PTFE framework and Si. This structure formed an aerophilic–hydrophilic functional layer, which enriched N_2 concentration at the Au active sites and suppressed HER by reducing proton availability. This

Table 2 Summary of representative developments in photocatalytic NH₃ synthesis

	Catalyst/electrode	Light source ^a	Hole scavenger	NH ₃ yield ^b	References
Photocatalyst	0.24 wt%Ru/TiO ₂	Xe lamp	Ethanol	29.4 μmol/(h g)	[128]
	JRC-TiO ₂ -6 (rutile)	Hg lamp ($\lambda > 280$ nm)	2-PrOH	0.73 μmol/(h g)	[132]
	Au/TiO ₂ nanosheet	Xe lamp ($\lambda > 420$ nm)	Methanol	74.7 μmol/(h g)	[134]
	BiOBr nanosheet	Xe lamp ($\lambda > 420$ nm)	None	104.2 μmol/(h g)	[135]
	TiO ₂ @C/g-C ₃ N ₄	Xe lamp ($\lambda > 420$ nm)	Methanol	250.6 μmol/(h g)	[142]
	Cu-Cr LDH	Xe lamp	None	73.9 μmol/(h g)	[148]
	Fe-Al@3DGraphene	Hg lamp	None	25.3 μmol/(h g)	[147]
	Bi ₅ O ₇ Br NT	Xe lamp ($\lambda > 400$ nm)	None	1380 μmol/(h g)	[149]
	BiO quantum dots	Xe lamp	None	1226 μmol/(h g)	[150]
	FeMoS chalcogel	Xe lamp, 100 mW/cm ²	Sodium ascorbate	91.6 μmol/(h g)	[151]
Photoelectrode	Au/Nb-SrTiO ₃ /Zr/ZrO _x	Xe lamp, 550–800 nm	ethanol	1.8×10^{-12} mol/(cm ² s) ^c	[160]
	Cr/black-Si/Au	Xe lamp, 200 mW/cm ²	Na ₂ SO ₃	2.2×10^{-11} mol/(cm ² s) ^c	[159]
	Au-PTFE/Ti/Si	Xe lamp, 100 mW/cm ²	Na ₂ SO ₃	3.1×10^{-10} mol/(cm ² s) ^d	[162]

^aUnless otherwise specified, the light intensities were not mentioned in the literature

^bFrom given or calculated data based on reference data in the literature

^cOperated without external applied potential

^dOperated under -0.2 V_{RHE}

long-term reaction is also an issue for future applications [163]. More progress will be made with the development of characterization and calculation techniques.

Plasma Catalysis for Ammonia Production

Plasma catalysis has drawn attention in the past few decades as a possible alternative to the H–B process for NH₃ production [14, 34]. By ionizing the source gases via an electric discharge, nonequilibrium plasma is generated; it contains highly excited atomic, molecular, ionic, and radical species. The energy transfer to form excited species is realized by collisions between reactant molecules and high-energy electrons, where the huge mass discrepancy results in the relatively low background temperature. For example, in nonthermal plasmas, the temperature of electrons reaches 10⁵ K because of their small mass, whereas large-mass ions/molecules and background gas are observed at RT. This finding is favorable for an exothermic process such as NH₃ synthesis [164] and could also reduce sintering or coking of catalysts. The highly reactive electrons, ions, atoms, and radicals in the plasma also greatly boost the kinetics, enabling NH₃ production at RT and atmospheric pressure [165].

On the other hand, the composition and properties of plasma are complicated, posing a challenge to the control and understanding of plasma-incorporated process, especially when catalysts are involved. For example, dielectric catalyst would change electric field distribution and affect the plasma characteristics [166]. In addition, the lifetime of

short-lived active species can be extended on the catalyst surface, making the media more favorable for reaction [167].

As an external stimulus, plasma could also help heterogeneous catalysts to overcome scaling relations by converting N₂ into vibrationally or electronically excited states, which decrease the activation energy for N₂ dissociation without affecting subsequent reaction steps.

In a nonthermal plasma reactor induced by dielectric barrier discharge (DBD), the highest energy efficiency of 2.3 g NH₃/kWh was achieved at a frequency of 10,000 Hz, an applied voltage of 6000 V, and a supplied N₂/H₂ ratio of 3:1. Ru catalyst with CNT support outperformed the others, where cesium acted as a promoter, and Molecular Sieve 13X and Amberlyst 15 served as microporous absorbents [168]. Iwamoto and colleagues [169] designed a wool-like copper electrode, which was found to be an effective catalyst for NH₃ synthesis, using nonthermal atmospheric-pressure plasma by glow discharge. The energy efficiency of NH₃ production reached 3.5% with an NH₃ production rate of 3.3 g NH₃/kWh. The catalytic activity increased during reaction runs, and this phenomenon was also observed on a series of other wool-like metal electrodes. This finding might be due to the increased catalyst surface area [170]. Mehta et al. [38] demonstrated that DBD-induced nonthermal plasma could overcome the scaling relations through vibrational excitation of N₂ in a plasma-enabled catalytic process. Based on a kinetic model that incorporates the effect of N₂ vibrational excitation in a nonthermal plasma, they observed that NH₃ production rates could be significantly improved over thermal catalytic rates at the same temperature and pressure. Additionally, the optimal catalyst shifted to sites that bind

nitrogen weakly, such as Co and Ni, instead of those for thermal catalysis, which were illustrated by both calculations and experiments (Fig. 14). This work represents the first demonstration of the computationally guided design of plasma-catalyst system for NH_3 synthesis.

Homogeneous Molecular Catalysis for Ammonia Production

Another important artificial nitrogen fixation system focuses on stoichiometric transformation of coordinated dinitrogen or homogeneous catalytic reduction of N_2 on transition metal–dinitrogen complexes [35]. As a synthetic functional analogue to nitrogenase, well-defined homogeneous catalysts allow researchers to gain more insights into the N_2 reduction mechanism because these materials can be thoroughly investigated through various spectroscopic techniques, which aid in identifying molecular reactivity and elementary reactions that occur in nitrogenases. The first report of catalytic reduction of N_2 by transition metal complexes came up in 2003, when Schrock and colleagues [171] synthesized a mononuclear molybdenum complex $\text{HIPTN}_3\text{NMo}(\text{N}_2)$ (HIPT refers to hexa-iso-propyl-terphenyl) to convert N_2 into NH_3 , with 8 equivalents of ammonia per Mo atom. Nishibayashi and coworkers [172] observed that dimolybdenum-dinitrogen complex bearing 2,6-bis(di-*tert*-butylphosphinomethyl)pyridine pincer ligands acted as an effective catalyst for N_2 reduction to NH_3 , with 23 equivalents of NH_3 being generated (12 equivalents of NH_3 produced per Mo atom). Early studies emphasized the effect of Mo as an essential element of nitrogenases. With the development of biochemical and spectroscopic studies on nitrogenase, Fe instead of Mo was determined as the site of N_2 binding in the FeMo cofactor [8], and the central atom in FeMo cofactor was confirmed to be carbon [173, 174]. In 2011, Holland and coauthors [175]

reported for the first time an example of complete stoichiometric N_2 reduction by Fe complexes, although this reaction was not a catalytic process. A tris(phosphine)borane-supported iron complex was discovered in 2013; it catalyzes the reduction of N_2 to NH_3 under mild conditions, where a single iron site can stabilize various N_xH_y intermediates generated during catalytic N_2 reduction. A flexible iron–boron interaction possibly plays an important role in this catalytic process [176]. Holland further studied a synthetic complex with a sulfur-rich coordination sphere, which provides structural and spectroscopic implication for FeMoco- N_2 binding and nitrogenase mechanism. The results illustrate that the sulfur-rich Fe site in the FeMoco causes N_2 activation, and that Fe-S bonds can be easily reduced and broken to allow N_2 binding [177]. In addition to Mo- and Fe-based transition metal complexes, other molecular complexes incorporating metals, such as titanium and uranium, were also investigated to understand the mechanism behind enzymatic or thermal NH_3 synthesis [178–180].

Summary and Outlook

Developing NH_3 synthesis using sustainable or distributed approaches is becoming important to face the challenges of energy, environment, and transport issues. Homogeneous molecular catalysts are ideal for deep mechanism studies and show high activity due to their well-defined structures and facile mass transfer in the single liquid phase. Nonetheless, the difficulty in separating and recovering costly catalysts limits their practical applications. Heterogeneous catalysts normally possess complicated structures, where the exploration of the reaction mechanism is challenging. Still, these materials are the most widely studied catalysts for ENRR at present given their easy separation properties, relatively high activities, and great practical application potential.

Fig. 14 **a** Computed comparison of N_2 vibrational–distribution-weighted (plasma-on) and thermal (plasma-off) NH_3 synthesis rates on step sites. **b** Measured plasma-catalytic NH_3 site–time yield on metal/ Al_2O_3 catalysts as a function of the DFT-calculated nitrogen adsorption energy. Reproduced with permission from Ref. [38]. Copyright 2018, Macmillan Publishers Limited

In an era when electricity is becoming more reliable for clean energy, electrochemical NH_3 synthesis is highly expected. With a tremendous potential, this process will need considerable advancement toward practical applications and require a minimum production rate in the magnitude of $10^{-7} \text{ mol}/(\text{cm}^2 \text{ s})$ [13]. In systems using aprotic electrolytes, the investigations should focus on enhancing current densities, improving catalyst/electrode lifetime, and reducing process temperatures. In systems using aqueous electrolytes, the utmost concern is how to prohibit HER as much as possible. Although limiting proton or electron availability at the electrode surface could improve the selectivity of NH_3 , it is not feasible for application under high current conditions.

Photocatalytic NH_3 synthesis uses photo-responsive catalysts or photoelectrodes, and the yields demonstrated are still far from meeting the requirements for practical use. Standardization of the operation conditions is significant for future researchers for fair evaluation and comparison.

Electron transfer and reactions on the catalyst surface are critical steps in both electro- and photocatalytic N_2 reduction. Therefore, surface reaction mechanism must be understood, and strategies that promote surface kinetics must be designed accordingly. Inspiration from enzymes and homogeneous systems demonstrate the potential to design complex active sites to improve catalyst performance at ambient conditions [181]. In situ characterization techniques, such as attenuated total reflectance–FTIR, SEIRAS, and in situ near ambient-pressure X-ray photo-electron spectroscopy, can detect reaction intermediates or active sites [81, 182]. Along with DFT simulations, the reaction mechanism and screen principles would be reasonably deduced [183]. Moreover, the structure of catalysts could be analyzed more precisely by X-ray absorption fine-structure and aberration-corrected TEM, which in turn contributes to the development of new catalytic materials such as single-atom catalysts [184–186]. In addition, designing new reaction configuration, such as semiconductor–biological systems [7], lithium cycling electrosynthesis [68], bio-electrochemical [187], or (solar thermal) chemical looping [188, 189], could decouple the linear scaling between nitrogen-binding energy and activation barrier for N_2 dissociation [190].

Considering the small NH_3 yield at present, a significant issue in (photo)electrocatalytic NH_3 synthesis is the rigorous protocol to prove that NH_3 truly comes from N_2 reduction. Ammonia contamination is caused by various potential sources during an experiment cycle, which would lead to a fake positive result. Special attention must be paid to catalysts that are either nitrogen-containing or prepared from nitrogen-containing precursors. In the premise of eliminating every possible exogenous contamination, a proper $^{15}\text{N}_2$ control experiment is essential before drawing a convincing conclusion. In addition, utilizing various NH_3 detection

methods simultaneously could make the results more accurate (for instance, NMR/indophenol method).

In plasma-enabled catalytic NH_3 synthesis, limited knowledge is available about the fundamental reaction mechanisms of the activated species. Further development in this direction could draw inspiration from traditional heterogeneous catalysis and focus on building kinetic models, which are based on in situ characterization and computational simulations.

Although molecular catalysis for N_2 reduction still requires development toward practical use, catalytic systems for N_2 fixation have been successfully developed, and molecular structures that reveal essential components for the N_2 reduction mechanism have been offered. More insightful molecule design and experimental/theoretical investigations could broaden the understanding behind reactions, providing insights into the design of heterogeneous catalysts.

Overall, flourishing alternative catalytic systems have been making great contributions to N_2 reduction reaction. With the intensive and collaborative research worldwide, sustainable NH_3 synthesis will eventually arrive and create renewable wealth for human society.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

1. Rosca V, Duca M, de Groot MT et al (2009) Nitrogen cycle electrocatalysis. *Chem Rev* 109(6):2209–2244
2. Jia HP, Quadrelli EA (2014) Mechanistic aspects of dinitrogen cleavage and hydrogenation to produce ammonia in catalysis and organometallic chemistry: relevance of metal hydride bonds and dihydrogen. *Chem Soc Rev* 43(2):547–564
3. Allen MB, Arnon DI (1955) Studies on nitrogen-fixing blue-green algae. I. Growth and nitrogen fixation by *Anabaena cylindrica* lemm. *Plant Physiol* 30(4):366–372
4. Houlton BZ, Wang YP, Vitousek PM et al (2008) A unifying framework for dinitrogen fixation in the terrestrial biosphere. *Nature* 454(7202):327–330
5. Salvagiotti F, Cassman KG, Specht JE et al (2008) Nitrogen uptake, fixation and response to fertilizer N in soybeans: a review. *Field Crop Res* 108(1):1–13
6. Hoffman BM, Lukoyanov D, Yang ZY et al (2014) Mechanism of nitrogen fixation by nitrogenase: the next stage. *Chem Rev* 114(8):4041–4062

7. Brown KA, Harris DF, Wilker MB et al (2016) Light-driven dinitrogen reduction catalyzed by a CdS: nitrogenase MoFe protein biohybrid. *Science* 352(6284):448–450
8. Hoffman BM, Dean DR, Seefeldt LC (2009) Climbing nitrogenase: toward a mechanism of enzymatic nitrogen fixation. *Acc Chem Res* 42(5):609–619
9. Raugei S, Seefeldt LC, Hoffman BM (2018) Critical computational analysis illuminates the reductive-elimination mechanism that activates nitrogenase for N₂ reduction. *Proc Natl Acad Sci* 115(45):E10521–E10530
10. Čorić I, Holland PL (2016) Insight into the iron-molybdenum cofactor of nitrogenase from synthetic iron complexes with sulfur, carbon, and hydride ligands. *J Am Chem Soc* 138(23):7200–7211
11. Smil V (1999) Detonator of the population explosion. *Nature* 400(6743):415
12. Fowler D, Coyle M, Skiba U et al (2013) The global nitrogen cycle in the twenty-first century. *Philos Trans R Soc B* 368(1621):20130164
13. Giddey S, Badwal SPS, Kulkarni A (2013) Review of electrochemical ammonia production technologies and materials. *Int J Hydrog Energy* 38(34):14576–14594
14. Patil BS, Wang Q, Hessel V et al (2015) Plasma N₂-fixation: 1900–2014. *Catal Today* 256:49–66
15. Christensen CH, Johannessen T, Sørensen RZ et al (2006) Towards an ammonia-mediated hydrogen economy? *Catal Today* 111(1–2):140–144
16. Klerke A, Christensen CH, Nørskov JK et al (2008) Ammonia for hydrogen storage: challenges and opportunities. *J Mater Chem* 18(20):2304–2310
17. Erisman JW, Sutton MA, Galloway J et al (2008) How a century of ammonia synthesis changed the world. *Nat Geosci* 1(10):636–639
18. Howarth RW (2008) Coastal nitrogen pollution: a review of sources and trends globally and regionally. *Harmful Algae* 8(1):14–20
19. Wang L, Xia MK, Wang H et al (2018) Greening ammonia toward the solar ammonia refinery. *Joule* 2(6):1055–1074
20. Jackson RB, Canadell JG, Le Quéré C et al (2016) Reaching peak emissions. *Nat Clim Change* 6(1):7–10
21. Brethomé FM, Williams NJ, Seipp CA et al (2018) Direct air capture of CO₂ via aqueous-phase absorption and crystalline-phase release using concentrated solar power. *Nat Energy* 3(7):553–559
22. Chen JG, Crooks RM, Seefeldt LC et al (2018) Beyond fossil fuel-driven nitrogen transformations. *Science* 360(6391):eaar6611
23. Medford AJ, Hatzell MC (2017) Photon-driven nitrogen fixation: current progress, thermodynamic considerations, and future outlook. *ACS Catal* 7(4):2624–2643
24. Cui XY, Tang C, Zhang Q (2018) A review of electrocatalytic reduction of dinitrogen to ammonia under ambient conditions. *Adv Energy Mater* 8(22):1800369
25. Wang K, Smith D, Zheng Y (2018) Electron-driven heterogeneous catalytic synthesis of ammonia: current states and perspective. *Carbon Resour Convers* 1(1):2–31
26. Kyriakou V, Garagounis I, Vasileiou E et al (2017) Progress in the electrochemical synthesis of ammonia. *Catal Today* 286:2–13
27. Shipman MA, Symes MD (2017) Recent progress towards the electrosynthesis of ammonia from sustainable resources. *Catal Today* 286:57–68
28. Renner JN, Greenlee LF, Ayres KE et al (2015) Electrochemical synthesis of ammonia: a low pressure, low temperature approach. *Electrochem Soc Interface* 24(2):51–57
29. Guo CX, Ran JR, Vasileff A et al (2018) Rational design of electrocatalysts and photo(electro)catalysts for nitrogen reduction to ammonia (NH₃) under ambient conditions. *Energy Environ Sci* 11(1):45–56
30. Amar IA, Lan R, Petit CTG et al (2011) Solid-state electrochemical synthesis of ammonia: a review. *J Solid State Electrochem* 15(9):1845–1860
31. Li J, Li H, Zhan GM et al (2017) Solar water splitting and nitrogen fixation with layered bismuth oxyhalides. *Acc Chem Res* 50(1):112–121
32. Yang JH, Guo YZ, Lu WZ et al (2018) Emerging applications of plasmons in driving CO₂ reduction and N₂ fixation. *Adv Mater* 30(48):1802227
33. Chen XZ, Li N, Kong ZZ et al (2018) Photocatalytic fixation of nitrogen to ammonia: state-of-the-art advancements and future prospects. *Mater Horiz* 5(1):9–27
34. Hong J, Praver S, Murphy AB (2018) Plasma catalysis as an alternative route for ammonia production: status, mechanisms, and prospects for progress. *ACS Sustain Chem Eng* 6(1):15–31
35. MacLeod KC, Holland PL (2013) Recent developments in the homogeneous reduction of dinitrogen by molybdenum and iron. *Nat Chem* 5(7):559–565
36. Licht S, Cui B, Wang B et al (2014) Ammonia synthesis by N₂ and steam electrolysis in molten hydroxide suspensions of nanoscale Fe₂O₃. *Science* 345(6197):637–640
37. Marnellos G, Stoukides M (1998) Ammonia synthesis at atmospheric pressure. *Science* 282(5386):98–100
38. Mehta P, Barboun P, Herrera FA et al (2018) Overcoming ammonia synthesis scaling relations with plasma-enabled catalysis. *Nat Catal* 1(4):269–275
39. Li CC, Wang T, Zhao ZJ et al (2018) Promoted fixation of molecular nitrogen with surface oxygen vacancies on plasmon-enhanced TiO₂ photoelectrodes. *Angew Chem Int Ed* 57(19):5278–5282
40. Greenlee LF, Renner JN, Foster SL (2018) The use of controls for consistent and accurate measurements of electrocatalytic ammonia synthesis from dinitrogen. *ACS Catal* 8(9):7820–7827
41. Iwahara H, Esaka T, Uchida H et al (1981) Proton conduction in sintered oxides and its application to steam electrolysis for hydrogen production. *Solid State Ionics* 3–4:359–363
42. Garagounis I, Kyriakou V, Skodra A et al (2014) Electrochemical synthesis of ammonia in solid electrolyte cells. *Front Energy Res* 2(1):1–10
43. Marnellos G, Zisekas S, Stoukides M (2000) Synthesis of ammonia at atmospheric pressure with the use of solid state proton conductors. *J Catal* 193(1):80–87
44. Li Z, Liu R, Wang J et al (2007) Preparation of double-doped BaCeO₃ and its application in the synthesis of ammonia at atmospheric pressure. *Sci Technol Adv Mater* 8(7–8):566–570
45. Xie YH, Wang JD, Liu RQ et al (2004) Preparation of La_{1.9}Ca_{0.1}Zr₂O_{6.95} with pyrochlore structure and its application in synthesis of ammonia at atmospheric pressure. *Solid State Ionics* 168(1):117–121
46. Wang JD, Xie YH, Zhang ZF et al (2005) Protonic conduction in Ca²⁺-doped La₂M₂O₇ (M = Ce, Zr) with its application to ammonia synthesis electrochemically. *Mater Res Bull* 40(8):1294–1302
47. Liu RQ, Xie YH, Wang JD et al (2006) Synthesis of ammonia at atmospheric pressure with Ce_{0.8}M_{0.2}O_{2-δ} (M = La, Y, Gd, Sm) and their proton conduction at intermediate temperature. *Solid State Ionics* 177(1–2):73–76
48. Xu G, Liu R, Wang J (2009) Electrochemical synthesis of ammonia using a cell with a Nafion membrane and SmFe_{0.7}Cu_{0.3-x}Ni_xO₃ (x = 0–0.3) cathode at atmospheric pressure and lower temperature. *Sci China Ser B* 52(8):1171–1175
49. Liu R, Xu G (2010) Comparison of electrochemical synthesis of ammonia by using sulfonated polysulfone and Nafion membrane with Sm_{1.5}Sr_{0.5}NiO₄. *Chin J Chem* 28(2):139–142

50. Zhang ZF, Zhong ZP, Liu RQ (2010) Cathode catalysis performance of $\text{SmBaCuMO}_5 + \delta$ ($M = \text{Fe Co, Ni}$) in ammonia synthesis. *J Rare Earths* 28(4):556–559
51. Amar IA, Lan R, Petit CTG et al (2011) Electrochemical synthesis of ammonia based on a carbonate-oxide composite electrolyte. *Solid State Ionics* 182(1):133–138
52. Wang BH, Wang JD, Liu RQ et al (2006) Synthesis of ammonia from natural gas at atmospheric pressure with doped ceria- $\text{Ca}_3(\text{PO}_4)_2$, 2- K_3PO_4 composite electrolyte and its proton conductivity at intermediate temperature. *J Solid State Electrochem* 11(1):27–31
53. Chen C, Ma GL (2009) Proton conduction in $\text{BaCe}_{1-x}\text{Gd}_x\text{O}_{3-\alpha}$ at intermediate temperature and its application to synthesis of ammonia at atmospheric pressure. *J Alloy Compd* 485(1–2):69–72
54. Kordali V, Kyriacou G, Lambrou C (2000) Electrochemical synthesis of ammonia at atmospheric pressure and low temperature in a solid polymer electrolyte cell. *Chem Commun* 17:1673–1674
55. Skodra A, Stoukides M (2009) Electrocatalytic synthesis of ammonia from steam and nitrogen at atmospheric pressure. *Solid State Ionics* 180(23–25):1332–1336
56. Amar IA, Lan R, Tao SW (2015) Synthesis of ammonia directly from wet nitrogen using a redox stable $\text{La}_{0.75}\text{Sr}_{0.25}\text{Cr}_{0.5}\text{Fe}_{0.5}\text{O}_{3-\delta}$ - $\text{Ce}_{0.8}\text{Gd}_{0.18}\text{Ca}_{0.02}\text{O}_{2-\delta}$ composite cathode. *RSC Adv* 5(49):38977–38983
57. Goto T, Tada M, Ito Y (1997) Electrochemical behavior of nitride ions in a molten chloride system. *J Electrochem Soc* 144(7):2271–2276
58. Goto T, Ito Y (1998) Electrochemical reduction of nitrogen gas in a molten chloride system. *Electrochim Acta* 43(21–22):3379–3384
59. Murakami T, Nishikiori T, Nohira T et al (2003) Electrolytic synthesis of ammonia in molten salts under atmospheric pressure. *J Am Chem Soc* 125(2):334–335
60. Murakami T, Nishikiori T, Nohira T et al (2005) Investigation of anodic reaction of electrolytic ammonia synthesis in molten salts under atmospheric pressure. *J Electrochem Soc* 152(5):D75–D78
61. Serizawa N, Miyashiro H, Takei K et al (2012) Dissolution behavior of ammonia electrosynthesized in molten LiCl-KCl-CsCl system. *J Electrochem Soc* 159(4):E87–E91
62. Murakami T, Nohira T, Goto T et al (2005) Electrolytic ammonia synthesis from water and nitrogen gas in molten salt under atmospheric pressure. *Electrochim Acta* 50(27):5423–5426
63. Murakami T, Nohira T, Araki Y et al (2007) Electrolytic synthesis of ammonia from water and nitrogen under atmospheric pressure using a boron-doped diamond electrode as a nonconsumable anode. *Electrochem Solid State Lett* 10(4):E4–E6
64. Murakami T, Nishikiori T, Nohira T et al (2005) Electrolytic ammonia synthesis from hydrogen chloride and nitrogen gases with simultaneous recovery of chlorine under atmospheric pressure. *Electrochem Solid State Lett* 8(8):D19–D21
65. Murakami T, Nohira T, Ogata YH et al (2005) Electrochemical synthesis of ammonia and coproduction of metal sulfides from hydrogen sulfide and nitrogen under atmospheric pressure. *J Electrochem Soc* 152(6):D109–D112
66. Murakami T, Nohira T, Ogata YH et al (2005) Electrolytic ammonia synthesis in molten salts under atmospheric pressure using methane as a hydrogen source. *Electrochem Solid State Lett* 8(4):D12–D14
67. Li FF, Licht S (2014) Advances in understanding the mechanism and improved stability of the synthesis of ammonia from air and water in hydroxide suspensions of nanoscale Fe_2O_3 . *Inorg Chem* 53(19):10042–10044
68. McEnaney JM, Singh AR, Schwalbe JA et al (2017) Ammonia synthesis from N_2 and H_2O using a lithium cycling electrification strategy at atmospheric pressure. *Energy Environ Sci* 10(7):1621–1630
69. Montoya JH, Tsai C, Vojvodica A et al (2015) The challenge of electrochemical ammonia synthesis: a new perspective on the role of nitrogen scaling relations. *Chemsuschem* 8(13):2180–2186
70. van der Ham CJM, Koper MTM, Hetterscheid DGH (2014) Challenges in reduction of dinitrogen by proton and electron transfer. *Chem Soc Rev* 43(15):5183–5191
71. Ertl G (2008) Reactions at surfaces: from atoms to complexity (nobel lecture). *Angew Chem Int Ed* 47(19):3524–3535
72. Skúlason E, Bligaard T, Gudmundsdóttir S et al (2012) A theoretical evaluation of possible transition metal electro-catalysts for N_2 reduction. *Phys Chem Chem Phys* 14(3):1235–1245
73. Suryanto BHR, Du HL, Wang DB et al (2019) Challenges and prospects in the catalysis of electroreduction of nitrogen to ammonia. *Nat Catal* 2(4):290–296
74. Deng GR, Wang T, Alshehri AA et al (2019) Improving the electrocatalytic N_2 reduction activity of Pd nanoparticles through surface modification. *J Mater Chem A* 7(38):21674–21677
75. Wu TW, Zhu XJ, Xing Z et al (2019) Greatly improving electrochemical N_2 reduction over TiO_2 nanoparticles by iron doping. *Angew Chem Int Ed* 58(51):18449–18453
76. Xie HT, Geng Q, Zhu XJ et al (2019) PdP_2 nanoparticles-reduced graphene oxide for electrocatalytic N_2 conversion to NH_3 under ambient conditions. *J Mater Chem A* 7(43):24760–24764
77. Zhang R, Ji L, Kong WH et al (2019) Electrocatalytic N_2 -to- NH_3 conversion with high faradaic efficiency enabled using a Bi nanosheet array. *Chem Commun* 55(36):5263–5266
78. Li Y, Li T, Zhu X et al (2020) DyF_3 : an efficient electrocatalyst for N_2 fixation to NH_3 under ambient conditions. *Chem Asian J* 15(4):487–489
79. Zhao RB, Liu CW, Zhang XX et al (2020) An ultrasmall Ru_2P nanoparticles-reduced graphene oxide hybrid: an efficient electrocatalyst for NH_3 synthesis under ambient conditions. *J Mater Chem A* 8(1):77–81
80. Zhu XJ, Mou SY, Peng QL et al (2020) Aqueous electrocatalytic N_2 reduction for ambient NH_3 synthesis: recent advances in catalyst development and performance improvement. *J Mater Chem A* 8(4):1545–1556
81. Yao ZhuSQ, Wang HJ et al (2018) A spectroscopic study on the nitrogen electrochemical reduction reaction on gold and platinum surfaces. *J Am Chem Soc* 140(4):1496–1501
82. Yang DS, Chen T, Wang ZJ (2017) Electrochemical reduction of aqueous nitrogen (N_2) at a low overpotential on (110)-oriented Mo nanofilm. *J Mater Chem A* 5(36):18967–18971
83. Bao D, Zhang Q, Meng FL et al (2017) Electrochemical reduction of N_2 under ambient conditions for artificial N_2 fixation and renewable energy storage using N_2/NH_3 cycle. *Adv Mater* 29(3):1604799
84. Shi MM, Bao D, Wulan BR et al (2017) Au sub-nanoclusters on TiO_2 toward highly efficient and selective electrocatalyst for N_2 conversion to NH_3 at ambient conditions. *Adv Mater* 29(17):1606550
85. Li SJ, Bao D, Shi MM et al (2017) Amorphizing of Au nanoparticles by CeO_x -RGO hybrid support towards highly efficient electrocatalyst for N_2 reduction under ambient conditions. *Adv Mater* 29(33):1700001
86. Wang J, Yu L, Hu L et al (2018) Ambient ammonia synthesis via palladium-catalyzed electrohydrogenation of dinitrogen at low overpotential. *Nat Commun* 9(1):1795
87. Hao YC, Guo Y, Chen LW et al (2019) Promoting nitrogen electroreduction to ammonia with bismuth nanocrystals and potassium cations in water. *Nat Catal* 2(5):448–456

88. Nguyen M-T, Seriani N, Gebauer R (2015) Nitrogen electrochemically reduced to ammonia with hematite: density-functional insights. *Phys Chem Chem Phys* 17(22):14317–14322
89. Chen SM, Perathoner S, Ampelli C et al (2017) Room-temperature electrocatalytic synthesis of NH_3 from H_2O and N_2 in a gas–liquid–solid three-phase reactor. *ACS Sustain Chem Eng* 5(8):7393–7400
90. Kong JM, Lim A, Yoon C et al (2017) Electrochemical synthesis of NH_3 at low temperature and atmospheric pressure using a $\gamma\text{-Fe}_2\text{O}_3$ catalyst. *ACS Sustain Chem Eng* 5(11):10986–10995
91. Chen SM, Perathoner S, Ampelli C et al (2017) Electrocatalytic synthesis of ammonia at room temperature and atmospheric pressure from water and nitrogen on a carbon-nanotube-based electrocatalyst. *Angew Chem Int Ed* 56(10):2699–2703
92. Xiang XJ, Wang Z, Shi XF et al (2018) Ammonia synthesis from electrocatalytic N_2 reduction under ambient conditions by Fe_2O_3 nanorods. *ChemCatChem* 10(20):4530–4535
93. Lv C, Yan CS, Chen G et al (2018) An amorphous noble-metal-free electrocatalyst that enables nitrogen fixation under ambient conditions. *Angew Chem Int Ed* 130(21):6181–6184
94. Zhang L, Ji XQ, Ren X et al (2018) Electrochemical ammonia synthesis via nitrogen reduction reaction on a MoS_2 catalyst: theoretical and experimental studies. *Adv Mater* 30(28):1800191
95. Li XH, Li TS, Ma YJ et al (2018) Boosted electrocatalytic N_2 reduction to NH_3 by defect-rich MoS_2 nanoflower. *Adv Energy Mater* 8(30):1801357
96. Azofra LM, Sun CH, Cavallo L et al (2017) Feasibility of N_2 binding and reduction to ammonia on Fe-deposited MoS_2 2D sheets: a DFT study. *Chem Eur J* 23(34):8275–8279
97. Suryanto BHR, Wang DB, Azofra LM et al (2019) MoS_2 polymorphic engineering enhances selectivity in the electrochemical reduction of nitrogen to ammonia. *ACS Energy Lett* 4(2):430–435
98. Azofra LM, Li N, MacFarlane DR et al (2016) Promising prospects for 2D $d^2\text{--}d^4$ M_3C_2 transition metal carbides (MXenes) in N_2 capture and conversion into ammonia. *Energy Environ Sci* 9(8):2545–2549
99. Cheng H, Ding LX, Chen GF et al (2018) Molybdenum carbide nanodots enable efficient electrocatalytic nitrogen fixation under ambient conditions. *Adv Mater* 30(46):1803694
100. Abghoui Y, Garden AL, Hlynsson VF et al (2015) Enabling electrochemical reduction of nitrogen to ammonia at ambient conditions through rational catalyst design. *Phys Chem Chem Phys* 17(7):4909–4918
101. Abghoui Y, Skúlason E (2017) Electrochemical synthesis of ammonia via Mars–van Krevelen mechanism on the (111) facets of group III–VII transition metal mononitrides. *Catal Today* 286:78–84
102. Abghoui Y, Garden AL, Howalt JG et al (2016) Electroreduction of N_2 to ammonia at ambient conditions on mononitrides of Zr, Nb, Cr, and V: a DFT guide for experiments. *ACS Catal* 6(2):635–646
103. Abghoui Y, Skúlason E (2017) Onset potentials for different reaction mechanisms of nitrogen activation to ammonia on transition metal nitride electro-catalysts. *Catal Today* 286:69–77
104. Yang X, Nash J, Anibal J et al (2018) Mechanistic insights into electrochemical nitrogen reduction reaction on vanadium nitride nanoparticles. *J Am Chem Soc* 140(41):13387–13391
105. Li QY, He LZ, Sun CH et al (2017) Computational study of MoN_2 monolayer as electrochemical catalysts for nitrogen reduction. *J Phys Chem C* 121(49):27563–27568
106. Zhang L, Ji XQ, Ren X et al (2018) Efficient electrochemical N_2 reduction to NH_3 on MoN nanosheets array under ambient conditions. *ACS Sustain Chem Eng* 6(8):9550–9554
107. Wang H, Wang L, Wang Q et al (2018) Ambient electrosynthesis of ammonia: electrode porosity and composition engineering. *Angew Chem Int Ed* 57(38):12360–12364
108. Liu YM, Su Y, Quan X et al (2018) Facile ammonia synthesis from electrocatalytic N_2 reduction under ambient conditions on N-doped porous carbon. *ACS Catal* 8(2):1186–1191
109. Lv C, Qian YM, Yan CS et al (2018) Defect engineering metal-free polymeric carbon nitride electrocatalyst for effective nitrogen fixation under ambient conditions. *Angew Chem Int Ed* 57(32):10246–10250
110. Zhang LL, Ding LX, Chen GF et al (2019) Ammonia synthesis under ambient conditions: selective electroreduction of dinitrogen to ammonia on black phosphorus nanosheets. *Angew Chem Int Ed* 131(9):2638–2642
111. Milton RD, Cai R, Abdellaoui S et al (2017) Bioelectrochemical Haber–Bosch process: an ammonia-producing H_2/N_2 fuel cell. *Angew Chem Int Ed* 56(10):2680–2683
112. Ma JL, Bao D, Shi MM et al (2017) Reversible nitrogen fixation based on a rechargeable lithium–nitrogen battery for energy storage. *Chemistry* 2(4):525–532
113. Shi MM, Bao D, Li SJ et al (2018) Anchoring PdCu amorphous nanocluster on graphene for electrochemical reduction of N_2 to NH_3 under ambient conditions in aqueous solution. *Adv Energy Mater* 8(21):1800124
114. Liu HM, Han SH, Zhao Y et al (2018) Surfactant-free atomically ultrathin rhodium nanosheet nanoassemblies for efficient nitrogen electroreduction. *J Mater Chem A* 6(7):3211–3217
115. Han JR, Liu ZC, Ma YJ et al (2018) Ambient N_2 fixation to NH_3 at ambient conditions: using Nb_2O_5 nanofiber as a high-performance electrocatalyst. *Nano Energy* 52:264–270
116. Singh AR, Rohr BA, Schwalbe JA et al (2017) Electrochemical ammonia synthesis—The selectivity challenge. *ACS Catal* 7(1):706–709
117. Zhou FL, Azofra LM, Ali M et al (2017) Electro-synthesis of ammonia from nitrogen at ambient temperature and pressure in ionic liquids. *Energy Environ Sci* 10(12):2516–2520
118. Tsuneto A, Kudo A, Sakata T (1993) Efficient electrochemical reduction of N_2 to NH_3 catalyzed by lithium. *Chem Lett* 22(5):851–854
119. Lee HK, Koh CSL, Lee YH et al (2018) Favoring the unfavored: selective electrochemical nitrogen fixation using a reticular chemistry approach. *Sci Adv* 4(3):eaar3208
120. Andersen SZ, Čolić V, Yang S et al (2019) A rigorous electrochemical ammonia synthesis protocol with quantitative isotope measurements. *Nature* 570(7762):504–508
121. Dabundo R, Lehmann MF, Treibergs L et al (2014) The contamination of commercial 15N_2 gas stocks with 15N -labeled nitrate and ammonium and consequences for nitrogen fixation measurements. *PLoS One* 9(10):e110335
122. Han C, Qi MY, Tang ZR et al (2019) Gold nanorods-based hybrids with tailored structures for photoredox catalysis: fundamental science, materials design and applications. *Nano Today* 27:48–72
123. Tang ZR, Han B, Han C et al (2017) One dimensional CdS based materials for artificial photoredox reactions. *J Mater Chem A* 5(6):2387–2410
124. Schrauzer GN, Strampach N, Hui LN et al (1983) Nitrogen photoreduction on desert sands under sterile conditions. *Proc Natl Acad Sci* 80(12):3873–3876
125. Schrauzer GN, Guth TD (1977) Photolysis of water and photoreduction of nitrogen on titanium dioxide. *J Am Chem Soc* 99(22):7189–7193
126. Endoh E, Leland JK, Bard AJ (1986) Heterogeneous photoreduction of nitrogen to ammonia on tungsten oxide. *J Phys Chem* 90(23):6223–6226

127. Khader MM, Lichtin NN, Vurens GH et al (1987) Photoassisted catalytic dissociation of water and reduction of nitrogen to ammonia on partially reduced ferric oxide. *Langmuir* 3(2):303–304
128. Ranjit KT, Varadarajan TK, Viswanathan B (1996) Photocatalytic reduction of dinitrogen to ammonia over noble-metal-loaded TiO_2 . *J Photochem Photobiol A Chem* 96(1–3):181–185
129. Hoshino K, Inui M, Kitamura T et al (2000) Fixation of dinitrogen to a mesoscale solid salt using a titanium oxide/conducting polymer system. *Angew Chem Int Ed* 39(14):2509–2512
130. Rusina O, Eremenko A, Frank G et al (2001) Nitrogen photofixation at nanostructured iron titanate films. *Angew Chem Int Ed* 40(21):3993–3995
131. Zhao WR, Zhang J, Zhu X et al (2014) Enhanced nitrogen photofixation on Fe-doped TiO_2 with highly exposed (101) facets in the presence of ethanol as scavenger. *Appl Catal B Environ* 144:468–477
132. Hirakawa H, Hashimoto M, Shiraishi Y et al (2017) Photocatalytic conversion of nitrogen to ammonia with water on surface oxygen vacancies of titanium dioxide. *J Am Chem Soc* 139(31):10929–10936
133. Kong M, Li YZ, Chen X et al (2011) Tuning the relative concentration ratio of bulk defects to surface defects in TiO_2 nanocrystals leads to high photocatalytic efficiency. *J Am Chem Soc* 133(41):16414–16417
134. Yang JH, Guo YZ, Jiang RB et al (2018) High-efficiency “working-in-tandem” nitrogen photofixation achieved by assembling plasmonic gold nanocrystals on ultrathin titania nanosheets. *J Am Chem Soc* 140(27):8497–8508
135. Li H, Shang J, Ai ZH et al (2015) Efficient visible light nitrogen fixation with BiOBr nanosheets of oxygen vacancies on the exposed 001 facets. *J Am Chem Soc* 137(19):6393–6399
136. Li H, Shang J, Shi JG et al (2016) Facet-dependent solar ammonia synthesis of BiOCl nanosheets via a proton-assisted electron transfer pathway. *Nanoscale* 8(4):1986–1993
137. Dong GH, Ho W, Wang CY (2015) Selective photocatalytic N_2 fixation dependent on g- C_3N_4 induced by nitrogen vacancies. *J Mater Chem A* 3(46):23435–23441
138. Cao SH, Zhou N, Gao FH et al (2017) All-solid-state Z-scheme 3,4-dihydroxybenzaldehyde-functionalized Ga_2O_3 /graphitic carbon nitride photocatalyst with aromatic rings as electron mediators for visible-light photocatalytic nitrogen fixation. *Appl Catal B Environ* 218:600–610
139. Hu SZ, Chen X, Li Q et al (2017) Fe^{3+} doping promoted N_2 photofixation ability of honeycombed graphitic carbon nitride: the experimental and density functional theory simulation analysis. *Appl Catal B Environ* 201:58–69
140. Hu SZ, Qu XY, Bai J et al (2017) Effect of Cu(I)–N active sites on the N_2 photofixation ability over flowerlike copper-doped g- C_3N_4 prepared via a novel molten salt-assisted microwave process: the experimental and density functional theory simulation analysis. *ACS Sustain Chem Eng* 5(8):6863–6872
141. Cao SH, Chen H, Jiang F et al (2018) Nitrogen photofixation by ultrathin amine-functionalized graphitic carbon nitride nanosheets as a gaseous product from thermal polymerization of urea. *Appl Catal B Environ* 224:222–229
142. Liu QX, Ai LH, Jiang J (2018) MXene-derived TiO_2 @C/g- C_3N_4 heterojunctions for highly efficient nitrogen photofixation. *J Mater Chem A* 6(9):4102–4110
143. Qiu PX, Xu CM, Zhou N et al (2018) Metal-free black phosphorus nanosheets-decorated graphitic carbon nitride nanosheets with CP bonds for excellent photocatalytic nitrogen fixation. *Appl Catal B Environ* 221:27–35
144. Brida D, Tomadin A, Manzoni C et al (2013) Ultrafast collinear scattering and carrier multiplication in graphene. *Nat Commun* 4:1987
145. Zhang TF, Chang HC, Wu YP et al (2015) Macroscopic and direct light propulsion of bulk graphene material. *Nat Photon* 9(7):471–476
146. Lu YH, Yang Y, Zhang TF et al (2016) Photoprompted hot electrons from bulk cross-linked graphene materials and their efficient catalysis for atmospheric ammonia synthesis. *ACS Nano* 10(11):10507–10515
147. Yang Y, Zhang TF, Ge Z et al (2017) Highly enhanced stability and efficiency for atmospheric ammonia photocatalysis by hot electrons from a graphene composite catalyst with Al_2O_3 . *Carbon* 124:72–78
148. Zhao YF, Zhao YX, Waterhouse GIN et al (2017) Layered-double-hydroxide nanosheets as efficient visible-light-driven photocatalysts for dinitrogen fixation. *Adv Mater* 29(42):1703828
149. Wang SY, Hai X, Ding X et al (2017) Light-switchable oxygen vacancies in ultrafine $\text{Bi}_5\text{O}_7\text{Br}$ nanotubes for boosting solar-driven nitrogen fixation in pure water. *Adv Mater* 29(31):1701774
150. Sun SM, An Q, Wang WZ et al (2017) Efficient photocatalytic reduction of dinitrogen to ammonia on bismuth monoxide quantum dots. *J Mater Chem A* 5(1):201–209
151. Banerjee A, Yuhas BD, Margulies EA et al (2015) Photochemical nitrogen conversion to ammonia in ambient conditions with FeMoS -chalcogels. *J Am Chem Soc* 137(5):2030–2034
152. Liu J, Kelley MS, Wu WQ et al (2016) Nitrogenase-mimic iron-containing chalcogels for photochemical reduction of dinitrogen to ammonia. *Proc Natl Acad Sci* 113(20):5530–5535
153. Walter MG, Warren EL, McKone JR et al (2010) Solar water splitting cells. *Chem Rev* 110(11):6446–6473
154. Li CC, Luo ZB, Wang T et al (2018) Surface, bulk, and interface: rational design of hematite architecture toward efficient photoelectrochemical water splitting. *Adv Mater* 30(30):1707502
155. Chang XX, Wang T, Gong JL (2016) CO_2 photo-reduction: insights into CO_2 activation and reaction on surfaces of photocatalysts. *Energy Environ Sci* 9(7):2177–2196
156. Dickson CR, Nozik AJ (1978) Nitrogen fixation via photoenhanced reduction on p-gallium phosphide electrodes. *J Am Chem Soc* 100(25):8007–8009
157. Zhu D, Zhang LH, Ruther RE et al (2013) Photo-illuminated diamond as a solid-state source of solvated electrons in water for nitrogen reduction. *Nature Mater* 12(9):836–841
158. Oshikiri T, Ueno K, Misawa H (2014) Plasmon-induced ammonia synthesis through nitrogen photofixation with visible light irradiation. *Angew Chem Int Ed* 53(37):9802–9805
159. Ali M, Zhou FL, Chen K et al (2016) Nanostructured photoelectrochemical solar cell for nitrogen reduction using plasmon-enhanced black silicon. *Nat Commun* 7:11335
160. Oshikiri T, Ueno K, Misawa H (2016) Selective dinitrogen conversion to ammonia using water and visible light through plasmon-induced charge separation. *Angew Chem Int Ed* 55(12):3942–3946
161. Li L, Wang YC, Vanka S et al (2017) Nitrogen photofixation over III-nitride nanowires assisted by ruthenium clusters of low atomicity. *Angew Chem Int Ed* 129(30):8827–8831
162. Zheng JY, Lyu YH, Qiao M et al (2019) Photoelectrochemical synthesis of ammonia on the aerophilic-hydrophilic heterostructure with 37.8% efficiency. *Chemistry* 5(3):617–633
163. Weng B, Qi MY, Han C et al (2019) Photocorrosion inhibition of semiconductor-based photocatalysts: basic principle, current development, and future perspective. *ACS Catal* 9(5):4642–4687
164. Jiao F, Xu BJ (2019) Electrochemical ammonia synthesis and ammonia fuel cells. *Adv Mater* 31(31):1805173
165. Hong J, Pancheshnyi S, Tam E et al (2017) Kinetic modelling of NH_3 production in N_2 – H_2 non-equilibrium atmospheric-pressure plasma catalysis. *J Phys D Appl Phys* 50(15):154005

166. Eliasson B, Kogelschatz U (1991) Modeling and applications of silent discharge plasmas. *IEEE Trans Plasma Sci* 19(2):309–323
167. Carrasco E, Jiménez-Redondo M, Tanarro I et al (2011) Neutral and ion chemistry in low pressure dc plasmas of H_2/N_2 mixtures: routes for the efficient production of NH_3 and NH_4^+ . *Phys Chem Chem Phys* 13(43):19561–19572
168. Peng P, Li Y, Cheng Y et al (2016) Atmospheric pressure ammonia synthesis using non-thermal plasma assisted catalysis. *Plasma Chem Plasma Process* 36(5):1201–1210
169. Aihara K, Akiyama M, Deguchi T et al (2016) Remarkable catalysis of a wool-like copper electrode for NH_3 synthesis from N_2 and H_2 in non-thermal atmospheric plasma. *Chem Commun* 52(93):13560–13563
170. Iwamoto M, Akiyama M, Aihara K et al (2017) Ammonia synthesis on wool-like Au, Pt, Pd, Ag, or Cu electrode catalysts in nonthermal atmospheric-pressure plasma of N_2 and H_2 . *ACS Catal* 7(10):6924–6929
171. Yandulov DV, Schrock RR (2003) Catalytic reduction of dinitrogen to ammonia at a single molybdenum center. *Science* 301(5629):76–78
172. Arashiba K, Miyake Y, Nishibayashi Y (2011) A molybdenum complex bearing PNP-type pincer ligands leads to the catalytic reduction of dinitrogen into ammonia. *Nat Chem* 3(2):120–125
173. Lancaster KM, Roemelt M, Ettenhuber P et al (2011) X-ray emission spectroscopy evidences a central carbon in the nitrogenase iron–molybdenum cofactor. *Science* 334(6058):974–977
174. Spatzal T, Aksoyoglu M, Zhang L et al (2011) Evidence for interstitial carbon in nitrogenase FeMo cofactor. *Science* 334(6058):940
175. Rodriguez MM, Bill E, Brennessel WW et al (2011) N_2 reduction and hydrogenation to ammonia by a molecular iron–potassium complex. *Science* 334(6057):780–783
176. Anderson JS, Rittle J, Peters JC (2013) Catalytic conversion of nitrogen to ammonia by an iron model complex. *Nature* 501(7465):84–87
177. Čorić I, Mercado BQ, Bill E et al (2015) Binding of dinitrogen to an iron–sulfur–carbon site. *Nature* 526(7571):96–99
178. Shima T, Hu SW, Luo G et al (2013) Dinitrogen cleavage and hydrogenation by a trinuclear titanium polyhydride complex. *Science* 340(6140):1549–1552
179. Falcone M, Chatelain L, Scopelliti R et al (2017) Nitrogen reduction and functionalization by a multimetallic uranium nitride complex. *Nature* 547(7663):332–335
180. Falcone M, Barluzzi L, Andrez J et al (2019) The role of bridging ligands in dinitrogen reduction and functionalization by uranium multimetallic complexes. *Nat Chem* 11(2):154–160
181. Foster SL, Bakovic SIP, Duda RD et al (2018) Catalysts for nitrogen reduction to ammonia. *Nat Catal* 1(7):490–500
182. Comer BM, Liu YH, Dixit MB et al (2018) The role of adventitious carbon in photo-catalytic nitrogen fixation by titania. *J Am Chem Soc* 140(45):15157–15160
183. An Q, Shen YD, Fortunelli A et al (2018) QM-mechanism-based hierarchical high-throughput in silico screening catalyst design for ammonia synthesis. *J Am Chem Soc* 140(50):17702–17710
184. Huang PC, Liu W, He ZH et al (2018) Single atom accelerates ammonia photosynthesis. *Sci China Chem* 61(9):1187–1196
185. Zhao JX, Chen ZF (2017) Single Mo atom supported on defective boron nitride monolayer as an efficient electrocatalyst for nitrogen fixation: a computational study. *J Am Chem Soc* 139(36):12480–12487
186. Liu X, Jiao Y, Zheng Y et al (2019) Building up a picture of the electrocatalytic nitrogen reduction activity of transition metal single-atom catalysts. *J Am Chem Soc* 141(24):9664–9672
187. Milton RD, Abdellaoui S, Khadka N et al (2016) Nitrogenase bioelectrocatalysis: heterogeneous ammonia and hydrogen production by MoFe protein. *Energy Environ Sci* 9(8):2550–2554
188. Michalsky R, Avram AM, Peterson BA et al (2015) Chemical looping of metal nitride catalysts: low-pressure ammonia synthesis for energy storage. *Chem Sci* 6(7):3965–3974
189. Gao WB, Guo JP, Wang PK et al (2018) Production of ammonia via a chemical looping process based on metal imides as nitrogen carriers. *Nat Energy* 3(12):1067–1075
190. Medford AJ, Vojvodic A, Hummelshøj JS et al (2015) From the Sabatier principle to a predictive theory of transition-metal heterogeneous catalysis. *J Catal* 328:36–42

Tuo Wang received his BS degree from Tianjin University and his PhD degree from the University of Texas at Austin, both in chemical engineering. After gaining another year of research experience as a postdoctoral associate, he joined Lam Research Corp. as a PECVD process development engineer in Tualatin, Oregon. He joined the faculty of the School of Chemical Engineering at Tianjin University, where he is currently a full professor. His research focuses on photoelectrochemical water splitting, CO_2 reduction and NH_3 reduction based on semiconductor thin films.