Correction to: Compositional analysis of Late Medieval glass from the western Balkan and eastern Adriatic hinterland

Nikolina Topić¹ · Iva Bogdanović Radović² · Stjepko Fazinić² · Žiga Šmit^{3,4} · Mirsad Sijarić⁵ · Ljubomir Gudelj⁶ · Tonči Burić⁷

Published online: 4 March 2019

© Springer-Verlag GmbH Germany, part of Springer Nature 2019

Correction to: Archaeological and Anthropological Sciences
<https://doi.org/10.1007/s12520-018-0712-9>

Cl is given as ClO (wt%) in Table 2. This should be corrected to Cl. Several oxides (TiO₂, Cr₂O₃, CoO, CuO, ZnO, As₂O₃, Rb₂O, Br, SrO, ZrO₂, PbO) are given as ppm while it is written that they are given as wt% in Table 3. New table captions for Tables 2 and 3 were provided. In Discussion section, the last part of the second sentence in the second paragraph should be deleted and read as: “The low quality of the purifying procedure is also demonstrated by diverse MgO concentrations.” Given in this article were the corrected Tables.

The original article has been corrected.

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

The online version of the original article can be found at <https://doi.org/10.1007/s12520-018-0712-9>

✉ Nikolina Topić
nikolinatopic@gmail.com

¹ Freelance Archaeologist, Zagreb, Croatia

² Laboratory for Ion Beam Interactions, Division of Experimental Physics, Ruđer Bošković Institute, P.O. Box 180, Bijenička cesta 54, HR-10001 Zagreb, Croatia

³ Faculty of Mathematics and Physics, University of Ljubljana, Jadranska 19, 1000 Ljubljana, Slovenia

⁴ Jožef Stefan Institute, Jamova 39, P.O. Box 3000, 1001 Ljubljana, Slovenia

⁵ National Museum of Bosnia and Herzegovina, Zmaja od Bosne 3, 71000 Sarajevo, Bosnia and Herzegovina

⁶ Museum of Croatian Archaeological Monuments, Stjepana Gunjače 3, HR-21000 Split, Croatia

⁷ Kaštel Lukšić, Croatia

Table 2 Concentrations are given in weight per cent for major and in $\mu\text{g/g}$ for minor elements. In general, uncertainties are at the level of about 5% for higher concentrations and 10% for lower concentrations

No.		Na ₂ O wt%	MgO wt%	Al ₂ O ₃ wt%	SiO ₂ wt%	P ₂ O ₅ wt%	SO ₃ wt%	Cl wt%	K ₂ O wt%	CaO wt%	TiO ₂ $\mu\text{g/g}$	V ₂ O ₅ $\mu\text{g/g}$	Cr ₂ O ₃ $\mu\text{g/g}$
1	Čačvina fortress	11.48	2.43	4.17	66.77	0.30	0.40	0.74	1.97	10.05	707	33	<7
2	Čačvina fortress	13.80	2.67	3.52	67.64	0.18	0.34	0.74	1.97	7.55	541	<10	<7
3	Čačvina fortress	13.49	2.72	1.10	70.74	0.27	0.27	0.66	2.27	7.10	426	<10	65
4	Čačvina fortress	13.53	2.63	1.19	70.29	0.23	0.27	0.64	2.34	7.01	479	<10	82
5	Čačvina fortress	13.62	3.26	1.47	70.02	0.16	0.35	0.72	1.94	7.32	560	<10	33
6	Čačvina fortress	13.31	3.41	1.78	68.46	0.21	0.28	0.63	2.00	8.65	587	<10	<7
7	Čačvina fortress	13.60	2.89	2.76	65.99	0.25	0.55	0.81	2.17	8.85	528	<10	<7
8	Čačvina fortress	11.89	3.72	2.00	67.67	0.30	0.32	0.68	2.29	8.91	431	<10	24
9	Čačvina fortress	12.19	2.57	2.18	71.77	0.27	0.16	0.78	2.27	6.53	486	11	29
10	Čačvina fortress	13.16	3.50	2.27	67.32	0.36	0.23	0.63	2.12	9.09	665	<10	<7
11	Čačvina fortress	14.52	2.78	3.43	65.48	0.25	0.17	0.52	2.15	8.40	853	<10	<7
12	Čačvina fortress	13.72	3.67	1.50	69.75	0.20	0.26	0.74	1.92	7.23	495	<10	10
13	Čačvina fortress	14.36	3.61	1.98	68.61	0.21	0.25	0.75	1.92	7.47	532	12	10
14	Čačvina fortress	12.66	2.63	3.57	67.84	0.23	0.43	0.58	2.14	8.17	650	29	13
15	Čačvina fortress	8.51	3.03	2.38	74.94	0.09	0.53	0.70	2.07	6.51	376	17	<7
16	Čačvina fortress	12.43	2.99	2.58	69.16	0.22	0.22	0.69	2.02	8.15	634	<10	20
17	Čačvina fortress	10.16	2.13	7.67	67.27	0.31	0.37	0.64	2.05	8.54	767	19	14
18	Čačvina fortress	10.09	3.03	1.52	73.99	0.24	0.30	0.68	2.38	6.94	428	15	<7
19	Čačvina fortress	8.47	2.68	2.03	76.16	0.15	0.29	0.69	1.61	6.95	351	13	<7
20	Čačvina fortress	13.68	2.81	3.04	69.33	0.19	0.34	0.67	1.92	7.31	589	<10	<7
21	Čačvina fortress	10.77	4.01	1.88	69.86	0.26	0.30	0.70	2.10	8.61	607	18	15
22	Čačvina fortress	11.62	2.52	1.71	71.95	0.19	0.28	0.59	1.66	8.07	464	21	<7
23	Čačvina fortress	10.43	2.68	4.28	70.01	0.19	0.38	0.62	2.02	8.43	700	<10	11
24	Čačvina fortress	13.46	2.54	2.61	70.01	0.21	0.24	0.69	2.26	6.68	486	<10	10
25	Čačvina fortress	14.81	2.11	3.27	68.64	0.18	0.07	0.61	2.06	7.36	591	15	13
26	Čačvina fortress	14.66	2.59	3.38	66.45	0.24	0.21	0.83	2.32	8.32	664	28	21
27	Čačvina fortress	13.87	3.80	1.44	69.61	0.18	0.25	0.75	1.93	7.41	486	<10	10
28	Čačvina fortress	10.94	2.46	4.26	70.83	0.25	0.28	0.83	2.57	6.85	531	<10	11
29	Čačvina fortress	18.24	1.37	2.67	67.48	0.33	0.32	1.05	1.90	5.46	898	17	8
30	Bribir	12.32	3.27	2.04	68.89	0.27	0.35	0.80	1.83	8.97	582	<10	8
31	Sokol-Konavle	12.90	3.45	1.59	68.87	0.21	0.24	0.80	2.04	8.59	476	39	8
32	Sokol-Konavle	15.71	2.95	1.01	69.48	0.27	0.30	0.81	2.11	6.68	310	16	<7
33	Sokol-Konavle	13.59	2.98	1.07	68.89	0.26	0.29	0.81	2.07	9.14	758	16	10
34	Sokol-Konavle	10.16	1.91	2.22	71.10	0.35	0.17	0.78	3.51	8.24	910	28	14
35	Sokol-Konavle	11.66	3.22	2.22	70.00	0.26	0.23	0.74	2.02	8.51	485	19	<7
36	Sokol-Konavle	13.28	2.98	1.24	68.89	0.23	0.40	0.75	1.98	8.95	984	36	<7
37	Sokol-Konavle	12.78	3.51	1.44	68.86	0.23	0.30	0.80	2.06	8.70	489	15	22
38	Sokol-Konavle	10.85	3.49	1.70	70.83	0.28	0.32	0.72	2.00	8.90	601	26	11
39	Sokol-Konavle	12.90	2.54	1.56	71.08	0.22	0.22	0.79	1.66	8.29	793	<10	15
40	Sokol-Konavle	12.41	2.93	1.70	70.64	0.26	0.23	0.74	1.97	8.06	567	<10	11
41	Sokol-Konavle	11.18	2.83	1.39	72.28	0.29	0.35	0.68	1.60	8.50	968	<10	19
42	Sokol-Konavle	13.10	3.23	2.24	68.31	0.31	0.29	0.64	2.18	8.66	613	25	11
43	Sokol-Konavle	13.56	3.38	2.08	69.22	0.19	0.18	0.73	2.49	7.40	335	25	19

Table 2 (continued)

44	Sokol-Konavle	pruned beaker	green	10.32	2.44	2.97	71.32	0.30	0.21	0.67	2.00	8.64	932	29	32
45	Sokol-Konavle	pruned beaker	green	11.60	2.91	3.02	69.39	0.32	0.14	0.69	2.06	9.12	749	18	23
46	Sokol-Konavle	beaker vert. ribs	pale yellowish	11.63	3.08	1.92	69.80	0.21	0.30	0.67	1.91	9.05	517	31	12
47	Sokol-Konavle	beaker vert. ribs	pale yellowish	11.48	2.96	1.32	72.78	0.25	0.30	0.66	1.69	7.62	420	<10	20
48	Sokol-Konavle	lamp	pale yellowish	12.11	3.64	1.91	68.91	0.23	0.34	0.69	2.31	8.60	558	28	<7
49	Sokol-Konavle	beaker appl. thr.	colourless	14.38	3.55	2.16	66.73	0.30	0.26	0.68	2.28	8.29	725	26	14
50	Sokol-Konavle	beaker vert. ribs	pale yellowish	11.94	3.46	1.51	69.93	0.22	0.28	0.70	2.11	8.64	430	20	11
51	Sokol-Konavle	beaker wavy ribbon	pale yellowish	14.81	2.59	1.50	68.25	0.45	0.30	0.67	1.88	8.34	740	21	31
52	Sokol-Konavle	beaker vert. ribs	pale yellowish	13.01	2.55	2.32	70.27	0.29	0.24	0.65	1.80	8.02	560	12	<7
53	Sokol-Konavle	beaker with arcades	pale yellowish	11.93	3.27	3.02	67.07	0.19	0.30	0.61	2.29	9.54	643	23	29
54	Sokol-Konavle	beaker slanted ribs	pale yellowish	14.12	3.06	1.17	68.24	0.25	0.30	0.78	2.17	9.14	818	16	27
55	Sokol-Konavle	beaker appl. thr.	pale yellowish	13.49	2.15	3.81	67.60	0.21	0.18	0.61	1.83	9.05	692	20	18
56	Sokol-Konavle	beaker wavy ribbon	colourless	12.03	3.35	1.66	70.13	0.28	0.34	0.67	1.86	8.50	455	19	9
57	Sokol-Konavle	beaker wavy ribbon	green	15.47	2.86	2.97	65.88	0.23	0.10	0.73	2.06	8.91	583	<10	13
58	Sokol-Konavle	beaker vert. ribs	yellowish	10.26	3.51	2.27	69.28	0.29	0.31	0.65	2.23	9.80	674	20	17
59	Sokol-Konavle	beaker slanted ribs	pale yellowish	12.28	2.62	1.76	70.32	0.23	0.25	0.74	1.94	8.89	750	<10	<7
60	Sokol-Konavle	beaker wavy ribbon	pale yellowish	11.91	2.45	2.47	70.32	0.22	0.22	0.75	1.99	8.85	743	30	25
61	Sokol-Konavle	beaker slanted ribs	colourless	10.98	2.85	1.36	69.77	0.37	0.22	0.76	2.26	10.34	1060	30	<7
62	Sokol-Konavle	beaker vert. ribs	pale yellowish	12.70	3.24	1.18	70.20	0.27	0.29	0.68	1.91	8.33	463	21	15
63	Sokol-Konavle	beaker wavy ribbon	colourless	13.02	2.39	2.43	69.14	0.24	0.24	0.73	2.00	8.88	838	<10	17
64	Sokol-Konavle	beaker appl. thr.	colourless	12.85	1.85	5.36	67.63	0.17	0.26	0.62	3.62	6.30	502	14	13
65	Sokol-Konavle	beaker with arcades	yellowish	10.34	1.98	2.21	69.91	0.37	0.16	0.85	3.72	8.44	1033	39	20
66	Sokol-Konavle	beaker without orn.	colourless	11.00	3.26	1.92	70.80	0.20	0.30	0.73	2.07	7.63	594	17	10
67	Sokol-Konavle	beaker vert. ribs	yellowish	10.31	3.07	2.89	69.55	0.25	0.27	0.59	2.03	9.57	664	20	15
68	Sokol-Konavle	beaker appl. thr.	colourless	14.51	2.91	1.76	67.38	0.26	0.18	0.73	2.07	8.68	653	24	11
69	Sokol-Konavle	beaker appl. thr.	colourless	12.38	3.63	1.70	67.56	0.32	0.31	0.63	2.16	9.82	694	20	22
70	Sokol-Konavle	beaker appl. thr.	colourless	13.61	2.96	2.49	69.89	0.28	0.27	0.70	2.18	6.77	522	<10	13
71	Sokol-Konavle	beaker appl. thr.	yellowish	12.28	3.12	2.19	68.48	0.28	0.32	0.69	2.09	9.50	662	<10	21
72	Sokol-Konavle	beaker appl. thr.	colourless	14.80	1.70	4.02	67.31	0.18	0.23	0.50	2.45	8.05	422	<10	9
73	Sokol-Konavle	beaker appl. thr.	colourless	15.55	2.47	1.65	68.18	0.23	0.25	0.78	2.12	7.94	477	12	9
74	Sokol-Konavle	beaker wavy ribbon	pale yellowish	7.34	2.35	2.05	71.91	0.21	0.47	0.92	2.56	10.31	1030	<10	27
75	Sokol-Konavle	beaker appl. thr.	pale yellowish	12.50	3.24	1.77	69.74	0.26	0.26	0.71	2.12	7.93	1127	24	109
76	Sokol-Konavle	beaker appl. thr.	pale green	12.36	3.23	2.69	67.10	0.29	0.22	0.54	2.40	9.58	798	16	32
77	Sokol-Konavle	beaker with arcades	yellowish	9.31	1.58	3.42	71.27	0.31	0.12	0.81	3.41	8.18	996	24	16
78	Sokol-Konavle	bowl	yellowish	12.83	2.81	1.91	67.49	0.30	0.24	0.61	2.31	10.40	658	16	33
79	Sokol-Konavle	bowl	yellowish	10.82	1.87	1.87	70.63	0.36	0.16	0.84	3.47	8.33	995	35	12
80	Sokol-Konavle	bowl	yellowish	11.27	2.00	2.28	69.16	0.36	0.15	0.75	3.93	8.11	998	44	20
81	Baba lokva	beaker wavy ribbon	yellowish	11.31	2.69	3.06	69.10	0.30	0.29	0.60	2.82	8.33	883	32	11
82	Baba lokva	beaker vert. ribs	pale yellowish	9.13	1.33	3.52	72.67	0.69	0.21	0.54	3.99	6.92	1109	27	17
83	Baba lokva	beaker vert. ribs	colourless	12.92	3.48	1.56	69.73	0.21	0.28	0.70	2.05	8.23	562	<10	14
84	Baba lokva	beaker wavy ribbon	pale yellowish	13.36	2.64	2.27	68.81	0.28	0.29	0.68	2.24	7.80	851	<10	25
85	Baba lokva	pruned beaker	green	12.89	3.08	2.00	70.45	0.28	0.14	0.68	2.32	7.46	547	<10	17
86	Baba lokva	pruned beaker	pale yellowish	11.09	3.43	2.03	70.04	0.31	0.34	0.71	2.07	8.09	764	15	8
87	Baba lokva	pruned beaker	pale green	12.07	3.04	2.11	70.70	0.23	0.25	0.68	2.09	7.67	538	<10	26
88	Vid	beaker vert. ribs	yellowish-greenish	12.05	3.18	2.36	67.81	0.29	0.31	0.72	2.73	8.61	776	50	14
89	Vid	beaker vert. ribs	pale yellowish	9.57	3.17	1.65	71.30	0.27	0.35	0.66	2.19	9.38	683	21	26
90	Vid	beaker vert. ribs	pale yellowish	11.03	3.69	1.40	70.12	0.33	0.27	0.79	2.60	8.56	421	46	<7

Table 2 (continued)

91	Vid		beaker blown ribs		pale yellowish	10.53	3.21	2.62	69.38	0.30	0.35	0.70	2.41	8.83	908	31	15	
92	Vid		beaker appl. thr.		colourless	10.03	3.82	1.80	69.85	0.24	0.33	0.87	2.14	9.54	637	24	<7	
93	Vid		beaker appl. thr.		pale yellowish	12.66	3.23	1.59	69.80	0.26	0.28	0.70	2.39	7.78	647	23	<7	
94	Vid		beaker wavy ribbon		yellowish-greenish	9.76	2.16	1.59	67.10	0.26	0.45	1.05	3.50	11.53	1016	46	33	
95	Dubrovnik - Rectors palace		beaker appl. thr. (?)		pale greenish	7.15	2.12	3.68	73.19		0.21	0.64	4.49	7.10	730	<10	<7	
No.	MnO wt%	Fe ₂ O ₃ wt%	CoO µg/g	NiO µg/g	Cu ₂ O µg/g	ZnO µg/g	As ₂ O ₅ µg/g	SnO ₂ wt%	SrO µg/g	ZrO ₂ µg/g	BaO µg/g	PbO µg/g					sample no	
1	0.86	0.72	44	11	51	203	18	<0.1	502	<45	175	<70					1	
2	0.55	0.58	42	<11	25	32	<17	0.41	514	113	<100	73					2	
3	0.45	0.36	59	33	38	53	<17	0.40	984	<45	<100	315					3	
4	0.46	0.76	671	67	1000	334	26	0.34	933	<45	<100	510					4	
5	0.04	0.63	346	252	385	877	<17	0.23	631	<45	<100	<70					5	
6	0.39	0.52	37	<11	28	71	<17	0.28	638	61	<100	<70					6	
7	0.41	0.60	158	89	186	172	52	0.28	828	<45	<100	<70					7	
8	0.75	0.70	246	208	269	103	69	<0.1	612	<45	254	<70					8	
9	0.04	0.66	2108	1686	1533	38	137	<0.1	465	81	147	73					9	
10	0.39	0.56	31	<11	40	30	<17	0.30	649	<45	<100	<70					10	
11	1.16	0.67	79	<11	72	65	21	0.36	658	93	<100	<70					11	
12	0.04	0.57	<30	<11	14	911	<17	0.26	599	<45	<100	<70					12	
13	0.05	0.64	32	<11	16	931	<17	<0.1	660	<45	110	<70					13	
14	0.81	0.65	59	14	116	56	<17	0.19	533	<45	167	<70					14	
15	0.46	0.37	23	<11	82	41	<17	0.19	371	<45	106	<70					15	
16	0.40	0.55	77	16	197	100	<17	0.42	1210	130	<100	<70					16	
17	0.06	0.73	38	<11	30	45	<17	<0.1	533	<45	139	<70					17	
18	0.46	0.33	69	<11	26	50	<17	0.29	504	<45	<100	165					18	
19	0.23	0.22	<30	28	113	48	<17	<0.1	461	<45	<100	<70					19	
20	0.25	0.36	46	<11	<10	33	32	<0.1	521	<45	223	<70					20	
21	0.59	0.49	32	17	226	23	<17	<0.1	679	<45	230	<70					21	
22	0.86	0.44	45	11	219	38	<17	<0.1	641	<45	177	<70					22	
23	0.19	0.64	95	86	145	67	<17	<0.1	655	<45	168	<70					23	
24	0.54	0.44	<30	<11	17	28	24	0.24	539	<45	128	<70					24	
25	0.12	0.69	33	15	39	136	<17	<0.1	481	53	101	<70					25	
26	0.16	0.64	40	15	69	100	<17	<0.1	639	<45	1087	115					26	
27	0.03	0.59	<30	<11	17	698	<17	<0.1	557	<45	111	<70					27	
28	0.04	0.59	<30	18	25	45	145	<0.1	<30	<45	110	<70					28	
29	0.39	0.63	32	<11	38	66	<17	<0.1	425	111	163	<70					29	
30	0.63	0.48	<30	<11	13	53	<17	<0.1	648	<45	99	<70					30	

Table 2 (continued)

31	0.68	0.47	<30	21	29	191	<17	<0.1	638	<45	208	<70	31
32	0.20	0.26	<30	<11	14	32	41	0.15	457	<45	<100	111	32
33	0.41	0.27	32	<11	50	72	<17	<0.1	615	150	247	129	33
34	0.74	0.67	47	<11	47	41	21	<0.1	780	<45	370	<70	34
35	0.58	0.40	36	15	328	80	<17	<0.1	562	<45	<100	<70	35
36	0.63	0.35	<30	36	102	72	<17	0.11	445	548	208	<70	36
37	0.72	0.46	<30	<11	36	213	<17	<0.1	718	<45	267	<70	37
38	0.31	0.49	<30	<11	160	56	<17	<0.1	612	<45	158	<70	38
39	0.26	0.26	<30	<11	164	60	<17	<0.1	504	164	179	210	39
40	0.57	0.40	<30	<11	20	43	<17	<0.1	465	<45	175	<70	40
41	0.38	0.35	<30	80	260	104	<17	<0.1	547	138	129	<70	41
42	0.36	0.49	<30	16	127	66	<17	<0.1	556	<45	135	118	42
43	0.33	0.31	31	<11	86	50	<17	<0.1	567	<45	172	249	43
44	0.31	0.65	48	<11	<10	46	<17	<0.1	370	<45	137	<70	44
45	0.07	0.56	<30	<11	60	110	<17	<0.1	557	<45	179	108	45
46	0.84	0.43	42	20	87	75	26	<0.1	618	<45	472	90	46
47	0.38	0.27	<30	<11	13	483	22	0.16	481	<45	287	<70	47
48	0.55	0.49	68	<11	325	65	65	<0.1	532	53	103	<70	48
49	0.67	0.51	39	18	300	142	<17	<0.1	532	<45	<100	184	49
50	0.70	0.38	36	<11	21	53	<17	<0.1	540	<45	399	<70	50
51	0.50	0.57	35	12	16	132	28	<0.1	650	<45	365	<70	51
52	0.32	0.39	<30	12	35	90	<17	<0.1	483	<45	258	<70	52
53	1.00	0.59	<30	21	42	120	20	<0.1	866	160	318	247	53
54	0.30	0.28	<30	28	233	86	<17	<0.1	494	186	346	<70	54
55	0.44	0.45	33	<11	<10	37	<17	<0.1	455	141	236	<70	55
56	0.71	0.36	<30	12	68	56	<17	<0.1	465	<45	399	78	56
57	0.16	0.54	34	27	22	114	<17	<0.1	488	44	130	<70	57
58	0.68	0.50	68	31	378	141	88	<0.1	707	<45	169	<70	58
59	0.39	0.28	<30	<11	57	56	<17	0.12	667	242	221	98	59
60	0.32	0.30	<30	<11	111	116	<17	<0.1	502	<45	338	160	60
61	0.41	0.39	47	11	137	117	<17	<0.1	1000	380	241	<70	61
62	0.33	0.38	<30	<11	13	54	35	0.18	589	<45	237	80	62
63	0.41	0.28	<30	18	53	72	<17	<0.1	618	215	220	75	63
64	0.68	0.54	43	12	201	52	74	<0.1	538	49	107	273	64
65	1.05	0.79	56	<11	15	35	<17	<0.1	917	<45	535	75	65
66	0.93	0.50	34	20	50	54	26	<0.1	809	<45	174	<70	66
67	0.66	0.49	47	<11	364	82	<17	0.13	730	<45	176	208	67

Table 2 (continued)

68	0.92	0.44	38	<11	62	68	<17	<0.1	504	<45	315	196	68
69	0.71	0.52	42	<11	383	131	<17	<0.1	739	<45	197	251	69
70	0.43	0.32	<30	<11	13	67	<17	<0.1	358	<45	311	<70	70
71	0.35	0.48	<30	21	32	83	<17	0.12	560	<45	170	<70	71
72	0.29	0.40	56	<11	21	79	46	<0.1	456	<45	<100	132	72
73	0.39	0.32	<30	<11	26	82	20	<0.1	628	<45	216	111	73
74	0.49	0.35	<30	<11	77	124	21	0.20	707	175	123	141	74
75	0.76	0.39	33	<11	292	59	<17	0.11	505	113	217	<70	75
76	0.68	0.64	42	12	249	88	<17	0.12	606	<45	157	203	76
77	0.72	0.70	49	<11	14	37	<17	<0.1	789	<45	404	<70	77
78	0.45	0.50	41	12	13	58	<17	<0.1	668	<45	295	98	78
79	0.73	0.71	<30	15	21	52	<17	<0.1	804	<45	409	111	79
80	1.05	0.78	54	14	15	43	<17	<0.1	675	<45	550	80	80
81	0.75	0.63	37	<11	229	57	<17	<0.1	465	<45	178	<70	81
82	0.37	0.31	72	<11	77	157	<17	<0.1	1576	<45	<100	<70	82
83	0.39	0.34	<30	16	28	56	<17	<0.1	503	<45	261	<70	83
84	0.84	0.65	46	22	172	99	<17	<0.1	583	<45	159	<70	84
85	0.09	0.52	<30	<11	35	57	<17	<0.1	434	<45	110	<70	85
86	0.92	0.59	<30	31	55	65	<17	0.27	755	<45	<100	72	86
87	0.65	0.41	31	<11	16	38	<17	<0.1	507	<45	146	<70	87
88	1.03	0.76	73	15	202	94	22	<0.1	685	115	248	128	88
89	0.56	0.45	32	12	34	63	<17	<0.1	81	<45	455	<70	89
90	0.46	0.40	<30	<11	96	9	29	0.29	356	<45	145	<70	90
91	0.73	0.76	204	85	427	71	<17	<0.1	680	50	119	<70	91
92	0.36	0.55	<30	<11	<10	37	<17	0.38	663	<45	153	<70	92
93	0.65	0.54	53	17	231	117	22	<0.1	499	<45	114	186	93
94	1.39	1.01	78	27	243	93	90	<0.1	1202	<45	189	225	94
95	0.88	0.58	<30	<11	23	29	20	<0.1	596	<45	<100	117	95

Table 3 Concentrations are given in weight per cent for major and in µg/g for minor elements. In general, uncertainties are at the level of about 5% for higher concentrations and 10% for lower concentrations

No.		Na ₂ O wt%	MgO wt%	Al ₂ O ₃ wt%	SiO ₂ wt%	P ₂ O ₅ wt%	SO ₃ wt%	Cl wt%	K ₂ O wt%	CaO wt%	TiO ₂ µg/g	Cr ₂ O ₃ µg/g	MnO wt%
96	Blagaj	9.92	3.82	4.55	66.4	<1	0.61	0.37	1.90	11.0	648	<50	0.54
97	Blagaj	11.4	3.98	2.08	65.4	<1	0.49	0.71	2.45	11.2	896	<50	1.35
103	Blagaj	11.2	4.10	2.50	66.7	<1	0.26	0.53	1.83	10.7	774	<50	1.08
98	Bobovac	11.4	3.72	2.09	67.4	<1	1.08	0.53	1.95	10.8	754	<50	0.2
99	Bobovac	12.5	3.83	2.07	65.9	<1	0.83	0.76	2.43	10.4	545	<50	0.18
100	Bobovac	11.9	3.60	1.41	66.9	<1	0.63	0.68	2.15	11.2	790	<50	0.92
101	Lisičići	8.36	4.74	1.96	67.0	<1	0.48	0.49	2.16	13.4	784	<50	0.5
102	Visoki	11.3	3.85	2.39	68.1	<1	0.27	0.57	2.09	9.81	954	<50	0.7
104	Visoki	12.7	3.83	2.00	68.7	<1	0.25	0.63	1.84	8.88	437	<50	0.58
105	Visoki	11.8	3.65	2.55	68.9	<1	0.21	0.61	2.08	8.96	540	<50	0.6
106	Zgošća	12.8	3.97	2.29	65.6	<1	0.40	0.69	1.90	10.0	534	<50	0.9
107	Zgošća	10.9	4.30	1.70	64.0	2.5	0.81	0.64	2.51	11.3	766	<50	0.27
108	Zgošća	11.8	3.96	2.10	65.6	<1	0.34	0.61	2.23	11.9	612	<50	0.69
109	Zgošća	12.2	3.92	1.72	66.0	<1	0.35	0.65	2.24	10.5	602	<50	1.52
110	Kraljeva Sutjeska	12.0	2.98	0.81	70.8	<1	0.42	0.71	2.25	9.22	274	<50	0.44
111	Kraljeva Sutjeska	13.0	4.28	1.23	66.7	<1	1.15	0.63	1.78	10.1	474	<50	0.48
112	Kraljeva Sutjeska	12.8	3.14	0.80	69.0	<1	0.45	0.72	1.71	10.5	701	<50	0.41
113	Kraljeva Sutjeska	13.2	3.19	0.64	69.3	<1	0.56	0.71	1.61	9.79	855	<50	0.54
114	Kraljeva Sutjeska	12.7	3.53	0.74	68.2	<1	0.57	0.69	1.61	10.6	1625	<50	0.7
115	Kraljeva Sutjeska	11.7	3.57	0.93	68.1	<1	0.41	0.69	1.69	11.7	791	<50	0.55
116	Kraljeva Sutjeska	11.3	5.47	1.28	65.8	<1	0.43	0.65	1.88	12.1	590	<50	0.5
117	Kraljeva Sutjeska	12.1	3.76	1.33	67.9	<1	0.81	0.66	1.99	10.1	438	<50	0.66
118	Kraljeva Sutjeska	11.1	3.94	1.89	65.5	<1	1.90	0.40	2.14	11.3	648	<50	0.99
119	Kraljeva Sutjeska	13.2	3.28	0.70	69.0	<1	0.89	0.62	1.47	9.85	842	<50	0.53
120	Kraljeva Sutjeska	13.5	3.52	0.95	68.5	<1	0.46	0.75	1.77	9.74	331	<50	0.39
121	Kraljeva Sutjeska	13.1	3.18	0.65	69.6	<1	0.69	0.64	1.61	9.58	874	<50	0.5
122	Kraljeva Sutjeska	13.3	3.42	0.73	68.8	<1	0.41	0.71	1.55	10.2	849	<50	0.51
123	Kraljeva Sutjeska	12.3	3.45	0.94	67.8	<1	0.43	0.69	1.88	11.3	1081	<50	0.69
124	Kraljeva Sutjeska	13.2	3.02	1.16	68.0	<1	1.53	0.53	2.26	8.91	1225	<50	0.75
125	Kraljeva Sutjeska	12.0	3.02	1.18	67.7	<1	2.03	0.55	1.65	10.5	1090	<50	0.81
126	Kraljeva Sutjeska	12.0	3.43	1.40	69.0	<1	0.50	0.77	1.95	9.76	441	<50	0.66
127	Kraljeva Sutjeska	9.89	4.40	1.68	66.5	<1	0.42	0.61	2.27	12.6	1187	110	0.78
128	Kraljeva Sutjeska	9.88	4.13	1.69	66.7	<1	0.45	0.62	2.31	12.7	1236	110	0.78
129	Kraljeva Sutjeska	13.6	3.51	0.63	68.6	<1	0.61	0.58	2.16	9.64	928	<50	0.28

No.	Fe ₂ O ₃ wt%	CoO µg/g	CuO µg/g	ZnO µg/g	As ₂ O ₃ µg/g	Br µg/g	Rb ₂ O µg/g	SrO µg/g	ZrO ₂ µg/g	PbO µg/g
96	0.72	<50	182	34	<5	32	18	807	40	21
97	0.8	<50	395	56	<5	34	21	653	35	126
103	0.9	<50	297	55	<5	34	11	687	38	73
98	0.69	<50	86	402	<5	39	20	684	41	51

Table 3 (continued)

99	0.96	<50	82	172	<5	34	12	547	34	172
100	0.47	<50	458	51	<5	31	11	646	24	40
101	0.73	<50	164	62	<5	13	11	649	21	12
102	0.74	<50	379	61	<5	30	11	640	10	89
104	0.45	<50	65	37	<5	46	11	604	11	17
105	0.46	<10	62	35	<5	44	9	544	18	25
106	0.94	1520	1580	40	127	36	9	603	26	3
107	0.92	<50	95	499	<5	32	18	655	18	73
108	0.65	<50	146	33	<5	38	13	687	25	13
109	0.72	<50	99	125	<5	43	9	749	14	71
110	0.25	<50	45	214	<5	26	9	535	11	18
111	0.51	<50	42	45	<5	45	6	662	21	19
112	0.28	<50	53	40	<5	32	9	613	169	9
113	0.28	<50	71	39	<5	31	11	561	241	15
114	0.36	<50	42	113	<5	33	5	644	589	12
115	0.49	<50	102	62	<5	46	4	661	153	45
116	0.42	<50	65	56	62	30	7	1050	<5	34
117	0.55	<50	170	74	17	33	6	724	26	10
118	0.69	<50	79	51	22	35	20	752	17	47
119	0.28	<50	69	62	<5	38	10	556	264	17
120	0.3	<50	69	38	<5	61	7	651	9	51
121	0.27	<50	61	37	13	26	9	504	220	9
122	0.27	<50	61	59	16	33	4	514	226	<3
123	0.36	<50	46	79	8	30	16	636	293	7
124	0.35	<50	75	134	18	34	11	548	459	12
125	0.38	<50	50	246	12	36	8	605	300	<3
126	0.43	<50	54	66	14	41	8	635	22	9
127	0.56	<50	324	68	19	29	15	912	98	23
128	0.56	<50	330	64	21	28	14	884	81	21
129	0.24	<50	47	41	9	23	11	488	279	3