Correction to: Characterization of Poultry Litter Ash in View of Its Valorization

L. Luyckx¹ · G. H. J. de Leeuw² · J. Van Caneghem¹

Published online: 31 July 2019
© Springer Nature B.V. 2019

Correction to: Waste and Biomass Valorization
<https://doi.org/10.1007/s12649-019-00750-6>

Unfortunately, Table 1 was published incorrectly in the original publication of the article. The correct version of Table 1 is provided here.

Publisher's Note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

The original article can be found online at <https://doi.org/10.1007/s12649-019-00750-6>.

✉ L. Luyckx
lorien.luyckx@kuleuven.be

¹ Materials Technology TC, KU Leuven, Campus Group
T, Andreas Vesaliusstraat 13 - box 2600, Leuven 3000,
Belgium

² BMC Moerdijk BV, Industrial Park M349, Middenweg 36a,
4782 PM Moerdijk, The Netherlands

Table 1 Average concentration $\pm$ standard deviation of P, K, Ca, Mg, Na, S, Si, Al, Cd, Cr, Cu, Fe, Mn, Mo, Ni, Pb, Ti and Zn in the bed, SH, ECO, ESP, bag and mixed ash (% of DM and mg/kg DM); n = 3

	Bed ash	SH ash	ECO ash	ESP ash	Bag ash	Mixed ash
P (% of DM)	5.0 $\pm$ 0.03	10.6 $\pm$ 0.11	8.9 $\pm$ 0.10	6.4 $\pm$ 0.06	2.3 $\pm$ 0.32	6.0 $\pm$ 0.08
K (% of DM)	9.4 $\pm$ 0.07	11.1 $\pm$ 0.06	11.5 $\pm$ 0.07	15.5 $\pm$ 1.32	14.3 $\pm$ 1.55	12.5 $\pm$ 0.30
Ca (% of DM)	20.2 $\pm$ 0.10	19.3 $\pm$ 0.11	20.1 $\pm$ 0.22	12.4 $\pm$ 0.08	20.6 $\pm$ 1.60	18.2 $\pm$ 0.36
Mg (% of DM)	2.6 $\pm$ 0.03	6.2 $\pm$ 0.06	5.2 $\pm$ 0.04	3.5 $\pm$ 0.01	1.2 $\pm$ 0.15	3.0 $\pm$ 0.56
Na (% of DM)	2.7 $\pm$ 0.02	2.6 $\pm$ 0.02	3.4 $\pm$ 0.01	3.6 $\pm$ 0.02	1.6 $\pm$ 0.12	1.9 $\pm$ 0.02
S (% of DM)	3.1 $\pm$ 0.02	1.7 $\pm$ 0.05	1.8 $\pm$ 0.02	6.0 $\pm$ 0.05	4.8 $\pm$ 0.48	3.1 $\pm$ 0.03
Si (% of DM)	9.2 $\pm$ 0.39	4.0 $\pm$ 0.03	5.6 $\pm$ 0.05	2.8 $\pm$ 0.04	1.4 $\pm$ 0.12	6.8 $\pm$ 0.27
Al (mg/kg DM)	6642 $\pm$ 113	7799 $\pm$ 84	9306 $\pm$ 69	5671 $\pm$ 42	2494 $\pm$ 69	5021 $\pm$ 187
Cd (mg/kg DM)	< 2	3.5 $\pm$ 0.2	2.7 $\pm$ 0.2	4.9 $\pm$ 0.3	3.1 $\pm$ 0.07	2.1 $\pm$ 0.02
Cr (mg/kg DM)	15.9 $\pm$ 0.5	29.7 $\pm$ 1.6	29.2 $\pm$ 0.8	31.2 $\pm$ 0.8	16.1 $\pm$ 0.6	18.7 $\pm$ 0.2
Cu (mg/kg DM)	391 $\pm$ 6	741 $\pm$ 49	568 $\pm$ 31	698 $\pm$ 36	353 $\pm$ 8	435 $\pm$ 6
Fe (mg/kg DM)	4423 $\pm$ 204	6787 $\pm$ 85	8168 $\pm$ 326	4444 $\pm$ 53	2216 $\pm$ 32	4284 $\pm$ 205
Mn (mg/kg DM)	1595 $\pm$ 20	3594 $\pm$ 15	3076 $\pm$ 47	2090 $\pm$ 17	761 $\pm$ 16	1939 $\pm$ 16
Mo (mg/kg DM)	15.0 $\pm$ 0.5	24.1 $\pm$ 1.1	19.9 $\pm$ 1.0	33.5 $\pm$ 2.4	22.8 $\pm$ 0.7	18.0 $\pm$ 0.1
Ni (mg/kg DM)	23.1 $\pm$ 0.6	46.4 $\pm$ 2.5	36.6 $\pm$ 1.0	33.7 $\pm$ 3.0	10.9 $\pm$ 0.3	25.2 $\pm$ 0.5
Pb (mg/kg DM)	< 2	8.0 $\pm$ 0.9	5.2 $\pm$ 0.1	13.6 $\pm$ 0.7	10.1 $\pm$ 0.5	4.5 $\pm$ 1.0
Ti (mg/kg DM)	226 $\pm$ 6	464 $\pm$ 27	514 $\pm$ 24	342 $\pm$ 22	121 $\pm$ 3	241 $\pm$ 1
Zn (mg/kg DM)	985 $\pm$ 32	2226 $\pm$ 99	1755 $\pm$ 68	2591 $\pm$ 205	1150 $\pm$ 19	1497 $\pm$ 39