Synthesis of nearly spherical AlN particles by an *in-situ* nitriding combustion route

Zhilei WEI^a, Kang LI^a, Bangzhi GE^a, Chaowei GUO^a,
Hongyan XIA^a, Yajie GUO^b, Zhongqi SHI^{a,*}

^aState Key Laboratory for Mechanical Behavior of Materials, Xi'an Jiaotong University, Xi'an 710049, China

^bEngineering Research Center of Transportation Materials of Ministry of Education, School of Materials Science and Engineering, Chang'an University, Xi'an 710064, China

Received: August 24, 2020; Revised: October 17, 2020; Accepted: November 12, 2020

© The Author(s) 2020.

Abstract: Spherical AlN powders with micrometer size have attracted great attention owing to their good fluidity and dispersity. However, the industrial preparation methods usually require high temperature and long soaking time, which lead to the high cost and limit the wide application of the products. Herein, nearly spherical AlN particles with the average size of 2.5 μm were successfully synthesized via an *in-situ* combustion synthesis method. The effect of N_2 pressure, NH_4Cl content, and Al particle size on the combustion reaction procedure, phase composition, and microstructure of the products was systematically investigated. The results showed that the decreased N_2 pressure, increased NH_4Cl content, and Al particle size led to the decreasing of combustion temperature and speed, which further affected the morphology of the products. As a result, low N_2 pressure (0.2 MPa), a small amount of NH_4Cl (0.5 wt%), and fine Al particles ($\sim 2.5 \mu\text{m}$) contributed to a moderate combustion temperature and facilitated the formation of nearly spherical AlN particles. In addition, based on the gas-releasing assisted quenching experiments and thermo-kinetic analysis, a two-step growth mechanism for the nearly spherical AlN particles was rationally proposed. The present method shows the advantages of low cost and high efficiency for preparing nearly spherical AlN particles, which can be used as raw materials for electronic substrates and fillers for packaging materials.

Keywords: combustion synthesis; AlN; microstructure; growth mechanism

1 Introduction

AlN, as an important III–V semiconductor material, has attracted great attention because of its high thermal conductivity, high electrical resistance, wide band gap, low dielectric constant, and low thermal expansion

coefficient [1,2]. Based on these excellent properties, it has good application prospects in terms of electronic substrates, packaging materials, heat sinks, and field-emission devices [3–6]. Recently, spherical AlN particles with micrometer size have shown significant promise for applications in raw materials for electronic substrates and fillers for packaging materials owing to their good fluidity and dispersity [7,8]. Hence, many efforts have been devoted to synthesis spherical AlN particles, including direct nitridation [9], carbothermal

* Corresponding author.

E-mail: zhongqishi@mail.xjtu.edu.cn

reduction-nitridation [10] as well as other two-step chemical routes [11]. However, these methods usually require high temperature, long soaking time or expensive raw materials, which will increase the cost and limit the industrial applications. Therefore, it is imperative to further exploit new synthetic routes for preparing spherical AlN particles.

Combustion synthesis (CS, also known as self-propagating high-temperature synthesis (SHS)), is considered as a promising synthesis route to fabricate AlN powders because of its low processing cost, high energy efficiency, and short reaction period [12–15]. However, because of the high thermal-gradient, high combustion temperature, and fast reaction speed, the morphology of the AlN powders is difficult to control and various grain morphologies, such as whiskers, faceted particles, and agglomerated particles are often observed [16–19], which impedes the CS process for wide application.

In previous studies, we have reported the synthesis of AlN nanowhiskers [20,21], porous-shell hollow spheres [22], and rod-like nanoparticles [23] with uniform morphologies by the CS method. The morphology of the products can be controlled through adjusting the CS parameters (such as diluent content and N_2 pressure) and introducing various additives (such as NH_4Cl , polytetrafluoroethylene (PTFE), and oxides). As a consequence, a “micro-reactor” can be *in-situ* formed at the original Al particle during the CS process, which provided an almost consistent environment for the growth of AlN crystal with uniform morphology in the products [24]. These results give us an inspiration for the synthesis of spherical AlN particles by CS route.

In this work, we developed an efficient CS route to directly prepare nearly spherical AlN particles by

in-situ nitridation of spherical Al powders. The effect of combustion parameters including N_2 pressure, NH_4Cl content, and Al particle size on the combustion reaction procedure, phase composition, and microstructure of the products was systematically investigated. Furthermore, the underlying growth mechanism for the nearly spherical AlN particles in the CS process was proposed by both experimental and thermo-kinetic analyses.

2 Materials and method

2.1 Materials

Four types of spherical Al powders with different particle sizes ($d_{50} = 2.5, 5, 10$, and $25\ \mu m$; purity > 99.9%; Henan Yuanyang Powder Technology Co., Ltd., China) were used as reactant materials. The morphologies of the spherical Al powders and their particle size distributions are shown Fig. 1. AlN powders (particle size: $\sim 2.5\ \mu m$; purity > 99.5%; self-prepared by the same procedure in this work) were adopted as the diluent, and NH_4Cl (purity > 99.5%, Sinopharm Chemical Reagent Co., Ltd., China) was chosen as the reaction controlling agent.

2.2 Sample preparation

In the CS procedure, Al and AlN powders were mixed with a molar ratio of 4:6, which was chosen to achieve pure AlN product [25]. Additionally, different amount of NH_4Cl (0, 0.5, 1 wt%) was also added. The raw powders were lightly mixed by a mortar for 20 min, and sieved through 150-mesh to disperse any large agglomerates. Then, 50 g of the powder mixture was

Fig. 1 Morphologies of the spherical Al powders and their particle size distributions: (a, e) $d_{50} = 2.5\ \mu m$; (b, f) $d_{50} = 5\ \mu m$; (c, g) $d_{50} = 10\ \mu m$; and (d, h) $d_{50} = 25\ \mu m$.

poured into a porous graphite crucible (Φ 50 mm $\times$ H 90 mm) which was lined with a layer of carbon felt (thickness: 2 mm) to improve the thermal insulation performance. The powder mixture with an apparent density of $0.6 \text{ g}\cdot\text{cm}^{-3}$ was ignited from the bottom of the crucible by a bar of graphite paper (150 mm $\times$ 5 mm $\times$ 0.6 mm) which was loaded by 40 A current at both sides, and high purity N_2 (99.999%) with different gas pressures (0.2, 0.5, 0.8, and 1.0 MPa) was used as the reaction medium. The samples prepared by different combustion parameters can be briefly denoted as P1.0N0R2.5, P0.8N0R2.5, P0.5N0R2.5, P0.2N0R2.5, P0.2N0.5R2.5, P0.2N1.0R2.5, P0.2N0.5R5, P0.2N0.5R10, and P0.2N0.5R25, which are illustrated detailly in Table 1. The combustion temperature and speed were measured by W–Re thermocouples. After the combustion reactions, all the as-fabricated AlN products were loose like dry cakes, which were dry milled for 30 min by a mortar and sieved through 150-mesh to obtain the dispersed powder products.

A gas-releasing assisted quenching method [26,27] was employed to disclose the growth mechanism for the nearly spherical AlN particles. The difference between this method and the above CS experiments lies in that N_2 was quickly released from the chamber when the combustion wave was passing through the sample. Because the residual N_2 was not enough to sustain the combustion reaction, the afterburning was inhibited and the combustion was quenched. By this means, the detailed information of the combustion reaction can be obtained.

2.3 Characterization

The phase composition of the as-synthesized products was examined by X-ray diffraction (XRD; X'Pert Pro,

Holland) with Cu $K\alpha$ radiation. Granulometric distribution of raw Al powders and the as-synthesized AlN powders was characterized using a laser diffraction analyser (Mastersizer 2000, Malvern, UK), and the morphology of the powders was observed by a field emission scanning electron microscope (FE-SEM; SU6600, Japan) equipped with energy dispersive spectrometer (EDS). Samples for SEM observations and EDS analysis were coated with thin films of sputtered gold to increase the electrical conductivity. The contents of N and O of the products were characterized by nitrogen oxygen analyzer (TCH600, Leco, USA) and the content of Al was analyzed by chemical titration. The focused ion beam (FIB) micromachining technique was used to slit the representative particles in different zones of the quenched samples and the cross-section morphology of the particles was observed by FE-SEM.

3 Results and discussion

3.1 Effects of combustion parameters on the reaction procedure

The combustion temperature–time curves of the samples prepared by different combustion parameters are shown in Fig. 2. Once the combustion reaction is triggered, the temperature increases rapidly close to its apex in several seconds and then slowly decreases after the combustion wave passes by. With the decrease of N_2 pressure from 1.0 to 0.2 MPa, the maximal combustion temperature decreases from 2536 (P1.0N0R2.5) to 2196 K (P0.2N0R2.5) and the corresponding combustion speed reduces from 0.31 to $0.19 \text{ mm}\cdot\text{s}^{-1}$. This indicates that higher N_2 pressure makes the combustion reaction more drastic since there are more active molecules per unit volume and the collision probability between Al and N_2 molecules increases.

Fig. 2 Combustion temperature–time curves of the samples synthesized by different combustion parameters.

Table 1 Experimental parameters for the CS of AlN powders

Sample	N_2 pressure (MPa)	NH_4Cl content (wt%)	Al particle size (μm)	Maximal combustion temperature (K)	Combustion speed ($\text{mm}\cdot\text{s}^{-1}$)
P1.0N0R2.5	1.0	0	2.5	2536	0.31
P0.8N0R2.5	0.8	0	2.5	2344	0.24
P0.5N0R2.5	0.5	0	2.5	2255	0.20
P0.2N0R2.5	0.2	0	2.5	2196	0.19
P0.2N0.5R2.5	0.2	0.5	2.5	2150	0.16
P0.2N1.0R2.5	0.2	1.0	2.5	1967	0.14
P0.2N0.5R5	0.2	0.5	5	1997	0.12
P0.2N0.5R10	0.2	0.5	10	1893	0.10
P0.2N0.5R25	0.2	0.5	25	1810	0.09

Besides, the combustion temperature and speed can be influenced by the amount of NH_4Cl additive because it absorbs sufficient heat from the reaction system through sublimation and dissociation [28]. Hence, as the content of NH_4Cl additive increases, the combustion temperature and speed sharply decrease (Fig. 2 and Table 1). Compared with the sample without NH_4Cl additive (P0.2N0R2.5), the maximal combustion temperature and speed of sample P0.2N1.0R2.5 decrease by 229 K and $0.05 \text{ mm}\cdot\text{s}^{-1}$, respectively.

Al particle size also affects the combustion temperature and speed. On condition that other combustion parameters (N_2 pressure, NH_4Cl content) are the same, as the Al particle size increases from ~ 2.5 (P0.2N0.5R2.5) to $\sim 25 \mu\text{m}$ (P0.2N0.5R25), the combustion temperature and speed decrease from 2150 to 1810 K and from 0.16 to $0.09 \text{ mm}\cdot\text{s}^{-1}$, respectively. This is mainly caused by the reduced surface area of Al particles, which further leads to the decreased contact area between Al and N_2 molecules. Therefore, the reaction procedure can be well controlled by adjusting the combustion parameters.

3.2 Effects of combustion parameters on the phase composition

Figure 3 shows the XRD patterns of the samples prepared by different combustion parameters, where all the diffraction peaks can be indexed to the AlN crystal (JCPDS No. 25-1133) with hexagonal wurtzite structure. The sharp diffraction peaks indicate the good crystallinity of the products. Besides, no characteristic peaks of impurities are detected in the patterns, which demonstrates that the AlN products with high purity can be obtained by using different Al powders as the reactant under different N_2 pressures and the addition of NH_4Cl does not affect the phase composition of the products [29]. The fabricated AlN products with high purity can be attributed to the strong exothermic reaction between Al and N_2 (Eq. (1)), which ensures the sufficient nitridation of Al powders.

3.3 Effects of combustion parameters on the morphology

Representative SEM images of the samples synthesized by different combustion parameters are displayed in

Fig. 3 XRD patterns of the synthesized AlN powders: (a) P0.2N0.5R25; (b) P0.2N0.5R10; (c) P0.2N0.5R5; (d) P0.2N1.0R2.5; (e) P0.2N0.5R2.5; (f) P0.2N0R2.5; (g) P0.5N0R2.5; (h) P0.8N0R2.5; and (i) P1.0N0R2.5.

Fig. 4. Apparently, when the N_2 pressure $\geq 0.8 \text{ MPa}$, large agglomerates are observed in the products of P1.0N0R2.5 and P0.8N0R2.5 (Figs. 4(a) and 4(b)). The AlN particles are all bonded by the sintering necks, which can be mainly ascribed to the high combustion temperature (Fig. 2). With the decrease of N_2 pressure, the combustion temperature decreases and the sintering of AlN particles weakens. As a result, the morphology of the products (P0.5N0R2.5 and P0.2N0R2.5) becomes more uniform and the percentage of nearly spherical particles with the grain size of $\sim 2.5 \mu\text{m}$ increases gradually (Figs. 4(c) and 4(d)). However, most of the particles are still bonded together by the sintering necks because the maximal combustion temperature is still higher than 2173 K (Fig. 2).

In order to improve the dispersity of nearly spherical AlN particles, NH_4Cl was added to the reaction system. It is observed that a small amount of NH_4Cl (0.5 wt%) facilitates the formation of AlN powders with uniform morphology, as shown in the SEM image of sample P0.2N0.5R2.5 (Fig. 4(e)). However, some fibrous particles are formed in the product P0.2N1.0R2.5 (Fig. 4(f)) when the NH_4Cl content further increases to 1 wt%. This can be ascribed to the catalysis of NH_4Cl , which promotes the growth of one dimensional AlN structures by vapor–solid (VS) mechanism [30].

Fig. 4 SEM images of the samples synthesized by different combustion parameters: (a) P1.0N0R2.5; (b) P0.8N0R2.5; (c) P0.5N0R2.5; (d) P0.2N0R2.5; (e) P0.2N0.5R2.5; (f) P0.2N1.0R2.5; (g) P0.2N0.5R5; (h) P0.2N0.5R10; and (i) P0.2N0.5R25.

The effect of Al particle size on the morphology of the products was also investigated. With the increase of Al particle size, hemispheric particles with core-shell structure appear in P0.20.5R5 and P0.2N0.5R10 samples, where the shells consist of small stacked granules and the cores are filled with large granules (Figs. 4(g) and 4(h)). This morphology can be ascribed to the high N_2 permeability and high supersaturation of the Al vapor [31]. When the Al particle size further increases to $\sim 25 \mu m$, the morphology of the product becomes more complicated, including core-shell structure, granules with different particle sizes and whiskers, as shown in Fig. 4(i). The formation of AlN whiskers can be attributed to the lower saturated pressure of Al vapor than the critical vapor pressure of uniform nucleation [32,33]. Above all, nearly spherical AlN particles can be synthesized only by adopting Al powder with small particle size, proper N_2 pressure, and NH_4Cl content to maintain moderate combustion temperature and speed.

3.4 Characterization of the nearly spherical AlN particles

Figure 5(a) shows the low-magnification SEM image of sample P0.2N0.5R2.5, where most of the AlN particles exhibit nearly spherical morphologies with good dispersity. The size distribution of these particles is shown in Fig. 5(b) and the d_{50} is about $2.5 \mu m$, which is

similar to that of the original Al particles, as shown in Figs. 1(a) and 1(e). Because of the similar shape and size, one can notice that the nearly spherical AlN particles could be evolved from the original Al particles. The high-magnification SEM image of a single particle is shown in Fig. 5(c). It can be clearly observed that the particle is endowed with nearly spherical shape. In addition, some steps appear on the surface of the AlN particle, illustrating that the VS mechanism plays an important role in the growth of AlN grains [34].

However, because of the lack of liquid phase and short soaking time at high temperatures in the CS process, it is difficult to form a perfect spherical particle. Figure 5(d) shows the chemical composition of the nearly spherical AlN particle confirmed by the EDS analysis. As observed, only peaks of Al, N, and O are detected. The atomic ratio of Al and N is nearly to the stoichiometric proportion of 1:1, indicating the sufficient nitridation of Al during the CS process. In order to accurately confirm the elementary composition of sample P0.2N0.5R2.5, the contents of N and O of the products were characterized by nitrogen oxygen analyzer and the content of Al was analyzed by chemical titration. The results show that the contents of Al, N, and O are 64.64, 31.68, and 1.79 wt%, respectively. The rests are impurity elements. Then the calculated atomic ratio of Al and N is approximately 51:49, similar to the EDS results (Fig. 5(d)).

Fig. 5 (a) Low-magnification SEM image, (b) particle size distribution, (c) high-magnification SEM image, and (d) EDS analysis of the nearly spherical AlN particles.

3.5 Growth mechanism for the nearly spherical particles

In order to investigate the phase transformation and morphology evolution of the nearly spherical AlN particles, a gas-releasing assisted quenching method was performed for the sample P0.2N0.5R2.5. Figure 6 shows the XRD patterns of the quenched sample in different regions. It can be seen that both Al and AlN peaks are detected in the preheated region (Fig. 6(a)), initial-combustion region (Fig. 6(b)), middle-combustion region (Fig. 6(c)), and post-combustion region (Fig. 6(d)). The peak intensity of Al in these regions gradually decreases, while that of AlN gradually increases. This indicates that Al is gradually nitrided to AlN as the combustion wave passes. Therefore, only a small amount of Al is detected in the post-combustion region and complete AlN product is obtained in the complete-combustion region (Fig. 6(e)).

To further study the growth process from Al particles to nearly spherical AlN particles, SEM, EDS, and FIB micromachining were carried out for the quenched sample in different regions. Figure 7(a) shows the SEM image of a single particle in the preheated region. The particle has smooth surface with ball-like morphology, which is similar to that of the raw Al particle (Fig. 1(a)). XRD (Fig. 6(a)) and EDS results also indicate that this is an un-nitrided Al particle. In the initial-combustion region, the surface of the Al particle becomes rough since numerous

Fig. 6 XRD patterns of the quenched sample P0.2N0.5R2.5 in different reaction regions: (a) preheated region, (b) initial-combustion region, (c) middle-combustion region, (d) post-combustion region, and (e) complete-combustion region.

island-like granules appear, as shown in Fig. 7(b). After slitting by FIB technique, the cross-sectional SEM image of the particle is obtained. EDS line-scan analysis of the major element distribution through the cross section of the particle reveals that the surface area mainly contains Al, N, and O, whereas the core area is dominated by Al signal. Combining with the XRD result (Fig. 6(b)), the core and island-like granules on the surface can be identified as Al and AlN, respectively.

Fig. 7 (a) SEM image and EDS analysis of the particle in the preheated region; (b) SEM image, cross-sectional SEM image, and EDS line-scan results of the particle in the initial-combustion region; (c–e) SEM images, cross-sectional SEM images of the particles, and the corresponding EDS mapping results of Al and N in the middle-combustion region, post-combustion region, and complete-combustion region, respectively.

In the middle-combustion region, the AlN granules on the surface of Al particle further grow and numerous gaps appear among the granules (Fig. 7(c)). According to the XRD pattern (Fig. 6(c)), cross-sectional morphology, and EDS mapping results (Fig. 7(c)), the nitrided layer is thicker than that of the initial-combustion region, while the core area is mainly composed of Al. For the post-combustion region, since the combustion wave has just passed, a nearly complete nitrided hollow AlN particle with many granules and gaps on its crust is formed (Fig. 7(d)). This can be confirmed by the XRD pattern in Fig. 6(d), where almost no diffraction peaks of Al can be observed. Besides, because of the high combustion temperature and speed, a small amount of Al vapor rushes out through the gaps among the AlN granules, which is then nitrided outside and hence the hollow sphere is formed [35]. Finally, the nearly spherical AlN particle is obtained in the complete-combustion region (Fig. 7(e)) and there are almost no residual pores or gaps in the particle. This could be mainly attributed to the *in-situ* sintering of AlN granules in the afterburning process because the maximal combustion temperature is higher than 2073 K.

According to the above analysis and discussion, a two-step growth mechanism, i.e., (1) nitridation of Al

particle from the surface into the interior and (2) *in-situ* sintering of AlN granules, for the CS of nearly spherical AlN particles, is reasonably proposed, as shown in Fig. 8. Firstly, the Al particle melts and reacts with N_2 gas at the surface of the particle to form numerous island-like AlN granules. Then, the N_2 gas diffuses through the surface gaps into the molten Al core and the nitridation process takes place from the particle's surface into the interior, which results in the thickening of nitrided layer. Subsequently, as the combustion wave propagates through the particle, the combustion temperature and speed rapidly rise, and a small amount of Al vapor rushes out from the gaps of the particle. Thus, the hollow particle is formed in the post-combustion region. When the combustion temperature further rises, the *in-situ* sintering of AlN granules occurs [36] and the nearly spherical AlN particle is finally obtained.

Therefore, the maximal combustion temperature is an important factor for the formation of nearly spherical AlN particles. When the combustion temperature is high enough, the sintering effect is intensive which benefits the densification of the AlN particle to form nearly spherical AlN particles. While at relatively low combustion temperature, the *in-situ* sintering of AlN

Fig. 8 Schematic of the growth mechanism for nearly spherical AlN particles.

granules is restrained and hollow spheres appear, as shown in the P0.2N0.5R5, P0.2N0.5R10, and P0.2N0.5R25 samples (Figs. 4(g)–4(i)).

3.6 Thermo-kinetic analysis

In order to confirm the above mechanism for the growth of nearly spherical AlN particles during the CS process, the thermo-kinetic analysis was carried out. Herein, it is assumed that Al vapor is nitrided to form AlN at a distance of

$$L = \beta r \quad (2)$$

where r is the radius of an Al particle ($1.25 \mu\text{m}$) and β is a constant ($\beta \leq 1$). When the supply of N_2 is sufficient and the system is in equilibrium, the evaporation rate of Al particle is equal to the diffusion rate of N_2 gas. The evaporation flux (J) of Al vapor can be calculated by the following equation [37,38]:

$$J = \frac{P_1 / \sqrt{2\pi M_1 RT}}{1 + 2r^3 / [(L^2 D) \times \sqrt{RT / (2\pi M_1)}]} \quad (3)$$

where M_1 is the molar weight of Al, R is the gas constant, T is the combustion temperature, D is the diffusion coefficient of the Al vapor in nitrogen, and P_1 is the equilibrium vapor pressure of Al vapor which rapidly increases with the combustion temperature ranging from 933 to 2793 K and their relationship is as follows [39]:

$$\lg P_1 = -16380/T - \lg T + 11.44 \quad (4)$$

In addition, D is determined by Eq. (5), in which C can be calculated from Eq. (6) [40]:

$$D = \frac{8.37 \times 10^{-3} T^{5/2}}{P_2 (V_1^{1/3} + V_2^{1/3})^2 (T + C)} \sqrt{\frac{1}{M_1} + \frac{1}{M_2}} \quad (5)$$

$$C = (1.504 - 3.43 \times 10^{-2} V_1 / V_2) \sqrt{T_1 T_2} \quad (6)$$

where P_2 is the pressure of N_2 in the system, M_2 is the molar weight of N_2 , V_1 and V_2 are the molar volumes

of Al and N_2 at their boiling points, and T_1 and T_2 are the boiling points of Al and N_2 , respectively. Besides, the time required for a spherical Al particle to completely vaporize and react with N_2 can be calculated from Eq. (7) [31]:

$$t = \frac{r \rho_{\text{Al}}}{J} \quad (7)$$

For the condition of preparing nearly spherical AlN particles ($P_2 = 0.2 \text{ MPa}$, $T = 2150 \text{ K}$), the calculated $C = 685 \text{ K}$, $D = 2.68 \times 10^{-5} \text{ m}^2 \cdot \text{s}^{-1}$, and $J \leq 0.048 \text{ kg} \cdot \text{m}^{-2} \cdot \text{s}^{-1}$. According to Eq. (7), the time required for a spherical Al particle to be completely nitrided should be equal to or more than 0.070 s . The experimental results for sample P0.2N0.5R2.5 show that the time required for the combustion wave to travel across an Al particle is 0.016 s , which is in the same order of magnitude with the calculated result.

During the combustion reaction process, although the combustion wave has passed, the nitridation of one particle has not yet completed because of the post-combustion period. Thus, the time for an Al particle to be completely nitrided is obviously longer than 0.016 s . Moreover, the equilibrium pressure of N_2 in the combustion system, which is inversely proportional to D (Eq. (5)), is actually lower than the gas pressure in the chamber. This phenomenon will make the calculated result (0.070 s) on the high side. Therefore, the thermo-kinetic results are possible to coincide with the experimental results.

However, when the Al particle size increases to ~ 5 , ~ 10 , and $\sim 25 \mu\text{m}$, the Al particles can be *in-situ* nitride completely, but the combustion temperatures are only 1997, 1893, and 1810 K, respectively. Such low temperature is insufficient for the densification of AlN granules. Therefore, core-shell morphologies instead of solid particles with smooth surface are obtained in the products, as shown in Figs. 4(g)–4(i).

4 Conclusions

In summary, nearly spherical AlN particles with the average size of 2.5 μm were successfully synthesized by an *in-situ* nitriding combustion synthesis method using spherical Al powders as reactant. The combustion reaction procedure, which affected the morphologies of the products, can be controlled by adjusting N_2 pressure, NH_4Cl content, and Al particle size. As a result, high purity of AlN powders with nearly spherical morphology can be obtained by using low N_2 gas pressure (0.2 MPa), a small amount of NH_4Cl (0.5 wt%), and small Al particles (2.5 μm). Moreover, based on the gas-releasing assisted quenching experiments and thermokinetic calculations, a two-step growth mechanism: (1) nitridation of Al particle from the surface into the interior and (2) *in-situ* sintering of intermediate AlN granules to form nearly spherical particle was rationally proposed. The present process for synthesis of nearly spherical AlN particles is simple, productive, energy-saving, and can be applied to produce raw materials for electronic substrates and fillers for packaging materials.

Acknowledgements

This work was supported by the National Natural Science Foundation of China (Nos. 51872222 and 51002115), the Shaanxi Innovation Capacity Support Program (2018TD-031), and the State Key Laboratory for Mechanical Behavior of Materials (20202208).

References

- [1] Mussler BH, Venigalla S, Johnson WC, *et al.* Advanced materials and powders. *Am Ceram Soc Bull* 2000, **79**: 45–56.
- [2] Sheppard LM. Aluminum nitride: A versatile but challenging material. *Am Ceram Soc Bull* 1990, **69**: 1801–1812.
- [3] Yin S, Tseng KJ, Zhao JY. Design of AlN-based micro-channel heat sink in direct bond copper for power electronics packaging. *Appl Therm Eng* 2013, **52**: 120–129.
- [4] Rutkowski PJ, Kata D. Thermal properties of AlN polycrystals obtained by pulse plasma sintering method. *J Adv Ceram* 2013, **2**: 180–184.
- [5] Tondare VN, Balasubramanian C, Shende SV, *et al.* Field emission from open ended aluminum nitride nanotubes. *Appl Phys Lett* 2002, **80**: 4813–4815.
- [6] Lee ES, Lee SM, Shanefield DJ, *et al.* Enhanced thermal conductivity of polymer matrix composite via high solids loading of aluminum nitride in epoxy resin. *J Am Ceram Soc* 2008, **91**: 1169–1174.
- [7] Shang QS, Wang ZJ, Li J, *et al.* Gel-tape-casting of aluminum nitride ceramics. *J Adv Ceram* 2017, **6**: 67–72.
- [8] Suehiro T, Tatami J, Meguro T, *et al.* Morphology-retaining synthesis of AlN particles by gas reduction–nitridation. *Mater Lett* 2002, **57**: 910–913.
- [9] Ohashi M, Kawakami S, Yokogawa Y, *et al.* Spherical aluminum nitride fillers for heat-conducting plastic packages. *J Am Ceram Soc* 2005, **88**: 2615–2618.
- [10] Wang Q, Cui W, Ge YY, *et al.* Preparation of spherical AlN granules directly by carbothermal reduction–nitridation method. *J Am Ceram Soc* 2015, **98**: 392–397.
- [11] Wan J, Qiao X, Wu LA, *et al.* Facile synthesis of monodisperse aluminum nitride microspheres. *J Sol-Gel Sci Technol* 2015, **76**: 658–665.
- [12] Merzhanov AG, Borovinskaya IP. A new class of combustion processes. *Combust Sci Technol* 1975, **10**: 195–201.
- [13] Gromov AA, Chukhlomina LN. *Nitride Ceramics-Combustion Synthesis, Properties, and Applications*. Weinheim (Germany): Wiley-VCH Verlag GmbH & Co. KGaA, 2014.
- [14] Zakorzhevskii VV, Borovinskaya IP, Sachkova NV. Combustion synthesis of aluminum nitride. *Inorg Mater* 2002, **38**: 1131–1140.
- [15] Zhang KB, Yin D, He ZS, *et al.* Combustion synthesis of Hf-doped zirconolite-rich composite waste forms and the aqueous durability. *J Adv Ceram* 2019, **8**: 448–455.
- [16] Fu R, Chen K, Agathopoulos S, *et al.* Factors which affect the morphology of AlN particles made by self-propagating high-temperature synthesis (SHS). *J Cryst Growth* 2006, **296**: 97–103.
- [17] Jiang GJ, Zhuang HR, Zhang J, *et al.* Morphologies and growth mechanisms of aluminum nitride whiskers by SHS method–Part I. *J Mater Sci* 2000, **35**: 57–62.
- [18] Jiang GJ, Zhuang HR, Zhang J, *et al.* Morphologies and growth mechanisms of aluminum nitride whiskers by SHS method–Part II. *J Mater Sci* 2000, **35**: 63–69.
- [19] Moya JS, Iglesias JE, Limpo J, *et al.* Single crystal AlN fibers obtained by self-propagating high-temperature synthesis (SHS). *Acta Mater* 1997, **45**: 3089–3094.
- [20] Shi ZQ, Radwan M, Kirihaara S, *et al.* Morphology-controlled synthesis of quasi-aligned AlN nanowhiskers by combustion method: Effect of NH_4Cl additive. *Ceram Int* 2009, **35**: 2727–2733.
- [21] Shi ZQ, Zhao CJ, Wang HL, *et al.* Combustion synthesis of AlN nanowhiskers with different metallic catalysts. *Mater Lett* 2014, **128**: 156–159.
- [22] Shi ZQ, Yang WL, Kang YF, *et al.* Synthesis of AlN porous-shell hollow spheres by a combustion route. *Ceram Int* 2013, **39**: 4663–4667.
- [23] Shi ZQ, Radwan M, Kirihaara S, *et al.* Combustion synthesis of rod-like AlN nanoparticles. *J Ceram Soc Japan* 2008, **116**: 975–979.
- [24] Shi ZQ, Miyamoto Y, Wang HL. Combustion synthesis of aluminum nitride (AlN) powders with controlled grain morphologies. In *Nitride Ceramics: Combustion Synthesis, Properties, and Applications*. Alexander A, Gromov, Liudmila

- N, Chukhlomina, Eds. Weinheim (Germany): Wiley-VCH Verlag GmbH & Co. KGaA, **2014**: 75–96.
- [25] Sakurai T, Yamada O, Miyamoto Y. Combustion synthesis of fine AlN powder and its reaction control. *Mater Sci Eng: A* 2006, **415**: 40–44.
- [26] Shi ZQ, Radwan M, Kirihaara S, *et al.* Formation and evolution of quasi-aligned AlN nanowhiskers by combustion synthesis. *J Alloys Compd* 2009, **476**: 360–365.
- [27] Wang HB, Han JC, Li ZQ, *et al.* Effect of additives on self-propagating high-temperature synthesis of AlN. *J Eur Ceram Soc* 2001, **21**: 2193–2198.
- [28] Rosenband V, Gany A. Activated self-propagating high-temperature synthesis of aluminum and titanium nitrides. *Exp Therm Fluid Sci* 2007, **31**: 461–467.
- [29] Radwan M, Bahgat M, El-Geassy AA. Formation of aluminium nitride whiskers by direct nitridation. *J Eur Ceram Soc* 2006, **26**: 2485–2488.
- [30] Radwan M, Miyamoto Y. Growth of quasi-aligned AlN nanofibers by nitriding combustion synthesis. *J Am Ceram Soc* 2007, **90**: 2347–2351.
- [31] Chen KX, Ge CC, Li JT, *et al.* Microstructure and thermokinetics analysis of combustion synthesized AlN. *J Mater Res* 1999, **14**: 1944–1948.
- [32] Evans CC. *Whiskers*. London (UK): Mills & Boon, 1972.
- [33] Harris B. *Whisker technology*. *Nat Phy Sci* 1971, **47**: 232.
- [34] Bradshaw SM, Spicer JL. Combustion synthesis of aluminum nitride particles and whiskers. *J Am Ceram Soc* 1999, **82**: 2293–2300.
- [35] Lee J, Lee I, Kim D, *et al.* Effect of starting powder morphology on AlN prepared by combustion reaction. *J Mater Res* 2005, **20**: 659–665.
- [36] Russias J, Cardinal S, Esnouf C, *et al.* Hot pressed titanium nitride obtained from SHS starting powders: Influence of a pre-sintering heat-treatment of the starting powders on the densification process. *J Eur Ceram Soc* 2007, **27**: 327–335.
- [37] Mukas'yan AS, Stepanov BV, Gal'chenko YA, *et al.* Mechanism of structure formation of silicon nitride with combustion of silicon in nitrogen. *Combust Explos Shock Waves* 1990, **26**: 39–45.
- [38] Ge YY, Cui W, Wang Q, *et al.* Microstructure and thermokinetics analysis in combustion synthesis of Si₃N₄ with high α -phase content. *J Am Ceram Soc* 2015, **98**: 263–268.
- [39] Liang YJ, Che YC, Liu XX. *Handbook of Inorganic Thermodynamic Data*. Shenyang (China): North-East University Press, 1993. (in Chinese)
- [40] Meng GY. *Chemical Vapor Deposition and Non-organic New Materials*. Beijing (China): Science Press, 1984. (in Chinese)

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made.

The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder.

To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.