Electrochemical performance of $\text{La}_2\text{NiO}_{4+\delta}\text{-Ce}_{0.55}\text{La}_{0.45}\text{O}_{2-\delta}$ as a promising bifunctional oxygen electrode for reversible solid oxide cells

Pengzhang LI^{a,*}, Wei YANG^a, Chuanjin TIAN^a, Wenyan ZHAO^a,
Zhe LÜ^b, Zhipeng XIE^{a,c}, Chang-An WANG^{a,c}

^aSchool of Materials Science and Engineering, Jingdezhen Ceramic Institute, Jingdezhen 333403, China

^bSchool of Physics, Harbin Institute of Technology, Harbin 150001, China

^cState Key Laboratory of New Ceramics and Fine Processing, School of Materials Science and Engineering, Tsinghua University, Beijing 100084, China

Received: July 31, 2020; Revised: November 29, 2020; Accepted: December 14, 2020

© The Author(s) 2020.

Abstract: In this work, $\text{La}_2\text{NiO}_{4+\delta}\text{-xCe}_{0.55}\text{La}_{0.45}\text{O}_{2-\delta}$ (denoted as LNO-*x*LDC) with various LDC contents (*x* = 0, 10, 20, 30, and 40 wt%) were prepared and evaluated as bifunctional oxygen electrodes for reversible solid oxide cells (RSOCs). Compared with the pure LNO, the optimum composition of LNO-30LDC exhibited the lowest polarization resistance (R_p) of 0.53 and 0.12 $\Omega\cdot\text{cm}^2$ in air at 650 and 750 °C, respectively. The enhanced electrochemical performance of LNO-30LDC oxygen electrode was mainly attributed to the extended triple phase boundary and more oxygen ionic transfer channels. The hydrogen electrode supported single cell with LNO-30LDC oxygen electrode displayed peak power densities of 276, 401, and 521 $\text{mW}\cdot\text{cm}^{-2}$ at 700, 750, and 800 °C, respectively. Moreover, the electrolysis current density of the single cell demonstrated 526.39 $\text{mA}\cdot\text{cm}^{-2}$ under 1.5 V at 800 °C, and the corresponding hydrogen production rate was 220.03 $\text{mL}\cdot\text{cm}^{-2}\cdot\text{h}^{-1}$. The encouraging results indicated that LNO-30LDC was a promising bifunctional oxygen electrode material for RSOCs.

Keywords: $\text{La}_2\text{NiO}_{4+\delta}$ (LNO); oxygen electrode; electrochemical performance; reversible solid oxide cells (RSOCs)

1 Introduction

Reversible solid oxide cells (RSOCs) are promising energy storage and regeneration devices, which have attracted worldwide attention due to its multi-function, high energy, low pollution, and so on [1,2]. RSOCs are capable of operation in the solid oxide fuel cell (SOFC mode) for electricity generation from fuel as well as

the solid oxide electrolysis cell (SOEC mode) for hydrogen generation from electrolysis of steam [3,4]. However, the polarization loss of the bifunctional oxygen electrode is the key factor limiting the overall performance of RSOCs, which is mainly dominated by its electrocatalytic activities for both the oxygen reduction reaction (ORR) and oxygen evolution reaction (OER) [5,6]. Considerable efforts have been devoted to reduce the polarization loss of the oxygen electrode by exploring novel materials [7,8]. However, oxygen electrode materials with satisfactory electrochemical

* Corresponding author.
E-mail: 15b911005@hit.edu.cn

performances for RSOCs are still elusive.

Alternatively, $\text{La}_2\text{NiO}_{4+\delta}$ (LNO) as the mixed ionic and electronic conductor (MIEC) material with the K_2NiF_4 -type structure has been regarded as a promising candidate oxygen electrode material due to its moderate thermal expansion coefficient ($\sim 13.0 \times 10^{-6} \text{ K}^{-1}$), high oxygen ion conductivity ($\sim 0.02 \text{ S} \cdot \text{cm}^{-1}$ at 700°C) and favorable electrochemical performance caused by the additional two-phase boundary (2PB) [9–11]. The crystal structure of LNO consists of alternating stacked LaO rocksalt layers and LaNiO_3 perovskite layers along the c direction [12,13]. Moreover, in order to reduce the structural stress between the La–O and Ni–O bondings, excess oxygen (denoted as δ) can accommodate into LaO rocksalt layers, which lead to the high ionic conductivity due to the migration of interstitial oxygen in rocksalt layers [14–16]. The electrochemical performance of LNO oxygen electrode has been investigated on SDC substrates, which demonstrated a low polarization resistance of $0.38 \Omega \cdot \text{cm}^2$ at 800°C [17]. In addition, LNO oxygen electrodes with thickness varying from 5 to $30 \mu\text{m}$ were also evaluated and confirmed that the electrocatalytic properties of LNO electrode with a thickness of about $20 \mu\text{m}$ achieved the lowest polarization resistance ($0.24 \Omega \cdot \text{cm}^2$ at 800°C) [18]. In contrast, the influence of microstructure on electrochemical performance of LNO electrode was also evaluated and indicated the role of surface diffusion of oxygen [19,20]. Furthermore, adding various electrolyte compositions (such as $\text{Sm}_{0.2}\text{Ce}_{0.8}\text{O}_{1.9}$ (SDC), $\text{Zr}_{0.84}\text{Y}_{0.16}\text{O}_{2-\delta}$ (YSZ), and $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{1.95}$ (GDC)) to form composite oxygen electrode is a common way to further improve the electrode/electrolyte/gas triple phase boundary (3PB) [21,22]. Hence, composite oxygen electrode prepared by LNO infiltration into porous electrolyte backbone or physically mixing the pristine materials exhibited improved performance. Although the LNO itself was thermodynamically stable, the possible solid state interaction between various components in LNO-based composite electrodes may occur at high temperature [23]. The reactivity test between LNO and GDC at 1200°C for 1 h and 800°C for 250 h conformed the interphase formation [24]. Decomposition of LNO in LNO–SDC composites was also observed after sintering at 1300°C for 5 h, which led to the formation of Sm, La co-doped ceria $\text{Sm}_{0.2}\text{La}_{0.23}\text{Ce}_{0.57}\text{O}_{2-\delta}$ [25]. Furthermore, a thermodynamics-based design for $\text{LNO}:\text{La}_x\text{Ce}_{1-x}\text{O}_{2-\delta}$ composite indicated the improved phase stability [26].

In this work, a series of $\text{La}_2\text{NiO}_{4+\delta-x}\text{La}_{0.45}\text{Ce}_{0.55}\text{O}_{2-\delta}$

(denoted as LNO– x LDC) were prepared by mixing LNO and LDC in various weight ratios. The electrochemical properties of LNO– x LDC oxygen electrodes were systematically investigated in detail to determine the optimal LDC content in the composite. The effects of LDC addition on the microstructures and electrochemical performances of oxygen electrodes were also discussed. Furthermore, the electrochemical properties of the hydrogen electrode supported single cell with the LNO–30LDC oxygen electrode were investigated both in the SOFC mode and SOEC mode at $700\text{--}800^\circ\text{C}$.

2 Experimental

2.1 Preparation of powders

All of the starting chemicals were analytical grade, which were used directly without any further purification. $\text{La}_2\text{NiO}_{4+\delta}$ (LNO) powders were synthesized by the sol–gel method using $\text{La}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$ (Guoyao Chemical Regent Co., Ltd., Shanghai, China) and $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ (Guoyao Chemical Regent Co., Ltd., Shanghai, China) as starting materials. All metal nitrates in the requisite stoichiometric ratio were dissolved in distilled water, followed by the introduction of citric acid as the complexing agent at a molar ratio of 1:1.5 for the total metal ions and citric acid. The solution was heated at 80°C for 4 h under stirring and then dried at 200°C for 12 h in order to remove residual water. Subsequently, the dry gel was successively pre-calcined at 800°C for 4 h, ground for 1 h, and then calcined at 1100°C for 4 h in air to obtain the final black LNO powders. $\text{Ce}_{0.55}\text{La}_{0.45}\text{O}_{2-\delta}$ (LDC) and $\text{Sm}_{0.2}\text{Ce}_{0.8}\text{O}_{1.9}$ (SDC) powders were also prepared by the same procedure as previously reported, respectively [27]. The final calcination condition of LDC and SDC powders was 800°C for 4 h. The composite samples were prepared by adding LDC powders in the amount of 10, 20, 30, and 40 wt% to LNO powders (LNO– x LDC). The mixtures were ground using a mortar for 2 h to ensure uniform distribution.

2.2 Fabrication of symmetric cells and single cells

The electrochemical performance was evaluated based on symmetrical cells with a LNO– x LDC|SDC|LNO– x LDC configuration. The SDC substrates for symmetrical cells were prepared with SDC powders via dry pressing uniaxially at 300 MPa for 1 min and then sintering at 1400°C for 4 h. The thickness of dense SDC disks was

about 350 μm . The slurry for each composite electrode was prepared by mixing electrode materials with terpeneol solution of 7 wt% ethylic cellulose in a weight ratio of 7:3. The slurry was coated on the one side of the SDC disk and then calcined at 800 $^{\circ}\text{C}$ for 2 h in air. Subsequently, the slurry was coated on the other side of the SDC disk as shown in Fig. S1 in the Electronic Supplementary Material (ESM). Finally, the symmetrical cell was calcined at 1100 $^{\circ}\text{C}$ for 4 h in air. The area of the oxygen electrode was 0.12 cm^2 . Moreover, the silver paste (DAD-87, Shanghai Research Institute of Synthetic Resins, China) was coated on surface of the oxygen electrode as current collector.

The hydrogen electrode supported single cell (NiO-YSZ|YSZ|SDC|LNO-30LDC) was fabricated by the similar procedure as previously described [28]. Briefly, NiO (Inco, Canada) and YSZ powders (TZ-8Y, Tosoh Corporation, Tokyo, Japan) with a weight ratio of 5:5 were mixed uniformly and pressed uniaxially at 300 MPa. NiO-YSZ disks (~ 350 μm -thick) were pre-sintered at 1000 $^{\circ}\text{C}$ for 2 h. Subsequently, the YSZ electrolyte layer (~ 25 μm -thick) was applied onto NiO-YSZ disks using the slurry spin coating method, which were sintered at 1400 $^{\circ}\text{C}$ for 4 h. The SDC barrier layer (~ 10 μm -thick) was also coated on the surface of the YSZ layer to prevent the detrimental interaction. Finally, the LNO-30LDC slurry was painted on hydrogen electrode supported half cells and sintered at 1100 $^{\circ}\text{C}$ for 4 h to form the porous oxygen electrode layer (~ 20 μm -thick).

2.3 Characterization on microstructure and electrochemical performance

Phase composition of LNO-30LDC was examined by X-ray diffraction (XRD, Rigaku D/max2200, Japan). The surface and cross-section microstructure of oxygen electrodes were observed by a field emission scanning electron microscope (SEM, HitachiSU800, Japan). Energy-dispersive X-ray spectroscopy analysis was applied to observe the distribution of various elements across the interface between the oxygen electrode and electrolyte.

The electrochemical impedance spectra (EIS) measurements of symmetric cells with LNO-*x*LDC were obtained under open-circuit voltage over the frequency range from 10 mHz to 100 kHz with the AC signal amplitude of 10 mV. Moreover, the hydrogen electrode supported single cell using LNO-30LDC as the oxygen electrode was tested at the temperature

range from 700 to 800 $^{\circ}\text{C}$ (50 $^{\circ}\text{C}$ intervals). The single cell was sealed on the top of an alumina tube. For power generation (SOFC mode), dry hydrogen at the flow rate of 50 $\text{mL}\cdot\text{min}^{-1}$ was fed to the hydrogen electrode, while the oxygen electrode was exposed to ambient air. Furthermore, for steam electrolysis (SOEC mode), steam with hydrogen carrier gas at a rate of 100 $\text{mL}\cdot\text{min}^{-1}$ was fed to the hydrogen electrode. The absolute humidity (AH, the volume percentage of humidity in the total gas volume) of the mixture gas was about 30 vol%. Hydrogen generation rate of steam electrolysis was calculated from the Faraday's law, assuming 100% current efficiency [29,30]. The current-voltage curves (*I*-*V*) and EIS data of the single cell were collected by an electrochemical workstation (Bio-logic VSP, France).

3 Results and discussion

The XRD patterns of LNO-30LDC powders after calcined at 900, 1000, and 1100 $^{\circ}\text{C}$ for 10 h were presented in Fig. 1. It clearly indicated that all peaks of LNO-30LDC can be identified with a physical mixture of LNO and LDC. No additional peaks were observed. The structures of LNO and LDC in LNO-30LDC after sintered at 900, 1000, and 1100 $^{\circ}\text{C}$ for 10 h remained unchanged, which revealed no obvious chemical reaction occurs. Hence, the result confirmed the chemical compatibility between LNO and LDC, which is consistent with the previous report [26].

The surface morphology of various composite oxygen electrodes was observed as shown in Fig. 2. The typical morphology as shown in Fig. 2(c) displayed that LNO particles were surrounded by the finer LDC particles. Clearly, the particle size of LNO was about

Fig. 1 X-ray diffraction patterns of LNO-30LDC composite after sintered at 900, 1000, and 1100 $^{\circ}\text{C}$ for 10 h.

Fig. 2 SEM images of electrode surface of samples with different LDC loading ($x = 10, 20, 30, 40$).

500–1000 nm, while LDC had a smaller particle size (about 100–300 nm). Sufficient contact between LNO and LDC particles was beneficial to the expansion of 3PB areas and the formation of oxygen ion transport channels, which could facilitate their electrocatalytic activities [31].

Furthermore, the cross section of the symmetrical cell with LNO-30LDC electrode was also observed (Fig. 3(a)). The LNO-30LDC electrode with a thickness of 22 µm was tightly bonded to the surface of the dense electrolyte without any cracks or separation. Energy-dispersive X-ray spectroscopy linear scan analysis across the interface between LNO-30LDC oxygen electrode and SDC electrolyte was also measured as shown in Fig. 3(b). Obviously, the content of La and Ni was decreased rapidly at the interface of SDC electrolyte and LNO-30LDC electrode, while the content of Ce increased sharply, which also indicated that there was no obvious elemental diffusion or

detrimental solid state interaction.

The impedance spectra of the symmetric cell with LNO- x LDC oxygen electrodes were measured to evaluate the electrochemical performance of various oxygen electrodes. The high frequency intercept dominated by the ohmic resistance (R_o) was normalized to zero in Nyquist plots. Figures 4(a) and 4(b) display the typical Nyquist plots of symmetrical cells with LNO- x LDC oxygen electrodes at temperature of 650 and 750 °C, respectively. The impedance spectra appears as an obviously asymmetrical and depressed semicircle in shape, inferring contributions from more than one electrode process [32,33]. Therefore, the $LR_o(R_1CPE_1)(R_2CPE_2)(R_3CPE_3)$ equivalent circuits (insets in Figs. 4(a) and 4(b)) were implemented to fit the impedance spectra to understand the electrode processes. The fitted parameters of electrochemical impedance spectra were listed in Table S1 in the ESM. Here, L is the inductance and total polarization resistance

Fig. 3 Cross-sectional SEM image (a) and linear scan analysis across the interface (b) of the LNO-30LDC oxygen electrode.

Fig. 4 Typical electrochemical impedance spectra of symmetrical cells using LNO-*x*LDC oxygen electrodes at 650 °C (a) and 750 °C (b); dependence of R_p (c) and Arrhenius plots (d) for LNO-*x*LDC oxygen electrodes with different LDC contents at 600–800 °C in air.

is expressed as $R_p = R_1 + R_2 + R_3$. (R_iCPE_i) ($i = 1, 2, 3$) corresponds to related electrode processes, where R_i and CPE_i represent the resistance and the constant phase element, respectively. The equivalent capacitance (C) and relaxation frequency (f) convey critical information of electrode processes, which can be calculated according to the following equations [34,35]:

$$C = \frac{(R \cdot CPE)^{1/n}}{R} \quad (1)$$

$$f = \frac{(R \cdot CPE)^{-1/n}}{2\pi} \quad (2)$$

The equivalent capacitance and relaxation frequency can be used as characteristic parameters to distinguish various electrode processes [36]. The relaxation frequencies of various electrodes were increased by one order of magnitude with increasing temperature from 650 to 750 °C, which can be assigned to the thermally activated mechanism [32]. The equivalent capacitances of the processes 1, 2, and 3 were on the orders of magnitude of $\sim 10^{-4}$, $\sim 10^{-3}$, and $\sim 10^{-2}$ F·cm², while the relaxation frequencies of the processes 1, 2, and 3 were on the orders of 10^3 – 10^4 , 10^2 – 10^3 , and 10 – 10^2 Hz, respectively. Accordingly, the processes 1, 2, and 3 can be assigned to electron transfer between the electrode

and oxygen species on the surface, adsorption and dissociation of molecular oxygen on the surface of the electrode as well as diffusion of oxygen through the porous electrode [33,34,36]. Furthermore, the value of R_2 accounted for the largest proportion of R_p , which indicated that adsorption and dissociation of molecular oxygen on the surface of the electrode made a larger contribution to the total polarization resistance.

The polarization resistance (R_p) of LNO-*x*LDC oxygen electrodes at 650 and 750 °C decreased with increasing x from 0 to 30 wt% and then increased. Among the evaluated various compositions, LNO-30LDC electrode possessed the lowest R_p (0.12 Ω·cm² at 750 °C and 0.53 Ω·cm² at 650 °C, respectively) as shown in Fig. 4(c), which were also lower than the literature data in Table 1.

It should be noted that the R_p at 750 °C of LNO-30LDC oxygen electrode was even comparable with the LNO infiltrated YSZ electrode, which mainly contributed to the effective connection between LNO and LDC particles as well as the expansion of 3PB [31,41]. The Arrhenius plots of the total R_p for LNO-*x*LDC composite electrodes displayed in Fig. 4(d). The activation energies of LNO, LNO-10LDC, LNO-20LDC, LNO-30LDC, and LNO-40LDC were 124.8, 125.1,

Table 1 Comparison of R_p values obtained in this study and reported in the literature

Electrode		Electrolyte	R_p ($\Omega \cdot \text{cm}^2$)		Reference
Composition	Sintering temperature ($^{\circ}\text{C}$)		650 $^{\circ}\text{C}$	750 $^{\circ}\text{C}$	
LNO–GDC	900	GDC	*	0.244	[37]
	1000	GDC	*	0.334	
	1100	GDC	*	0.698	
LNO infiltrated YSZ	850	YSZ	*	0.120	[38]
LNO	900	SDC	2.46	0.59	[33]
LNO+La ₄ Ni ₃ O _{10-δ}	1000	LSGM	1.37	*	[39]
La _{1.6} Sr _{0.4} NiO ₄ nanofibers	900	GDC	0.80	*	[40]
LNO	1100	SDC	0.93	0.21	This work
LNO–30LDC	1100	SDC	0.53	0.12	This work

* Not reported or could not get precise values.

118.9, 113.2, and 118.1 kJ·mol^{−1}, respectively. The activation energy of LNO–30LDC oxygen electrode was relatively lower than that of LNO cathode (124.8 kJ·mol^{−1}) in this work as well as the 121.9 kJ·mol^{−1} of LNO electrode reported previously [42].

To further explain the mechanism of oxygen reduction reaction, the possible sub-steps of oxygen reduction reaction in LNO and LNO– x LDC oxygen electrode on SDC electrolyte were schematically illustrated in Fig. 5. The overall oxygen reduction reaction on the oxygen electrode can be described as

which contains several sub-steps, such as the gaseous oxygen adsorption–dissociation on the oxygen electrode surface ($\text{O}_2(\text{g}) \rightleftharpoons \text{O}_{2,\text{ads}}$ and $\text{O}_{2,\text{ads}} \rightleftharpoons 2\text{O}_{\text{ads}}$), the charge transfer process ($\text{O}_{\text{ads}} + 2\text{e}^- + \text{V}_{\text{O}}^{\bullet\bullet} \rightleftharpoons \text{O}_{\text{O}}^{\times}$) as well as the ionic oxygen transfer process ($\text{O}_{3\text{PB}}^{\times} + \text{V}_{\text{O}}^{\bullet\bullet} \rightleftharpoons \text{O}_{\text{O}}^{\times}$) [43]. For the pure LNO oxygen electrode (Fig. 5(a)), the total oxygen electrode surface could be

applied as active sites for oxygen reduction reaction, which signified the active region extends from the interface of the oxygen electrode and electrolyte to the entire oxygen electrode surface [44]. The electrochemical reactions of the oxygen electrode in the SOEC mode are the inverse to sub-steps in the SOFC mode. Hence, the expansion of the active region also contributes to the enhanced electrochemical performance of the oxygen electrode in SOEC mode [28].

Moreover, the addition of LDC with proper content in LNO not only provided more oxygen ionic transfer channels but also formed more 3PB due to the extensive contact between LNO and LDC particles as shown in Fig. 5(b), which played a vital role in the enhanced electrochemical performance of LNO–30LDC (Fig. 5(c)) [17]. However, the electronic transfer channels could not be effectively built up for LNO–40LDC with the addition of excess LDC, which led to the sharp increase of R_p . Simultaneously, discontinuous electronic transport channels also resulted in the high ohmic

Fig. 5 Schematic illustration of the possible process of oxygen reduction reaction in (a) LNO and (b) LNO– x LDC oxygen electrodes.

resistance of composite oxygen electrode [45].

Furthermore, the electrochemical performance of LNO–30LDC oxygen electrode was also evaluated using the hydrogen electrode supported single cell (NiO–YSZ|YSZ|SDC|LNO–30LDC). Figure 6 presented the I – V curves and corresponding I – P curves of the single cell in the SOFC mode with dry H_2 as the fuel at 700–800 °C. The open circuit voltage was 1.05 V at 700 °C. The maximum power densities of the single cell achieved 276, 401, and 521 $mW \cdot cm^{-2}$ at 700, 750, and 800 °C, respectively. Moreover, Fig. 7(a) displays the impedance spectra of single cell with LNO–30LDC oxygen electrode at various temperatures. R_p was decreased with the increase of operation temperature due to the higher electrocatalytic activity of LNO–30LDC oxygen electrode at the elevated temperature. As can be observed in Fig. 7(b), the intermediate to low frequency range features the dominating process [46]. Moreover, the Bode plot peaks shift towards low frequencies with increasing temperature, which mainly corresponds to impedances related to diffusion or mass transport processes [47]. Hence, LNO–30LDC oxygen electrode displayed encouraging performance in the SOFC mode.

In order to evaluate the overall performance of the LNO–30LDC oxygen electrode in RSOCs operation, the hydrogen electrode supported single cell was measured at 700–800 °C under both the SOFC mode and the SOEC mode. When the open circuit voltage was higher than the applied voltage, the cell operated in the SOFC mode and generated electricity with the consumption of fuel. By contrast, when the open circuit voltage was lower than the applied voltage, the cell operated in the SOEC mode and split H_2O into H_2 and O_2 with the consumption of electricity [48]. As

Fig. 6 I – V and corresponding I – P curves of the single cell with LNO–30LDC oxygen electrode measured at various temperatures.

Fig. 7 (a) EIS spectra and (b) Bode plots of the single cell with LNO–30LDC oxygen electrode measured at various temperatures.

shown in Fig. 8(a), the open circuit voltage values of the single cell were around 1.01 V, which indicated the cell was well sealed. The slope of I – V curves increased with operation temperature increasing from 700 to 800 °C. Moreover, the electrolysis current density was increased with the increasing of applied electrolysis voltage from the open circuit voltage to 1.5 V. The current densities achieved 270.86, 445.06, and 526.39 $mA \cdot cm^{-2}$ at 700, 750, and 800 °C under applied electrolysis voltage of 1.5 V, respectively. To further reveal the hydrogen generation properties of the single cell with LNO–30LDC oxygen electrode, hydrogen production rates can be directly calculated according the measured current data as following equation [29]:

$$\Delta N_{H_2} = \frac{-I}{2F} \quad (3)$$

The molar rate of hydrogen generation is expressed as ΔN_{H_2} . I and F are the electrical current and the Faraday's constant, respectively. Hydrogen production rates was 113.22, 186.03, and 220.03 $mL \cdot cm^{-2} \cdot h^{-1}$ at 700, 750, and 800 °C under 1.5 V, respectively. All above very promising results revealed that LNO–30LDC was a good candidate as the oxygen electrode for RSOCs.

Fig. 8 (a) I - V curves of the single cell with LNO-30LDC oxygen electrode operated under SOFC mode and SOEC mode at various temperatures; (b) hydrogen production rates of the cell in SOEC mode at 700–800 °C.

4 Conclusions

In summary, a series of $\text{La}_2\text{NiO}_{4+\delta-x}\text{Ce}_{0.55}\text{La}_{0.45}\text{O}_{2-\delta}$ composites (LNO- x LDC) with various LDC contents ($x = 0$ –40 wt%) were investigated as oxygen electrodes for RSOCs. The XRD results revealed no other by-product phases occurred in LNO-30LDC after sintering at 900, 1000, and 1100 °C for 4 h. Proper adding of LDC in LNO- x LDC revealed improved electrochemical performance compared with that of pristine LNO, which was mainly attributed to the expansion of 3PB and more oxygen ionic transfer channels. LNO-30LDC oxygen electrode displayed the lowest R_p value ($0.12 \Omega \cdot \text{cm}^2$) at 750 °C. Furthermore, the maximum power density of hydrogen electrode supported single cell with LNO-30LDC oxygen electrode achieved $521 \text{ mW} \cdot \text{cm}^{-2}$ at 800 °C. The electrolysis current density of the single cell demonstrated $526.39 \text{ mA} \cdot \text{cm}^{-2}$ under 1.5 V at 800 °C, and the corresponding hydrogen production rate was $220.03 \text{ mL} \cdot \text{cm}^{-2} \cdot \text{h}^{-1}$. All above results suggested that LNO-30LDC was a promising bifunctional oxygen electrode material for RSOCs.

Acknowledgements

The authors gratefully acknowledge financial support from the Science and Technology Project of Jiangxi Provincial Education Department (GJJ190734) and the National Natural Science Foundation of China (51962015).

Electronic Supplementary Material

Supplementary material is available in the online version of this article at <https://doi.org/10.1007/s40145-020-0445-y>.

References

- [1] Irvine JTS, Neagu D, Verbracken MC, *et al.* Evolution of the electrochemical interface in high-temperature fuel cells and electrolyzers. *Nat Energ* 2016, **1**: 15014.
- [2] He ZL, Zhang L, He S, *et al.* Cyclic polarization enhances the operating stability of $\text{La}_{0.57}\text{Sr}_{0.38}\text{Co}_{0.18}\text{Fe}_{0.72}\text{Nb}_{0.1}\text{O}_{3-\delta}$ oxygen electrode of reversible solid oxide cells. *J Power Sources* 2018, **404**: 73–80.
- [3] Gómez SY, Hotza D. Current developments in reversible solid oxide fuel cells. *Renew Sustain Energy Rev* 2016, **61**: 155–174.
- [4] Chen KF, Liu SS, Ai N, *et al.* Why solid oxide cells can be reversibly operated in solid oxide electrolysis cell and fuel cell modes? *Phys Chem Chem Phys* 2015, **17**: 31308–31315.
- [5] Lee SI, Kim J, Son JW, *et al.* High performance air electrode for solid oxide regenerative fuel cells fabricated by infiltration of nano-catalysts. *J Power Sources* 2014, **250**: 15–20.
- [6] Tong XF, Ovtar S, Brodersen K, *et al.* Large-area solid oxide cells with $\text{La}_{0.6}\text{Sr}_{0.4}\text{CoO}_{3-\delta}$ infiltrated oxygen electrodes for electricity generation and hydrogen production. *J Power Sources* 2020, **451**: 227742.
- [7] Mogensen MB. Materials for reversible solid oxide cells. *Curr Opin Electrochem* 2020, **21**: 265–273.
- [8] Zhang YL, Han MF, Sun ZH. High performance and stability of nanocomposite oxygen electrode for solid oxide cells. *Int J Hydrog Energy* 2020, **45**: 5554–5564.
- [9] Zhao K, Xu Q, Huang DP, *et al.* Electrochemical evaluation of $\text{La}_2\text{NiO}_{4+\delta}$ -based composite electrodes screen-printed on $\text{Ce}_{0.8}\text{Sm}_{0.2}\text{O}_{1.9}$ electrolyte. *J Solid State Electrochem* 2012, **16**: 2797–2804.
- [10] Yoo YS, Choi M, Hwang JH, *et al.* $\text{La}_2\text{NiO}_{4+\delta}$ as oxygen electrode in reversible solid oxide cells. *Ceram Int* 2015, **41**: 6448–6454.
- [11] Egger A, Schrödl N, Gspan C, *et al.* $\text{La}_2\text{NiO}_{4+\delta}$ as electrode material for solid oxide fuel cells and electrolyzer cells. *Solid State Ionics* 2017, **299**: 18–25.
- [12] Hou J, Zhu ZW, Qian J, *et al.* A new cobalt-free proton-blocking composite cathode $\text{La}_2\text{NiO}_{4+\delta}$ - $\text{LaNi}_{0.6}\text{Fe}_{0.4}\text{O}_{3-\delta}$ for $\text{BaZr}_{0.1}\text{Ce}_{0.7}\text{Y}_{0.2}\text{O}_{3-\delta}$ -based solid oxide fuel cells. *J*

- Power Sources* 2014, **264**: 67–75.
- [13] Nirala G, Yadav D, Upadhyay S. Ruddlesden–Popper phase A_2BO_4 oxides: Recent studies on structure, electrical, dielectric, and optical properties. *J Adv Ceram* 2020, **9**: 129–148.
 - [14] Ekaterina K, Kiryl Z, Alexander V, *et al.* Impact of oxygen deficiency on the electrochemical performance of K_2NiF_4 -type $(La_{1-x}Sr_x)_2NiO_{4-\delta}$ oxygen electrodes. *ChemSusChem* 2017, **10**: 600.
 - [15] Huang JB, Gao RF, Mao ZQ, *et al.* Investigation of $La_2NiO_{4+\delta}$ -based cathodes for SDC–carbonate composite electrolyte intermediate temperature fuel cells. *Int J Hydrog Energy* 2010, **35**: 2657–2662.
 - [16] Amow G, Davidson I, Skinner S. A comparative study of the Ruddlesden–Popper series, $La_{n+1}Ni_nO_{3n+1}$ ($n = 1, 2$ and 3), for solid-oxide fuel-cell cathode applications. *Solid State Ionics* 2006, **177**: 1205–1210.
 - [17] Zhao K, Wang YP, Chen M, *et al.* Electrochemical evaluation of $La_2NiO_{4+\delta}$ as a cathode material for intermediate temperature solid oxide fuel cells. *Int J Hydrog Energy* 2014, **39**: 7120–7130.
 - [18] Wang YP, Zhao K, Xu Q, *et al.* Optimization on the electrochemical properties of $La_2NiO_{4+\delta}$ cathodes by tuning the cathode thickness. *Int J Hydrog Energy* 2018, **43**: 4482–4491.
 - [19] Hildenbrand N, Nammensma P, Blank DHA, *et al.* Influence of configuration and microstructure on performance of $La_2NiO_{4+\delta}$ intermediate-temperature solid oxide fuel cells cathodes. *J Power Sources* 2013, **238**: 442–453.
 - [20] Sharma RK, Burriel M, Dessemond L, *et al.* An innovative architectural design to enhance the electrochemical performance of $La_2NiO_{4+\delta}$ cathodes for solid oxide fuel cell applications. *J Power Sources* 2016, **316**: 17–28.
 - [21] Liu ZB, Zhang XM, Huang ZD, *et al.* Co-synthesized $(La_{0.8}Sr_{0.2})_{0.9}MnO_3$ – $Y_{0.15}Zr_{0.85}O_2$ composite for solid oxide fuel cell cathode. *Int J Hydrog Energy* 2016, **41**: 21385–21393.
 - [22] Ai N, Chen ML, He S, *et al.* High performance nanostructured bismuth oxide–cobaltite as a durable oxygen electrode for reversible solid oxide cells. *J Mater Chem A* 2018, **6**: 6510–6520.
 - [23] Vibhu V, Flura A, Rougier A, *et al.* Electrochemical ageing study of mixed lanthanum/praseodymium nickelates $La_{2-x}Pr_xNiO_{4+\delta}$ as oxygen electrodes for solid oxide fuel or electrolysis cells. *J Energy Chem* 2020, **46**: 62–70.
 - [24] Vibhu V, Vinke IC, Eichel RA, *et al.* $La_2Ni_{1-x}Co_xO_{4+\delta}$ ($x = 0.0, 0.1$ and 0.2) based efficient oxygen electrode materials for solid oxide electrolysis cells. *J Power Sources* 2019, **444**: 227292.
 - [25] Cetin D, Poizeau S, Pietras J, *et al.* Decomposition of La_2NiO_4 in $Sm_{0.2}Ce_{0.8}O_2$ – La_2NiO_4 composites for solid oxide fuel cell applications. *Solid State Ionics* 2017, **300**: 91–96.
 - [26] Cetin D, Poizeau S, Pietras J, *et al.* Decomposition of La_2NiO_4 in $Sm_{0.2}Ce_{0.8}O_2$ – La_2NiO_4 composites for solid oxide fuel cell applications. *Solid State Ionics* 2017, **307**: 14–20.
 - [27] Li PZ, Wang ZH, Huang XQ, *et al.* Enhanced electrochemical performance of co-synthesized $La_2NiO_{4+\delta}$ – $Ce_{0.55}La_{0.45}O_{2-\delta}$ composite cathode for IT-SOFCs. *J Alloys Compd* 2017, **705**: 105–111.
 - [28] Jiang W, Wei B, Lv Z, *et al.* Performance and stability of co-synthesized $Sm_{0.5}Sr_{0.5}CoO_3$ – $Sm_{0.2}Ce_{0.8}O_{1.9}$ oxygen electrode for reversible solid oxide cells. *Electrochimica Acta* 2015, **180**: 1085–1093.
 - [29] Tan Y, Duan NQ, Wang A, *et al.* Performance enhancement of solution impregnated nanostructured $La_{0.8}Sr_{0.2}Co_{0.8}Ni_{0.2}O_{3-\delta}$ oxygen electrode for intermediate temperature solid oxide electrolysis cells. *J Power Sources* 2016, **305**: 168–174.
 - [30] Yang CH, Coffin A, Chen FL. High temperature solid oxide electrolysis cell employing porous structured $(La_{0.75}Sr_{0.25})_{0.95}MnO_3$ with enhanced oxygen electrode performance. *Int J Hydrog Energy* 2010, **35**: 3221–3226.
 - [31] Dos Santos-Gómez L, Zamudio-García J, Porras-Vázquez JM, *et al.* Highly efficient $La_{0.8}Sr_{0.2}MnO_{3-\delta}$ – $Ce_{0.9}Gd_{0.1}O_{1.95}$ nanocomposite cathodes for solid oxide fuel cells. *Ceram Int* 2018, **44**: 4961–4966.
 - [32] Wang Y-P, Xu Q, Huang D-P, *et al.* Survey on electrochemical properties of $La_{2-x}Sr_xNiO_{4\pm\delta}$ ($x = 0.2$ and $0.8, \delta > 0$) cathodes related with structural stability under cathodic polarization conditions. *Int J Hydrog Energy* 2017, **42**: 6290–6302.
 - [33] Zhao K, Xu Q, Huang DP, *et al.* Microstructure and electrochemical properties of porous $La_2NiO_{4+\delta}$ electrode screen-printed on $Ce_{0.8}Sm_{0.2}O_{1.9}$ electrolyte. *J Solid State Electrochem* 2012, **16**: 9–16.
 - [34] Garali M, Kahlaoui M, Mohammed B, *et al.* Synthesis, characterization and electrochemical properties of $La_{2-x}Eu_xNiO_{4+\delta}$ Ruddlesden–Popper-type layered nickelates as cathode materials for SOFC applications. *Int J Hydrog Energy* 2019, **44**: 11020–11032.
 - [35] Kahlaoui M, Inoubli A, Chefi S, *et al.* Electrochemical and structural study of neodymium nickelate thick film deposited by spin coating on an oxyapatite electrolyte. *Ionics* 2014, **20**: 1729–1735.
 - [36] Wang Y-P, Xu Q, Huang D-P, *et al.* Evaluation of $La_{1.8}Sr_{0.2}NiO_{4+\delta}$ as cathode for intermediate temperature solid oxide fuel cells. *Int J Hydrogen Energy* 2016, **41**: 6476–6485.
 - [37] Jeong C, Lee JH, Park M, *et al.* Design and processing parameters of $La_2NiO_{4+\delta}$ -based cathode for anode-supported planar solid oxide fuel cells (SOFCs). *J Power Sources* 2015, **297**: 370–378.
 - [38] Choi S, Yoo S, Shin JY, *et al.* High performance SOFC cathode prepared by infiltration of $La_{n+1}Ni_nO_{3n+1}$ ($n = 1, 2$, and 3) in porous YSZ. *J Electrochem Soc* 2011, **158**: B995–B999.
 - [39] Woolley RJ, Skinner SJ. Novel $La_2NiO_{4+\delta}$ and $La_4Ni_3O_{10-\delta}$ composites for solid oxide fuel cell cathodes. *J Power*

- Sources 2013, **243**: 790–795.
- [40] Li Q, Sun LP, Zhao H, *et al.* $\text{La}_{1.6}\text{Sr}_{0.4}\text{NiO}_4$ one-dimensional nanofibers as cathode for solid oxide fuel cells. *J Power Sources* 2014, **263**: 125–129.
- [41] Kim YT, Shikazono N. Evaluation of electrochemical reaction mechanisms of $\text{La}_{0.6}\text{Sr}_{0.4}\text{CoO}_{3-\delta}$ – $\text{Gd}_{0.1}\text{Ce}_{0.9}\text{O}_{2-\delta}$ composite cathodes by 3D numerical simulation. *Solid State Ionics* 2018, **319**: 162–169.
- [42] Lu LH, Guo YB, Zhang H, *et al.* Electrochemical performance of $\text{La}_2\text{NiO}_{4+\delta}$ – $\text{La}_{0.6}\text{Sr}_{0.4}\text{Co}_{0.2}\text{Fe}_{0.8}\text{O}_{3-\delta}$ composite cathodes for intermediate temperature solid oxide fuel cells. *Mater Res Bull* 2010, **45**: 1135–1140.
- [43] Zhou J, Chen G, Wu K, *et al.* $\text{La}_{0.8}\text{Sr}_{1.2}\text{CoO}_{4+\delta}$ –CGO composite as cathode on $\text{La}_{0.9}\text{Sr}_{0.1}\text{Ga}_{0.8}\text{Mg}_{0.2}\text{O}_{3-\delta}$ electrolyte for intermediate temperature solid oxide fuel cells. *J Power Sources* 2013, **232**: 332–337.
- [44] Laguna-Bercero MA, Monzón H, Larrea A, *et al.* Improved stability of reversible solid oxide cells with a nickelate-based oxygen electrode. *J Mater Chem A* 2016, **4**: 1446–1453.
- [45] Gu HT, Chen H, Gao L, *et al.* Electrochemical properties of $\text{LaBaCo}_2\text{O}_{5+\delta}$ – $\text{Sm}_{0.2}\text{Ce}_{0.8}\text{O}_{1.9}$ composite cathodes for intermediate-temperature solid oxide fuel cells. *Electrochimica Acta* 2009, **54**: 7094–7098.
- [46] Ortiz-Vitoriano N, Bernuy-López C, Hauch A, *et al.* Electrochemical characterization of $\text{La}_{0.6}\text{Ca}_{0.4}\text{Fe}_{0.8}\text{Ni}_{0.2}\text{O}_3$ cathode on $\text{Ce}_{0.8}\text{Gd}_{0.2}\text{O}_{1.9}$ electrolyte for IT-SOFC. *Int J Hydrog Energy* 2014, **39**: 6675–6679.
- [47] Han GD, Neoh KC, Bae K, *et al.* Fabrication of lanthanum strontium cobalt ferrite (LSCF) cathodes for high performance solid oxide fuel cells using a low price commercial inkjet printer. *J Power Sources* 2016, **306**: 503–509.
- [48] Bi L, Boulfrad S, Traversa E. Reversible solid oxide fuel cells (R-SOFCs) with chemically stable proton-conducting oxides. *Solid State Ionics* 2015, **275**: 101–105.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made.

The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder.

To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.