Applications of Carbon Nanotubes in the Internet of Things Era

Cite as

Nano-Micro Lett.

(2021) 13:191

Received: 24 June 2021

Accepted: 11 August 2021

Published online: 11 September 2021

© The Author(s) 2021

Jinbo Pang¹ , Alicja Bachmatiuk^{2,3}, Feng Yang⁴, Hong Liu^{1,5}, Weijia Zhou¹, Mark H. Rummeli^{6,7,8,9,10}, Gianaurelio Cuniberti^{11,12}

HIGHLIGHTS

- The Internet of Things era related electronics were updated based on carbon nanotube transistors, radiofrequency circuits and energy storage devices.
- The applications in healthcare and biomedical devices were discussed including sensory, data processors and actuators.
- The fabrication of wafer-scale carbon nanotubes has been introduced as well as the machine learning strategy for prediction of optimal synthesis parameters.

ABSTRACT The post-Moore's era has boosted the progress in carbon nanotube-based transistors. Indeed, the 5G communication and cloud computing stimulate the research in applications of carbon nanotubes in electronic devices. In this perspective, we deliver the readers with the latest trends in carbon nanotube research, including high-frequency transistors, biomedical sensors and actuators, brain-machine interfaces, and flexible logic devices and energy storages. Future opportunities are given for calling on scientists and engineers into the emerging topics.

KEYWORDS Carbon nanotubes; Transistors; Sensors; Actuators; Brain-machine interfaces; Energy storage

Jinbo Pang, jinbo.pang@hotmail.com; ifc_pangjb@ujn.edu.cn; Gianaurelio Cuniberti, gianaurelio.cuniberti@tu-dresden.de

¹ Collaborative Innovation Center of Technology and Equipment for Biological Diagnosis and Therapy, Institute for Advanced Interdisciplinary Research (IAIR), Universities of Shandong, University of Jinan, Shandong, Jinan 250022, People's Republic of China

² PORT Polish Center for Technology Development, Łukasiewicz Research Network, Ul. Stabłowicka 147, 54-066 Wrocław, Poland

³ Centre of Polymer and Carbon Materials, Polish Academy of Sciences, M. Curie-Skłodowskiej 34, 41-819 Zabrze, Poland

⁴ Department of Chemistry, Southern University of Science and Technology, Shenzhen 518055, People's Republic of China

⁵ State Key Laboratory of Crystal Materials, Center of Bio & Micro/Nano Functional Materials, Shandong University, 27 Shandan Road, Jinan 250100, People's Republic of China

⁶ College of Energy, Institute for Energy and Materials Innovations, Soochow University, Suzhou, Soochow 215006, People's Republic of China

⁷ Key Laboratory of Advanced Carbon Materials and Wearable Energy Technologies of Jiangsu Province, Soochow University, Suzhou 215006, People's Republic of China

⁸ Centre of Polymer and Carbon Materials, Polish Academy of Sciences, M. Curie Skłodowskiej 34, 41-819 Zabrze, Poland

⁹ Institute for Complex Materials, Leibniz Institute for Solid State and Materials Research Dresden (IFW Dresden), 20 Helmholtz Strasse, 01069 Dresden, Germany

¹⁰ Institute of Environmental Technology, VŠB-Technical University of Ostrava, 17. Listopadu 15, Ostrava 708 33, Czech Republic

¹¹ Institute for Materials Science and Max Bergmann Center of Biomaterials, Center for Advancing Electronics Dresden, Technische Universität Dresden, 01069 Dresden, Germany

¹² Dresden Center for Computational Materials Science, Dresden Center for Intelligent Materials (GCL DCIM), Technische Universität Dresden, 01062 Dresden, Germany

1 Introduction

The integration of more transistors in a chip has facilitated improved circuit performances for meeting the requirement of Internet of Things [1–4], which feature the emerging trend of 5G communication, cloud computing, and lightweight consumer electronics. Indeed, the currently available transistors for high-frequency electronics rely on three types of materials, i.e., Si-based complementary metal oxide semiconductor, GaAs and carbon nanotubes. The former two types of materials do not meet the strict requirement of radio-frequency transistors. Therefore, the carbon nanotube-based transistors have provided an effective solution for the post-Moore's era. In this perspective, we list the applications of carbon nanotubes in emerging electronics, such as high-frequency transistors and the Internet of Things [5]. Also, the biomedical engineering of carbon nanotubes is demonstrated by the brain-machine interface and actuators for artificial muscles. Next, the trends for materials optimization and properties prediction are given based on big data and machine learning approaches. Eventually, future opportunities for carbon nanotubes research are delivered to the readers.

2 Emerging Opportunities for Carbon Nanotube Applications

2.1 The Internet of Things (IoT)

As a computing ecosystem, IoT connects everything with embedded electronics through wireless communication. In the

Fig. 1 The emerging applications of carbon nanotube-based electronics

IoT system (Fig. 1), sensors first acquire the physical and environmental variables, process the electrical signals, and upload the information wirelessly to a processor for computing [6].

Carbon nanotubes have been aligned with shear forces and deposited as thin film onto dielectric/metal substrate for fabricating microstrip patch antennas [7]. The weight saving of CNT antenna for radio-frequency communication has achieved 5% compared with copper antenna [8]. The CNT-based antennas can be integrated into flexible and wearable devices for information transmission and reception. Carbon nanotubes-based antennas show high radiation efficiency at 10 GHz, comparable with copper antennas [8].

The random-access memory based on carbon nanotubes has been proposed for boosting the reading/writing rate by processor [9–11]. Besides, the composite materials have been developed for the non-volatile memory [12] for data storage [13]. The input devices start emerging with the keypad [14], joystick [15], and touchpad [16]. Meanwhile, the output devices such as display were demonstrated based on CNT driving electrodes [17] and lightening [18–20]. There emerge the carbon nanotube-based analog circuits [21]. Besides, the terahertz imaging system based on CNT has promised the non-destructive detection of industrial products [22].

Hardware true random number generators (TRNGs) are utilized to generate encryption keys for allowing access to sensitive data. The Internet of Things requires flexible true random number generators. The TRNG of SWCNTs [23] has been demonstrated with the devices of static random-access memory. The security protocols are strictly robust, with random numbers from digitizing thermal noise into random 0 and 1 numbers.

2.2 Transparent Conducting Films

The performances of CNT-based transparent conducting films were comparable to the ITO films a decade ago [24, 25]. It has been demonstrated in the touch panel for smart phone [26] and other transparent devices [27–29]. Then, the transparent films were printed with the inks of CNTs [30] or mixtures [31, 32]. The doping of Au nanoparticles could enhance the conductivity of CNT film [33]. Recently, the CNT-based transparent conducting film has been fabricated with blown aerosol technique assisted CVD [34], which demonstrated a high optoelectronic performance,

i.e., 90% transmittance and $40 \Omega \text{ sq}^{-1}$ sheet resistance. The upcoming opportunities remain in the roll-to-roll technique, blending of carbon nanotubes with the metal nanomesh for both improving the transmittance and conductivity as well as reducing the fabrication cost. In addition, the heat dissipation [35] could be a bonus when integrating CNTs into the smart phones.

2.3 Wearable and Stretchable Electronics

Wearable and stretchable electronic devices are often fabricated onto polymer materials [36, 37] or fabric [38, 39], which could be produced by fiber-to-yarn conversion compatible with textile manufacturing [40, 41]. The devices have advantages of stretchability for the production of sportswear [42], nano-energy generation [43], and implantable healthcare devices [44]. Due to the extraordinary mechanical and electronic properties of CNTs, they have been separated [45] and blended [46] into the polymer-based composite yarns for strain sensing [47], triboelectric energy production [48], and health monitoring [49]. Besides, the flexible CNT-based integrated circuits demonstrate the advantage of low energy consumption [50]. Future opportunities remain in the mechanical durability of materials and retention of device performances for long-term operation and wearing.

2.4 Mimicking Human Sensory Systems

The five conventional human sensory are vision, hearing, smell, taste, and touch [51–53]. With the processing and comprehension of these five types of sensing signals, the brain assists the human beings to understand the world and generate reflexes upon stimulus [54, 55]. Here, the update of the carbon nanotube-based sensors for mimicking the five sensory are briefly listed as follows (Fig. 2). First, CNT-based retina converts the projected image, i.e., illuminating light, into electrical pulses [56], which imitates the photo-detection [57] and guarantees machine vision [58]. Second, the eardrum was fabricated of CNT piezoresistance devices [59]. Third, the electronic nose detects the flavors with a chemoresistive sensor array [60, 61]. Forth, the electronic tongue can recognize the taste by the detection of liquid substances. Typically, electrochemical devices were employed for sensing the glucose [62] and tea taste [63]. Fifth, the tactile sensors lead to the development of electronic skins

Fig. 2 The system integration of carbon nanotubes-based artificial intelligence. Three kinds of devices compose the system, including the Internet of Things-based sensory, data processing, and response

[64–66]. The fusion of these five sensory will generate a precise acquisition of the environmental information by the smart sensor systems.

2.5 Healthcare Products

The CNT-based devices show great promises in healthcare and biomedical devices. The CNT materials have shown efficient therapy in musculoskeletal tumors [67], restoration of neural activity [68], engineering vascularized oriented tissues [69], and treatment of cancer [70, 71] as well as artificial joint materials [72]. Besides, CNT transistor-based sensors provide early diagnosis by acquiring the sodium concentration of sweat [73] and respiration gases [74]. The electronic skin based on piezoelectronics and synaptic transistor [75] provides promising intelligent prosthetics [76]. The strain engineering of CNTs leads to the health monitoring, i.e., the recognition of human motion [77, 78], the collection of arterial pulse waves [79], and electrocardiogram signals [80]. Future attention could be paid onto the implantable and biodegradable devices for medical curing, data processing [81] as well as multiple sensing platform for real-time health monitoring.

2.6 Actuators for Artificial Muscles

Carbon nanotubes sheets have been testified as electromechanical actuator for generating large stress and strain at several volts [82]. The CNTs, as actuation electrodes [83], were integrated and packaged into a nanofiber yarn, which formed an electrochemical cell by stacking the separator, electrodes, and electrolytes. Moreover, micrometer-scale robots [84] have been reported with electrochemical actuators driven by the voltage from silicon photovoltaic devices. It provides a universal platform [85] for incorporating half a century of knowledge in electronics techniques. Electromechanical SWCNT actuators have shown excellent performances with high stress and strain with the mechanism of double-layer charging [82].

Moreover, carbon nanotube aerogel has mimicked the function of artificial muscles and bionic soft robots in object motion. Yarns of graphene/CNT exhibit the role of artificial muscles [86]. Besides, the elastomer/CNT composite demonstrates high deformation capability upon photothermal stimuli [87]. Then, the elastomer/CNT composite renders an actuator for the shaping and locomotion of soft robotics [88].

2.7 Brain–Machine Interfaces

Neural interfaces [89] have been designed for direct communication with neural tissues. The CNT fiber has rendered an electrode for magnetic resonance imaging (MRI) examination [90]. Compared with commercial Pt/Ir electrode, the CNT fiber as a brain–machine interface [91] decreases its diameter to 5 nm with advantages of easy repositioning and long duration detection. Moreover, CNT fiber has been employed in the recordings and stimulations of neuronal electrical activity [92]. Close electrode–tissue contact with excellent electrical fidelity has been created with a composite of carbon nanotubes and poly(3,4-ethylenedioxythiophene) (PEDOT) as a thin interface layer [93]. The electrochemical impedance of such an electrode exhibits a 50 times reduction compared with a pure gold electrode with the stimulation of biological 1 kHz signal. Besides, a similar composite of CNT/DNA/silica provides an intimate interface for stem cell cultivation [94].

In addition, CNT/polyethylene terephthalate (PET) as a tape [95] has led to imaging and circuit analysis of brain ultrastructure analysis. Besides, the stretchable ionics based

on flexible hydrogels show promising applications in the human–machine interface [96].

2.8 Flexible Energy Storage Devices

Wearable electronics and the Internet of Things demand flexible and stretchable energy storage devices such as micro-supercapacitors [115, 116] and thin-film secondary ion batteries [117]. Indeed, commercial lithium-ion batteries and supercapacitors are generally rigid and heavy-weight. Therefore, stretchable energy storage emerges for satisfying integrated miniaturized energy storage [118] for consumer electronics [119]. This section briefly lists the recent advances for flexible energy storage devices, including materials innovation [120] and architecture development [121, 122].

One focuses on the anode materials when developing conventional lithium-ion batteries [123]. Indeed, various anode materials are based on carbon nanotubes. They are different composites such as yarns of carbon nanotubes and their fiber composite [118].

But for flexible lithium-ion batteries [124], the complete battery architecture shall be compatible with flexibility and stretchability. Indeed, thin-film lithium-ion batteries with solid electrolytes retain a large energy density. For example, porous textile conductor [125], as an alternative of metal collector, has shown high mass loading of anode materials and large capacity with flexibility. Moreover, CNT films have rendered the binder-free and current collector-free anode materials for the flexible lithium-ion batteries [126]. The efforts for fabricating low-cost secondary ion batteries are made in the intercalation and extraction of larger ions other than lithium ions [127], e.g., zinc [128], sodium [129], and potassium [130].

In addition, flexible CNT-based biofuel cells demonstrate a high-power density, which is conformal as integrated into a cotton textile cloth [131]. The fiber modified by enzyme/carbon nanotube composite guarantees the power supply when bending into an S shape. Besides, carbon nanotubes serve as metal-free catalyst [132], e.g., for flexible Li-CO₂ batteries [133].

Micro-supercapacitors serve as the flexible power sources with the advantages of long lifetime and high-power density. Different CNT/polymer composites have been developed for high-performance flexible supercapacitors [134]. The CNT/

poly(3-methylthiophene) composite provides high pseudocapacitance in an asymmetric supercapacitor [135]. Yarn of CNTs shows superior electrode performances in supercapacitors for textiles [136]. CNTs provide a large specific area for depositing MnO_2 of pseudocapacitance [137]. The supercapacitors show excellent gravimetric capacitance with electrodes of CVD grown helically coiled carbon nanotubes over carbon fiber. The CNT-based hybrid hydrogel demonstrates environmentally friendly electrode material with dissolving salt in water as an electrolyte for supercapacitor [138]. And the CNT aerogels provide high-rate capacitive performances [139].

Future opportunities in flexible supercapacitors emerge with continuously improving the areal and volumetric capacitance [140], large specific area [141], the handing rate, and the interfaces for coupling various energy nanogenerators. Besides, the CNT-based inks could facilitate the direct printing of supercapacitor electrodes [142]. The understanding of storage mechanisms matters for promoting the performances [143].

General requirements remain for both batteries [144] and supercapacitors, i.e., the lightweight [145], facile synthesis strategies [146], mass production, and mechanical stability [147]. Besides, the stretchability and conformal adhesion with textiles matters, i.e., CNT fibers could be woven into textiles as conducting electrodes for supercapacitors and batteries [148]. The continuous advances of CNT composites-based electrodes [149, 150] require the understanding of the performance enhancement mechanism by synergistic effect [151]. Besides, stretchable solid-state electrolytes are still required to match the available architecture of supercapacitor and batteries, such as cross-linked gel electrolyte or human sweat on carbon thread [152]. In addition, soft packing materials still recall efforts for their optimization and developments, such as human-skin comfortable materials [153] and self-healing polymers [154, 155]. Eventually, the safety and production costs are topmost for paving the way for practical products [156].

Besides, carbon nanotubes have shown the high capability of storing mechanical energy [157], e.g., flywheels for kinetic energy storage [158], which could be utilized in an uninterruptable power supply. CNT yarn twist can convert mechanical energy into electricity [159].

2.9 System Integration

In consumer electronics, the applied electronics as a system require the integration of multiple functional devices,

including sensing and signal processing, data communication, and data display. In the Internet of Things era, the wireless sensing becomes dominant. Here, CNT-based electronic systems employ the wireless communication modules including the Bluetooth communication [97], and data acquisition with WiFi route [98], RFID-based wireless data-transmitting sensor [99]. Besides, the human-machine interaction provides the approaches of obtaining human gesture and motion signals [100]. In addition, CNT devices guarantee the remotely controlled actuation [101], and wireless energy transfer [102]. The upcoming efforts should be put into the self-powered sensing system by energy harvesting from the environment and motion energy.

3 Materials Optimization Based on Machine Learning

The CNT synthesis has evolved continuously with the assistance of machine learning as well as the wafer-scale preparation (Fig. 3).

Machine learning for materials discovery. The quantum computational chemistry has boosted the materials science by providing structure–property relation [103]. With the aid of machine learning [104], the computational chemistry shows the capability of predication of the composition, structure, and properties of existing and unknown materials. Indeed, machine learning provides the design rule and guidelines for new materials findings [105–107].

Fig. 3 The upcoming machine learning algorithms for obtaining the properties, quality, and growth rate of carbon nanotube synthesis as well as the target of wafer-scale carbon nanotube synthesis

Furthermore, the chemical reaction processes could be calculated with machine learning [108, 109]. Two mainstreaming algorithms, i.e., support vector regression [110] and artificial neural networks [111], are being developed for optimizing the chemical processes, including the catalysis [112] and carbon nanotube growth [113].

Firstly, the machine learning based on support vector regression algorithm [110] leads to the direct generation of multiple parameters of the optimal synthesis conditions, which is superior to human-centered parameter optimization, viz., one can only optimize one individual parameter (other than several parameters) in the same synthesis operation. By such a set of optimal parameters, the synthetic carbon nanotubes show improved sheet resistance [110] by the floating-catalyst chemical vapor deposition.

Secondly, an artificial neural network algorithm-based machine learning has been utilized for the guide of experimental parameters over the synthetic CNT quality [111]. Indeed, five synthesis parameters, e.g., the pressure of feedstock, types of feedstocks, substrate temperature, and synthesis time, have been chosen as input for the machine learning. The calculated output data predict the quality of the synthetic CNTs, i.e., yield, tube diameter, and defects, which matches the characterization of experimentally synthetic CNTs well.

Third, the autonomy for material design and performance predictions has been developed by assembling a research robot, termed Autonomous Research System, with machine learning and artificial intelligence techniques [114]. Here, the growth rate of CNTs can be extracted by automated instrument operation for hundreds of experiments, with the assistance of *in situ* Raman characterization as closed-loop feedback. Indeed, such a robot based on machine learning may accelerate the materials discovery by reducing the participation of human resources and other production cost.

Wafer-scale deposition of aligned CNTs is highly preferred for the fabrications of transistor-based device arrays. Two mainstreaming routes remain for continuous evolution. One is the solution processing-based strategy [165, 166], which involves the dip-coating [167, 168] or vacuum filtration [169] of semiconducting nanotubes, after going through CVD production, dispersion, centrifugation, and sorting. At early stage, CNT thin-film transistors have been developed for integrated circuits [169] and artificial skins [170]. The CNT dispersions serve as inks, which are highly compatible with printed electronics [171]. Based on this

approach, functional devices based on individual carbon nanotube transistors have been fabricated for arithmetic logic unit [172], ring oscillators [173], analog amplifiers [174], and DNA recognition [175] applications. Also, the CNT transistors can be fabricated onto flexible biodegradable surfaces [176]. Besides, the carbon nanotube-based heterostructures have shown success in logic inverters [177], photodetectors [178], and solar cells [179]. The second route, termed dry processing [180], can be divided into two categories, i.e., direct CVD growth of horizontal CNTs over dielectric substrates [181] and stretching-pressing of CNT vertical forest film [182]. The horizontally aligned CNTs are preferable for individual CNT transistors [183] while the CNT films are good for thin-film transistors or conductors for touch screen and displays. The horizontally aligned CNTs have led to the iontronics and biocomputing [184]. Future efforts are still required for reducing the production cost and improving the compatibility with the Si-based processing techniques.

4 Perspective and Summary

The carbon nanotubes have been intensively investigated for near three decades, but controlled growth of SWCNTs with specific structure and properties remain still challenging. Recent progress on growing specific chirality SWCNTs indicates that catalyst design and growth kinetics are two key points. However, the mechanism of chirality-controlled growth is still unclear. Thanks to the recently developed advanced *in situ* techniques [160, 161], such as aberration-corrected environmental TEM and X-ray absorption, atomic scaled and dynamic information on catalyst and nanotube have been achieved [162]. However, the relation between CVD condition depended SWCNT growth kinetics is complicated to reveal with an *in situ* means, which bring more complex mechanisms [163]. More chiral SWCNTs with high purity need to be achieved by the precise catalyst design and modulation of growth conditions [164]. The cloning growth of SWCNTs from their segments is promising; however, the improvement of growth efficiency and chiral selectivity remain two challenges. Indeed, the control in synthesizing the specific chirality still requires excellent input from the community. Besides, the controlled CNT-based heterostructures become emerging trends for compatibility with device configurations.

In individual theoretical work, the entropy in thermodynamics has driven the formation of chirality-specific carbon nanotubes [185], which may enrich the big data of synthesis parameters and resultant features of carbon nanotubes. Therefore, big-data-driven research could accelerate the materials discovery and feedback the hardware for operating machine learning [186].

The physical and chemical properties of carbon nanotubes remain hot topics. First, the mechanical properties of individual chiral single-walled carbon nanotube are still of great interest, i.e., superlong fatigue lifetime [187]. Indeed, the noncontact acoustic resonance examination enables the *in situ* fatigue tests. Besides, high tensile strength beyond 80 GPa has been achieved with bundles of carbon nanotubes [188].

Breakthrough has been made on carbon nanotube-based electronics, e.g., carbon nanotube transistors, transparent conducting films, triboelectric nanogenerators, and electronic skins. Quite recently, the alignment of dense semiconducting carbon nanotubes has been reported with transistor performances [189], exceeding silicon techniques based on conventional metal–oxide–semiconductor configurations. The high integration density of CNT transistors with wafer-scale homogeneity may demonstrate superior to conventional silicon electronics. Recently, a 16-bit microprocessor has been fabricated with 14,000 CMOS CNT transistors [190]. Furthermore, the three-dimensional integration has emerged with incorporating the complete units of von Neumann architecture into one single chip [191], i.e., the central processor of CNT FET-based logic circuits, data storage with resistive random-access memory, input, and output. The device physics of individual single-walled carbon nanotube requires experimentally proven progress in theoretical predictions.

The development of memristors [192] and ionic floating-gate transistor arrays [193] have shed light on neuromorphic computing based on carbon nanotubes. The collaboration between materials scientists, computer engineers, neuroscientists is highly required to demonstrate a stretchable soft machine [194] and a neuromorphic computer system [195].

Printable dielectrics such as ion gel may shed light on the fabrication of high-performance flexible carbon nanotube transistors [171]. Moreover, the flexible and stretchable electronics based on carbon nanotubes continue to amaze society and the community with more breakthroughs.

In summary, SWCNTs have demonstrated enormous excellence in electronics, biosensing, artificial intelligence, and the Internet of Things. Indeed, the understanding of the chirality-controlled synthesis of carbon nanotubes has pushed closer its applications to industrial mass production.

Acknowledgements The authors acknowledge the financial funds of the National Key Research and Development Program of China (2016YFA0201904; 2017YFB0405400) and the Project of “20 items of University” of Jinan (2018GXRC031). W.Z thanks NSFC (No. 52022037) and Taishan Scholars Project Special Funds (tsqn201812083). J.P. shows his gratitude to the NSFC (51802116) and the Natural Science Foundation of Shandong Province, China (Grant No. ZR2019BEM040). F.Y. was supported by NSFC (52002165), Beijing National Laboratory for Molecular Science (BNLMS202013), Guangdong Provincial Natural Science Foundation (2021A1515010229), Shenzhen Basic Research Project (JCYJ20210317150714001), and the Innovation Project for Guangdong Provincial Department of Education (2019KTSCX155). M.H.R. thanks the National Science Foundation China (NSFC, Project 52071225), the National Science Center and the Czech Republic under the ERDF program “Institute of Environmental Technology—Excellent Research” (No. CZ.02.1.01/0.0/0.0/16_019/0000853) and the Sino-German Research Institute for support (Project No. GZ 1400).

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article’s Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article’s Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

1. J.M. Perkel, The internet of things comes to the lab. *Nature* **542**(7639), 125–126 (2017). <https://doi.org/10.1038/542125a>
2. R. Haight, W. Haensch, D. Friedman, ENGINEERING. solar-powering the internet of things. *Science* **353**(6295), 124–125 (2016). <https://doi.org/10.1126/science.aag0476>
3. E. Hittinger, P. Jaramillo, Internet of things: energy boon or bane? *Science* **364**(6438), 326–328 (2019). <https://doi.org/10.1126/science.aau8825>
4. M. Hvistendahl, China Pushes the “Internet of Things.” *Science* **336**(6086), 1223–1223 (2012). <https://doi.org/10.1126/science.336.6086.1223>

5. Q.F. Shi, B.W. Dong, T.Y.Y. He, Z.D. Sun, J.X. Zhu et al., Progress in wearable electronics/photronics-Moving toward the era of artificial intelligence and internet of things. *Info-Mat* **2**(6), 1131–1162 (2020). <https://doi.org/10.1002/inf2.12122>
6. J.A. Cardenas, J.B. Andrews, S.G. Noyce, A.D. Franklin, Carbon nanotube electronics for IoT sensors. *Nano Futures* **4**(1), 012001 (2020). <https://doi.org/10.1088/2399-1984/ab5f20>
7. E. Amram Bengio, D. Senic, L.W. Taylor, D.E. Tsentalovich, P. Chen et al., High efficiency carbon nanotube thread antennas. *Appl. Phys. Lett.* **111**(16), 163109 (2017)
8. E. Amram Bengio, D. Senic, L.W. Taylor, R.J. Headrick, M. King et al., Carbon nanotube thin film patch antennas for wireless communications. *Appl. Phys. Lett.* **114**(20), 203102 (2019)
9. B. Gervasi, Will carbon nanotube memory replace DRAM? *IEEE Micro* **39**(2), 45–51 (2019). <https://doi.org/10.1109/mm.2019.2897560>
10. Y. Sun, W. He, Z. Mao, H. Jiao, V. Kursun, Monolithic 3D carbon nanotube memory for enhanced yield and integration density. *IEEE Trans. Circuits Syst.* **67**(7), 2431–2441 (2020). <https://doi.org/10.1109/tcsi.2020.2980074>
11. P.S. Kanhaiya, C. Lau, G. Hills, M.D. Bishop, M.M. Shulaker, Carbon nanotube-based CMOS SRAM: 1 kbit 6T SRAM arrays and 10T SRAM cells. *IEEE Trans. Electron Devices* **66**(12), 5375–5380 (2019). <https://doi.org/10.1109/ted.2019.2945533>
12. X. Wang, K.-C. Chang, Z. Zhang, Q. Liu, L. Li et al., Performance enhancement and mechanism exploration of all-carbon-nanotube memory with hydroxylation and dehydration through supercritical carbon dioxide. *Carbon* **173**(88), 97–104 (2021). <https://doi.org/10.1016/j.carbon.2020.10.084>
13. T.Y. Qu, Y. Sun, M.L. Chen, Z.B. Liu, Q.B. Zhu et al., A flexible carbon nanotube sen-memory device. *Adv. Mater.* **32**(9), 1907288 (2020). <https://doi.org/10.1002/adma.201907288>
14. S. Kim, M. Amjadi, T.I. Lee, Y. Jeong, D. Kwon et al., Wearable, ultrawide-range, and bending-insensitive pressure sensor based on carbon nanotube network-coated porous elastomer sponges for human interface and healthcare devices. *ACS Appl. Mater. Interfaces* **11**(26), 23639–23648 (2019). <https://doi.org/10.1021/acsami.9b07636>
15. G. Choi, H. Jang, S. Oh, H. Cho, H. Yoo et al., A highly sensitive and stress-direction-recognizing asterisk-shaped carbon nanotube strain sensor. *J. Mater. Chem. C* **7**(31), 9504–9512 (2019). <https://doi.org/10.1039/c9tc02486g>
16. W. Lee, H. Koo, J. Sun, J. Noh, K.S. Kwon et al., A fully roll-to-roll gravure-printed carbon nanotube-based active matrix for multi-touch sensors. *Sci. Rep.* **5**(88), 17707 (2015). <https://doi.org/10.1038/srep17707>
17. T.Y. Zhao, D.D. Zhang, T.Y. Qu, L.L. Fang, Q.B. Zhu et al., Flexible 64 x 64 pixel AMOLED displays driven by uniform carbon nanotube thin-film transistors. *ACS Appl. Mater. Interfaces* **11**(12), 11699–11705 (2019). <https://doi.org/10.1021/acsami.8b17909>
18. Y.C. Kim, S.H. Park, C.S. Lee, T.W. Chung, E. Cho et al., A 46-inch diagonal carbon nanotube field emission backlight for liquid crystal display. *Carbon* **91**(88), 304–310 (2015). <https://doi.org/10.1016/j.carbon.2015.04.093>
19. M.A. McCarthy, B. Liu, E.P. Donoghue, I. Kravchenko, D.Y. Kim et al., Low-voltage, low-power, organic light-emitting transistors for active matrix displays. *Science* **332**(6029), 570–573 (2011). <https://doi.org/10.1126/science.1203052>
20. C. Wang, J. Zhang, K. Ryu, A. Badmaev, L.G. De Arco et al., Wafer-scale fabrication of separated carbon nanotube thin-film transistors for display applications. *Nano Lett.* **9**(12), 4285–4291 (2009). <https://doi.org/10.1021/nl902522f>
21. R. Ho, C. Lau, G. Hills, M.M. Shulaker, Carbon nanotube CMOS analog circuitry. *IEEE Trans. Nanotechn.* **18**(88), 845–848 (2019). <https://doi.org/10.1109/tnano.2019.2902739>
22. D. Suzuki, Y. Kawano, Flexible terahertz imaging systems with single-walled carbon nanotube films. *Carbon* **162**(88), 13–24 (2020). <https://doi.org/10.1016/j.carbon.2020.01.113>
23. W.A. Gaviria Rojas, J.J. McMorow, M.L. Geier, Q. Tang, C.H. Kim et al., Solution-processed carbon nanotube true random number generator. *Nano Lett.* **17**(8), 4976–4981 (2017)
24. A. Sandhu, Strictly nanotubes in Beijing. *Nat. Nanotechnol.* **4**(7), 398–399 (2009). <https://doi.org/10.1038/nnano.2009.164>
25. C. Feng, K. Liu, J.-S. Wu, L. Liu, J.-S. Cheng et al., Flexible, stretchable, transparent conducting films made from super-aligned carbon nanotubes. *Adv. Funct. Mater.* **20**(6), 885–891 (2010). <https://doi.org/10.1002/adfm.200901960>
26. L. Yu, C. Shearer, J. Shapter, Recent development of carbon nanotube transparent conductive films. *Chem. Rev.* **116**(22), 13413–13453 (2016). <https://doi.org/10.1021/acs.chemrev.6b00179>
27. D. Chen, K. Jiang, T. Huang, G. Shen, Recent advances in fiber supercapacitors: materials, device configurations, and applications. *Adv. Mater.* **32**(5), 1901806 (2020). <https://doi.org/10.1002/adma.201901806>
28. F.N. Ishikawa, H.K. Chang, K. Ryu, P.C. Chen, A. Badmaev et al., Transparent electronics based on transfer printed aligned carbon nanotubes on rigid and flexible substrates. *ACS Nano* **3**(1), 73–79 (2009). <https://doi.org/10.1021/nn800434d>
29. P.-C. Chen, G. Shen, S. Sukcharoenchoke, C. Zhou, Flexible and transparent supercapacitor based on In₂O₃ nanowire/carbon nanotube heterogeneous films. *Appl. Phys. Lett.* **94**(4), 043113 (2009). <https://doi.org/10.1063/1.3069277>
30. Y. He, H. Jin, S. Qiu, Q. Li, A novel strategy for high-performance transparent conductive films based on double-walled carbon nanotubes. *Chem. Commun.* **53**(20), 2934–2937 (2017). <https://doi.org/10.1039/c6cc10252b>
31. E. Roh, B.U. Hwang, D. Kim, B.Y. Kim, N.E. Lee, Stretchable, transparent, ultrasensitive, and patchable strain sensor for human-machine interfaces comprising a nanohybrid of carbon nanotubes and conductive elastomers. *ACS Nano* **9**(6), 6252–6261 (2015). <https://doi.org/10.1021/acs.nano.5b01613>

32. P.M. Martinez, A. Ishteev, A. Fahimi, J. Velten, I. Jurewicz et al., Silver nanowires on carbon nanotube aerogel sheets for flexible, transparent electrodes. *ACS Appl. Mater. Interfaces* **11**(35), 32235–32243 (2019). <https://doi.org/10.1021/acsami.9b06368>
33. A.E. Goldt, O.T. Zaremba, M.O. Bulavskiy, F.S. Fedorov, K.V. Larionov et al., Highly efficient bilateral doping of single-walled carbon nanotubes. *J. Mater. Chem. C* **9**(13), 4514–4521 (2021). <https://doi.org/10.1039/d0tc05996j>
34. Q. Zhang, W. Zhou, X. Xia, K. Li, N. Zhang et al., Transparent and freestanding single-walled carbon nanotube films synthesized directly and continuously via a blown aerosol technique. *Adv. Mater.* **32**(39), 2004277 (2020). <https://doi.org/10.1002/adma.202004277>
35. W. Yu, C.H. Liu, S.S. Fan, High water-absorbent and phase-change heat dissipation materials based on super-aligned cross-stack CNT films. *Adv. Engin. Mater.* **21**(5), 1801216 (2019). <https://doi.org/10.1002/adem.201801216>
36. J.A. Rogers, T. Someya, Y. Huang, Materials and mechanics for stretchable electronics. *Science* **327**(5973), 1603–1607 (2010). <https://doi.org/10.1126/science.1182383>
37. L. Xiang, H. Zhang, Y. Hu, L.-M. Peng, Carbon nanotube-based flexible electronics. *J. Mater. Chem. C* **6**(29), 7714–7727 (2018). <https://doi.org/10.1039/c8tc02280a>
38. Z. Ma, Q. Huang, Q. Xu, Q. Zhuang, X. Zhao et al., Permeable superelastic liquid-metal fibre mat enables biocompatible and monolithic stretchable electronics. *Nat. Mater.* **20**(6), 859–868 (2021). <https://doi.org/10.1038/s41563-020-00902-3>
39. D.C. Kim, H.J. Shim, W. Lee, J.H. Koo, D.H. Kim, Material-based approaches for the fabrication of stretchable electronics. *Adv. Mater.* **32**(15), 1902743 (2020). <https://doi.org/10.1002/adma.201902743>
40. K. Qi, Y. Zhou, K. Ou, Y. Dai, X. You et al., Weavable and stretchable piezoresistive carbon nanotubes-embedded nanofiber sensing yarns for highly sensitive and multimodal wearable textile sensor. *Carbon* **170**(88), 464–476 (2020). <https://doi.org/10.1016/j.carbon.2020.07.042>
41. H. Kim, T.H. Kang, J. Ahn, H. Han, S. Park et al., Spirally wrapped carbon nanotube microelectrodes for fiber optoelectronic devices beyond geometrical limitations toward smart wearable E-textile applications. *ACS Nano* **14**(15), 17213–17223 (2020). <https://doi.org/10.1021/acsnano.0c07143>
42. N. Matsuhisa, X. Chen, Z. Bao, T. Someya, Materials and structural designs of stretchable conductors. *Chem. Soc. Rev.* **48**(11), 2946–2966 (2019). <https://doi.org/10.1039/c8cs00814k>
43. H. Wu, Y. Huang, F. Xu, Y. Duan, Z. Yin, Energy harvesters for wearable and stretchable electronics: from flexibility to stretchability. *Adv. Mater.* **28**(45), 9881–9919 (2016). <https://doi.org/10.1002/adma.201602251>
44. Y.J. Hong, H. Jeong, K.W. Cho, N. Lu, D.H. Kim, Wearable and implantable devices for cardiovascular healthcare: from monitoring to therapy based on flexible and stretchable electronics. *Adv. Funct. Mater.* **29**(19), 1808247 (2019). <https://doi.org/10.1002/adfm.201808247>
45. T. Lei, I. Pochorovski, Z. Bao, Separation of semiconducting carbon nanotubes for flexible and stretchable electronics using polymer removable method. *Acc. Chem. Res.* **50**(4), 1096–1104 (2017). <https://doi.org/10.1021/acs.accounts.7b00062>
46. E. Oh, T. Kim, J. Yoon, S. Lee, D. Kim et al., Highly reliable liquid metal-solid metal contacts with a corrugated single-walled carbon nanotube diffusion barrier for stretchable electronics. *Adv. Funct. Mater.* **28**(51), 1806014 (2018). <https://doi.org/10.1002/adfm.201806014>
47. J. Lee, S. Pyo, D.S. Kwon, E. Jo, W. Kim et al., Ultrasensitive strain sensor based on separation of overlapped carbon nanotubes. *Small* **15**(12), 1805120 (2019). <https://doi.org/10.1002/sml.201805120>
48. M. Matsunaga, J. Hirotani, S. Kishimoto, Y. Ohno, High-output, transparent, stretchable triboelectric nanogenerator based on carbon nanotube thin film toward wearable energy harvesters. *Nano Energy* **67**(88), 104297 (2020). <https://doi.org/10.1016/j.nanoen.2019.104297>
49. Y. Liu, M. Pharr, G.A. Salvatore, Lab-on-skin: a review of flexible and stretchable electronics for wearable health monitoring. *ACS Nano* **11**(10), 9614–9635 (2017). <https://doi.org/10.1021/acsnano.7b04898>
50. T. Lei, L.L. Shao, Y.Q. Zheng, G. Pitner, G. Fang et al., Low-voltage high-performance flexible digital and analog circuits based on ultrahigh-purity semiconducting carbon nanotubes. *Nat. Commun.* **10**(1), 2161 (2019). <https://doi.org/10.1038/s41467-019-10145-9>
51. T. Li, Y. Li, T. Zhang, Materials, structures, and functions for flexible and stretchable biomimetic sensors. *Acc. Chem. Res.* **52**(2), 288–296 (2019). <https://doi.org/10.1021/acs.accounts.8b00497>
52. F. Sun, Q. Lu, S. Feng, T. Zhang, Flexible artificial sensory systems based on neuromorphic devices. *ACS Nano* **15**(3), 3875–3899 (2021). <https://doi.org/10.1021/acsnano.0c10049>
53. Y. Ma, H. Li, S. Chen, Y. Liu, Y. Meng et al., Skin-like electronics for perception and interaction: materials, structural designs, and applications. *Adv. Intell. Syst.* **3**(4), 2000108 (2020). <https://doi.org/10.1002/aisy.202000108>
54. Q. Zhang, L. Tan, Y. Chen, T. Zhang, W. Wang et al., Human-like sensing and reflexes of graphene-based films. *Adv. Sci.* **3**(12), 1600130 (2016). <https://doi.org/10.1002/advs.201600130>
55. Y.H. Jung, B. Park, J.U. Kim, T.I. Kim, Bioinspired electronics for artificial sensory systems. *Adv. Mater.* **31**(34), 1803637 (2019). <https://doi.org/10.1002/adma.201803637>
56. L. Bareket, N. Waiskopf, D. Rand, G. Lubin, M. David-Pur et al., Semiconductor nanorod-carbon nanotube biomimetic films for wire-free photostimulation of blind retinas. *Nano Lett.* **14**(11), 6685–6692 (2014). <https://doi.org/10.1021/nl5034304>
57. Y. Liu, N. Wei, Q. Zeng, J. Han, H. Huang et al., Room temperature broadband infrared carbon nanotube photodetector with high detectivity and stability. *Adv. Opt. Mater.* **4**(2), 238–245 (2016). <https://doi.org/10.1002/adom.201500529>

58. D. Berco, D. Shenp Ang, Recent progress in synaptic devices paving the way toward an artificial cogni-retina for bionic and machine vision. *Adv. Intell. Syst.* **1**(1), 1900003 (2019). <https://doi.org/10.1002/aisy.201900003>
59. Y. Gu, X. Wang, W. Gu, Y. Wu, T. Li et al., Flexible electronic eardrum. *Nano Res.* **10**(8), 2683–2691 (2017). <https://doi.org/10.1007/s12274-017-1470-1>
60. S. Orzechowska, A. Mazurek, R. Swislocka, W. Lewandowski, Electronic nose: recent developments in gas sensing and molecular mechanisms of graphene detection and other materials. *Materials* **13**(1), 80 (2019). <https://doi.org/10.3390/ma13010080>
61. S.Y. Park, Y. Kim, T. Kim, T.H. Eom, S.Y. Kim et al., Chemoresistive materials for electronic nose: Progress, perspectives, and challenges. *InfoMat* **1**(3), 289–316 (2019). <https://doi.org/10.1002/inf2.12029>
62. T. Zhu, Y. Zhang, L. Luo, X. Zhao, Facile fabrication of NiO-decorated double-layer single-walled carbon nanotube buckypaper for glucose detection. *ACS Appl. Mater. Interfaces* **11**(11), 10856–10861 (2019). <https://doi.org/10.1021/acsami.9b00803>
63. N.A. Fikri, A.H. Adom, A.YMd. Shakaff, M.N. Ahmad, A.H. Abdullah et al., Development of human sensory mimicking system. *Sensor Lett.* **9**(1), 423–427 (2011). <https://doi.org/10.1166/sl.2011.1492>
64. L.Y. Hsiao, L. Jing, K.R. Li, H.T. Yang, Y. Li et al., Carbon nanotube-integrated conductive hydrogels as multifunctional robotic skin. *Carbon* **161**(88), 784–793 (2020). <https://doi.org/10.1016/j.carbon.2020.01.109>
65. A. Chortos, J. Liu, Z. Bao, Pursuing prosthetic electronic skin. *Nat. Mater.* **15**(9), 937–950 (2016). <https://doi.org/10.1038/nmat4671>
66. X. Wang, L. Dong, H. Zhang, R. Yu, C. Pan et al., Recent progress in electronic skin. *Adv. Sci.* **2**(10), 1500169 (2015). <https://doi.org/10.1002/advs.201500169>
67. K. Aoki, N. Ogihara, M. Tanaka, H. Haniu, N. Saito, Carbon nanotube-based biomaterials for orthopaedic applications. *J. Mater. Chem. B* **8**(40), 9227–9238 (2020). <https://doi.org/10.1039/d0tb01440k>
68. V. Mathur, S. Talapatra, S. Kar, Z. Hennighausen, In vivo partial restoration of neural activity across severed mouse spinal cord bridged with ultralong carbon nanotubes. *ACS Appl. BioMater.* **4**(5), 4071–4078 (2021). <https://doi.org/10.1021/acsabm.1c00248>
69. Y. Fang, L. Ouyang, T. Zhang, C. Wang, B. Lu et al., Optimizing bifurcated channels within an anisotropic scaffold for engineering vascularized oriented tissues. *Adv. Healthc. Mater.* **9**(24), 2000782 (2020). <https://doi.org/10.1002/adhm.202000782>
70. J. Chen, L. Wang, T. Wang, C. Li, W. Han et al., Functionalized carbon nanotube-embedded poly(vinyl alcohol) microspheres for efficient removal of tumor necrosis factor- α . *ACS Biomater. Sci. Eng.* **6**(8), 4722–4730 (2020). <https://doi.org/10.1021/acsbiomaterials.9b01916>
71. W. Chen, S. Yang, X. Wei, Z. Yang, D. Liu et al., Construction of aptamer-siRNA chimera/PEI/5-FU/carbon nanotube/collagen membranes for the treatment of peritoneal dissemination of drug-resistant gastric cancer. *Adv. Healthc. Mater.* **9**(21), 2001153 (2020). <https://doi.org/10.1002/adhm.202001153>
72. A. Sobajima, T. Okihara, S. Moriyama, N. Nishimura, T. Osawa et al., Multiwall carbon nanotube composites as artificial joint materials. *ACS Biomater. Sci. Eng.* **6**(12), 7032–7040 (2020). <https://doi.org/10.1021/acsbiomaterials.0c00916>
73. S.-C. Park, H.J. Jeong, M. Heo, J.H. Shin, J.-H. Ahn, Carbon nanotube-based ion-sensitive field-effect transistors with an on-chip reference electrode toward wearable sodium sensing. *ACS Appl. Electron. Mater.* **3**(6), 2580–2588 (2021). <https://doi.org/10.1021/acsaelm.1c00152>
74. T. Nguyen, T. Dinh, V.T. Dau, C.-D. Tran, H.-P. Phan et al., A wearable, bending-insensitive respiration sensor using highly oriented carbon nanotube film. *IEEE Sens. J.* **21**(6), 7308–7315 (2021). <https://doi.org/10.1109/jsen.2020.3048236>
75. H. Wan, Y. Cao, L.W. Lo, J. Zhao, N. Sepulveda et al., Flexible carbon nanotube synaptic transistor for neurological electronic skin applications. *ACS Nano* **14**(8), 10402–10412 (2020). <https://doi.org/10.1021/acsnano.0c04259>
76. H. Xu, Y. Xie, E. Zhu, Y. Liu, Z. Shi et al., Supertough and ultrasensitive flexible electronic skin based on nanocellulose/sulfonated carbon nanotube hydrogel films. *J. Mater. Chem. A* **8**(13), 6311–6318 (2020). <https://doi.org/10.1039/d0ta00158a>
77. T. Yamada, Y. Hayamizu, Y. Yamamoto, Y. Yomogida, A. Izadi-Najafabadi et al., A stretchable carbon nanotube strain sensor for human-motion detection. *Nat. Nanotechnol.* **6**(5), 296–301 (2011). <https://doi.org/10.1038/nnano.2011.36>
78. K.-H. Kim, S.K. Hong, S.-H. Ha, L. Li, H.W. Lee et al., Enhancement of linearity range of stretchable ultrasensitive metal crack strain sensor via superaligned carbon nanotube-based strain engineering. *Mater. Horizons* **7**(10), 2662–2672 (2020). <https://doi.org/10.1039/d0mh00806k>
79. G. Zu, X. Wang, K. Kanamori, K. Nakanishi, Superhydrophobic highly flexible doubly cross-linked aerogel/carbon nanotube composites as strain/pressure sensors. *J. Mater. Chem. B* **8**(22), 4883–4889 (2020). <https://doi.org/10.1039/c9tb02953b>
80. X.W. Xu, Y.C. Chen, P. He, S. Wang, K. Ling et al., Wearable CNT/Ti₃C₂T_x MXene/PDMS composite strain sensor with enhanced stability for real-time human healthcare monitoring. *Nano Res.* **14**(8), 2875–2883 (2021). <https://doi.org/10.1007/s12274-021-3536-3>
81. K. Umapathi, V. Vanitha, L. Anbarasu, M. Zivkovic, N. Bacanin et al., Predictive data regression technique based carbon nanotube biosensor for efficient patient health monitoring system. *J. Ambient Intell. Humanized Comput.* (2021). <https://doi.org/10.1007/s12652-021-03063-6>
82. R.H. Baughman, C. Cui, A.A. Zakhidov, Z. Iqbal, J.N. Barisci et al., Carbon nanotube actuators. *Science* **284**(5418), 1340–1344 (1999). <https://doi.org/10.1126/science.284.5418.1340>

83. R.H. Baughman, Materials science. Playing nature's game with artificial muscles. *Science* **308**(5718), 63–65 (2005)
84. M.Z. Miskin, A.J. Cortese, K. Dorsey, E.P. Esposito, M.F. Reynolds et al., Electronically integrated, mass-manufactured, microscopic robots. *Nature* **584**(7822), 557–561 (2020). <https://doi.org/10.1038/s41586-020-2626-9>
85. A.M. Brooks, M.S. Strano, A conceptual advance that gives microrobots legs. *Nature* **584**(7822), 530–531 (2020). <https://doi.org/10.1038/d41586-020-02421-2>
86. J.S. Hyeon, J.W. Park, R.H. Baughman, S.J. Kim, Electrochemical graphene/carbon nanotube yarn artificial muscles. *Sens. Actuators B* **286**(88), 237–242 (2019). <https://doi.org/10.1016/j.snb.2019.01.140>
87. H. Kim, J.A. Lee, C.P. Ambulo, H.B. Lee, S.H. Kim et al., Intelligently actuating liquid crystal elastomer-carbon nanotube composites. *Adv. Funct. Mater.* **29**(48), 1905063 (2019). <https://doi.org/10.1002/adfm.201905063>
88. J. Liu, Y. Gao, H. Wang, R. Poling-Skutvik, C.O. Osuji et al., Shaping and locomotion of soft robots using filament actuators made from liquid crystal elastomer-carbon nanotube composites. *Adv. Intell. Syst.* **2**(6), 1900163 (2020). <https://doi.org/10.1002/aisy.201900163>
89. G.H. Kim, K. Kim, E. Lee, T. An, W. Choi et al., Recent progress on microelectrodes in neural interfaces. *Materials* **11**(10), 1995 (2018). <https://doi.org/10.3390/ma11101995>
90. L. Lu, X. Fu, Y. Liew, Y. Zhang, S. Zhao et al., Soft and MRI compatible neural electrodes from carbon nanotube fibers. *Nano Lett.* **19**(3), 1577–1586 (2019). <https://doi.org/10.1021/acs.nanolett.8b04456>
91. S. Waldert, (2016) Invasive vs. non-invasive neuronal signals for brain-machine interfaces: will one prevail? *Front. Neurosci* <https://doi.org/10.3389/fnins.2016.00295>
92. N.T. Alvarez, E. Buschbeck, S. Miller, A.D. Le, V.K. Gupta et al., Carbon nanotube fibers for neural recording and stimulation. *ACS Appl. Bio-Mater.* **3**(9), 6478–6487 (2020). <https://doi.org/10.1021/acsabm.0c00861>
93. N. Chen, B. Luo, A.C. Patil, J. Wang, G.G.L. Gammad et al., Nanotunnels within poly(3,4-ethylenedioxythiophene)-carbon nanotube composite for highly sensitive neural interfacing. *ACS Nano* **14**(7), 8059–8073 (2020). <https://doi.org/10.1021/acsnano.0c00672>
94. Y. Hu, C.M. Dominguez, J. Bauer, S. Weigel, A. Schipperges et al., Carbon-nanotube reinforcement of DNA-silica nanocomposites yields programmable and cell-instructive biocoatings. *Nat. Commun.* **10**(1), 5522 (2019). <https://doi.org/10.1038/s41467-019-13381-1>
95. Y. Kubota, J. Sohn, S. Hatada, M. Schurr, J. Straehle et al., A carbon nanotube tape for serial-section electron microscopy of brain ultrastructure. *Nat. Commun.* **9**(1), 437 (2018). <https://doi.org/10.1038/s41467-017-02768-7>
96. H.R. Lee, C.C. Kim, J.Y. Sun, Stretchable ionics - a promising candidate for upcoming wearable devices. *Adv. Mater.* **30**(42), 1704403 (2018). <https://doi.org/10.1002/adma.201704403>
97. J.B. Andrews, J.A. Cardenas, C.J. Lim, S.G. Noyce, J. Mullett et al., Fully printed and flexible carbon nanotube transistors for pressure sensing in automobile tires. *IEEE Sens. J.* **18**(19), 7875–7880 (2018). <https://doi.org/10.1109/jsen.2018.2842139>
98. M. He, R.G. Croy, J.M. Essigmann, T.M. Swager, Chemiresistive carbon nanotube sensors for N-nitrosodialkylamines. *ACS Sens.* **4**(10), 2819–2824 (2019). <https://doi.org/10.1021/acssensors.9b01532>
99. P. Gou, N.D. Kraut, I.M. Feigel, H. Bai, G.J. Morgan et al., Carbon nanotube chemiresistor for wireless pH sensing. *Sci. Rep.* **4**(88), 4468 (2014). <https://doi.org/10.1038/srep04468>
100. L. Zhang, J. He, Y. Liao, X. Zeng, N. Qiu et al., A self-protective, reproducible textile sensor with high performance towards human-machine interactions. *J. Mater. Chem. A* **7**(46), 26631–26640 (2019). <https://doi.org/10.1039/c9ta10744d>
101. Y. Liu, F. Zhang, J. Leng, K. Fu, X.L. Lu et al., Remotely and sequentially controlled actuation of electroactivated carbon nanotube/shape memory polymer composites. *Adv. Mater. Technol.* **4**(12), 1900600 (2019). <https://doi.org/10.1002/admt.201900600>
102. C.B. Sweeney, A.G. Moran, J.T. Gruener, A.M. Strasser, M.J. Pospisil et al., Radio frequency heating of carbon nanotube composite materials. *ACS Appl. Mater. Interfaces* **10**(32), 27252–27259 (2018). <https://doi.org/10.1021/acsami.8b06268>
103. K.T. Butler, D.W. Davies, H. Cartwright, O. Isayev, A. Walsh, Machine learning for molecular and materials science. *Nature* **559**(7715), 547–555 (2018). <https://doi.org/10.1038/s41586-018-0337-2>
104. M.I. Jordan, T.M. Mitchell, Machine learning: trends, perspectives, and prospects. *Science* **349**(6245), 255–260 (2015). <https://doi.org/10.1126/science.aaa8415>
105. M. Umehara, H.S. Stein, D. Guevarra, P.F. Newhouse, D.A. Boyd et al., (2019) Analyzing machine learning models to accelerate generation of fundamental materials insights. *npj Comput. Mater.* **5**(1), 34
106. K. Kaufmann, C. Zhu, A.S. Rosengarten, D. Maryanovsky, T.J. Harrington et al., Crystal symmetry determination in electron diffraction using machine learning. *Science* **367**(6477), 564–568 (2020). <https://doi.org/10.1126/science.aay3062>
107. B. Sanchez-Lengeling, A. Aspuru-Guzik, Inverse molecular design using machine learning: generative models for matter engineering. *Science* **361**(6400), 360–365 (2018). <https://doi.org/10.1126/science.aat2663>
108. Z. Zhou, X. Li, R.N. Zare, Optimizing Chemical Reactions with Deep Reinforcement Learning. *ACS Cent Sci.* **3**(12), 1337–1344 (2017). <https://doi.org/10.1021/acscentsci.7b00492>
109. Z. Li, S. Wang, H. Xin, Toward artificial intelligence in catalysis. *Nat. Catal.* **1**(9), 641–642 (2018). <https://doi.org/10.1038/s41929-018-0150-1>
110. E.M. Khabushev, D.V. Krasnikov, O.T. Zaremba, A.P. Tsapenko, A.E. Goldt et al., Machine learning for tailoring

- optoelectronic properties of single-walled carbon nanotube films. *J. Phys. Chem. Lett.* **10**(21), 6962–6966 (2019). <https://doi.org/10.1021/acs.jpclett.9b02777>
111. V.Y. Iakovlev, D.V. Krasnikov, E.M. Khabushev, J.V. Kolodiazhaia, A.G. Nasibulin, Artificial neural network for predictive synthesis of single-walled carbon nanotubes by aerosol CVD method. *Carbon* **153**(88), 100–103 (2019). <https://doi.org/10.1016/j.carbon.2019.07.013>
 112. S. Kapse, S. Janwari, U.V. Waghmare, R. Thapa, Energy parameter and electronic descriptor for carbon based catalyst predicted using QM/ML. *Appl. Catal. B* **286**(88), 119866 (2021). <https://doi.org/10.1016/j.apcatb.2020.119866>
 113. Z.-H. Ji, L. Zhang, D.-M. Tang, C.-M. Chen, T.E.M. Nordling et al., High-throughput screening and machine learning for the efficient growth of high-quality single-wall carbon nanotubes. *Nano Res.* (2021). <https://doi.org/10.1007/s12274-021-3387-y>
 114. P. Nikolaev, D. Hooper, F. Webber, R. Rao, K. Decker et al., Autonomy in materials research: a case study in carbon nanotube growth. *npj Comput. Mater.* **2**(1), 16031 (2016). <https://doi.org/10.1038/npjcompumats.2016.31>
 115. C. Cao, Y. Zhou, S. Ubnoske, J. Zang, Y. Cao et al., Highly stretchable supercapacitors via crumpled vertically aligned carbon nanotube forests. *Adv. Energy Mater.* **9**(22), 1900618 (2019). <https://doi.org/10.1002/aenm.201900618>
 116. Y. Wang, Y. Zhang, G. Wang, X. Shi, Y. Qiao et al., Direct graphene-carbon nanotube composite ink writing all-solid-state flexible microsupercapacitors with high areal energy density. *Adv. Funct. Mater.* **30**(16), 1907284 (2020). <https://doi.org/10.1002/adfm.201907284>
 117. C.J. Zhang, S.H. Park, O. Ronan, A. Harvey, A. Seral-Ascaso et al., Enabling flexible heterostructures for Li-ion battery anodes based on nanotube and liquid-phase exfoliated 2D gallium chalcogenide nanosheet colloidal solutions. *Small* **13**(34), 1701677 (2017). <https://doi.org/10.1002/sml.201701677>
 118. E.B. Pomerantseva, Francesco Feng, Xinliang Cui, Yi Gogotsi, Yury, Energy storage: The future enabled by nanomaterials. *Science* **366**(6468), eaan8285 (2019). <https://doi.org/10.1126/science.aan8285>
 119. T.J. Mun, S.H. Kim, J.W. Park, J.H. Moon, Y. Jang et al., Wearable energy generating and storing textile based on carbon nanotube yarns. *Adv. Funct. Mater.* **30**(23), 2000411 (2020). <https://doi.org/10.1002/adfm.202000411>
 120. I.A. Kinloch, J. Suhr, J. Lou, R.J. Young, P.M. Ajayan, Composites with carbon nanotubes and graphene: an outlook. *Science* **362**(6414), 547–553 (2018). <https://doi.org/10.1126/science.aat7439>
 121. T. Lv, Y. Yao, N. Li, T. Chen, Wearable fiber-shaped energy conversion and storage devices based on aligned carbon nanotubes. *Nano Today* **11**(5), 644–660 (2016). <https://doi.org/10.1016/j.nantod.2016.08.010>
 122. W. Lyu, W. Zhang, H. Liu, Y. Liu, H. Zuo et al., Conjugated microporous polymer network grafted carbon nanotube fibers with tunable redox activity for efficient flexible wearable energy storage. *Chem. Mater.* **32**(19), 8276–8285 (2020). <https://doi.org/10.1021/acs.chemmater.0c02089>
 123. Z. Guo, H. Nie, Z. Yang, W. Hua, C. Ruan et al., 3D CNTs/graphene-S-Al₃Ni₂ cathodes for high-sulfur-loading and long-life lithium-sulfur batteries. *Adv. Sci.* **5**(7), 1800026 (2018). <https://doi.org/10.1002/adv.201800026>
 124. Z. Fang, J. Wang, H. Wu, Q. Li, S. Fan et al., Progress and challenges of flexible lithium ion batteries. *J. Power Sources* **454**(88), 227932 (2020). <https://doi.org/10.1016/j.jpowsour.2020.227932>
 125. L. Hu, F. La Mantia, H. Wu, X. Xie, J. McDonough et al., Lithium-ion textile batteries with large areal mass loading. *Adv. Energy Mater.* **1**(6), 1012–1017 (2011). <https://doi.org/10.1002/aenm.201100261>
 126. S. Yoon, S. Lee, S. Kim, K.-W. Park, D. Cho et al., Carbon nanotube film anodes for flexible lithium ion batteries. *J. Power Sources* **279**(88), 495–501 (2015). <https://doi.org/10.1016/j.jpowsour.2015.01.013>
 127. H. Geng, Y. Peng, L. Qu, H. Zhang, M. Wu, Structure design and composition engineering of carbon-based nanomaterials for lithium energy storage. *Adv. Energy Mater.* **10**(10), 1903030 (2020). <https://doi.org/10.1002/aenm.201903030>
 128. F. Wan, S. Huang, H. Cao, Z. Niu, Freestanding potassium vanadate/carbon nanotube films for ultralong-life aqueous zinc-ion batteries. *ACS Nano* **14**(6), 6752–6760 (2020). <https://doi.org/10.1021/acs.nano.9b10214>
 129. S. Shi, C. Sun, X. Yin, L. Shen, Q. Shi et al., FeP quantum dots confined in carbon-nanotube-grafted P-doped carbon octahedra for high-rate sodium storage and full-cell applications. *Adv. Funct. Mater.* **30**(10), 1909283 (2020). <https://doi.org/10.1002/adfm.201909283>
 130. S. Zhang, G. Wang, B. Wang, J. Wang, J. Bai et al., 3D carbon nanotube network bridged hetero-structured Ni-Fe-S nanocubes toward high-performance lithium, sodium, and potassium storage. *Adv. Funct. Mater.* **30**(24), 2001592 (2020). <https://doi.org/10.1002/adfm.202001592>
 131. S. Yin, Z. Jin, T. Miyake, Wearable high-powered biofuel cells using enzyme/carbon nanotube composite fibers on textile cloth. *Biosens. Bioelectron.* **141**(88), 111471 (2019). <https://doi.org/10.1016/j.bios.2019.111471>
 132. C. Hu, Y. Lin, J.W. Connell, H.M. Cheng, Y. Gogotsi et al., Carbon-based metal-free catalysts for energy storage and environmental remediation. *Adv. Mater.* **31**(13), 1806128 (2019). <https://doi.org/10.1002/adma.201806128>
 133. X. Li, J. Zhou, J. Zhang, M. Li, X. Bi et al., Bamboo-like nitrogen-doped carbon nanotube forests as durable metal-free catalysts for self-powered flexible Li-CO₂ batteries. *Adv. Mater.* **31**(39), 1903852 (2019). <https://doi.org/10.1002/adma.201903852>
 134. C. Zhang, H. Li, A. Huang, Q. Zhang, K. Rui et al., Rational design of a flexible CNTs@PDMS film patterned by bio-inspired templates as a strain sensor and supercapacitor. *Small* **15**(18), 1805493 (2019). <https://doi.org/10.1002/sml.201805493>
 135. Y. Zhou, X. Wang, L. Acauan, E. Kalfon-Cohen, X. Ni et al., Ultrahigh-areal-capacitance flexible supercapacitor

- electrodes enabled by conformal P3MT on horizontally aligned carbon-nanotube arrays. *Adv. Mater.* **31**(30), 1901916 (2019). <https://doi.org/10.1002/adma.201901916>
136. C. Choi, J.A. Lee, A.Y. Choi, Y.T. Kim, X. Lepro et al., Flexible supercapacitor made of carbon nanotube yarn with internal pores. *Adv. Mater.* **26**(13), 2059–2065 (2014). <https://doi.org/10.1002/adma.201304736>
 137. J.H. Jeong, J.W. Park, D.W. Lee, R.H. Baughman, S.J. Kim, Electrodeposition of α - MnO_2 / γ - MnO_2 on carbon nanotube for yarn supercapacitor. *Sci. Rep.* **9**(1), 11271 (2019). <https://doi.org/10.1038/s41598-019-47744-x>
 138. E. Gilshtein, C. Flox, F.S.M. Ali, B. Mehrabimatin, F.S. Fedorov et al., Superior environmentally friendly stretchable supercapacitor based on nitrogen-doped graphene/hydrogel and single-walled carbon nanotubes. *J. Energy Storage* **30**(88), 101505 (2020). <https://doi.org/10.1016/j.est.2020.101505>
 139. K.L. Van Aken, C.R. Pérez, Y. Oh, M. Beidaghi, Y. Joo Jeong et al., High rate capacitive performance of single-walled carbon nanotube aerogels. *Nano Energy* **15**(88), 662–669 (2015)
 140. S.K. Kim, H.J. Koo, J. Liu, P.V. Braun, Flexible and wearable fiber microsupercapacitors based on carbon nanotube-agarose gel composite electrodes. *ACS Appl. Mater. Interfaces* **9**(23), 19925–19933 (2017). <https://doi.org/10.1021/acsami.7b04753>
 141. J. Miao, Z. Lang, T. Xue, Y. Li, Y. Li et al., Revival of zeolite-templated nanocarbon materials: recent advances in energy storage and conversion. *Adv. Sci.* **7**(20), 2001335 (2020). <https://doi.org/10.1002/adv.202001335>
 142. J. Zhao, H. Lu, Y. Zhang, S. Yu, O.I. Malyi et al., Direct coherent multi-ink printing of fabric supercapacitors. *Sci. Adv.* **7**(3), eabd6978 (2021). <https://doi.org/10.1126/sciadv.abd6978>
 143. M. Salanne, B. Rotenberg, K. Naoi, K. Kaneko, P.L. Taberna et al., Efficient storage mechanisms for building better supercapacitors. *Nat. Energy* **1**(6), 16070 (2016). <https://doi.org/10.1038/nenergy.2016.70>
 144. L. Zeng, L. Qiu, H.-M. Cheng, Towards the practical use of flexible lithium ion batteries. *Energy Storage Mater.* **23**(88), 434–438 (2019). <https://doi.org/10.1016/j.ensm.2019.04.019>
 145. F. Guo, Y. Jiang, Z. Xu, Y. Xiao, B. Fang et al., Highly stretchable carbon aerogels. *Nat. Commun.* **9**(1), 881 (2018). <https://doi.org/10.1038/s41467-018-03268-y>
 146. S. Zheng, X. Shi, P. Das, Z.S. Wu, X. Bao, The road towards planar microbatteries and micro-supercapacitors: From 2D to 3D device geometries. *Adv. Mater.* **31**(50), 1900583 (2019). <https://doi.org/10.1002/adma.201900583>
 147. X. Zhang, W. Lu, G. Zhou, Q. Li, Understanding the mechanical and conductive properties of carbon nanotube fibers for smart electronics. *Adv. Mater.* **32**(5), 1902028 (2020). <https://doi.org/10.1002/adma.201902028>
 148. Z. Wu, K. Liu, C. Lv, S. Zhong, Q. Wang et al., Ultrahigh-energy density lithium-ion cable battery based on the carbon-nanotube woven macrofilms. *Small* **14**(22), 1800414 (2018). <https://doi.org/10.1002/sml.201800414>
 149. Q. Wu, L. Yang, X. Wang, Z. Hu, Carbon-based nanocages: a new platform for advanced energy storage and conversion. *Adv. Mater.* **32**(27), 1904177 (2020). <https://doi.org/10.1002/adma.201904177>
 150. X. Gao, X. Du, T.S. Mathis, M. Zhang, X. Wang et al., Maximizing ion accessibility in MXene-knotted carbon nanotube composite electrodes for high-rate electrochemical energy storage. *Nat. Commun.* **11**(1), 6160 (2020). <https://doi.org/10.1038/s41467-020-19992-3>
 151. S. Deng, H. Zhu, G. Wang, M. Luo, S. Shen et al., Boosting fast energy storage by synergistic engineering of carbon and deficiency. *Nat. Commun.* **11**(1), 132 (2020). <https://doi.org/10.1038/s41467-019-13945-1>
 152. N. Lima, A.C. Baptista, B.M.M. Faustino, S. Taborda, A. Marques et al., Carbon threads sweat-based supercapacitors for electronic textiles. *Sci. Rep.* **10**(1), 7703 (2020). <https://doi.org/10.1038/s41598-020-64649-2>
 153. K. Hatakeyama-Sato, H. Wakamatsu, K. Yamagishi, T. Fujie, S. Takeoka et al., Ultrathin and stretchable rechargeable devices with organic polymer nanosheets conformable to skin surface. *Small* **15**(13), 1805296 (2019). <https://doi.org/10.1002/sml.201805296>
 154. M.D. Hager, B. Esser, X. Feng, W. Schuhmann, P. Theato et al., Polymer-based batteries-flexible and thin energy storage systems. *Adv. Mater.* **32**(39), 2000587 (2020). <https://doi.org/10.1002/adma.202000587>
 155. W. Mai, Q. Yu, C. Han, F. Kang, B. Li, Self-healing materials for energy-storage devices. *Adv. Funct. Mater.* **30**(24), 1909912 (2020). <https://doi.org/10.1002/adfm.201909912>
 156. S. Chen, L. Qiu, H.M. Cheng, Carbon-based fibers for advanced electrochemical energy storage devices. *Chem. Rev.* **120**(5), 2811–2878 (2020). <https://doi.org/10.1021/acs.chemrev.9b00466>
 157. H. Zhan, G. Zhang, J.M. Bell, V.B.C. Tan, Y. Gu, High density mechanical energy storage with carbon nanothread bundle. *Nat. Commun.* **11**(1), 1905 (2020). <https://doi.org/10.1038/s41467-020-15807-7>
 158. Y. Bai, B. Shen, S. Zhang, Z. Zhu, S. Sun et al., Storage of mechanical energy based on carbon nanotubes with high energy density and power density. *Adv. Mater.* **31**(9), 1800680 (2019). <https://doi.org/10.1002/adma.201800680>
 159. S.H. Kim, C.S. Haines, N. Li, K.J. Kim, T.J. Mun et al., Harvesting electrical energy from carbon nanotube yarn twist. *Science* **357**(6353), 773–778 (2017). <https://doi.org/10.1126/science.aam8771>
 160. L. Zhang, M. He, T.W. Hansen, J. Kling, H. Jiang et al., Growth termination and multiple nucleation of single-wall carbon nanotubes evidenced by in situ transmission electron microscopy. *ACS Nano* **11**(5), 4483–4493 (2017). <https://doi.org/10.1021/acs.nano.6b05941>
 161. F. Yang, H. Zhao, W. Wang, Q. Liu, X. Liu et al., Carbon-involved near-surface evolution of cobalt nanocatalysts: an in situ study. *CCS Chem.* **3**(1), 154–167 (2021)
 162. X. Zhang, F. Yang, D. Tian, H. Zhao, R. Wang et al., Atomic Scale Evolution of Graphitic Shells Growth via Pyrolysis

- of Cobalt Phthalocyanine. *Adv. Mater. Interfaces* **7**(23), 2001112 (2020). <https://doi.org/10.1002/admi.202001112>
163. R. Rao, D. Liptak, T. Cherukuri, B.I. Yakobson, B. Maruyama, In situ evidence for chirality-dependent growth rates of individual carbon nanotubes. *Nat. Mater.* **11**(3), 213–216 (2012). <https://doi.org/10.1038/nmat3231>
 164. X. Yang, X. Zhao, T. Liu, F. Yang, Precise synthesis of carbon nanotubes and one-dimensional hybrids from templates. *Chinese J. Chem.* **39**(6), 1726–1744 (2021). <https://doi.org/10.1002/cjoc.202000673>
 165. M.D. Bishop, G. Hills, T. Srimani, C. Lau, D. Murphy et al., Fabrication of carbon nanotube field-effect transistors in commercial silicon manufacturing facilities. *Nat. Electron.* **3**(8), 492–501 (2020). <https://doi.org/10.1038/s41928-020-0419-7>
 166. R.J. Headrick, D.E. Tsentalovich, J. Berdegue, E.A. Bengio, L. Liberman et al., Structure-property relations in carbon nanotube fibers by downscaling solution processing. *Adv. Mater.* **30**(9), 1704482 (2018). <https://doi.org/10.1002/adma.201704482>
 167. M.L. Geier, J.J. McMorow, W. Xu, J. Zhu, C.H. Kim et al., Solution-processed carbon nanotube thin-film complementary static random access memory. *Nat. Nanotechnol.* **10**(11), 944–948 (2015). <https://doi.org/10.1038/nnano.2015.197>
 168. K. Liu, Y. Sun, P. Liu, X. Lin, S. Fan et al., Cross-stacked superaligned carbon nanotube films for transparent and stretchable conductors. *Adv. Funct. Mater.* **21**(14), 2721–2728 (2011). <https://doi.org/10.1002/adfm.201100306>
 169. D. Zhong, Z. Zhang, L. Ding, J. Han, M. Xiao et al., Gigahertz integrated circuits based on carbon nanotube films. *Nat. Electron.* **1**(1), 40–45 (2017). <https://doi.org/10.1038/s41928-017-0003-y>
 170. C. Wang, K. Takei, T. Takahashi, A. Javey, Carbon nanotube electronics—moving forward. *Chem. Soc. Rev.* **42**(7), 2592–2609 (2013). <https://doi.org/10.1039/c2cs35325c>
 171. M. Zhu, H. Xiao, G. Yan, P. Sun, J. Jiang et al., Radiation-hardened and repairable integrated circuits based on carbon nanotube transistors with ion gel gates. *Nat. Electron.* **3**(10), 622–629 (2020). <https://doi.org/10.1038/s41928-020-0465-1>
 172. Y. Yang, L. Ding, J. Han, Z. Zhang, L.M. Peng, High-performance complementary transistors and medium-scale integrated circuits based on carbon nanotube thin films. *ACS Nano* **11**(4), 4124–4132 (2017). <https://doi.org/10.1021/acsnano.7b00861>
 173. S.J. Han, J. Tang, B. Kumar, A. Falk, D. Farmer et al., High-speed logic integrated circuits with solution-processed self-assembled carbon nanotubes. *Nat. Nanotechnol.* **12**(9), 861–865 (2017). <https://doi.org/10.1038/nnano.2017.115>
 174. A. Gaviria Rojas, M.E. Beck, V.K. Sangwan, S. Guo, M.C. Hersam, Ohmic-contact-gated carbon nanotube transistors for high-performance analog amplifiers. *Adv. Mater.* **8**(88), 2100994 (2021). <https://doi.org/10.1002/adma.202100994>
 175. Y. Liang, M. Xiao, D. Wu, Y. Lin, L. Liu et al., Wafer-scale uniform carbon nanotube transistors for ultrasensitive and label-free detection of disease biomarkers. *ACS Nano* **14**(7), 8866–8874 (2020). <https://doi.org/10.1021/acsnano.0c03523>
 176. L. Xiang, H. Zhang, G. Dong, D. Zhong, J. Han et al., Low-power carbon nanotube-based integrated circuits that can be transferred to biological surfaces. *Nat. Electron.* **1**(4), 237–245 (2018). <https://doi.org/10.1038/s41928-018-0056-6>
 177. C. Ma, S. Clark, Z. Liu, L. Liang, Y. Firdaus et al., Solution-processed mixed-dimensional hybrid perovskite/carbon nanotube electronics. *ACS Nano* **14**(4), 3969–3979 (2020). <https://doi.org/10.1021/acsnano.9b07888>
 178. W. Su, D.H. Yang, J.M. Cui, F.T. Wang, X.J. Wei et al., Ultrafast wafer-scale assembly of uniform and highly dense semiconducting carbon nanotube films for optoelectronics. *Carbon* **163**(88), 370–378 (2020). <https://doi.org/10.1016/j.carbon.2020.03.032>
 179. Y. Zhang, S.W. Ng, X. Lu, Z. Zheng, Solution-processed transparent electrodes for emerging thin-film solar cells. *Chem. Rev.* **120**(4), 2049–2122 (2020). <https://doi.org/10.1021/acs.chemrev.9b00483>
 180. J. Di, X. Wang, Y. Xing, Y. Zhang, X. Zhang et al., Dry-processable carbon nanotubes for functional devices and composites. *Small* **10**(22), 4606–4625 (2014). <https://doi.org/10.1002/sml.201401465>
 181. R. Zhang, Y. Zhang, F. Wei, Horizontally aligned carbon nanotube arrays: growth mechanism, controlled synthesis, characterization, properties and applications. *Chem. Soc. Rev.* **46**(12), 3661–3715 (2017). <https://doi.org/10.1039/c7cs00104e>
 182. Q. Liu, M. Li, Y. Gu, Y. Zhang, S. Wang et al., Highly aligned dense carbon nanotube sheets induced by multiple stretching and pressing. *Nanoscale* **6**(8), 4338–4344 (2014). <https://doi.org/10.1039/c3nr06704a>
 183. Z. Zhu, N. Wei, W. Cheng, B. Shen, S. Sun et al., Rate-selected growth of ultrapure semiconducting carbon nanotube arrays. *Nat. Commun.* **10**(1), 4467 (2019). <https://doi.org/10.1038/s41467-019-12519-5>
 184. R. Peng, Y.Y. Pan, Z. Li, S.L. Zhang, A.R. Wheeler et al., Ionotronics based on horizontally aligned carbon nanotubes. *Adv. Funct. Mater.* **30**(38), 2003177 (2020). <https://doi.org/10.1002/adfm.202003177>
 185. Y. Magnin, H. Amara, F. Ducastelle, A. Loiseau, C. Bichara, Entropy-driven stability of chiral single-walled carbon nanotubes. *Science* **362**(6411), 212–215 (2018). <https://doi.org/10.1126/science.aat6228>
 186. K.A. Brown, S. Brittman, N. Maccaferri, D. Jariwala, U. Celano, Machine learning in nanoscience: big data at small scales. *Nano Lett.* **20**(1), 2–10 (2020). <https://doi.org/10.1021/acs.nanolett.9b04090>
 187. Y. Bai, H. Yue, J. Wang, B. Shen, S. Sun et al., Super-durable ultralong carbon nanotubes. *Science* **369**(6507), 1104–1106 (2020). <https://doi.org/10.1126/science.aay5220>
 188. Y. Bai, R. Zhang, X. Ye, Z. Zhu, H. Xie et al., Carbon nanotube bundles with tensile strength over 80 GPa. *Nat. Nanotechnol.* **13**(7), 589–595 (2018). <https://doi.org/10.1038/s41565-018-0141-z>
 189. L. Liu, J. Han, L. Xu, J. Zhou, C. Zhao et al., Aligned, high-density semiconducting carbon nanotube arrays for

- high-performance electronics. *Science* **368**(6493), 850–856 (2020). <https://doi.org/10.1126/science.aba5980>
190. F. Kreupl, Carbon-nanotube computer scaled up. *Nature* **572**(7771), 588–589 (2019). <https://doi.org/10.1038/d41586-019-02519-2>
191. M.M. Shulaker, G. Hills, R.S. Park, R.T. Howe, K. Saraswat et al., Three-dimensional integration of nanotechnologies for computing and data storage on a single chip. *Nature* **547**(7661), 74–78 (2017). <https://doi.org/10.1038/nature22994>
192. S. Pi, C. Li, H. Jiang, W. Xia, H. Xin et al., Memristor crossbar arrays with 6-nm half-pitch and 2-nm critical dimension. *Nat. Nanotechnol.* **14**(1), 35–39 (2018). <https://doi.org/10.1038/s41565-018-0302-0>
193. E.J. Fuller, S.T. Keene, A. Melianas, Z. Wang, S. Agarwal et al., Parallel programming of an ionic floating-gate memory array for scalable neuromorphic computing. *Science* **364**(6440), 570–574 (2019). <https://doi.org/10.1126/science.aaw5581>
194. S. Ham, M. Kang, S. Jang, J. Jang, S. Choi et al., One-dimensional organic artificial multi-synapses enabling electronic textile neural network for wearable neuromorphic applications. *Sci. Adv.* **6**(28), eaba1178 (2020). <https://doi.org/10.1126/sciadv.aba1178>
195. V.K. Sangwan, M.C. Hersam, Neuromorphic nanoelectronic materials. *Nat. Nanotechnol.* **15**(7), 517–528 (2020). <https://doi.org/10.1038/s41565-020-0647-z>