Correction to: Influence of inclusions on hydrogen-induced delayed cracking in hot stamping steels

Yong Chen^{1,2} · Jing Liu¹ · Feng Huang¹ · Ling Chen³ · Yan-jing Su³ · Gui-feng Zhou²

Published online: 17 March 2021

© China Iron and Steel Research Institute Group 2021

Correction to: J. Iron Steel Res. Int. (2019) 26:1199–1208
<https://doi.org/10.1007/s42243-019-00312-z>

The original version of this article unfortunately contained a mistake. Table 6 was incorrect. The corrected table is given below.

The line 11 of page 1205 is revised as “The diffusion coefficient of hydrogen in CSPS is $2.76 \times 10^{-7} \text{ cm}^2/\text{s}$, which is lower than that of CRS”.

The line 17 of page 1206 is revised as “ N_T in CSPS is $3.47 \times 10^{25} \text{ cm}^{-3}$, which is much higher than that of CRS”.

Fortunately, the conclusions are still valid though the calculated parameters are revised.

Table 6 Hydrogen permeation parameter of CSPS and CRS

Sample	Thickness/mm	$t_{0.63}/\text{s}$	$J_{\infty}/(\text{mol cm}^{-2} \text{ s}^{-1})$	$D_{\text{eff}}/(\text{cm}^{-2} \text{ s}^{-1})$	C_0	N_T/cm^{-3}
CRS	1.36	7864	2.69×10^{-11}	3.92×10^{-7}	0.93×10^{-6}	2.45×10^{25}
CSPS	0.99	5909	2.39×10^{-11}	2.76×10^{-7}	0.85×10^{-6}	3.47×10^{25}

The original article can be found online at
<https://doi.org/10.1007/s42243-019-00312-z>.

✉ Jing Liu
liujing@wust.edu.cn

✉ Gui-feng Zhou
zhouguifeng@wisco.com.cn

¹ School of Materials and Metallurgy, Wuhan University of Science and Technology, Wuhan 430080, Hubei, China

² Wuhan Branch of Baosteel Central Research Institute (R&D Center) of Wuhan Iron & Steel Co., Ltd., Wuhan 430080, Hubei, China

³ Institute for Advanced Materials and Technology, University of Science and Technology Beijing, Beijing 100083, China