

SCIENTIFIC REPORTS



OPEN

“A novel highly stable and injectable hydrogel based on a conformationally restricted ultrashort peptide”

Chaitanya Kumar Thota*, Nitin Yadav* & Virander Singh Chauhan

Received: 14 March 2016

Accepted: 13 July 2016

Published: 10 August 2016

Nanostructures including hydrogels based on peptides containing non protein amino acids are being considered as platform for drug delivery because of their inherent biocompatibility and additional proteolytic stability. Here we describe instantaneous self-assembly of a conformationally restricted dipeptide, Leu Δ Phe, containing an α,β -dehydrophenylalanine residue into a highly stable and mechanically strong hydrogel, under mild physiological aqueous conditions. The gel successfully entrapped several hydrophobic and hydrophilic drug molecules and released them in a controlled manner. Leu Δ Phe was highly biocompatible and easily injectable. Administration of an antineoplastic drug entrapped in the gel in tumor bearing mice significantly controlled growth of tumors. These characteristics make Leu Δ Phe an attractive candidate for further development as a delivery platform for various biomedical applications.

Molecular self-assembly involves many non-covalent interactions with which basic molecular building blocks organize spontaneously and reversibly into novel, supramolecular, functional nano-scale architectures. This bottom-up approach is being used in fabricating various nanostructures for potential applications in biomedical, electronic and optical fields¹. Self-assembly is also used in generation of hydrogels which are three dimensional (3D) networks of fibrillar chains that retain large amount (>90%) of water and are composed of either high molecular weight natural biopolymers such as polypeptides and polysaccharides or synthetic polymers such as poly(vinyl alcohol), poly(acrylic acid) and poly(ethylene oxide)². Novel approaches in polymer design have revolutionized the field of biocompatible hydrogels. Self-assembly of these polymers into hydrogels under physiologically compatible conditions provides opportunities to develop efficient drug delivery system for wide range of biologically active compounds. Their characteristic properties like high water content, high mechanical strength, biodegradability and biocompatibility make them suitable for potential applications in drug delivery as an encapsulating matrix, as scaffold for 3D growth of cells, wound dressing, synthetic extracellular matrix, implantable devices, biosensors, microfluidics and hygiene products³. A number of hydrogels are under investigation and in clinical trials. However, most hydrogels described in literature have a few inherent limitations such as their poor mechanical strength (~2 kPa for gelatine hydrogel)⁴, relatively low homogeneity, poor loading of hydrophobic drugs and lack of biodegradability and biocompatibility which need to be addressed before their effective and safe human use.

Self-assembling peptides serves as attractive candidate for the development of hydrogels with well-controlled biological, mechanical and material properties. Peptide based hydrogels offer several advantages such as their easy synthesis, characterization and decoration, biodegradability and most importantly their very high biocompatibility⁵. Recent findings that relatively short peptides (di-, tri- and tetra-peptides) can readily self-assemble into ordered nanostructures including hydrogels, have made this area of research very active and exciting^{6,7}.

Here, we report spontaneous self-assembly of a dipeptide, Leucine- α,β -dehydrophenylalanine, containing a non-protein amino acid, α,β -dehydrophenylalanine (Δ Phe) at its C-terminal, into a highly stable hydrogel under physiological conditions. Δ Phe is an analogue of phenylalanine, with a double bond between C _{α} and C _{β} atoms, whose incorporation in peptide sequences introduces conformational constraint in the peptide backbone and

International Centre for Genetic Engineering & Biotechnology Aruna Asaf Ali Marg, New Delhi-110067, India. *These authors contributed equally to this work. Correspondence and requests for materials should be addressed to V.S.C. (email: virander@icgeb.res.in)




Figure 1. Instant self-assembly of Leu Δ Phe into a highly stable hydrogel at room temperature and its possible applications in biomedical field.

provides increased resistance to enzymatic degradation^{8–10}. The hydrogel formed by Leu Δ Phe was translucent, self-supportive, fractal-like in nature, of high mechanical strength, non-toxic, injectable, proteolytically stable and responsive to external stimuli like ionic strength, pH and temperature. Fibrillar network of the dipeptide gel could encapsulate and release various hydrophobic and hydrophilic drug molecules in a controlled manner. The gel restored its original strength after disruption of its structure, indicating its thixotropic behaviour. Administration of the antineoplastic drug, mitoxantrone, entrapped in Leu Δ Phe hydrogel in tumor bearing mice, significantly controlled growth of tumors and enhanced the antitumor activity of the drug. These unique characteristics of this low molecular weight dipeptide hydrogel make it an exciting candidate for further development as a drug delivery platform.

Results and Discussion

We synthesized and investigated self-assembly of a large panel of peptides (Supplementary information Table-S1), all containing a C-terminal Δ Phe and found that only one, Leu Δ Phe self-assembled instantaneously in 0.8 M sodium acetate buffer pH-7 into a strong hydrogel at room temperature (Fig. 1). Hydrogel formed by Leu Δ Phe (Dp gel) was self-supporting, colourless and translucent. DLS experiment with increasing peptide concentration showed an increase in size of the nanostructures. However, beyond 0.4wt% DLS could not be carried out due to increase in size of self-assembled structures ($\sim 2\ \mu\text{m}$) (Supplementary information Figure S-1A). Thio T experiment was also carried out in the same range (0.05wt–0.4wt%), which also supported the DLS results (Supplementary information Figure S-1B). Turbidity measurement experiment^{11,12} carried out for gel formation kinetics did not show significant changes till 0.4wt%. However beyond this concentration there was a steep increase in turbidity, indicating formation of dense fibrillar structures at higher concentrations (Supplementary information Figure S-2). TEM showed a distinct increase in self-assembly with increase in concentration. At 0.3wt%, fibrils of $>100\ \text{nm}$ in length were observed (Fig. 2A). Length of fibrils increased to micrometers along with branching at 0.4wt% (Fig. 2B) which suggested the fibrillar mesh to be the structural basis of the gel¹³. A highly dense network of fibrils was observed in 0.5wt% Dp gel (Fig. 2C), which was also supported by SEM (Fig. 2D). Morphology of Dp gel was investigated using environmental scanning electron microscopy (ESEM) and we found that the fibrils formed by Leu Δ Phe exhibited long tubular structures with porous sponge like surface morphologies (Fig. 2E–H).

Molecular structure of the gel was investigated using CD and FTIR spectroscopy. CD spectrum of Dp gel showed a large negative peak at $\sim 202\ \text{nm}$ and a strong positive peak at $229\ \text{nm}$, representing π - π^* transition and n - π^* transitions respectively, indicating the presence of a mixture of β -like as well as extended structures¹⁴. The positive peak at $229\ \text{nm}$ is also reported to represent interactions between aromatic chromophores like phenylalanine in peptides¹⁵. The strong negative peak observed at $275\ \text{nm}$ can be assigned to excitation splitting of the electronic transition of Δ Phe chromophore, probably from a rigid mutual disposition of two or more Δ Phe residues (Supplementary information Figure S-3A). This type of splitting also represents a system of consecutive β -turns¹⁶. IR spectrum of the gel showed a small characteristic peak at $1645\ \text{cm}^{-1}$ (amide I) and another strong peak at $1579\ \text{cm}^{-1}$ (amide II). The position of amide I band supported the presence of β -like structure in the gel whereas the band at $3489\ \text{cm}^{-1}$ was suggestive of extensive hydrogen bonding in the peptide backbone (Supplementary information Figure S-3B)^{17,18}.




Figure 2. Electron micrographs of Dp gel at different concentrations. (A) TEM image of 0.3wt% Dp gel showing small fibrils of >100 nm length. (B) TEM image of 0.4wt% Leu Δ Phe showing relatively longer and branched fibrils of length in micrometers. (C) TEM image of 0.5wt% Dp gel indicating presence of dense network of fibrils. (D) SEM image of 0.5wt% Leu Δ Phe showing dense fibrillar network of the gel. (E–H) ESEM images showing porous fibrillar mesh of 0.5wt% Dp gel.

Leu-Phe, a natural analogue and Ile Δ Phe, an isomeric peptide of Leu Δ Phe did not form hydrogel in 0.8 M sodium acetate buffer pH-7 (data not shown). Evidently, conformational constraints brought in by the presence of Δ Phe in both, the peptide backbone as well as in the side chain, have assisted in gel formation likely through enhanced π - π^* interactions due to extended stacking. This clearly underscores that the small but subtle changes in structure can significantly alter the outcome and nature of the self-assembly of a peptide (Supplementary information Figure S-4)^{8,9}. Instantaneous gel formation by Leu Δ Phe, with both the N- and C- terminals free,




Figure 3. Mechanical strength and self-recovery of Dp gel (A) Storage modulus (G' values) of Dp gel at different peptide concentrations (0.4wt%, 0.5 wt%, 0.75wt% and 1.0wt%), showing increase in gel strength with increasing peptide concentration. Graphs represent mean \pm standard deviation ($n = 3$). Significance values determined by t-test are marked with asterisks (ns for P -value > 0.05 , * for P -value < 0.05 , ** for P -value < 0.01 , *** for P -value < 0.001 , **** for P -value < 0.0001). (B) Syringeability results showing recovery of gel (1.0wt%) after disruption of its structure. (C) Thixotropic time dependent step-strain data of Dp gel (1.0wt%) showing self-healing property of Dp gel. Higher G' values and G'' values ($G' > G''$) initially at lower strain (0.1%) indicate solid like structure of the gel while on increasing strain to 50%, G' and G'' values were declined ($G' < G''$), indicating transition of gel into liquid-like material. Finally on removal of high strain, the gel restored its original strength ($G' > G''$). Three cycles were performed to verify reproducibility.

is exceptional in comparison to other short peptide based hydrogels described in the literature⁷. For example, a dipeptide like Fmoc-FF also gels but has its N-terminal protected with a large aromatic protecting group which plays a crucial role in gelation, as also in case of single Fmoc protected amino acids (Fmoc-F, Fmoc-T) that can form gels^{19,20}.

Appropriate mechanical strength, and stability, especially under physiological conditions are key factors for hydrogels to be considered as delivery platforms. To measure mechanical strength of the gel, storage modulus (G') values were measured and we found that G' values increased with increase in peptide concentration (5.46 ± 0.58 kPa at 0.4wt%, 12.0 ± 2.7 kPa at 0.5wt%, 63.2 ± 14.0 kPa for 0.75wt% and 136.0 ± 29.8 kPa at 1.0wt%) (Fig. 3A). Clearly gel strength increased with increasing peptide concentration. These G' values compare extremely well with other reported peptide based hydrogels like for RADA16 gel (8 kPa)²¹, for LN-NS gel (7 kPa)²¹, for polypeptide-DNA gel (5 kPa)²² and for Fmoc-FF gel (10 kPa)²³.

Frequency sweep rheology experiment (1–100 rad/s) carried out with Dp gels (0.5wt% and 1.0wt%) showed that the G' and G'' (loss modulus) values were independent on frequency suggesting their high stability (Supplementary information Figures S-5A and S-5B).

In recent years, increasing efforts have been made to design and develop hydrogels with self-healing properties for their applications in drug delivery and cell therapy purposes^{24–26}. To explore self-healing behaviour of Dp gel, 0.5wt% and 1.0wt% Dp gels were subjected to syringeability and time dependent step-strain rheological tests^{27–29}. Upon structural disruption and passage through the syringe needle, 0.5wt% Dp gel was not able to fully recover




Figure 4. CD spectra showing effect of different parameters on formation of Dp gel and its thermal stability (A) CD spectrum showing conformational changes in the structure of Leu Δ Phe on self-assembly in different salt (acetate) conditions. (B) CD spectrum showing effect of changes in pH of the buffer (sodium acetate buffer) condition on Leu Δ Phe self-assembly into hydrogel. (C) CD temperature scan of Dp gel (0.5wt%) showing its stability at physiological temperatures.

its strength while at 1.0wt% the gel regained its original strength as observed in tube inversion test (Fig. 3B). Time dependent step-strain rheology experiment was done on Dp gel (1.0wt%) in which a low strain (0.1%) was applied initially followed by an increase in strain to 50%, representing the force experienced by hydrogels during injection and finally reducing the strain back to 0.1%. Dp gel showed stable and higher G' values and G'' values ($G' > G''$) initially representing its solid like structure, but when the applied strain was increased to 50%, the gel was disrupted and G' and G'' values were rapidly declined and become $G' < G''$, representing transition of solid gel into liquid-like material. Upon removal of high stress the gel restored its original strength ($G' > G''$) (Fig. 3C). Taken together results of these experiments clearly suggest that the Dp gel has the ability to withstand stress and regain its original structure.

Since peptide self-assembly is sensitive to changes in environmental conditions (like pH, salt concentration, temperature etc.), it is essential to identify and optimize suitable conditions for the development of these systems. Self-assembly of Leu Δ Phe at different salt concentrations was probed by CD spectroscopy. An increase in concentration of sodium acetate saw the appearance of a negative peak at 275 nm (at 0.4 M and 0.8 M) which decreased in intensity at higher salt concentration (1.2 M) (Fig. 4A). As also reported for other hydrogels^{30,31}; there seems to be a critical salt concentration above which self-assembled structures become unstable. Self-assembly of Leu Δ Phe in different pH conditions was also investigated. Intensity of the band at 275 nm decreased by 40% at pH 2 compared to at neutral pH, and a blue shift from 275 nm at neutral to 280 nm at alkaline pH (pH 10) was observed (Fig. 4B). Tube inversion test also showed that Leu Δ Phe did not form gel like structure at both acidic (pH-2) and basic pH (pH-10) (supplementary information Figure S-6). This could be due to alteration of $\text{NH}_2/\text{NH}_3^+$ or COOH/COO^- content in the peptide on pH changes as also reported for other peptide based gels^{21,32,33}.

Thermal scanning CD spectroscopy with Dp gel (0.5wt%) showed no significant changes in the 275 nm band till 50°C. However at higher temperatures more than 60°C there was significant decrease in the intensity at 275 nm, suggesting that the gel may not be stable above this temperature (Fig. 4C). Similar thermal stability




Figure 5. Percentage release of drugs from Dp gel, indicating their continuous & slow release.

patterns have also been reported for other peptide based gelators including Phe Δ Phe, N-terminal protected dipeptide and h9e polypeptide (19 amino acids)^{13,34,35}. One of the major shortcoming of peptide based systems is their high susceptibility to enzymatic degradation under *in-vivo* conditions³⁶. TEM images of Dp gel treated with trypsin and cell culture supernatant showed no observable changes in the fibrillar network compared to the untreated gel (Supplementary information Figure S-7A,S-7B). Tube inversion test of Dp gel after trypsin and cell culture supernatant treatment also showed no changes in its strength even after 5 days of incubation (Supplementary information Figure S-7C,S-7D). RP-HPLC analysis further supported these results (Supplementary information Figure S-7E), suggesting its suitability for *in vivo* & cell culture applications.

A major factor that restricts development of hydrogels as drug delivery vehicles is their inability to effectively entrap poorly water soluble drugs due to their own extreme hydrophilic nature^{37,38} and, if it happens, large aggregates may form and give a burst release with high local concentration resulting in toxicity at the site of administration³⁸. We tested entrapment in and release from the gel matrix of various drugs including some well known anti-cancer, anti-fungal, anti-TB and antibiotics covering a wide range of molecular weights, charge and physiochemical properties (Supplementary information Table-S2). Interestingly, both hydrophilic and hydrophobic drug molecules were efficiently entrapped in the gel. The unprotected N- and C- terminals in Leu Δ Phe lend polar character while the side chains of Leu and Δ Phe provide a strong hydrophobic character and this amphipathic nature is likely responsible for the entrapment of both hydrophilic and hydrophobic drugs in the gel matrix. Entrapment of water insoluble drug, curcumin, showed a uniform distribution inside the gel with no observable aggregates (Supplementary information Figure S-8)³⁰. Next, release of entrapped drugs was investigated and we found that the drug molecules, both hydrophilic as well as hydrophobic, released in a slow and continuous manner without any burst release (Fig. 5).

Diffusion coefficient values (D) of the drugs released ranged from 0.01×10^{-10} for a hydrophobic drug like curcumin to 6.0×10^{-10} for a hydrophilic drug like isoniazid. In case of hydrophilic drugs, the D-values correlated with their ClogP values, molecular weight and net charge of drugs. There was no correlation between release of hydrophobic drugs with their molecular mass, but their D-values decreased with increase in their ClogP values (Supplementary information Figure S-9A), suggesting a determining role of hydrophobic interactions between drug molecules and the gel matrix. We observed that D-values of hydrophilic drugs decreased with increase in molecular weight and net charge of drugs, and increased with increase in their clog p values (Supplementary information Figure S-9B–9D), this is likely to be due to gel matrix controlled movement of drugs and presence of electrostatic or hydrophobic interactions between drugs and gel matrix. These results suggested that the controlled release of hydrophilic drugs from Dp gel may be affected by any of the three parameters i.e. molecular mass, net charge or ClogP values of these drugs.

Conventional therapy involves frequent dosing of therapeutic drugs causing various adverse effects and poor patient compliance because of under or over dosage of drugs³⁹. Sustained and controlled release formulations are likely to improve therapeutic index of drugs. The release pattern of both hydrophilic and hydrophobic drugs from the Dp gel was superior to other peptide and polymer based reported hydrogels. For example, for paclitaxel, the release from Dp gel was ~6 times slower than RADA 16 gel⁴⁰ while mitoxantron was completely released within 8 hrs from another dipeptide hydrogel¹³. Thus, Dp gel can entrap a wide range of hydrophobic and hydrophilic drug molecules and act as a reservoir for controlled release of drugs.

In order to achieve a stimuli responsive release of drugs, it is necessary for the delivery system to be able to sense and respond to small changes in the external environment like pH, and temperature⁴¹. To investigate if the release of an entrapped drug can be modulated by changes in pH, we chose curcumin as an example. When the pH was changed from neutral to acidic (pH-3 and pH-5.6) or basic pH (pH-8.5 and pH-10), the cumulative percentage release of curcumin from Dp gel (0.5wt%) was increased substantially (Supplementary information Figure S-10). Similar pH responsive drug delivery from peptide based hydrogels has been also reported in literature^{32,42,43}.

In peptide based hydrogels, concentration of the peptide can also play a key role in regulating their mesh size and other interactions responsible for holding drugs inside the gel matrix⁴⁴. Also, for any drug delivery system, retention of bioactivity of entrapped drugs is essential for their potential applications in clinic. To address these issues, we again chose curcumin⁴⁵ and found that the amount of curcumin released over time (48 hr) decreased




Figure 6. (A) Cumulative percentage release of curcumin from Dp gels (at 0.5wt% and 1wt%) showing decrease in curcumin release on increase in peptide concentration, indicating its peptide concentration based tunability. (B) Percentage cytotoxicity of released curcumin on HeLa cells from Dp gels (0.5wt%), entrapped with 0mM, 2mM and 4mM curcumin, assessed by LDH assay. Graphs represent mean \pm standard deviation ($n = 3$). Significance values determined by t-test are marked with asterisks (ns for P-value > 0.05 , * for P-value < 0.05 , ** for P-value < 0.01 , *** for P-value < 0.001 , **** for P-value < 0.0001).




Figure 7. Cytotoxicity of Dp gel (A) Percentage cell viability of HEK293T cells treated with Dp gels of different peptide concentration, indicating its biocompatibility. (B) Live/Dead assay results showing no change in percentage population of live cells in the presence of Dp gel compared to control, indicating its high biocompatibility. Graph represents mean \pm standard deviation ($n = 3$).

with increasing peptide concentration from 0.5wt% to 1.0wt% (Fig. 6A), this is likely due to increased fibrillar mesh and hydrophobic interactions between drug molecules and fibrillar network of the gel, as has been reported for other hydrogels^{46,47}. To determine the activity of drug entrapped in the gel matrix, Dp gels (0.5wt%) entrapped with different concentrations of curcumin were exposed to HeLa cells and cytotoxicity of the curcumin released was monitored by LDH assay. Significantly higher cell death was observed at 4mM ($35.6 \pm 0.53\%$) than at 2mM ($22 \pm 2.61\%$) curcumin entrapped gel while Dp gel alone did not show any cytotoxicity (Fig. 6B). These results suggested that not only the amount of drug release may be regulated by changing the peptide concentration or amount of drug entrapped in the peptide gel but also that a drug like curcumin retains its activity.

In the development of new materials for drug delivery and other biomedical applications, biocompatibility is the prerequisites criterion for their clinical use^{48,49}. Biocompatibility of Dp gel was assessed by MTT and live/dead assay using HEK293T cells. In MTT and live/dead assay, HEK293T cells were exposed to gels of different peptide concentrations and we found that the growth of cells was unaffected even at higher peptide concentrations (Fig. 7A,B) (Supplementary information Figure S-11), indicating no cellular cytotoxicity and high biocompatibility of the gel.




Figure 8. Tumor regression study in mice xenograft model showing changes in relative tumor volume of different groups of mice treated with different formulations with time. Graph represents mean \pm standard deviation ($n = 4$).

We next investigated whether Dp gel can be useful for *in-vivo* delivery purposes. For this as a proof of principle, we used a mice xenograft tumor model and mitoxantrone as the anticancer drug. Four groups of tumor bearing mice were treated with PBS, Dp gel, mitoxantrone (MT) and MT entrapped in Dp gel. In mice receiving PBS or Dp gel alone, a continuous tumor growth was observed. In mice treated with MT alone, while growth was arrested there was no reduction in the size of tumors (Fig. 8), suggesting that MT was more effective when delivered as entrapped in the gel. There was no body weight loss in mice injected with Dp gel alone, suggesting its biocompatibility *in vivo*. A minor decrease in body weight was observed in mice treated with MT and MT entrapped in Dp gel (Supplementary information Figure S-12). During cancer treatment, chemotherapy involves various side effects due to toxicity of anticancer drugs and may cause body weight loss. Such weight loss in mice treated with anticancer drugs have also been reported earlier^{50,51}. All these results suggest that Leu Δ Phe forms a biocompatible hydrogel suitable for *in-vivo* applications.

Methods and Materials

Synthesis of Leucine- α,β -dehydrophenylalanine. Dipeptide Leu Δ Phe was synthesized at 5 mM scale by solution phase peptide synthesis described earlier (Supplementary Information text)^{8,9}.

Preparation of dipeptide hydrogel. Leu Δ Phe was dissolved in minimum amount of methanol (50 mg/mL) using 10 min sonication. Instantaneous dipeptide gel formation was achieved by addition of 0.8 M sodium acetate buffer pH 7 to the peptide solution at room temperature.

Turbidity. Peptide concentration dependent self-assembly of Leu Δ Phe was investigated by monitoring turbidity of Dp gel prepared at different concentrations (0.05wt%, 0.1wt%, 0.2wt%, 0.3wt%, 0.4wt%, 0.5wt%, 0.75wt% and 1.0wt%) using U.V spectroscopy at 360 nm (Supplementary information text)^{11,12}.

Dynamic light scattering (DLS) studies. Self-assembly kinetics of Leu Δ Phe at different concentrations (0.05–0.4 wt%) was investigated by DLS. DLS studies at different time points (1 hr, 2 hr, 3 hr, 4 hr, 5 hr and 6 hr) were probed using Zetasizer Nano-ZS (Malvern Instruments) at a light scattering angle of 90° using 632 nm laser. All studies were conducted at room temperature.

Thioflavin-T (ThioT) fluorescence assay. Self-assembly kinetics of Leu Δ Phe at different (0.05–0.4 wt%) peptide concentrations was again determined by ThioT fluorescence assay using Victor fluorescence multi-well plate reader (PerkinElmer) at 440 nm excitation and 482 nm emission filter. Freshly prepared ThioT dye was added (2 μ l of 2 mM stock per 200 μ l sample) to the samples at different time intervals (1 hr, 2 hr, 3 hr, 4 hr, 5 hr, 6 hr, 7 hr and 8 hrs) and fluorescence was measured using fluorescence spectrophotometer.

Transmission electron microscopy (TEM). Samples for TEM analysis were prepared by negative staining method. A 10 μ l of each gel sample (diluted to 1:1 ratio with water just before sample loading) was spotted on a 200 mesh 3 mm carbon coated nickel grid, stained with 1% uranyl acetate and viewed under the 120 kV mode of a transmission electron microscope (Tecnaei 12 BioTWIN, FEI Netherlands). Photomicrographs were digitally recorded using a Megaview II (SIS, Germany) digital camera. Image analysis was carried using Analysis II (Megaview, SIS, Germany) software packages.

Scanning Electron Microscopy (SEM). A 0.5 wt% gel sample was spreaded over the double sided tape already placed on the SEM holder and gold coated by ion sputtering (E1010, Hitachi, Japan) for 30 s at operating vacuum of 10 Pa. SEM images were acquired with a ZEISS EVO 50 (Carl Zeiss Microscopy, GmbH, Germany) with 2.0 nm resolution at an acceleration voltage of 0.2 to 30 kV.

Environmental scanning electron microscopy (ESEM). Environmental scanning electron microscopy (ESEM) images were recorded using a field emission scanning electron microscope (FE-SEM), Quanta 200F, FEI (Eindhoven, Netherlands). Dp gel (0.5wt%) was spreaded over carbon tape placed on specimen holder and imaged. Images were obtained in environmental wet mode at a low vacuum and collected using large-field gaseous secondary electron detector (GSED).

Circular dichroism (CD) spectroscopy. CD experiments were carried out in a 0.1 cm path length quartz cuvette using JASCO-810 polarimeter equipped with peltier temperature controller at 0.2 mg/ml peptide concentration. UV-CD (from 190 nm to 350 nm) spectra were taken for gels prepared in buffers having different sodium acetate concentrations (0 M–1.2 M) to investigate the effect of salt concentration on gelation. To monitor the effect of pH on self-assembly of Leu Δ Phe, the CD spectra of gels prepared at different pH conditions i.e. acidic and basic, and neutral were collected. To investigate the thermal stability of gel, CD spectra were collected in the temperature range of 20–100 °C. An average of 5 scans was used for all spectra.

Fourier Transform Infrared (FTIR) Spectroscopy. IR spectra of 0.5wt% Dp gel were collected using Varian FTIR spectrometer to determine molecular structure of Dp gel (Supplementary Information text).

Syringeability and rheology Studies. Syringeability and rheology experiments were performed to determine strength, stability and self-healing property of the Dp gel (Supplementary Information text)^{27–29}.

Drug loading & release. Drug loaded Dp gels (0.5wt%) were prepared by incorporating drugs (to a final concentration of 4 mM) during gel formation and were kept undisturbed for 30 min, washed three times with PBS to remove the untrapped drug. For release study, 5 mL of PBS was placed on top of the gels and 1.0 mL of samples were withdrawn from the release medium at different time intervals (2 hr, 4 hr, 8 hr, 16 hr, 24 hr, 48 hr, 72 hr, 96 hr and 120 hr) and replaced with fresh PBS. Contents of both hydrophilic and hydrophobic drugs into the overlying PBS was monitored by methods reported earlier^{13,52–56} using UV-vis spectroscopy. The percentage release was calculated using an equation: Percentage Release = (Absorbance of drug released in PBS/Absorbance of total drug encapsulated in gel) X 100. To study the effect of environmental pH on release rate of drugs entrapped in the peptide hydrogel, Dp gels (0.5wt%) were prepared by incorporating curcumin (4 mM), kept undisturbed for 30 min and washed three times with PBS to remove the untrapped drug. The pH of the media was adjusted to pH-3, 5.6, 7.4, 8.5 and 10 using 0.1 M HCl and 1 N NaOH and 5 ml of the respective media was placed on top of the gels. 1.0 ml samples were withdrawn from the release media at different time intervals (1 hr, 2 hr, 4 hr, 8 hr, 24 hr & 48 hr) and replaced with fresh 1 ml media. The amount of curcumin released was determined by UV-vis spectroscopy^{13,56}.

The relative diffusion coefficient (D) of drugs in the gel matrix was calculated by using the non-steady state diffusion model equation given as: $M_t/M_\infty = 4 \times (D_t/\pi \lambda^2)^{1/2}$, where, M_t is the total amount of drug released at the time of measurement, M_∞ is the total amount of drug that was kept in the matrix, λ represents the hydrogel thickness, t is the time of measurement, and D is the diffusion coefficient of the drug⁵⁵. The ClogP values of the drugs were obtained from “drug bank” and “pubchem”.

Activity of drug entrapped in Dp gel. Dp gels (0.5wt%) containing different curcumin concentrations (0 mM, 2 mM and 4 mM) were prepared, washed with PBS and transferred to 24-well 0.4 μ m pore size polyester transwells. HeLa cells were plated (1×10^5 Cells/well) in TCTP 24-well plate and incubated overnight. Next day, transwells containing curcumin entrapped gels were placed into 24-well plate containing HeLa cells and incubated for 3 hrs at 37 °C. Cells were imaged for morphological changes due released curcumin and cytotoxicity was determined using standard LDH assay⁵⁷. All experiments were performed in triplicate.

Cell viability and live/dead assay. Hek293T cells were grown in DMEM culture media supplemented with 10% FBS and 0.1% gentamycin respectively, on TCTP culture plates at 37 °C in a humidified atmosphere containing 5% CO₂. Subconfluent cells were trypsinized, harvested and counted using hemocytometer. Cell suspensions were diluted with culture medium and seeded at a concentration of 1×10^3 cells/well in TCTP 96-well plate for MTT (methyl thiazolyl tetrazolium) assay and 5×10^4 cells/well in 24 well plate for live/dead assay. The plates were incubated at 37 °C in a humidified atmosphere containing 5% CO₂ for 24 hr to allow cell spreading and attachment. Dp gels of different peptide concentrations (0.1wt%, 0.25wt%, 0.5wt%, 0.75wt% & 1.0wt% gel) were prepared and kept in hood overnight for methanol evaporation. Next day, gels (50 μ l each in triplicate) were added to the respective wells and incubated for 24 hr. Cells treated with culture medium alone were used as control group. Cell viability was determined by standard MTT assay⁵⁷ while live/dead assay was performed using FACS⁵⁸.

For live/dead assay, after 24 hr treatment, cell culture supernatants were removed and cells were trypsinized (100 μ l/well), neutralized with DMEM culture media (1 ml/well) and transferred to eppendorf tubes. Cells were washed and resuspended in FACS buffer (PBS containing 0.2% FBS) before staining. eFluor[®] 780 staining solution was prepared freshly in FACS buffer, added (50 μ l each) to the cell suspensions and incubated for 30 min in dark. Unbound dye was removed by washing with FACS buffer (2 times) and samples were processed on FACS CANTO-II flow cytometer (BD Bioscience, San Jose, CA, USA). Fluorescence of eFluor[®] 780 was collected in the APC-Cy7 channel, equipped with a 780 nm band pass filter. A total of 1 lakh events from each sample were acquired to ensure adequate data, and histograms representing live/dead population of cells were plotted using FlowJo software (FlowJo Enterprises).

In vivo efficacy of Dp gel. To determine *in vivo* efficacy of Dp gel as drug reservoir for controlled release of drugs, tumor regression study using mice xenograft model was carried out⁵⁹. Dp gel containing mitoxantrone

(4 mM) was prepared and incubated in laminar hood overnight in dark for methanol evaporation. Untrapped drug was separated from entrapped drug by centrifugation (800 x g for 15 minutes) using 4 ml Amicon Ultra-4 centrifugal filter (Ultracel – 3 kDa, Merck Millipore Ltd. Tullagreen, Carrigtwohill). Female mice (Balb/c), 4–6 weeks old, weighing 18–22 g were housed in a temperature and light controlled room. All animal experiments were approved by the Institutional Animal Care and Use Committee at International Centre for Genetic Engineering & Biotechnology, Delhi, India and were in compliance with all regulatory guidelines. B₁₆F₁₀ Cells (Mouse melanoma cells) were used and cultured in RPMI 640 culture media supplemented with 10% FBS and 0.1% gentamycin for tumor generation in mice. Subconfluent B₁₆F₁₀ cells were trypsinized, harvested, washed thrice with cold PBS and counted using hemocytometer. Cell suspension was again diluted with cold PBS to a concentration of 1×10^6 cells/100 μ l of PBS. Each mouse was injected subcutaneously with 1×10^6 B₁₆F₁₀ cells in the abdomen for tumor generation. After 14 days of tumor cell inoculation, mice were divided into four different groups (4 mice each group) i.e. control (treated with PBS), Dp gel alone, mitoxantrone alone and Dp gel entrapped with mitoxantrone. Tumor bearing mice were treated with different gel samples (intraperitoneal injection near tumor) after every 7 days (0th, 8th and 16th day). Every 4th day, changes in tumor size were monitored using vernier calliper and the day of first injection was taken as 0th day. Mice weight was also recorded and tumor volume and relative tumor volume were calculated using equations⁶⁰: Tumor Volume = $(L \times W^2)/2$ and relative tumor volume = $(TV_n)/(TV_0)$, where, L and W are length (longest diameter) and width (shortest diameter) of tumor (in mm) respectively and TV₀ and TV_n are the volume of tumor (in mm³) on 0th and nth day respectively.

Proteolytic Stability of the Dipeptide Gel. Enzymatic stability of Dp gel was determined by incubating Dp gel with cell culture supernatant and trypsin (a serine protease) solution for 5 days. To examine gel stability, RPHPLC, tube inversion test and TEM imaging were carried out.

Statistical Analysis. All statistical analyses were carried out using SigmaStat 5.0 (Systat Software, San Jose, Ca) and data presented as mean values \pm SD.

Conclusion

We have found that an ultrashort peptide containing α , β -dehydrophenylalanine, Leu Δ Phe, spontaneously forms strong and stable hydrogel under physiological conditions. Leu Δ Phe forms hydrogel at relatively low concentrations and has high mechanical strength and stability to shear stress under physiological conditions. The gel efficiently entrapped a number of hydrophobic and hydrophilic drug molecules and released them in a controlled manner. The gel entrapped and released mitoxantrone and significantly controlled tumor growth in an *in-vivo* mouse model. Its features like ease of synthesis and derivatization, high mechanical strength, injectability, proteolytic stability, non-cytotoxicity, ability to entrap and release drug like molecules make it an attractive candidate for drug delivery.

References

- Zhang, S. Fabrication of novel biomaterials through molecular self-assembly. *Nature biotechnology* **21**, 1171–1178 (2003).
- Kobsa, S. & Saltzman, W. M. Bioengineering approaches to controlled protein delivery. *Pediatric research* **63**, 513–519 (2008).
- Zhang, R., Tang, M., Bowyer, A., Eisenthal, R. & Hubble, J. A novel pH- and ionic-strength-sensitive carboxy methyl dextran hydrogel. *Biomaterials* **26**, 4677–4683, (2005).
- Xing, Q., Yates, K., Vogt, C., Qian, Z., Frost, M. C. & Zhao, F. Increasing mechanical strength of gelatin hydrogels by divalent metal ion removal. *Scientific reports* **4**, 1–10, (2014).
- Black, K. A. *et al.* Biocompatibility and characterization of a Peptide amphiphile hydrogel for applications in peripheral nerve regeneration. *Tissue Engineering Part A* **21**, 1333–1342 (2015).
- Saini, A. & Chauhan, V. S. Self-assembling properties of peptides derived from TDP-43 C-terminal fragment. *Langmuir* **30**, 3845–3856 (2014).
- Seow, W. Y. & Hauser, C. A. Short to ultrashort peptide hydrogels for biomedical uses. *Materials Today* **17**, 381–388 (2014).
- Gupta, M., Bagaria, A., Mishra, A., Mathur, P., Basu, A., Ramakumar, S. & Chauhan, V. S. Self-Assembly of a Dipeptide-Containing Conformationally Restricted Dehydrophenylalanine Residue to Form Ordered Nanotubes. *Advanced Materials* **19**, 858–861 (2007).
- Mishra, A., Panda, J. J., Basu, A. & Chauhan, V. S. Nanovesicles based on self-assembly of conformationally constrained aromatic residue containing amphiphilic dipeptides. *Langmuir* **24**, 4571–4576 (2008).
- Panda, J. J., Kaul, A., Kumar, S., Alam, S., Mishra, A. K., Kundu, G. C. & Chauhan, V. S. Modified dipeptide-based nanoparticles: vehicles for targeted tumor drug delivery. *Nanomedicine* **8**, 1927–1942 (2013).
- Lytova, E. M., Kasakov, A. S. & Gurvits, B. Y. Effects of arginine on kinetics of protein aggregation studied by dynamic laser light scattering and turbidimetry techniques. *Biotechnology progress* **23**, 1411–1416 (2007).
- De Groot, N. S., Parella, T., Aviles, F. X., Vendrell, J. & Ventura, S. Ile-Phe dipeptide self-assembly: clues to amyloid formation. *Biophysical journal* **92**, 1732–1741 (2007).
- Panda, J. J., Mishra, A., Basu, A. & Chauhan, V. S. Stimuli responsive self-assembled hydrogel of a low molecular weight free dipeptide with potential for tunable drug delivery. *Biomacromolecules*, **9**, 2244–2250 (2008).
- Tinker, D. A., Krebs, E. A., Feltham, I. C., Attah-Poku, S. K. & Ananthanarayanan, V. S. Synthetic beta-turn peptides as substrates for a tyrosine protein kinase. *Journal of Biological Chemistry* **263**, 5024–5026 (1988).
- Gopal, R., Park, J. S., Seo, C. H. & Park, Y. Applications of circular dichroism for structural analysis of gelatin and antimicrobial peptides. *International journal of molecular sciences* **13**, 3229–3244 (2012).
- Skelton, N. J., Blandl, T., Russell, S. J., Starovasnik, M. A. & Cochran, A. G. β -hairpin polypeptides by design and selection. *Journal of Spectroscopy*, **17**, 213–230 (2003).
- Ramagopal, U. A., Ramakumar, S., Mathur, P., Joshi, R. & Chauhan, V. S. Dehydrophenylalanine zippers: strong helix–helix clamping through a network of weak interactions. *Protein engineering*, **15**, 331–335 (2002).
- Ajayaghosh, A. & George, S. J. First phenylenevinylene based organogels: self-assembled nanostructures via cooperative hydrogen bonding and π -stacking. *Journal of the American Chemical Society* **123**, 5148–5149 (2001).
- Fichman, G. & Gazit, E. Self-assembly of short peptides to form hydrogels: Design of building blocks, physical properties and technological applications. *Acta biomaterialia* **10**, 1671–1682 (2014).
- Jayawarna, V., Richardson, S. M., Hirst, A. R., Hodson, N. W., Saiani, A., Gough, J. E. & Ulijn, R. V. Introducing chemical functionality in Fmoc-peptide gels for cell culture. *Acta biomaterialia* **5**, 934–943 (2009).

21. Wang, B., Sun, C., Shao, Z., Yang, S., Che, B., Wu, Q. & Liu, J. Designer self-assembling Peptide nanofiber scaffolds containing link protein N-terminal peptide induce chondrogenesis of rabbit bone marrow stem cells. *BioMed research international* **2014**, 1–10, (2014).
22. Li, C. *et al.* Rapid Formation of a Supramolecular Polypeptide–DNA Hydrogel for *In Situ* Three-Dimensional Multilayer Bioprinting. *Angewandte Chemie International Edition* **54**, 3957–3961 (2015).
23. Mahler, A., Reches, M., Rechter, M., Cohen, S. & Gazit, E. Rigid, Self-Assembled Hydrogel Composed of a Modified Aromatic Dipeptide. *Advanced Materials* **18**, 1365–1370 (2006).
24. Yu, L. & Ding, J. Injectable hydrogels as unique biomedical materials. *Chemical Society Reviews* **37**, 1473–1481 (2008).
25. Nguyen, M. K. & Lee, D. S. Injectable biodegradable hydrogels. *Macromolecular bioscience* **10**, 563–579 (2010).
26. Tan, H. & Marra, K. G. Injectable, biodegradable hydrogels for tissue engineering applications. *Materials* **3**, 1746–1767 (2010).
27. Zawaneh, P. N., Singh, S. P., Padera, R. F., Henderson, P. W., Spector, J. A. & Putnam, D. Design of an injectable synthetic and biodegradable surgical biomaterial. *Proceedings of the National Academy of Sciences* **107**, 11014–11019 (2010).
28. Baral, A., Roy, S., Dehsorkhi, A., Hamley, I. W., Mohapatra, S., Ghosh, S. & Banerjee, A. Assembly of an injectable noncytotoxic peptide-based hydrogelator for sustained release of drugs. *Langmuir* **30**, 929–936 (2014).
29. Tian, Z., Chen, C. & Allcock, H. R. Injectable and biodegradable supramolecular hydrogels by inclusion complexation between poly (organophosphazenes) and α -cyclodextrin. *Macromolecules* **46**, 2715–2724 (2013).
30. Altunbas, A., Lee, S. J., Rajasekaran, S. A., Schneider, J. P. & Pochan, D. J. Encapsulation of curcumin in self-assembling peptide hydrogels as injectable drug delivery vehicles. *Biomaterials* **32**, 5906–5914 (2011).
31. Caplan, M. R., Moore, P. N., Zhang, S., Kamm, R. D. & Lauffenburger, D. A. Self-assembly of a β -sheet protein governed by relief of electrostatic repulsion relative to van der Waals attraction. *Biomacromolecules* **1**, 627–631 (2000).
32. Lange, S. C., Unsleber, J., Drücker, P., Galla, H. J., Waller, M. P. & Ravoo, B. J. pH response and molecular recognition in a low molecular weight peptide hydrogel. *Organic & biomolecular chemistry* **13**, 561–569 (2015).
33. Toksoz, S., Mammadov, R., Tekinay, A. B. & Guler, M. O. Electrostatic effects on nanofiber formation of self-assembling peptide amphiphiles. *Journal of colloid and interface science* **356**, 131–137 (2011).
34. Nanda, J. & Banerjee, A. β -Amino acid containing proteolytically stable dipeptide based hydrogels: encapsulation and sustained release of some important biomolecules at physiological pH and temperature. *Soft Matter* **8**, 3380–3386 (2012).
35. Huang, H., Ding, Y., Sun, X. S. & Nguyen, T. A. Peptide hydrogelation and cell encapsulation for 3D culture of MCF-7 breast cancer cells. *PLoS One* **8**, e59482 (2013).
36. Swanekamp, R. J., Welch, J. J. & Nilsson, B. L. Proteolytic stability of amphipathic peptide hydrogels composed of self-assembled pleated β -sheet or coassembled rippled β -sheet fibrils. *Chemical Communications* **50**, 10133–10136 (2014).
37. Chen, M. C., Tsai, H. W., Liu, C. T., Peng, S. F., Lai, W. Y., Chen, S. J. & Sung, H. W. A nanoscale drug-entrapment strategy for hydrogel-based systems for the delivery of poorly soluble drugs. *Biomaterials* **30**, 2102–2111 (2009).
38. Woldum, H. S., Larsen, K. L. & Madsen, F. Cyclodextrin controlled release of poorly water-soluble drugs from hydrogels. *Drug delivery* **15**, 69–80 (2008).
39. Tiwari, G., Tiwari, R., Sriwastawa, B., Bhati, L., Pandey, S., Pandey, P. & Bannerjee, S. K. Drug delivery systems: An updated review. *International journal of pharmaceutical investigation* **2**, 2 (2012).
40. Liu, J., Zhang, L., Yang, Z. & Zhao, X. Controlled release of paclitaxel from a self-assembling peptide hydrogel formed *in situ* and antitumor study *in vitro*. *International Journal of Nanomedicine* **6**, 2143–53 (2011).
41. James, H. P., John, R., Alex, A. & Anoop, K. R. Smart polymers for the controlled delivery of drugs—a concise overview. *Acta Pharmaceutica Sinica B* **4**, 120–127 (2014).
42. Peppas, N. A. & Klier, J. Controlled release by using poly (methacrylic acid-g-ethylene glycol) hydrogels. *Journal of Controlled Release* **16**, 203–214 (1991).
43. Aluri, S., Janib, S. M. & Mackay, J. A. Environmentally responsive peptides as anticancer drug carriers. *Advanced drug delivery reviews* **61**, 940–952 (2009).
44. Hoare, T. R. & Kohane, D. S. Hydrogels in drug delivery: progress and challenges. *Polymer* **49**, 1993–2007 (2008).
45. Shen, L. & Ji, H. F. Theoretical study on physicochemical properties of curcumin. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* **67**, 619–623 (2007).
46. Koutsopoulos, S., Unsworth, L. D., Nagai, Y. & Zhang, S. Controlled release of functional proteins through designer self-assembling peptide nanofiber hydrogel scaffold. *Proceedings of the National Academy of Sciences* **106**, 4623–4628 (2009).
47. Branco, M. C., Pochan, D. J., Wagner, N. J. & Schneider, J. P. Macromolecular diffusion and release from self-assembled β -hairpin peptide hydrogels. *Biomaterials* **30**, 1339–1347 (2009).
48. Ghanaati, S. *et al.* Dynamic *in vivo* biocompatibility of angiogenic peptide amphiphile nanofibers. *Biomaterials* **30**, 6202–6212 (2009).
49. Kayser, O., Lemke, A. & Hernandez-Trejo, N. The impact of nanobiotechnology on the development of new drug delivery systems. *Current pharmaceutical biotechnology* **6**, 3–5 (2005).
50. Keese, M., Gasimova, L., Schwenke, K., Yagublu, V., Shang, E., Faissner, R. & Löhr, M. Doxorubicin and mitoxantrone drug eluting beads for the treatment of experimental peritoneal carcinomatosis in colorectal cancer. *International Journal of Cancer* **124**, 2701–2708 (2009).
51. Ci, T., Chen, L., Yu, L. & Ding, J. Tumor regression achieved by encapsulating a moderately soluble drug into a polymeric thermogel. *Scientific reports* **4**, 1–13, (2014).
52. Basotra, M., Singh, S. K. & Gulati, M. Development and Validation of a Simple and Sensitive Spectrometric Method for Estimation of Cisplatin Hydrochloride in Tablet Dosage Forms: Application to Dissolution Studies. *ISRN Analytical Chemistry* **2013**, 1–8 (2013).
53. Liu, J., Zhang, L., Yang, Z. & Zhao, X. Controlled release of paclitaxel from a self-assembling peptide hydrogel formed *in situ* and antitumor study *in vitro*. *International Journal of Nanomedicine* **6**, 2143–2153 (2011).
54. Briuglia, M. L., Urquhart, A. J. & Lamprou, D. A. Sustained and controlled release of lipophilic drugs from a self-assembling amphiphilic peptide hydrogel. *International journal of pharmaceuticals* **474**, 103–111 (2014).
55. Díaz, D. D., Morin, E., Schön, E. M., Budin, G., Wagner, A. & Remy, J. S. Tailoring drug release profile of low-molecular-weight hydrogels by supramolecular co-assembly and thiol-ene orthogonal coupling. *Journal of Materials Chemistry* **21**, 641–644 (2011).
56. Gonçalves, C., Pereira, P., Schellenberg, P., Coutinho, P. J. & Gama, F. M. Self-assembled dextrin nanogel as curcumin delivery system. **3**, Article ID **18937**, 1–7 (2012).
57. Banquy, X. *et al.* Effect of mechanical properties of hydrogel nanoparticles on macrophage cell uptake. *Soft Matter* **5**, 3984–3991 (2009).
58. Reiner, C. R., Liu, H. & Chang, C. H. Flow cytometric determination of allergen-specific T lymphocyte proliferation from whole blood in experimentally asthmatic cats. *Veterinary immunology and immunopathology* **149**, 1–5 (2012).
59. Mittal, A., Tabasum, S. & Singh, R. P. Berberine in combination with doxorubicin suppresses growth of murine melanoma B16F10 cells in culture and xenograft. *Phytomedicine* **21**, 340–347 (2014).
60. Sanceau, J., Poupon, M. F., Delattre, O., Sastre-Garau, X. & Wietzerbin, J. Strong inhibition of Ewing tumor xenograft growth by combination of human interferon-alpha or interferon-beta with ifosfamide. *Oncogene* **21**, 7700–7709 (2002).

Acknowledgements

We are thankful to the core funding at ICGEB, Delhi and Department of Biotechnology, India, for financial assistance. We thank Girish for mass spectroscopy, Dr. Shiva and Ram for FACS analysis, ICGEB Delhi, AIRF facility of JNU, Delhi for FTIR study, Dr. Shantanu and Ms. Kumud for helping in SEM and ESEM study at IIT Delhi.

Author Contributions

N.Y. and C.K.T. performed the experiments and contributed equally. Prof. V.S.C. supervised and directed the project. Prof. V.S.C. and N.Y. drafted the manuscript and all the authors contributed to scientific discussions of the manuscript.

Additional Information

Supplementary information accompanies this paper at <http://www.nature.com/srep>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Thota, C. K. *et al.* "A novel highly stable and injectable hydrogel based on a conformationally restricted ultrashort peptide". *Sci. Rep.* **6**, 31167; doi: 10.1038/srep31167 (2016).



This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>

© The Author(s) 2016