RESEARCH ARTICLE

Open Access

Modified Mesoporous Silica (SBA-15) with Trithiane as a new effective adsorbent for mercury ions removal from aqueous environment

Mehdi Esmaili Bidhendi^{1*}, Gholam Reza Nabi Bidhendi¹, Nasser Mehrdadi¹ and Hamid Rashedi²

Abstract

Background: Removal of mercury from aqueous environment has been highly regarded in recent years and different methods have been tested for this purpose. One of the most effective ways for mercury ions (Hg^{+2}) removal is the use of modified nano porous compounds. Hence, in this work a new physical modification of mesoporous silica (SBA-15) with 1, 3, 5 (Trithiane) as modifier ligand and its application for the removal of Hg^{+2} from aqueous environment has been investigated. SBA-15 and Trithiane were synthesized and the presence of ligand in the silica framework was demonstrated by FTIR spectrum. The amounts of Hg^{+2} in the samples were determined by cold vapor generation high resolution continuum source atomic absorption spectroscopy. Also, the effects of pH, stirring time and weight of modified SBA-15 as three major parameters for effective adsorption of Hg^{+2} were studied.

Results: The important parameter for the modification of the adsorbent was Modification ratio between ligand and adsorbent in solution which was 1.5. The results showed that the best Hg^{+2} removal condition was achieved at pH = 5.0, stirring time 15 min and 15.0 mg of modified adsorbent. Moreover, the maximum percentage removal of Hg^{+2} and the capacity of adsorbent were 85% and 10.6 mg of Hg^{+2} /g modified SBA-15, respectively.

Conclusions: To sum up, the present investigation introduced a new modified nano porous compound as an efficient adsorbent for removal of Hg^{+2} from aqueous environment.

Keywords: Mercury, Mesoporous Silica, Adsorbent, Modified, Wastewater, SBA-15, Trithiane

Introduction

Mercury as a kind of heavy metal is present in industrial wastewater such as chemical industry, mining, refining petrochemical and a wide variety of industrial activities [1,2]. This toxic and hazardous chemical compound has harmful effects on the environment and human health. In fact, mercury due to its bioaccumulation property the same as other heavy metals [3], has damaging effects on vital organs such as heart, brain, liver and fatty texture and will result in different cancers. Therefore, this compound is considered as one of the most toxic metals found in the environment and a main source of pollution [4,5]. Hence, nowadays mercury ions removal from aqueous environment (water & wastewater) as one of

the major challenges for hygienic management of societies has been the subject of extensive technological research [6]. Several methods including solvent extraction chemical precipitation, vacuum evaporation, membrane technologies, ion exchange, adsorption and membrane separation have been developed and used to remove Hg^{+2} from environment [1,7-10], but some of these methods such as adsorption owing to different problems like low mechanical and thermal stability and a weak chemical union with the Hg^{+2} , are often costly or inefficient for removing Hg^{+2} from dilute solutions [1,10,11]. Thus, the scientific community has felt obliged to look for a new method to remove Hg^{+2} from the environment [10]. Hence, synthesis and modification of adsorbents for the removal Hg^{+2} and other heavy metals ions from water and wastewater is a continuing research objective for the control of environmental pollution [12-17]. In this regard, the development of modified mesoporous materials based on

* Correspondence: Esmailib@ut.ac.ir

¹Department of Environmental Engineering, Graduate Faculty of Environment, University of Tehran, Tehran, Iran

Full list of author information is available at the end of the article

MCM-41 and SBA-15 [18] because of their great advantages among large surface area, uniform pore size and controlled surface chemistry for adsorption applications including removal and determination of metal ions [19-24], radio nuclides [25], dyes [26], organics [27], and anionic complexes [28,29], has generated considerable interest [30]. According to the abovementioned, SBA-15 as one of the main types of mesoporous silica materials [31] is a highly common material possessing a regular two dimensional hexagonal array of channels [30]. This material is prepared with non-ionic amphiphilic triblock copolymer micelles as the template under acidic reaction conditions [10]. The pore size of this material typically can be varied between 7–10 nm [30], by varying the synthesis temperature (between 30 and 90°C) and the template [10]. Furthermore, a variety of functional groups such as organic ligands can be grafted or incorporated chemically or physically on the surface of mesoporous channels and prepare highly effective and selective adsorbents [32,33]. Therefore, in this research, 1, 3, 5 Trithiane due to its ability to adsorb Hg^{+2} has been chosen as the ligand for the modification of SBA-15 resulting in a new adsorbent for removing Hg^{+2} from aqueous environment and the Batch method was applied in order to examine the capability of this new adsorbent.

Materials and methods

Reagents and chemicals

All chemicals and reagents used in this research were of analytical grade purchased from Merck Company (Darmstadt, Germany). Also, doubly distilled deionized water was used throughout for preparing all solutions. A stock solution (1000 mg L^{-1}) of Hg^{+2} was prepared by dissolving the appropriate amounts of $\text{Hg}(\text{NO}_3)_2$ in doubly distilled deionized water and also a stock standard acetate buffer solution with pH 5.0 was prepared by mixing 14.8 mL 0.2 M acetic acid with 35.2 mL 0.2 M sodium acetate trihydrate and volume with doubly distilled deionized water to 100 mL.

Apparatus

An Analytik Jena cold vapor generation high resolution continuum source atomic absorption spectroscopy (model: contrAA 700) was used for the determination of Hg^{+2} in the samples. The optimized default conditions of this instrument conformed to Aspect CS 1.5.6 software released by the company. FTIR analyses of the modified and non-modified SBA-15 were performed in a Fourier transform infrared spectroscopy (Bruker-Tensor 27). The samples pH values were measured by a Metrohm pH-meter (model: 713, Herisau, Switzerland) equipped with a glass-combined electrode.

Synthesis of SBA-15

SBA-15 preparation was based on the procedure in the literature [34]. 2.0 g of triblock copolymer P123 ($\text{EO}_{20}\text{PO}_{70}\text{EO}_{20}$) was dissolved in 60.0 g of 2 M Hydrochloric acid (HCl) aqueous solution stirred at 40°C. Then 4.3 g of Tetraethylorthosilicate (TEOS) was added to the homogeneous solution and stirred at this temperature for 24 h. Finally, it was heated to 100°C and held at this temperature for 24 h under static conditions. The prepared sample was filtered, and then washed with water and air-dried at room temperature. The removal of the template was carried out at 550°C in air for 5 h.

Synthesis of 1, 3, 5 Trithiane as Modifier

Since SBA-15 as the base adsorbent is not efficient for metal ions removal from aqueous environment, it needs modifying. One organic ligand that has the ability to form complex with Hg^{+2} is 1, 3, 5 Trithiane which was previously reported by research in literature [35]. This organic compound (Figure 1) as modifier ligand was prepared based on the procedure in literature [36]. A mixture of 32.6 g of Formaldehyde solution %36 (w/w) and 70 cc of concentrated Hydrochloric acid were used and then Hydrogen sulfide passed through the solution until no more precipitate was formed. In order to facilitate the process, the accumulated mass of crystals was removed by filtration from time to time. Afterward, the product was purified by the inverted filtration method.

Figure 1 Chemical structure of Trithiane.

Modification of SBA-15

Modification of the prepared SBA-15 was performed by dissolving 60 mg of Trithiane in adequate amount of Acetonitrile and adding 40 mg of SBA-15 and mixing for 15 min. Next, the solution was filtered and the solid phase as the functionalized product was exposed to atmosphere and used as a new sorbent for this research.

Metal adsorption experiments

The general procedure for removal of Hg^{+2} by the modified SBA-15 was as follows: A batch system was employed for the removal of Hg^{+2} and removing was performed in a beaker containing 10 mL (10 mg L^{-1}) Hg^{+2} solutions. About 10 mg modified SBA-15 was added to the solution. Then the mixture was stirred for 10 min to remove Hg^{+2} from the solution. Finally, filtration was performed and Hg^{+2} concentrations were determined by cold vapor generation high resolution continuum source atomic absorption spectroscopy (model: contrAA 700).

Results and discussion

SBA-15 modification seems essential through suitable ligand because this mesoporous adsorbent has a major problem removing Hg^{+2} from aqueous environment selectively and efficiently. Previous studies [35] indicated that 1, 3, 5 Trithiane as organic ligand has an efficient interaction with Hg^{+2} . Hence, it was used in the modification of SBA-15 for the removal of Hg^{+2} . The preliminary experiments showed that the removal of Hg^{+2} ions by non-modified and modified SBA-15 was obviously different and the former cannot remove Hg^{+2} quantitatively.

FTIR analysis

For the characterization of the modified SBA-15, infrared spectrum was recorded on Bruker-Tensor 27 spectrophotometer in the region $400 - 4000 \text{ cm}^{-1}$ using spectra quality KBr powder. According to Figure 2 the distinguished band at 1508 cm^{-1} can be assigned to Trithiane.

Effect of Modified Ratio (Ligand / SBA)

Modification ratio between ligand and adsorbent shown in this research as (Ligand / SBA-15) is one of the parameters affecting the prepared efficient modified adsorbent. In this study, mesoporous silica has been modified by Trithiane ligand by 3 modification ratios as 0.5, 1 and 1.5 (w/w). Then all the modified adsorbents were tested for removing Hg^{+2} from the samples. The results showed that the adsorbent modified by 1.5 (Ligand/SBA-15 w/w) has the maximum percentage of Hg^{+2} removal from the samples compared to the other two modification ratios. According to the obtained results, higher modification ratios were not studied in this research because the modified adsorbent has to be economical. On the other hand, the Hg^{+2} removal process revealed that by raising the modification ratio from 0.5 to 1 and 1 to 1.5, the percentage of removal increased slightly. Therefore, in the subsequent experiments we used 1.5 (Ligand / SBA-15 w/w) modification ratio.

Effect of pH

The aqueous samples pH adjustment is one of the major parameters in order to obtain efficient removal of toxic metal ions by specific adsorbents such as modified mesoporous silica. Hence, in this research the

Figure 2 FTIR spectrum of modified SBA-15.

Figure 3 Effect of pH on the removal of Hg²⁺.

effect of pH on the removal of Hg²⁺ ions with modified adsorbent was studied at different pH values ranging from 4.0 to 8.0. As shown in Figure 3, the percentage of Hg²⁺ ions adsorption increased significantly between pH 4.0 – 5.0 and then at pH higher than 5.0 decreased extremely. In pH values higher than 8.0, modified mesoporous silica may be hydrolyzed in alkali solutions due to the breaking of the Si-O-Si bonds by hydroxide ions attack so this range of pH was not studied. Also, pH values lower than 4.0, were not studied in this research because this range due to decreasing pH value causes the ligand to be surrounded by H⁺ ions and prevents Hg²⁺ from reaching the ligand to form complexes for its removal from the environment. Therefore, pH value of

the sample solutions was adjusted at 5.0 in the subsequent experiments.

Effect of Weight of Adsorbent

The optimum amount of the modified SBA-15 for maximum removal of Hg²⁺ was investigated by testing different amounts of modified sorbent (1, 2, 5, 10, 15, 30 and 45 mg) for Hg²⁺ uptake from the samples. As can be seen from Figure 4 in which the results are given, by raising the sorbent amount from 1 to 15 mg the percentage of Hg²⁺ removal increased significantly and in the range of 15 to 45 mg the percentage of removal was almost constant. Hence, in the experiments 15.0 mg of modified SBA-15 was used thereafter.

Figure 4 Effect of amount of adsorbent on the removal of Hg²⁺.

Figure 5 Effect of amount of stirring time on the removal of Hg²⁺.

Effect of the stirring time on removal yield

The effect of stirring time on Hg²⁺ ions removal was investigated by performing a series of removal experiments with the same conditions and at several times (1, 3, 5, 10, 15 and 20 min). According to the results shown in Figure 5, Hg²⁺ removal up to 15 min increased and then was nearly constant. Therefore, the 15-min stirring time was used afterward.

Capacity of the modified SBA-15

The adsorbent capacity is an important parameter in adsorption processes because it determines how much adsorbent is required to quantitatively remove a specific amount of metal ions from the solutions [37]. Thus, the adsorption capacity of Hg²⁺ per unit weight of the modified adsorbent at time *t*, *q_t* (mg g⁻¹), was calculated from the mass balance:

$$q_t = \frac{(C_0 - C_t) \times V}{m}$$

Where *C*₀ (mg L⁻¹) is the initial concentration of Hg²⁺ and *C_t* (mg L⁻¹) is Hg²⁺ concentration at time *t*. *V* is the volume of Hg²⁺ solutions and *m* is the mass of the modified mesoporous. The capacity of the modified adsorbent was found to be 10.6 mg of Hg²⁺/g modified SBA-15.

Conclusion

In the present research, new and effective modified mesoporous silica was prepared and tested in batch mode for Hg²⁺ removal from the aqueous samples. The results demonstrated a successful application of modified SBA-15 for the effective removal of Hg²⁺ as a rapid and easy method. Maximum percentage of removal happened

at pH equal to 5.0, 15-min stirring time and using 15 mg of modified adsorbent. As adsorbents are used in wastewater treatment plants, the preparation of an applicable form of adsorbent such as an adsorption column and the determination of its effective parameters proves necessary so the authors will focus on this target in the future.

Competing interests

The authors declare that they have no competing interests.

Authors' contributions

This research is a part of the thesis by MEB who prepared the literature survey and performed the experiments. NM and HR participated in the design of the study, data analysis, and manuscript preparation. GRNB was the advisor. All the authors have read and approved the final manuscript.

Acknowledgment

The authors acknowledge the financial and scientific support provided by the Center of excellence in electrochemistry and Graduate faculty of Environment at the University of Tehran.

Author details

¹Department of Environmental Engineering, Graduate Faculty of Environment, University of Tehran, Tehran, Iran. ²Department of Chemical Engineering, Faculty of Engineering, University of Tehran, Tehran, Iran.

Received: 8 February 2014 Accepted: 17 June 2014

Published: 25 June 2014

References

1. Rostamian R, Najafi M, Rafati AA: **Synthesis and characterization of thiol-functionalized silica nano hollow sphere as a novel adsorbent for removal of poisonous heavy metal ions from water: Kinetics, isotherms and error analysis.** *Chem Eng J* 2011, **171**:1004–1011.
2. Aguado J, Arsuaga JM, Arencibia A, Lindo M, Gascon V: **Aqueous heavy metals removal by adsorption on amine-functionalized mesoporous silica.** *J Hazard Mater* 2009, **163**:213–221.
3. Boening DW: **Ecological effects, transport, and fate of mercury: a general review.** *Chemosphere* 2000, **40**(12):1335–1351.
4. Evangelista SM, Deoliveira E, Castro GR, Zara LF, Prado AGS: **Hexagonal mesoporous silica modified with 2-mercaptothiazoline for removing mercury from water solution.** *Surf Sci* 2007, **601**:2194–2202.

5. Esmaeili Bidhendi M, Karbassi AR, Baghvand A, Saeedi M, Pejman AH: Potential of natural bed soil in adsorption of heavy metals in industrial waste landfill. *Int J Environ Sci Tech* 2010, **7**(3):545–552.
6. Lee B, Kim Y, Lee H, Yi J: Synthesis of functionalized porous via templating method as heavy metal ion adsorbents: the introduction of surface hydrophilicity onto the surface of adsorbents. *Micropor Mesopor Mater* 2001, **50**:77–90.
7. Nabi SA, Shahadat M, Bushra R, Shalla AH, Ahmed F: Development of composite ion-exchange adsorbent for pollutants removal from environmental wastes. *Chem Eng J* 2010, **165**:405–412.
8. Najafi M, Rostamian R, Rafati AA: Chemically modified silica gel with thiol group as an adsorbent for retention of some toxic soft metal ions from water and industrial effluent. *Chem Eng J* 2011, **168**:426–432.
9. Huuha TS, Kurniawan TA, Sillanpaa MET: Removal of silicon from pulping whitewater using integrated treatment of chemical precipitation and evaporation. *Chem Eng J* 2010, **158**:584–592.
10. Quintanilla DP, Hierro ID, Fajardo M, Sierra I: 2-Mercaptothiazoline modified mesoporous silica for mercury removal from aqueous media. *J Hazard Mater* 2006, **B134**:245–256.
11. Babel S, Kurniawan TA: Low-cost adsorbents for heavy metals uptake from contaminated water: a review. *J Hazard Mater* 2003, **97**:219–243.
12. Mahmoud ME, Osman MM, Hafez OF, Hegazi AH, Elmelegy E: Removal and preconcentration of lead (II) and other heavy metals from water by alumina adsorbents developed by surface-adsorbed-dithione. *Desalination* 2010, **251**:123–130.
13. Mahmoud ME, Kenawy IMM, Hafez MAH, Lashein RR: Removal, preconcentration and determination of trace heavy metal ions in water samples by AAS via chemically modified silica gel N-(1-carboxy-6-hydroxy) benzylidenepropylamine ion exchanger. *Desalination* 2010, **250**:62–70.
15. Burham N: Separation and pre concentration system for lead and cadmium determination in natural samples using 2-aminoacetylthiophenol modified polyurethane foam. *Desalination* 2009, **249**:1199–1205.
16. Ciftci H, Yalcin H, Eren E, Olcucu A, Sekerci M: Enrichment and determination of Ni^{2+} ions in water samples with a diamino-4-(4-nitro-phenylazo)-1H-pyrazole (PDANP) by using FAAS. *Desalination* 2010, **256**:48–53.
17. Chakravarty P, Sen Sarma N, Sarma HP: Removal of lead (II) from aqueous solution using heartwood of Areca catechu powder. *Desalination* 2010, **256**:16–21.
18. Lei B, Li B, Zhang HR, Lu SZ, Zheng ZH, Li WL, Wang Y: Mesoporous Silica Chemically Doped with Rull as a Superior Optical Oxygen Sensor. *Adv Funct Mater* 2006, **16**(14):1883–1891.
19. Perez-Quintanilla D, Sanchez A, Del Hierro I, Fajardo M, Sierra I: Preparation of 2-mercaptobenzenothiazole-derivatized mesoporous silica and of Hg (II) from aqueous solution. *J Environ Monit* 2006, **8**:214–222.
20. Perez-Quintanilla D, Sanchez A, Del Hierro I, Fajardo M, Sierra I: Preconcentration of Zn (II) in water samples using a new hybrid SBA-15-based material. *J Hazard Mater* 2009, **166**:1449–1458.
21. Perez-Quintanilla D, Sanchez A, Del Hierro I, Fajardo M, Sierra I: Solid phase extraction of Pb(II) in water samples using a new hybrid inorganic-organic mesoporous silica prior to its determination by FAAS. *Microchim Acta* 2009, **165**:291–298.
22. Kang T, Park Y, Choi K, Sang Leec J, Yi J: Ordered mesoporous silica (SBA-15) derivatized with imidazole-containing functionalities as a selective adsorbent of precious metal ions. *J Mater Chem* 2004, **14**:1043–1049.
23. Ganjali MR, Hajiaghababaei L, Badiei AR, Saberyan K, Salavati-Niasari M, Ziarani GM, Behbahani SMR: A novel method for fast enrichment and monitoring of hexavalent and trivalent chromium at the PPT level with modified silica MCM-41 and its determination by inductively coupled plasma optical emission spectrometry. *Quim Nova* 2006, **29**:440–443.
24. Ganjali MR, Hajiaghababaei L, Badiei AR, Ziarani GM, Tarlani A: Novel method for the fast preconcentration and monitoring of a ppt level of lead and copper with a modified hexagonal mesoporous silica compound and inductively coupled plasma atomic emission spectrometry. *Anal Sci* 2004, **20**:725–729.
25. Ju YH, Webb OF, Dai S, Lin JS, Barnes CE: Synthesis and characterization of ordered mesoporous anion-exchange inorganic hybrid resins for radionuclide separation. *Ind Eng Chem Res* 2000, **39**:550–553.
26. Ho KY, McKay G, Yeung KL: Selective adsorbents from ordered mesoporous silica. *Langmuir* 2003, **19**:3019–3024.
27. Lim MH, Stein A: Comparative studies of grafting and direct syntheses of inorganic-organic hybrid mesoporous materials. *Chem Mater* 1999, **11**:3285–3295.
28. Lee B, Bao LL, Im HJ, Dai S, Hagaman EW, Lin JS: Synthesis and characterization of organic-inorganic hybrid mesoporous anion-exchange resin for perhenate (ReO_4^-) anion adsorption. *Langmuir* 2003, **19**:4246–4252.
29. Fryxell GE, Liu J, Hauser TA, Nie Z, Ferris KF, Mattigod S, Gong M, Hallen RT: Design and synthesis of selective mesoporous anion traps. *Chem Mater* 1999, **11**:2148–2154.
30. Hajiaghababaei L, Badiei A, Ganjali MR, Heydari S, Khaniani Y, Mohammadi Ziarani G: Highly efficient removal and preconcentration of lead and cadmium cations from water and wastewater samples using ethylenediamine functionalized SBA-15. *Desalination* 2011, **266**:182–187.
31. Zhao D, Huo Q, Feng J, Chmelka BF, Stucky GD: Nonionic triblock and star diblock copolymer and oligomeric surfactant syntheses of highly ordered, hydrothermally stable, mesoporous silica structures. *J Am Chem Soc* 1998, **120**:6024–6037.
32. Badiei A, Norouzi P, Tousi F: Study of electrochemical behavior and adsorption mechanism of $[\text{Co}(\text{en})_2\text{C}_{12}]^+$ on mesoporous modified carbon paste electrode. *Eur J Sci Res* 2005, **12**:39–45.
33. Badiei A, Bonnevot L, Crowther N, Mohammadi Ziarani G: Surface tailoring control in micelle templated silica. *J Organomet Chem* 2006, **691**:5923–5931.
34. Murty DSR, Chakrapani G: Preconcentration of rare earth elements on activated carbon and its application to groundwater and sea-water analysis. *J Anal At Spectrom* 1996, **11**:815–820.
35. Ercan Ö, Aydinb A: Removal of Mercury, Antimony, Cadmium and Lead from Aqueous Solution using 1,3,5-Trithiane as an Adsorbent. *J Braz Chem Soc* 2013, **24**(5):865–872.
36. Organic Syntheses. In Coll. Vol. 2, p.610 (1943); Vol. 16, p.81 (1936). [http://www.orgsyn.org/Content/pdfs/procedures/CV2P0610.pdf]
37. Dev K, Rao GN: Preparation and analytical properties of a chelating resin containing bicine groups. *Talanta* 1995, **42**:591–596.

doi:10.1186/2052-336X-12-100

Cite this article as: Esmaeili Bidhendi et al.: Modified Mesoporous Silica (SBA-15) with Trithiane as a new effective adsorbent for mercury ions removal from aqueous environment. *Journal of Environmental Health Science & Engineering* 2014 **12**:100.

Submit your next manuscript to BioMed Central and take full advantage of:

- Convenient online submission
- Thorough peer review
- No space constraints or color figure charges
- Immediate publication on acceptance
- Inclusion in PubMed, CAS, Scopus and Google Scholar
- Research which is freely available for redistribution

Submit your manuscript at
www.biomedcentral.com/submit