

NANO EXPRESS

Open Access

A large-scale fabrication of flower-like submicrometer-sized tungsten whiskers via metal catalysis

Yunzhu Ma^{*}, Jing Li, Wensheng Liu and Yubin Shi

Abstract

Tungsten powder mixed with an appropriate amount of nickel and iron powders is used as raw material to fabricate large-scale tungsten whisker-like structure. The morphology, microstructure and composition of the whisker-like tungsten are observed and tested by scanning electron microscope and FESEM, transmission electron microscopy, X-ray spectroscopy, and X-ray diffraction, respectively. The main component of the tungsten whisker-like structure is tungsten, which has the axial growth along the $\langle 100 \rangle$ direction with large aspect ratio and possesses flower-like structure. Large-scale submicrometer-sized whisker-like tungsten was fabricated via vapor phase deposition approach with the aid of metal catalysts at 800°C by holding for 6 h in the appropriate atmosphere. The growth procedure of flower-like tungsten whisker is probably based on the vapor–liquid–solid mechanism at beginning of the formation of tungsten nuclei, then vapor–solid mechanism is dominant.

Keywords: Nanomaterials, Tungsten whisker-like, Metal catalysis-assisted, Flower-like, Growth mechanism, Large scale fabrication

Background

One-dimensional nanomaterials of tungsten have excellent performance of chemical, physical, electrical, and mechanical properties [1], so metallic tungsten one-dimensional nanomaterials have attracted considerable attention as promising materials for field emitters [2-4], displays [5], sensors [6,7], etc. Many approaches were used to prepare tungsten one-dimensional nanomaterials, such as metal catalysis induction method [8,9], vapor deposition [10,11], template [12] or substrate [13], etching [14,15], sputtering [2] or electron beam-induced deposition [3,16], etc. However, organizing these one-dimensional nanomaterials into highly ordered arrays can be extremely challenging. The key problem in the preparation of tungsten one-dimensional nanomaterials is to control their morphology, size and uniformity effectively at the same time. So, many growth mechanisms had been proposed according to the experiment results to control the growth of tungsten one-dimensional nanomaterials accurately.

It is crucial to understand the tungsten one-dimensional nanomaterial (e.g., nanowires, nanofibers, nanorods, nano-needles) growth mechanism for the growth control of tungsten nanomaterials accurately. Because of its high melting point, low atomic diffusion rate and other special properties, there are both similarities and differences between the growth mechanism of tungsten nanomaterials and general inorganic nanomaterials. For this reason, the researchers had proposed a number of growth models which could be used for reference, for example, VS model [17,18], vapor–liquid–solid (VLS) model [19-22], VSS model [8,23], etc. The growth mechanism is different with distinct preparation conditions.

In this research, a novel route with low cost was used, and large-scale flower-like submicrometer-sized tungsten whiskers were prepared by the vapor phase deposition method with the aid of metal catalysts. According to the experiment results, the growth model of tungsten whisker-like structure was proposed.

Methods

The raw materials are tungsten powders (purity, 99.5 wt.%; particle size, 1 to 3 μm), carbonyl iron powders (purity, 99.5 wt.%; particle size, 3 to 5 μm) and carbonyl nickel

* Correspondence: zhuzipm@csu.edu.cn
State Key Laboratory for Powder Metallurgy, Central South University,
Changsha, Hunan Province 410083, People's Republic of China




Figure 1 Morphologies of flower-like tungsten whisker produced. (a) Single-bundle flower-like tungsten whiskers; (b) large-scale flower-like tungsten whiskers.

powders (purity, 99.5 wt.%; particle size, 3 to 5 μm). The mixed powders (weight ratio of W:Ni:Fe equals 93:4.9:2.1) were obtained by wet milling for 2 h, then the mixed powders with a weight of 2.0 g were reacted by holding for 6 h in a horizontal tube furnace at 800°C. The atmosphere was a mixed gas of N_2 , H_2 and a little water vapor. The flow rates of N_2 and H_2 were 0.3 and 0.03 L/min, respectively. The water vapor was brought into the system by the water bath of H_2 , and the water bath temperature was 80°C. The as-products were characterized by X-ray diffraction (XRD), scanning electron microscopy and FESEM, energy dispersive spectroscopy (EDS) and transmission electron microscopy (TEM), respectively.

Results and discussion

Characteristics of the submicrometer-sized tungsten whiskers

Figure 1 shows the morphology of as-produced tungsten whiskers. It has a flower-like figuration with a sinter as its growing center. The results indicated that the tungsten whisker-like structure was grown from the sintered powder, and the corresponding EDS pattern was shown in Figure 2.

The XRD pattern of the as-products (Figure 3) indicated that the main phase was tungsten with little tungsten oxide.

Figure 4 shows the effect of Fe element on morphology of the flake-like structure. It implied that Fe element was benefit to the nucleation of tungsten flakes, and the aggregation formed by sintering possessed the highest content of Fe element, namely 23.58 wt.%. From bottom to top of the flake, the content of Fe element reduced gradually. Otherwise, the content of the Ni element only appeared a little.

During the experiment, besides the segregation of Fe element, the segregation of Ni element also existed. Figure 5 shows a typical structure in which the whisker-like tungsten grew from the Ni element segregation configuration and the EDS patterns of different proportion. It showed that the content of Ni element reduced gradually from the bottom to the upper of the whisker-like structure. The aggregation structure resulted from melt containing the higher content of Ni element. The tip of the whisker had the lower content of Ni element, and at the same time, the content of Fe element changed a little. It implied that Ni element was benefit to the nucleation of tungsten whiskers.





Figure 2 EDS pattern of whisker-like tungsten produced. ZAF, Z is atomic number correction factor, A is absorption correction factor, and F is fluorescence correction factor.






Figure 6 shows a series of images of different structures during the growing process of the tungsten whisker-like structure for different times. Figure 6a shows some imperceptible tungsten nanowires which grew from sintered powder by holding for 3 h; Figure 6b shows an initial large-scale tungsten whisker-like structure by holding for 4.5 h; and Figure 6c shows large-scale flower-like tungsten whisker structure caused by growing along different grains in the same pre-sintering aggregation by holding for 6 h. Figure 7 is the TEM image and SAED of the tungsten whisker-like structure with the axial growth along $\langle 100 \rangle$ direction.


Growth mechanism

It is well known that the reaction between W and humid H_2 is a complex process. Much research had been made about this process. Reaction with water vapor or humid H_2 in the temperature range from 20°C to 500°C results in the formation of a WO_3 layer. The thickness of the






oxide layer increases with the increase of temperature. When the temperature increases to 500°C or 600°C, it can be severely oxidized to form WO₃, which starts to evaporate with the formation of WO₂(OH)₂. At the temperature > 600°C, gaseous WO₂(OH)₂ is the most volatile compound formed in system W-O-H. It is responsible for all vapor-phase transport processes [24]. When the temperature reaches to 800°C, it can form large quantity of volatile. In the high water vapor content, W can react with water vapor directly, which can be expressed in the following:



The reaction of oxides of tungsten with water vapor can be expressed as follows:



The formation and decomposition process of volatile compounds of WO₂(OH)₂ can be expressed as in the equation below:



According to van't Hoff isotherm, Gibbs free energy of Equation 3 can be calculated as follows:

$$\begin{aligned} \Delta_r G &= \Delta_r G^\ominus + RT \ln Q = -RT \ln K_p + RT \ln Q \\ &= -\frac{4}{3} RT \ln \frac{P_{H_2O}^\ominus}{P_{H_2}^\ominus \cdot P_{WO_2(OH)_2}^\ominus} + \frac{4}{3} RT \ln \frac{P_{H_2O}}{P_{H_2} \cdot P_{WO_2(OH)_2}} \end{aligned} \quad (4)$$

where $\Delta_r G$ is the Gibbs free energy diversification of the reduction system; $\Delta_r G^\ominus$ is the Gibbs free energy at the standard state; R is constant, equal to 8.314 J·K⁻¹·mol⁻¹; T is reaction temperature; Q is pressure ratio of the materials at actual conditions; K_p is equilibrium constant; P_{H₂O}, P_{H₂}, and P_{WO₂(OH)₂} are the partial pressures of H₂O, H₂ and WO₂(OH)₂, respectively.




Figure 6 Typical flower-like structures formed in growing process of whisker-like tungsten for different times. (a) Nanowire-like structure by holding for 3 h; (b) initial large-scale tungsten whisker-like structure by holding for 4.5 h; (c) large-scale flower-like tungsten whisker structures by holding for 6 h.

The oxidation of W by water vapor and the reduction of WO_3 by H_2 are reversible processes. The direction of reaction can be changed by adjusting the partial pressure ratio of $[H_2O]/[H_2]$ and further affects the growing

process of tungsten whisker-like structure. For the presence of volatile compounds of $WO_2(OH)_2$ in the chemical reaction, the reaction atmosphere has a significant impact on the final product. The premise of ensuring $\Delta_r G \leq 0$, increasing partial pressure ratio of water vapor and hydrogen, is conducive to the generation of many volatile compounds of $WO_2(OH)_2$, which is the origin of fabrication of tungsten whiskers by vapor phase transmission and reduction of hydrogen.





Figure 7 The TEM image of tungsten whisker-like structure. Inset: SAED pattern of tungsten whisker-like structure.

According to above-reported results, the most distinct characteristic of the formed whisker-like structure is that the whisker-like tungsten has Ni-enriched structure at the bottom. We summarized the growth process of flower-like tungsten whiskers as follows: firstly, the W powder mixed with Ni and Fe was oxidized by water vapor, which would release lots of heat. The produced heat would bring the local temperature up to the melting point of Ni and Fe, this would lead to the formation of little liquid phase area, and the melting heat with the melting process would improve the temperature of the liquid system. The emergence of liquid phase caused the segregation of Ni or Fe element in some part of the system (Figure 8a). Secondly, in the atmosphere of H_2 , gaseous $WO_2(OH)_2$ produced by the oxidation of tungsten and tungsten oxide by water vapor will be reduced and decomposed to form tungsten fluid phase with highly free energy (Figure 8b). This fluid phase was a



kind of metastable phase, it tended to form crystalline phase to reduce its Gibbs free energy. So, driven by the phase transition force, the tungsten fluid phase cohered to form tungsten embryos (Figure 8c). The tungsten embryos whose radius increased up to the critical nucleus radius will deposit at the site with appropriate liquid concentration of Ni and Fe to form tungsten nuclei (Figure 8c,d). The newly formed tungsten atoms in fluid phase will be adsorbed and deposited preferentially at the crystal plane of $\langle 100 \rangle$ because of the difference of different crystal face in surface energy. Then, tungsten atoms diffuse along the side to the top, finally integrate with the top of the nanocrystal via the homoepitaxial growth, and thus lead to the axial growth along the $\langle 100 \rangle$ direction (Figure 8e). Under the guidance of crystal defects and high surface energy, the tungsten whisker-like structure was generated through pro-plane growth. During the growing of axial direction, the radial direction expanded at the same time because some tungsten atoms lingered around. The vapor phase transmission W atoms will be adsorbed preferentially on the sides and the tops of the W $\langle 100 \rangle$ nanocrystallite that protruded from the W substrates (Figure 8f). From Figures 1, 4, 5 and 6, it was very clear that mixing

powder was pre-sintering and came into the aggregation, which included many small tungsten particles and little local liquid phase areas. Every small liquid phase area exposed to vapor phase may form tungsten whisker-like structures according to the above description. So, flower-like tungsten whiskers formed on the aggregation.

Due to the appearance of local high-temperature area, Ni and W can come into little solid solution (Ni_4W). Otherwise, because of a considerable solid solution of W in Ni (about 16 at%) at 950°C and the very low solid solubility of Ni in W (about 0.05at%) [24], W atoms may dissolve into Ni particles to form solid Ni-W alloyed particles, and it is easy to reach saturation. W atoms diffuse through the solid Ni-W particle to form the nucleus of pure W nanocrystal. The subsequent W atoms integrate directly with the preformed W $\langle 100 \rangle$ layer and result in the formation of a protrudent W $\langle 100 \rangle$ whisker-like structure.

According to above description, the growth procedure of flower-like tungsten whiskers is probably based on the VLS mechanism at beginning of the formation of tungsten nuclei, that is, the VLS stage is from Figure 8a-d. After that, vapor-solid mechanism is dominant (Figure 8e,f).

Conclusions

In summary, a novel route with low-cost to large-scale flower-like submicrometer-sized tungsten whiskers were fabricated by the vapor phase deposition method with the aid of metal catalysts. A large-scale submicrometer-sized tungsten whisker-like structure had the axial growth along the $\langle 100 \rangle$ direction with large aspect ratio and possessed flower-like structure grown from the aggregation formed by sintering of W powder mixed with Ni powder. The growth procedure of flower-like tungsten whiskers is probably based on the VLS mechanism at beginning of the formation of tungsten nuclei. After that, vapor-solid mechanism is dominant.

Competing interests

The authors declare that they have no competing interests.

Authors' contributions

YM carried out the experiments, participated in the sequence analysis and drafted the manuscript. JL carried out the partial experiments and participated in the mechanism analysis. WL participated in the design of the study and performed partial analysis. YS participated in the partial experiments. All authors read and approved the final manuscript.

Acknowledgments

The authors thank the National Natural Science Foundation of China (grant no. 50774098) and Creative Research Group of National Natural Science Foundation of China (grant no. 50721003) for the financial support.

Received: 20 May 2012 Accepted: 10 June 2012

Published: 21 June 2012

References

1. Kuchibhatla SVNT, Karakoti AS, Bera D, Seal S: **One dimensional nanostructured materials.** *Prog Mater Sci* 2007, **52**(5):699–913.
2. Umnov AG, Shiratori Y, Hiraoka H: **Giant field amplification in tungsten nanowires.** *Appl Phys A* 2003, **77**:159–161.
3. Yang X, Simpson ML, Randolph SJ, Rack PD, Baylor LR, Cui H, Gardner WL: **Integrated tungsten nanofiber field emission cathodes selectively grown by nanoscale electron beam-induced deposition.** *Appl Phys Lett* 2005, **86**:183106.
4. Baek Y, Song Y, Yong K: **A novel heteronanostructure system: hierarchical W nanothorn arrays on WO₃ nanowhiskers.** *Adv Mater* 2006, **18**:3105–3110.
5. Spindt CA, Holland CE, Brodie I, Mooney JB, Westerberg ER: **Field-emitter arrays applied to vacuum fluorescent display.** *IEEE Trans Electron Devices* 1989, **36**:225.
6. Zhao YM, Zhu YQ: **Room temperature ammonia sensing properties of W₁₈O₄₉ nanowires.** *Sensor Actuator B Chem* 2009, **137**(1):27–31.
7. Ponzoni A, Comini E, Sberveglieri G, Zhou J, Deng SZ, Xu NS, Ding Y, Wang ZL: **Ultrasensitive and highly selective gas sensors using three-dimensional tungsten oxide nanowire networks.** *Appl Phys Lett* 2006, **88**:203101.
8. Wang SL, He YH, Zou J, Wang Y, Huang H, Huang BY, Liu CT, Liaw PK: **Catalytic growth of metallic tungsten whiskers based on the vapor-solid-solid mechanism.** *Nanotechnology* 2008, **19**:345604–345608.
9. Wang C, He Y, Wang S, Zhang Q, Liu X: **Low-temperature growth of tetragonal tungsten nanowire arrays on tungsten substrate using Ni solid catalysts.** *Journal of Crystal Growth* 2012, **338**:214–217.
10. Vaddiraju S, Chandrasekaran H, Sunkara MK: **Vapor phase synthesis of tungsten nanowires.** *J Am Chem Soc* 2003, **125**(36):10792–10793.
11. Bien DCS, Saman RM, Badaruddin SAM, Lee HW: **Selective formation of tungsten nanowires.** *Nanoscale Research Letters* 2011, **6**(1):543.
12. Li YD, Li XL, Zhou BC: **From surfactant-inorganic mesostructures to tungsten nanowires.** *Angew Chem* 2002, **114**(2):343.
13. Song MH, Mitsuishi K, Furuya K: **Fabrication of free-standing tungsten-nanowhiskers on SiO₂ substrates with electron-beam induced deposition.** *Mater Trans* 2007, **48**(10):2551–2555.
14. Guise OL, Ahner JW, Jung MC, Goughnour PC, Yates JT: **Reproducible electrochemical etching of tungsten probe tips.** *Nano Letters* 2002, **2**(3):191–193.
15. Onoda J, Mizuno S: **Fabrication of $\langle 110 \rangle$ oriented tungsten nano-tips by field-assisted water etching.** *Appl Surf Sci* 2011, **257**:8427–8432.
16. Chen CL, Arakawa K, Mori H: **Two-dimensional metallic tungsten nanowire network fabricated by electron-beam-induced deposition.** *Nanotechnology* 2010, **21**:285304–285307.
17. Brenner SS, Sears GW: **Mechanism of whisker growth-III nature of growth sites.** *Acta Metallurgica* 1956, **4**(3):268–270.
18. Yang PD, Lieber CM: **Nanostructured high-temperature superconductors: creation of strong-pinning columnar defects in nanorod/superconductor composites.** *J Mater Res* 1997, **12**(11):2981–2996.
19. Wagner RS, Ellis WC: **Vapor-liquid-solid mechanism of single-crystal growth.** *Appl Phys Lett* 1964, **4**(5):89–90.
20. Xia Y, Yang P, Sun Y, Wu Y, Mayers B, Gates B, Yin Y, Kim F, Yan H: **One-dimensional nanostructures: synthesis, characterization, and applications.** *Adv Mater* 2003, **15**(5):353–389.
21. Givargizov EI: **Fundamental aspects of VLS growth.** *Journal of Crystal Growth* 1975, **31**:20–30.
22. Wagner RS: **In VLS mechanism of crystal growth,** In *Whisker Technology.* Edited by Levitt AP. New York: Wiley-Interscience; 1970:47–119.
23. Persson AI, Larsson MW, Stenström S, Ohlsson BJ, Samuelson L, Wallenberg LR: **Solid-phase diffusion mechanism for GaAs nanowire growth.** *Nat Mater* 2004, **3**(10):677–681.
24. Lassner E, Schubert WD: *Tungsten: Properties, Chemistry, Technology of the Element, Alloys, and Chemical Compounds.* New York: Kluwer Academic/Plenum Publishers; 1998 (Chapter 3).

doi:10.1186/1556-276X-7-325

Cite this article as: Ma et al.: A large-scale fabrication of flower-like submicrometer-sized tungsten whiskers via metal catalysis. *Nanoscale Research Letters* 2012 **7**:325.

Submit your manuscript to a SpringerOpen® journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at ► springeropen.com