

NANO REVIEW

Open Access



Conductive Gels: Properties and Applications of Nanoelectronics

Nguyen Dinh Trung¹, Dinh Tran Ngoc Huy^{2,3}, Maria Jade Catalan Opuencia⁴, Holya A. Lafta⁵, Azher M. Abed⁶, Dmitry Olegovich Bokov^{7,8}, Kahramon Shomurodov⁹, Hoang Van Thuc Master¹⁰, Ali Thaeir Hammid¹¹ and Ehsan Kianfar^{12,13*}

Abstract

Conductive gels are a special class of soft materials. They harness the 3D micro/nanostructures of gels with the electrical and optical properties of semiconductors, producing excellent novel attributes, like the formation of an intricate network of conducting micro/nanostructures that facilitates the easy movement of charge carriers. Conductive gels encompass interesting properties, like adhesion, porosity, swelling, and good mechanical properties compared to those of bulk conducting polymers. The porous structure of the gels allows the easy diffusion of ions and molecules and the swelling nature provides an effective interface between molecular chains and solution phases, whereas good mechanical properties enable their practical applications. Due to these excellent assets, conductive gels are promising candidates for applications like energy conversion and storage, sensors, medical and biodevices, actuators, superhydrophobic coatings, etc. Conductive gels offer promising applications, e.g., as soft sensors, energy storage, and wearable electronics. Hydrogels with ionic species have some potential in this area. However, they suffer from dehydration due to evaporation when exposed to the air which limits their applications and lifespan. In addition to conductive polymers and organic charge transfer complexes, there is another class of organic matter called “conductive gels” that are used in the organic nanoelectronic industry. The main features of this family of organic materials include controllable photoluminescence, use in photocopy conversion technology, and storage of optical energy and its conversion into electricity. Various parameters change the electronic and optical behaviors of these materials, which can be changed by controlling some of the structural and chemical parameters of conductive gels, their electronic and optical behaviors depending on the applications. If the conjugated molecules with π bonds come together spontaneously, in a relative order to form non-covalent bonds, they form a gel-like structure that has photoluminescence properties. The reason for this is the possibility of excitation of highest occupied molecular orbital level electrons of these molecules due to the collision of landing photons and their transfer to the lowest unoccupied molecular orbital level. This property can be used in various nanoelectronic applications such as field-effect organic transistors, organic solar cells, and sensors to detect explosives. In this paper, the general introduction of conductive or conjugated gels with π bonds is discussed and some of the physical issues surrounding electron excitation due to incident radiation and the mobility of charge carriers, the position, and role of conductive gels in each of these applications are discussed.

Keywords: Polymer, π bond, Mobility, Molecular, Receptor molecule, Photoluminescence, Conductive gel, Field-effect transistor, Solar cells, Sensor

Introduction

The organs of some marine animals have structures rich in water and organic matter. For example, mermaid tissues are composed of 1% organic matter in 96% water and are a good example of functional hydrogels.

*Correspondence: e-kianfar94@iau-arak.ac.ir; ehsan_kianfar2010@yahoo.com; ehsankianfar775@gmail.com

¹² Department of Chemical Engineering, Arak Branch, Islamic Azad University, Arak, Iran

Full list of author information is available at the end of the article

Chemists and materials engineers have long sought to mimic nature and make materials with the function of natural hydrogels. “Gels” are examples of these materials that can trap very large volumes of solutions in their three-dimensional lattice-like structure. These semisolid viscoelastic materials are used today in various parts of human life, including food and cosmetics. The process of gelation or synthesis of hydrogels is accelerated by the formation of non-covalent bonds (i.e., hydrogen bonds, ionic bonds, π bonds, and van der Waals bonds in low molecular weight organic molecules) [1–3]. “Conjugated polymers with π -bonds” are another class of materials that are widely used in optoelectronic applications. The physical foundations, electronic properties, and nano-electronic applications of this family of materials have been studied in detail in other articles on the Nano Education site. As mentioned, conductive polymers are often used as main components in organic electronics such as light-emitting diodes (LEDs), organic field-effect transistors (OFETs), and organic solar cells. Organic solar cells (OSCs) are used. The performance and efficiency of these devices are controlled by the degree of crystallinity of these materials in the process of making thin layers. Controlling the morphology and crystallinity of conductive polymers along with limited access to high purity in the synthesis process and low solubility of conjugated polymers in aqueous solutions is one of the problems and challenges facing the organic electronics industry. These challenges often lead to the formation of undesirable arrays of organic and non-uniform molecules of chemical composition and crystal structure. To solve these problems, “supramolecular polymers made of conjugated molecules with π bonds” have been developed [4–6]. The

formation of these large molecule polymers under certain conditions leads to the formation of conductive or conjugated gels with π bonds (π gels). In fact, the molecular structure of conductive gels consists of regular arrays of conjugated molecules of various shapes and dimensions [7–11]. Conductive gels, due to the dynamic nature of molecular arrays, have the ability to regulate some electronic properties such as photoluminescence, mobility of charge carriers, and electrical conductivity. In this paper, recent developments in the field of conductive gels and their applications in the field of nanoelectronics will be reviewed [12–17]. Many conjugated organic materials with π bonds have a wide band gap and exhibit semiconductor behaviors when doped with appropriate materials [18–21]. Tetrathiafulvalene (TTF) and its derivatives are an exception to this rule and, if properly doped, show very high electrical conductivity [23–26]. In recent years, some researchers have sought to make conductive gels based on TTF in order to obtain a very high electrical conductivity [27–30]. The chemical structure of this substance is shown in Fig. 1 (Structure 1) [31]. The current curve according to the voltage of this material, if not doped with a suitable additive, is in the form of a yellow horizontal line, which is shown in Fig. 1b. This curve shows that with any voltage difference, the current flowing through the material is very small. On the other hand, by doping compound I_2 at room temperature, the electrical conductivity of these materials is improved. A new solution to increase the conductivity of these materials is to bind gold nanoparticles to the ligands of TTF molecules. This is shown in Fig. 1 as structures 16 and 17. As can be seen, the addition of gold nanoparticles leads to metallic behaviors in TTF-based conductive gels. In




Fig. 1 a Molecular structure of tetrathiafulvalene (TTF)-based conductive gels; b current–voltage diagrams obtained by atomic force microscopy (AFM) for conductive gels in the presence and absence of structures 2 and 3 and doping conditions with I_2 [37]

general, in order to be able to use conductive gels in the manufacture of nanoelectronic devices, the method of doping or adding conductive nanoparticles is very helpful [32–36]. As another practical example, large molecules of conductive gels can be produced as nanofibers after doping and their conductivity behaviors in different molecular arrangements can be investigated [37–42]. For example, Fig. 2 shows two different molecular structures in oligothiophene-based conductive gels that are produced as continuous, cohesive fibers. The current–voltage diagram of these nanofibers shows that the molecular structure and chemical composition of large molecules and their self-arrangement strongly affect the electrical resistance of these materials. Therefore, to achieve the highest electrical conductivity in conductive gels, control of the spatial arrangement of molecules is very important [43–45]. Table 1 shows the summary of properties and nanoelectronic applications of conductive gels.

Conductive polymers have been researched over the past few decades owing to their unique ability to provide tunable electrical conductivity and flexibility during processing [46–48]. The conductivity of conductive polymers depends on the molecular structures of the constituent materials, the level of doping, and the ordering of the molecular packing. With the rapid emergence of nanoscience and nanotechnology, it is anticipated that conductive polymers with well-defined nanostructure can translate the properties of their bulk forms and exhibit

unusual chemical/physical properties because of the confined dimensions of the nanomaterials [49–54].

Conductive polymers with various nanostructures including 0D nanoparticles, [55] 1D nanofibers [56, 57], and 2D nanosheets [58] have been developed and applied in a range of technological areas, such as sensors, electronics, and energy storage and conversion devices. However, the electrical properties of these nanostructured conductive polymers could be weakened by structural defects induced by inhomogeneous aggregation, severe restacking, and poor contacts during processing and assembly [59]. The development of nanostructured conductive polymers with tunable microstructures and controllable chemical/physical properties still remains a challenge [60–63].

Inspired by the chemical/structural features and synthetic approaches of natural gels [64], conductive polymer gels (CPGs) with 3D networked structures were recently developed by cross-linking the conjugated polymer chains using molecules with multiple functional groups [65]. CPGs show the unique features of gel materials: They are dilute cross-linked systems and exhibit no flow when in a steady state. This monolithic structure inherits the conductive properties of the conjugated polymeric chains and generates highly tunable chemical/physical properties derived from its cross-linked network [2, 48, 50–54, 60–63, 66–70], including flexibility, stretchability, ionic conductivity, electrochemical activity,




Table 1 Summary of properties and nanoelectronic applications of conductive gels

Conductive components	Materials	Optical property	Application	References
Metallic nanoparticles/nanowires	Ag/Au/Cu nanoparticles	Transparent or semitransparent	Biosensor drug delivery, tissue engineering	[85, 87, 99]
Carbon-based materials	CNTs	Mostly black or semitransparent	Strain sensor, tissue engineering, biosensor, supercapacitor, drug delivery	[99–113]
Carbon-based materials	GO/rGO/graphene	Mostly black or semitransparent	Strain sensor, tissue engineering, biosensor, supercapacitor drug delivery	[99–113]
Conducting polymers	Polyaniline	Mostly black and rarely transparent	Tissue engineering, biosensor, drug delivery, supercapacitor, bioelectrode, strain sensor	[114–139]
Conducting polymers	Polypyrrole	Mostly black and rarely transparent	Tissue engineering, biosensor, drug delivery, supercapacitor, bioelectrode, strain sensor	[114–135, 140–143]
Conducting polymers	PEDOT:PSS	Mostly black and rarely transparent	Tissue engineering, biosensor, drug delivery, supercapacitor, bioelectrode, strain sensor	[114–135, 144–147]
Hybrid	Pt/Ag/(GO + rGO)/SWCNTs + polyaniline	Usually black or semitransparent	Biosensor, battery, fuel cell, supercapacitor, tissue engineering, pressure sensor, strain sensor	[148–163]
Hybrid	Au/(Fe + Co)/Fe ₃ O ₄ /CNTs + polypyrrole	Usually black or semitransparent	Biosensor, battery, fuel cell, supercapacitor, tissue engineering, pressure sensor, strain sensor	[148–160, 164–167]
Hybrid	Graphene/GO + Ni/Ni(OH) ₂	Usually black or semitransparent	Biosensor, battery, fuel cell, supercapacitor, tissue engineering, pressure sensor, strain sensor	[148–160, 168–172]
Hybrid	GO + PEDOT:PSS	Usually black or semitransparent	Biosensor, battery, fuel cell, supercapacitor, tissue engineering, pressure sensor, strain sensor	[148–160]
Hybrid	GO + CuS + carbon dot	Usually black or semitransparent	Biosensor, battery, fuel cell, supercapacitor, tissue engineering, pressure sensor, strain sensor	[148–160, 173–175]
Acids	H ₂ SO ₄ /H ₃ PO ₄	Transparent	Supercapacitor	[176–187]
Metallic salts	LiCl/Na ⁺ /Ca ²⁺	Transparent or semitransparent	Supercapacitor, solar cell, nanogenerator, actuator, electronic eel/fish, displays, touch panels, pressure sensor, strain sensor, biosensor	[180–182, 188–221]
Metallic salts	Al ³⁺ /Fe ³⁺ /Tb ³⁺ /K ⁺	Transparent or semitransparent	Supercapacitor, solar cell, nanogenerator, actuator, electronic eel/fish, displays, touch panels, pressure sensor, strain sensor, biosensor	[183–185, 188–221]
Metallic salts	Na ₂ S + sulfur + NaOH	Transparent or semitransparent	Supercapacitor, solar cell, nanogenerator, actuator, electronic eel/fish, displays, touch panels, pressure sensor, strain sensor, biosensor	[186–221, 227–230]
Ionic liquids	Ionic liquids	1-Ethyl-3-methylimidazolium chloride	Semitransparent	[222]
Electron conductive	Na ⁺ + Au nanoparticles	Usually black or opaque	Supercapacitor, biosensor, pressure sensor, battery strain sensor, tissue engineering	[223]

Table 1 (continued)

Conductive components	Materials	Optical property	Application	References
components and ions	HCl/HClO ₄ /(Na ⁺ + SWCNTs) + polyaniline		Supercapacitor, biosensor, pressure sensor, battery strain sensor, tissue engineering	[224–226]


and so forth. Meanwhile, CPGs have emerged as a unique material platform to develop functional materials by building interpenetrating structures with a second polymeric network, loading specific nanoparticles, or serving as a precursor for graphitic carbon frameworks [71].

Conductive hydrogels have drawn significant attention in the field of stretchable/wearable sensors due to their intrinsic stretchability, tunable conductivity, biocompatibility, multi-stimuli sensitivity, and self-healing ability. Recent advancements in hydrogel- and organohydrogel-based sensors, including a novel sensing mechanism, outstanding performance, and broad application scenarios, suggest the great potential of hydrogels for stretchable electronics. However, a systematic summary of hydrogel- and organohydrogel-based sensors in terms of their working principles, unique properties, and promising applications is still lacking. In this spotlight, we present recent advances in hydrogel- and organohydrogel-based stretchable sensors with four main sections: improved stability of hydrogels, fabrication and characterization of organohydrogel, working principles, and performance of different types of sensors. We particularly highlight our recent work on ultrastretchable and high-performance strain, temperature, humidity, and gas sensors based on polyacrylamide/carrageenan double-network hydrogel and ethylene glycol/glycerol-modified organohydrogels obtained via a facile solvent displacement strategy. The organohydrogels display higher stability (drying and freezing tolerances) and sensing performances than corresponding hydrogels. The sensing mechanisms, key factors influencing the performance, and application prospect of these sensors are revealed. Particularly, we find that the hindering effect of polymer networks on the ionic transport is one of the key mechanisms applicable for all four of these kinds of sensors [12].

Electronic Properties of Conductive Gels


Chromophore is the part of a molecule that causes color in it. Chromaticity occurs when matter can absorb a certain wavelength of visible light and pass or reflect the rest. A chromophore is a region of a molecule where the energy balance difference between two molecular orbitals is within the energy range of part of the incident beam spectrum [56]. A certain wavelength of light due to a collision with a molecule can be absorbed by its electrons and excite them from the ground state to the

excited state. What is very important in conductive gels and affects the efficiency of absorption of light energy by conductive gels is the arrangement and spatial arrangement of chromophores giving and receiving electron with optimal distance and orientation. To date, a wide range of conductive gels have been developed as high-performance scaffolds for energy transfer or conversion. In each case, they have seized it, despite obstacles we can scarcely imagine. In other words, it is generally preferred that the chromophores giving and receiving conductive gels can be arranged on their own and that the electron excitation properties of these materials due to light beam can be optimized by controlling the molecular self-arranging property and increasing the energy conversion efficiency [57]. In other words, by controlling the amount of energy transfer between the donor and electron acceptor molecules in the three-dimensional structure and network like conductive gels, the optical energy absorption or optical behavior of the material can be adjusted and used to make optical emitting devices (LEDs). In order to be able to use conductive gels in the nanoelectronics and organic electronics industries, it is necessary for the three-dimensional structure of these materials to be able to transfer excited electrons at a macroscopic distance. The emergence of this feature requires regular arrangement of electron donor and receiver centers in different directions. In practice, the self-arrangement of donor and receptor molecules does this. Figure 3 shows a diagram of the molecular structure of multi-chromophore conductive gels arranged in self-assembled nanofibers. The core of each nanofiber is composed of an elongated chain of conjugated molecules with π bonds that, with their regular arrangement, lead to the formation of a continuous structure. The gel changes color when exposed to ultraviolet light and its macroscopic appearance changes from dark orange to yellow. The reason for this discoloration is the excitation of electron donor and electron acceptor chromophores by the collision of ultraviolet light and their movement in the three-dimensional structure of the gel. Today, photon upconversion is one of the most important applications of electron excitation in conductive gels. In this phenomenon, several weak and low-energy photons are absorbed by the material due to electron excitation, and in return, a higher-energy photon is emitted by the material. It has been observed that in conductive gels, the electron donor



centers can be combined in a polymer field containing electron acceptor centers; with a special arrangement, the photon upconversion property in the gel can be

achieved. Take Fig. 4, for example. In this form, the conducting gel of 9,10-diphenylanthracene as the electron receptor is doped by Pt (II) octaethylporphyrin (PtOEP)




as the electron donor. As can be seen, the collision of the incident beam leads to the excitation of electrons in the donor centers and the transfer of charge carriers to the recipient centers. Finally, matter emits a higher energy beam for several electrons excited at a lower energy [58]. The photoluminescence spectrum diagram of this conductive gel shows that the output beam has a relatively wide range of wavelengths in the range of 400 to 475 nm.

Electron Transfer Due to Optical Excitation

In addition to controllable photoluminescence behavior, one of the main approaches to the development of conjugated gels with π bonds is the conversion of optical energy into electrical energy by electron excitation. In other words, scientists are looking for conductive gels to emit their excited electrons through an electronic circuit, instead of emitting light or exhibiting photon upconversion due to electron stimulation after exposure to the incoming beam. Collected and stored. Observations show that conductive gels are a good option for converting solar energy into electric current, because the electron donor and receiver centers in the three-dimensional structure of these materials are arranged independently and in a controllable arrangement, and the possibility of electron transfer at macroscopic distances [59, 62]. There is: One method of producing conductive gel-based systems to convert solar energy into electricity is to functionalize conductive gels with electron donor–receiver units. What is very important in these gel structures is to prevent the recombination of electrons, which is also

done by choosing the right chromophores for giving and receiving electrically charged carriers. Recently, efforts have been made to design and synthesize gels with optimal conversion and storage properties of electric current through visible light absorption. One of these systems is a gel-like structure, which is schematically shown in Fig. 5. In this gel, naphthalimide as electron donor and perylene monoimide as electron receptor are dissolved in hexane/dichloromethane solution and then functionalized with α,β -dihydroxypropyl chains. The functionalization of these compounds leads to the self-assembly of these molecules and the formation of regular molecular structures within the solution at low concentrations (Fig. 5a). As the concentration of the solution increases, non-covalent bonds predominate and the cell turns into a gel (Fig. 5b). It has been observed that at concentrations above a critical limit, a nanostructured gel is formed in which the charge carriers generated by the excitation of visible light are transferred from the naphthalimide unit to the perylene monoimide unit, and thus, the electric current in it flows inside the network structure like a conductive gel. Also, if indole is used as the electron donor, the electron transfer process will be accelerated and the electron path will be from naphthalimide to indole and finally to perylene monoimide, respectively. It should be noted that in biphasic conducting gels, the rate of electron–hole recombination is much lower than the rate of electron production due to light excitation, and the reason for this is the self-assembly arrangement of the large molecules that make up the gel. Such a stable transfer



from charge carriers can be used in water splitting and artificial photosynthesis.


Mobility of Electric Charge Carriers


As a general rule, the overall efficiency and performance of organic electronics, such as FETs and heterogeneous solar cells, depend on the mobility of the active charge carriers in the system. Self-assembly materials obtained from conjugated gels with π bonds are good options for making organic electronic devices, because the regular molecular arrangement in the gel structure can contribute to the greater mobility of the electric charge carriers in these structures [73, 74]. However, it is very difficult to measure the mobility of charge carriers in gels without destroying their molecular arrangement. Conductive gels with thienylenevinylene base are among the gels in which electric charge carriers have high mobility. Figure 6a shows two examples of these molecular structures (structures 11a and 11b). The large molecules in these gels self-assemble into continuous fibers. The absorption spectra of these materials show that the mobility of the electrons in the mentioned gels is due to the very regular molecular self-arrangement of these materials and the overlap of the band structure of the electron donor and receiver units. Also, if *N,N*-bis(2,5-di-*tert*-butylphenyl)-3,4,9,10-perylenedicarboximide (PDI) is used in these

gel structures, the mobility of the electrons will increase (Fig. 6b). In fact, it helps to gel more gel on a molecular scale, thereby increasing the mobility of energy carriers. On the other hand, the electron mobility in gel structures is relatively low compared to xerogel structures of the same material (Fig. 6c). It should be noted that if the gel dries at relatively low temperatures, it becomes a very porous solid product called xerogel.

Sensors for Explosives

Photoluminescence is one of the most attractive properties of conductive gels. This is done by absorbing colliding photons with organic matter, stimulating electrons at its HOMO level, and transferring them to the LUMO level. Studies show that if the macromolecules of a conductive gel (which are rich in excited electrons) are exposed to electron-deficient analyses, the gel-stimulated electrons are rapidly transferred to the analytic band structure and photoluminescence properties of these materials they destroy [71, 75]. This interesting phenomenon has recently become the basis for the identification of nitro-aromatic explosives using conductive gels. For example, the presence of TNT explosives in very small amounts (in the range) can be detected using pentafluoroarene functional groups. This is shown in Fig. 7. When these functional groups form a gel-like structure,





the macromolecules assume a relatively orderly arrangement and are expected to exhibit photoluminescence properties. Now, if this gel is placed on a special paper in a thin layer, in the presence of sunlight, it will show a special color. If some of the TNT explosives come in contact with the surface of the paper, the photoluminescence property of the gel is rapidly lost, and the rate of drop of this property is directly related to the amount of explosive. The higher the concentration of the explosive, the lower the intensity of the light emitted by the gel, and the presence of an explosive can be detected by the color change. It should be noted that the reason for the suitability of conductive gels for the detection of TNT explosives is the efficient absorption of these materials into the self-assembled structure of the gel molecules and energy absorption by it.

Applications

Recently, conductive gels have been used in the manufacture of many nanoelectronic devices due to their controllable conductivity. The most important of these applications are organic field-effect transistors (OFETs), organic solar cells, and organic sensors. In the following, the role of these materials in the mentioned applications is described. It should be noted that one of the main applications of conductive gels is the production of hydrogen using water splitting, but since the present article deals with the nanoelectronic applications of conductive gels, this issue will not be discussed [76, 77].

Field-Effect Organic Transistors (OFETs)

Organic semiconductors are preferred over silicon-based semiconductors in many applications, including integrated circuits, sensors, and electronic chips, due to their

low weight and flexibility. The relatively regular arrangement of the large molecules in these materials due to the processing of the solution phase can provide continuous conduction paths for the electrons and cavities (percolation network) and increase the efficiency and electrical efficiency of the devices. Since conductive gels are prepared from solution phase and in which large molecule chromophores have the ability of molecular self-assembly, these materials are a very good option for making active materials in field-effect organic transistors (OFETs) [78, 79]. Before discussing the application of conductive gels in OFETs transistors, it is advisable to discuss the general structure of field-effect capacitors. The most common structure of field-effect transistors often consists of a n- and p-type semiconductor junction with two layers of oxide insulating material (such as silicon oxide) and a conductive layer (non-crystalline metal or silicon). Figure 8 shows a schematic of this structure. As can be seen, these transistors consist of three main parts: The main body is a p-type semiconductor that holds two separate n-type semiconductor parts at a certain distance from each other. One type n region is called the source terminal, and the other is called the drain terminal. The area between the source and discharge terminals is covered by a thin, insulating layer of metal oxide, and the conductive layer is placed on top of the oxide layer. The whole area between the two terminals is called the gate terminal. Due to the nature of n-type semiconductors, the concentration of electrons is higher in the areas near the source terminal and discharge, but there is no current between the two regions [80, 81]. Now, if a positive voltage is applied to the gate terminal and the source terminal is connected to ground and the discharge terminal is connected to a positive potential, the negative electrons tend




Fig. 8 **a** Schematic of the three-dimensional structure of field-effect transistors based on p-type semiconductors. **b** Schematic of the two-dimensional structure of field-effect transistors and the potentials applied to it [57]

to accumulate in the gate region due to the positive voltage of the gate terminal. If we increase the gate voltage and the positive voltage applied to the discharge source sufficiently, the negative charges accumulated under the metal oxide layer will tend to move toward the gate terminal and the discharge terminal. By doing this, applying a gate voltage and a positive voltage to the discharge terminal causes the electron current to flow from the source terminal to the discharge terminal. In other words, no current of electrons will be established between the two terminals until the gate voltage reaches a critical level. Conversely, if the gate voltage increases exponentially, a path of positive charges in the gate region is created and the intensity of the electron current flux increases. Therefore, the gate terminal acts as a valve for the electron flow tube. It should be noted that if the main body of the field-effect transistor is made of p-type semiconductor, it is called P-FETs and if it is n-type, it is called N-FETs. The same mechanism applies to both types of transistors. In recent years, many attempts have been made to use new materials as the main body or substrate of FETs transistors on which the source and discharge terminals as well as the gate are mounted. Conductive gels are one of these emerging materials. For example, Hong et al. used single nanofibers made of conjugated gels with π bonds as the


main body of nanotransistors (Fig. 9). Due to its one-dimensional self-arrangement and chemical structure, this fiber behaves similarly to the p-type semiconductor. The mobility of cavities in this fiber is in the range of 0.48–0.1 cm/s [82]. As shown in Fig. 9, an increase in gate voltage leads to an increase in the current flow from the source terminal to the discharge terminal. In some studies, a thin layer of conductive gels has been used as the main body of OFETs transistors. Figure 5 shows an example of these structures. As can be seen, a field-effect transistor with a downward gate terminal can be produced using a thin layer of conductive gel with a 23 structure. The important point is that the large molecules of this conductive gel have the property of molecular self-assembly, and this leads to high mobility of charge carriers in this thin layer. The structure 23 behaves similarly to the n-type semiconductor, and the majority charge carriers are electrons, the gate voltage is negative and the voltage applied to the discharge terminal is positive. Also, the current–voltage diagrams in Fig. 10 clearly show that as the gate voltage increases and the voltage difference between the source terminal and the discharge increases, the current passing through the transistor increases exponentially. However, the effect of gate voltage on the current density is greater than the discharge terminal voltage.

Organic Solar Cells

Organic solar cells (OSCs) have relatively low efficiencies in converting solar energy into electrical energy, but very low weight, low cost, and flexibility of organic matter relative to inorganic semiconductors are the focus of energy industries. Has attracted. Has attracted Conductive gels, on the other hand, have been considered in comparison with other semiconductor or non-conductive organic materials for several important reasons for making OSCs [83, 84]:

- (a) Ease of processing, coating, production of thin films, and production of nanometer fibers.
- (b) The possibility of making heterogeneous connections from chromophores giving or receiving large molecules in mesa- or nanodimensions.
- (c) Possibility of easy self-assembly of large molecules and engineering of three-dimensional arrangement of electron donor and receiver chromophores to achieve high energy conversion efficiency.

In this section, a sample of organic solar cells based on conductive gels is reviewed. But before entering into this discussion, it is better to introduce the general structure of organic solar cells. Figure 10 schematically shows the layer structure of an organic solar cell. As can be seen,



these cells consist of several main parts: (1) glass, (2) a transparent conductive oxide layer (such as indium tin oxide or ITO), (3) a conductive transparent polymer (such as PEDOT, PSS), (4) an active layer or absorber, (5) a bonding layer and (6) a conductive metal layer. In general, the conductive metal layer and the transparent metal oxide layer act as “contact points” to connect to the external circuit. A thin layer of transparent conductive polymer such as PEDOT: PSS is usually used as the cavity conductor material directly above the ITO electrode. What plays the most effective role in building an organic solar cell is the “active layer.” Solar cells are divided into several categories in terms of number of layers and electronic architecture (Fig. 10):


- Organic monolayer solar cells

These solar cells are the simplest type of photovoltaic device in terms of energy storage conversion mechanism. In the structure of these devices, an organic

semiconductor is placed between two thin layers of conductive metal. One of these metal layers, such as indium tin oxide (ITO), has a very high working function, and the other layer, such as aluminum or magnesium, has a relatively lower working function (Fig. 10a). The mechanism of storage of electric charge is such that due to the collision of the landing photon, a large number of excitations (electron–hole pair) are formed in the band structure of the organic semiconductor layer. These electrons begin to move due to the electric field created between the two metal layers due to the difference in their working function [84]. They flow toward the positive metal electrode and the cavity toward the negative electrode. The band structure of this type of solar cell and the path of electrons and holes are shown in Fig. 10a.

- Organic bilayer solar cells


This type of solar cell is made of two separate organic layers with completely different electronegativity



between conductive metal layers. This difference in electronegativity leads to the creation of an electrostatic field between two metal layers. The semiconductor layer that has a high electronegativity tends to absorb more electrons and the other organic layer tends to give electrons. Therefore, when a landing


photon strikes these two semiconductor layers, it leads to the formation of an electron–hole pair at the LUMO level of the band structure of the two materials, and the electrons and holes due to the electrostatic field created between the two layers begin to separate and move. They do it in the opposite direction. In other words, the


layer with high electronegativity acts as the electron acceptor and repulse of the cavity, and the layer with lower electronegativity acts as the electron giver and the absorber of the cavity. In this way, the exactions are separated from each other and placed in holes in the outer circuit by holes and electrons through metal layers. The band structure of this group of solar cells and the path of electron–hole motion are shown in Fig. 11.



- Organic solar cells with mass heterogeneous connections

In organic solar cells, two metal layers (mostly aluminum and ITO) are used as the two points of contact for the external circuit. Also, conductive gels are often used as the organic layer between these two conductive metal layers. This layer is also called the active layer. Recently, some researchers have used organic gels based on conductive polymers as the active layer in organic solar cells [85]. Figure 12 shows the chemical structure of two types of polymer molecules (structures 26a and 26b). These two molecules are similar in molecular structure, but one of them has a CN functional group. The use of these materials as an active layer in organic solar cells has been shown to improve the energy storage efficiency of these systems by 1.7%. This efficiency is also increased if heat annealing is used to convert the solution containing these molecules into gel structures in which molecules 26a and 26b are self-arranged. This shows how much the gelling of solutions containing conjugated polymers with π bonds can affect the self-assembly of molecules and energy storage efficiency. Figure 12 shows the increase in efficiency of generated solar cells in the form of stored current density graphs. Molecular structure 29 in Fig. 13 is another example of the application of conductive gels in the fabrication of solar organic cells as the active layer. These large molecules can affect energy conversion efficiency, depending on the number of repetitive units and the degree to which they are self-assembled. As can be seen in Fig. 13, gelling and self-assembly of large molecules significantly increase the slope of changes in the energy conversion efficiency diagram. Efforts to replace





various types of conductive gels in the main body of organic solar cells continue today.

Conclusion

- In the organic nanoelectronics industry, in addition to organic charge transfer complexes and conductive polymers, conjugated gels with π bonds are also used. These materials are large molecules that, similar to organic charge transfer complexes, have electron donor and receptor components. And, like conductive polymers, are composed of conjugated molecules with π bonds. These large molecular units in gel structures are placed next to each other with non-covalent bonds, increasing the viscosity of the system. One of the main features of conductive gels is the ability to change the optical behavior of these materials by changing chromophores, viscosity, arrangement of molecular arrays, and doping with other molecules. These materials can also be used in photon upconversion technology. Conductive gels are now used in the manufacture of solar cells to convert solar energy into electricity.
- In the present paper, the nanoelectronic applications of conductive gels were reviewed. The most important of these applications are sensors for detecting explosives, thin-film organic solar cells, and field-effect nanotransistors. As mentioned, conductive gels can be used as non-intrinsic semiconductors due to the self-arrangement of large molecules and can be used as the active layer in organic solar cells or the

main body of semiconductors in field-effect transistors. The basis of these materials is the excitation of HOMO level electrons and their transfer to the LUMO level. The efficiency and performance of this group of materials are strongly related to the kinetics of the process of excitation and transfer of charge carriers due to the collision of landing photons. Conductivity can significantly increase the conductivity of conductive gels. The most important method is to dope or add a specific functional group to the molecular arrays of these materials. More details of the mentioned applications are discussed in the present article.

Abbreviations

HOMO: Highest occupied molecular orbital; LUMO: Lowest unoccupied molecular orbital; TTF: Tetrathiafulvalene.

Acknowledgements

Department of Chemical Engineering, Arak Branch, Islamic Azad University, Arak, Iran. Young Researchers and Elite Club, Gachsaran Branch, Islamic Azad University, Gachsaran, Iran.

Author contributions

Therefore, on this basis NDT, DTNH, MJCO, and HAL contributed to investigation, concept and design, experimental studies, writing—original draft, and reviewing and editing, and AMA, DOB, KS, HVTM, ATH, and EK were involved in investigation, concept and design, and data curation. All authors read and approved the final manuscript.

Funding

There is no funding to report for this submission.

Availability of data and materials

Not applicable.

Declarations

Ethics approval and consent to participate

I wrote to you in regard to your question about naming some people in my article, I must point out that in some cases, help was sought from people and it was necessary to mention the names of these people in order to maintain professional ethics in research issues.

Consent for publication

Not applicable.

Competing interests

The authors declare that they have no competing interests.

Author details

¹National Economics University (NEU), Hanoi, Vietnam. ²Banking University HCMC, Ho Chi Minh city, Vietnam. ³International University of Japan, Niigata, Japan. ⁴College of Business Administration, Ajman University, Ajman, United Arab Emirates. ⁵Al-Nisour University College, Baghdad, Iraq. ⁶Department of Air Conditioning and Refrigeration, Al-Mustaqbal University College, Babylon, Iraq. ⁷Institute of Pharmacy, Sechenov First Moscow State Medical University, 8 Trubetskaya St., bldg. 2, Moscow, Russian Federation 119991. ⁸Laboratory of Food Chemistry, Federal Research Center of Nutrition, Biotechnology and Food Safety, 2/14 Ustyynsky pr., Moscow, Russian Federation 109240. ⁹Department of Maxillo-Facial Surgery, Tashkent State Dental Institute, Makhtumkuli 103, Tashkent, Uzbekistan 100147. ¹⁰Thai Nguyen University, University of Information and Communication Technology, Thái Nguyên, Vietnam. ¹¹Computer Engineering Department, Imam Ja'afar Al-Sadiq University, Baghdad, Iraq. ¹²Department of Chemical Engineering, Arak Branch, Islamic Azad University, Arak, Iran. ¹³Young Researchers and Elite Club, Gachsaran Branch, Islamic Azad University, Gachsaran, Iran.

Received: 5 September 2021 Accepted: 20 April 2022

Published online: 02 May 2022

References

1. Haedler AT, Kreger K, Issac A, Wittmann J, Kivala M, Hammer N, Köhler J, Schmidt H-W, Hildner R (2015) Long-range energy transport in single supramolecular anofibers at room temperature. *Nature* 523(7559):196–199
2. Haedler AT, Beyer SR, Hammer N, Hildner R, Kivala M, Köhler J, Schmidt H-W (2014) Synthesis, photophysical properties of multichromophoric carbonyl-bridged diarylamines. *Chem Eur J* 20(37):11708–11718
3. Ogawa T, Yanai N, Maraguzzi A, Kimizuka N (2015) Highly efficient photon up-conversion in self-assembled light-harvesting molecular systems. *Sci Rep* 5:1–9
4. Cherian JT, Manna AB, Hariharan M (2014) Light harvesting vesicular donor-acceptor scaffolds the rate of charge recombination in the presence of an electron donor. *Energy Environ Sci* 7(5):1661–1669
5. Prasadnkumar S, Saeki A, Seki S, Ajayaghosh A (2010) Solution phase in situ self-assembly high charge-carrier mobility nanofibers of semi-conducting molecular gelators. *J Am Chem Soc* 132(26):8866–8867
6. Ghosh S, Praveen VK, Ajayaghosh A (2016) The chemistry applications of π-gels. *Annu Rev Mater Res* 46:235–262
7. He Q, Liu J, Liang J, Liu X, Li W, Liu Z, Ding Z, Tuo D (2018) Towards improvements for penetrating the blood-brain barrier—recent progress from a material and pharmaceutical perspective. *Cells* 7:24. <https://doi.org/10.3390/cells7040024>
8. Zhou T, Xiao X, Li G (2012) Microwave accelerated selective soxhlet extraction for the determination of organophosphorus and carbamate pesticides in ginseng with gas chromatography/mass spectrometry. *Anal Chem* 84(13):5816–5822. <https://doi.org/10.1021/ac301274r>
9. Wu Y, Deng P, Tian Y et al (2020) Simultaneous and sensitive determination of ascorbic acid, dopamine and uric acid via an electrochemical sensor based on PVP-graphene composite. *J Nanobiotechnol* 18:112. <https://doi.org/10.1186/s12951-020-00672-9>
10. Li GL, Zhong P, Ye YB, Wan X, Cai ZT, Yang SH, Xia YH, Li Q, Liu J, He QG (2019) A highly sensitive and stable dopamine sensor using

shuttle-like alpha-Fe2O3 nanoparticles/electro-reduced graphene oxide composites. *J Electrochem Soc* 166(15):B1552–B1561

11. Tian Y, Deng P, Wu Y, Liu J, Li J, Li G, He Q (2020) High sensitive voltammetric sensor for nanomolarity vanillin detection in food samples via manganese dioxide nanowires hybridized electrode. *Microchem J* 157:104885
12. Wu Z, Yang X, Wu J (2021) Conductive hydrogel- and organo-hydrogel-based stretchable sensors. *ACS Appl Mater Interfaces* 13(2):2128–2144. <https://doi.org/10.1021/acsami.0c21841>
13. Zhang X, Tang Y, Zhang F, Lee C (2016) A novel aluminum-graphite dual-ion battery. *Adv Energy Mater* 6(11):1502588. <https://doi.org/10.1002/aenm.201502588>
14. Wang M, Jiang C, Zhang S, Song X, Tang Y, Cheng H (2018) Reversible calcium alloying enables a practical room-temperature rechargeable calcium-ion battery with a high discharge voltage. *Nat Chem* 10(6):667–672. <https://doi.org/10.1038/s41557-018-0045-4>
15. Mu S, Liu Q, Kidkhunthod P, Zhou X, Wang W, Tang Y (2020) Molecular grafting towards high-fractional active nanodots implanted in N-doped carbon for sodium dual-ion batteries. *Natl Sci Rev*. <https://doi.org/10.1038/s41524-021-0178>
16. Zhu W, Deng M, Chen D, Zhang Z, Chai W, Chen D, Xi H, Zhang J, Zhang C, Hao Y (2021) Dual-phase CsPbCl3–Cs4PbCl6 perovskite films for self-powered, visible-blind UV photodetectors with fast response. *ACS Appl Mater Interfaces* 12(29):32961–32969. <https://doi.org/10.1021/acsami.0c09910>
17. Liu Y, Zhang Q, Yuan H, Luo K, Li J, Hu W, Bazaka K (2021) Comparative study of photocatalysis and gas sensing of ZnO/Ag nanocomposites synthesized by one- and two-step polymer-network gel processes. *Alloys Compd* 868:158723. <https://doi.org/10.1016/j.jallcom.2021.158723>
18. Liu W, Zheng Y, Wang Z, Wang Z, Yang J, Chen M, Qi M, Ur Rehman S, Shum PP, Zhu L, Wei L (2021) Ultrasensitive exhaled breath sensors based on anti-resonant hollow core fiber with in situ grown ZnO–Bi2O3 nanosheets. *Adv Mater Interfaces*. <https://doi.org/10.1002/admi.202001978>
19. Zhang Z, Feng L, Liu H, Wang L, Wang S, Tang Z (2021) Mo6+–P5+ co-doped Li2ZnTi3O8 anode for Li-storage in a wide temperature range and applications in LiNi0.5Mn1.5O4/Li2ZnTi3O8 full cells. *Inorg Chem Front* 9(1):35–43. <https://doi.org/10.1039/D1QI01077H>
20. Zhang Y, Li C, Jia D, Zhang D, Zhang X (2015) Experimental evaluation of the lubrication performance of MoS2/CNT nanofluid for minimal quantity lubrication in Ni-based alloy grinding. *Int J Mach Tools Manuf* 99:19–33
21. Zhang Y, Li C, Ji H, Yang X, Yang M, Jia D, Zhang X, Li R, Wang J (2017) Analysis of grinding mechanics and improved predictive force model based on material-removal and plastic-stacking mechanisms. *Int J Mach Tools Manuf* 122:81–97
22. Yang M, Li C, Zhang Y, Jia D, Zhang X, Hou Y, Li R, Wang J (2017) Maximum undeformed equivalent chip thickness for ductile-brittle transition of zirconia ceramics under different lubrication conditions. *Int J Mach Tools Manuf* 122:55–65
23. Li B, Li C, Zhang Y, Wang Y, Jia D, Yang M, Zhang N, Wu Q, Han Z, Sun K (2017) Heat transfer performance of MQL grinding with different nanofluids for Ni-based alloys using vegetable oil. *J Clean Prod* 154:1–11
24. Guo S, Li C, Zhang Y, Wang Y, Li B, Yang M, Zhang X, Liu G (2017) Experimental evaluation of the lubrication performance of mixtures of castor oil with other vegetable oils in MQL grinding of nickel-based alloy. *J Clean Prod* 140(3):1060–1076
25. Wang Y, Li C, Zhang Y, Li B, Yang M, Zhang X, Guo S, Liu G (2016) Experimental evaluation of the lubrication properties of the wheel/workpiece interface in MQL grinding with different nanofluids. *Tribol Int* 99(1):198–210
26. Salimi M, Pirouzfard V, Kianfar E (2017) Enhanced gas transport properties in silica nanoparticle filler-polystyrene nanocomposite membranes. *Colloid Polym Sci* 295:215–226. <https://doi.org/10.1007/s00396-016-3998-0>
27. Kianfar E (2018) Synthesis and characterization of AlPO4/ZSM-5 catalyst for methanol conversion to dimethyl ether. *Russ J Appl Chem* 91:1711–1720. <https://doi.org/10.1134/S1070427218100208>

28. Kianfar E (2019) Ethylene to propylene conversion over Ni-W/ZSM-5 catalyst. *Russ J Appl Chem* 92:1094–1101. <https://doi.org/10.1134/S1070427219080068>
29. Kianfar E (2019) Ethylene to propylene over zeolite ZSM-5: improved catalyst performance by treatment with CuO. *Russ J Appl Chem* 92:933–939. <https://doi.org/10.1134/S1070427219070085>
30. Kianfar E, Shirshahi M, Kianfar F et al (2018) Simultaneous prediction of the density, viscosity and electrical conductivity of pyridinium-based hydrophobic ionic liquids using artificial neural network. *SILICON* 10:2617–2625. <https://doi.org/10.1007/s12633-018-9798-z>
31. Babu SS, Praveen VK, Ajayaghosh A (2014) Functional π -gelator their applications. *Chem Rev* 114(4):1973–2129
32. Salimi M, Pirouzfard V, Kianfar E (2017) Novel nanocomposite membranes prepared with PVC/ABS and silica nanoparticles for C₂H₆/CH₄ separation. *Polym Sci Ser A* 59:566–574. <https://doi.org/10.1134/S0965545X17040071>
33. Kianfar F, Kianfar E (2019) Synthesis of isophthalic acid/aluminum nitrate thin film nanocomposite membrane for hard water softening. *J Inorg Organomet Polym* 29:2176–2185. <https://doi.org/10.1007/s10904-019-01177-1>
34. Kianfar E, Azimikia R, Faghih SM (2020) Simple and strong dative attachment of α -diimine nickel (II) catalysts on supports for ethylene polymerization with controlled morphology. *Catal Lett* 150:2322–2330. <https://doi.org/10.1007/s10562-020-03116-z>
35. Kianfar E (2019) Nanozeolites: synthesized, properties, applications. *J Sol Gel Sci Technol* 91:415–429. <https://doi.org/10.1007/s10971-019-05012-4>
36. Liu H, Kianfar E (2020) Investigation the synthesis of nano-SAPO-34 catalyst prepared by different templates for MTO process. *Catal Lett* <https://doi.org/10.1007/s10562-020-03333-6>
37. Puigmartí-Luis J, Pérez del Pino Á, Laukhina E, Esquena J, Laukhina E, Rovira C, Vidal-Gancedo J et al (2008) Shaping supramolecular nanofibers with nanoparticles forming complementary hydrogen bonds. *Angew Chem Int Ed* 47(10):1861–1865
38. Kianfar E, Salimi M, Hajimirzaee S, Koohestani B (2018) Methanol to gasoline conversion over CuO/ZSM-5 catalyst synthesized using sonochemistry method. *Int J Chem React Eng* 17
39. Kianfar E, Salimi M, Pirouzfard V, Koohestani B (2018) Synthesis of modified catalyst and stabilization of CuO/NH₄-ZSM-5 for conversion of methanol to gasoline. *Int J Appl Ceram Technol* 15:734–741. <https://doi.org/10.1111/ijac.12830>
40. Kianfar E, Salimi M, Pirouzfard V, Koohestani B (2018) Synthesis and modification of zeolite ZSM-5 catalyst with solutions of calcium carbonate (CaCO₃) and sodium carbonate (Na₂CO₃) for methanol to gasoline conversion. *Int J Chem React Eng* 16(7):20170229. <https://doi.org/10.1515/ijcre-2017-0029>
41. Ehsan K (2019) Comparison and assessment of zeolite catalysts performance dimethyl ether and light olefins production through methanol: a review. *Rev Inorg Chem* 39:157–177
42. Ehsan K, Salimi M (2020) A review on the production of light olefins from hydrocarbon cracking and methanol conversion. In: Taylor JC (ed) *Advances in chemistry research*, vol 59. Chapter: 1. Nova Science Publishers, New York
43. Ehsan K, Razavi A (2020) Zeolite catalyst based selective for the process MTO: a review. In: Mahler A (ed) *Zeolites: advances in research and applications*. Chapter: 8. Nova Science Publishers, New York
44. Ehsan K (2020) Zeolites: properties, applications, modification and selectivity. In: Mahler A (ed) *Zeolites: advances in research and applications*, Chapter: 1. Nova Science Publishers, New York
45. Kianfar E, Hajimirzaee S, Musavian SS, Mehr AS (2020) Zeolite-based catalysts for methanol to gasoline process: a review. *Microchem J* 156:104822
46. Shi Y, Yu G (2016) Designing hierarchically nanostructured conductive polymer gels for electrochemical energy storage and conversion. *Chem Mater* 28:2466–2477
47. Kianfar E, Baghernejad M, Rahimdashti Y (2015) Study synthesis of vanadium oxide nanotubes with two template hexadecylamin and hexylamine. *Biol Forum* 7:1671–1685
48. Ehsan K (2020) Synthesizing of vanadium oxide nanotubes using hydrothermal and ultrasonic method. Lambert Academic Publishing, Sunnyvale, pp 1–80
49. Shi Y, Peng L, Ding Y, Zhao Y, Yu G (2015) Nanostructured conductive polymers for advanced energy storage. *Chem Soc Rev* 44:6684–6696. <https://doi.org/10.1039/C5CS00362H>
50. Kianfar E, Pirouzfard V, Sakhaeinia H (2017) An experimental study on absorption/stripping CO₂ using Mono-ethanol amine hollow fiber membrane contactor. *J Taiwan Inst Chem Eng* 80:954–962
51. Kianfar E, Viet C (2021) Polymeric membranes on base of PAA/PM-ethyl methacrylate for air separation: a review. *J Mater Res Technol* 10:1437–1461
52. Faravar P, Zarei Z, Monjezi MG (2020) Modeling and simulation absorption of CO₂ using hollow fiber membranes (HFMs) with mono-ethanol amine with computational fluid dynamics. *J Environ Chem Eng* 8(4):103946
53. Yang Z, Zhang L, Zhou Y, Wang X, Wen L, Liang J et al (2020) Investigation of effective parameters on Cu₂O-3d nano catalyst the methanol-to-olefin conversion process: a review. *Res Inorg Chem* 40(3):91–105
54. Gao C, Liao J, Jingqiong Lu, Jia J, Kianfar E (2020) The effect of nanoparticles on gas permeability with polyimide membranes and network hybrid membranes: a review. *Res Inorg Chem*. <https://doi.org/10.1515/revic-2020-0017>
55. To JWF, Chen Z, Li H, He J, Kim K, Chou H-H, Pan L, Wilcox J, Cui Y, Bao Z (2015) Ultrahigh surface area three-dimensional porous graphitic carbon and conjugated polymeric molecular framework. *ACS Cent Sci* 1:68–74. <https://doi.org/10.1021/acscentsci.5b00149>
56. Stone D, Tayi AS, Goldberger JE, Palmer LC, Stupp SI (2011) Self-assembly conductivity of hydrogen-bonded oligothiophene nanofiber networks. *Chem Commun* 47(20):5702–5704
57. <https://olli.informatik.uni-oldenburg.de/weTEIS/weteis/transistor1.htm>
58. Hong J-P, Um M-C, Nam S-R, Hong J-I, Lee S (2009) Organic single-nanofiber transistors organogels. *Chem Commun* 3:310–312
59. Tsai W-W, Tevis ID, Tayi AS, Cui H, Stupp SI (2010) Semiconducting nanowires hairpin-shaped self-assembling sexithiophenes. *J Phys Chem B* 114(45):14778–14786
60. Kianfar E, Salimi M, Koohestani B (2020) Zeolite CATALYST: a review on the production of light olefins. Lambert Academic Publishing, Sunnyvale, pp 1–116
61. Ehsan K (2020) Investigation on catalysts of “Methanol to light Olefins.” Lambert Academic Publishing, Sunnyvale, pp 1–168
62. Kianfar E (2020) Application of nanotechnology in enhanced recovery oil and gas importance & applications of nanotechnology, chapter 3, vol 5. MedDocs Publishers, Reno, pp 16–21
63. Kianfar E (2020) Catalytic properties of nanomaterials and factors affecting it. Importance & applications of nanotechnology, chapter 4, vol 5. MedDocs Publishers, Reno, pp 22–25
64. Shi Y, Peng L, Yu G (2015) Nanostructured conducting polymer hydrogels for energy storage applications. *Nanoscale* 7:12796–12806. <https://doi.org/10.1039/C5NR03403E>
65. Zhao Y, Liu B, Pan L, Yu G (2013) 3D nanostructured conductive polymer hydrogels for high-performance electrochemical devices. *Energy Environ Sci* 6:2856–2870. <https://doi.org/10.1039/c3ee40997j>
66. Kartha KK, Babu SS, Srinivasan S, Ajayaghosh A (2012) Attogram sensing of trinitrotoluene with a self-assembled molecular gelator. *J Am Chem Soc* 134(10):4834–4841
67. Kianfar E (2020) Introducing the application of nanotechnology in lithium-ion battery importance & applications of nanotechnology, chapter 4, vol 4. MedDocs Publishers, Reno, pp 1–7
68. Ehsan K, Mazaheri H (2020) Synthesis of nanocomposite (CAU-10-H) thin-film nanocomposite (TFN) membrane for removal of color from the water. *Fine Chem Eng* 1:83–91
69. Ehsan K, Salimi M, Koohestani B (2020) Methanol to gasoline conversion over CuO/ZSM-5 catalyst synthesized and influence of water on conversion. *Fine Chem Eng* 1:75–82
70. Kianfar E (2020) An experimental study PVDF and PSF hollow fiber membranes for chemical absorption carbon dioxide. *Fine Chem Eng* 1:92–103
71. Zhang C et al (2017) Broadband metamaterial for optical transparency and microwave absorption. *Appl Phys Lett* 110(14):143511
72. Dennler G, Scharber MC, Brabec CJ (2009) Polymer-fullerene bulk-heterojunction solar cells. *Adv Mater* 21(13):1323–1338
73. Kim BG, Jeong EJ, Park HJ, Bilby D, Guo LJ, Kim J (2011) Effect of polymer aggregation on the open circuit voltage in organic photovoltaic

- cells: aggregation-induced conjugated polymer gels application for preventing open circuit voltage drop. *ACS Appl Mater Interfaces* 3(3):674–680
74. Yagai S, Suzuki M, Lin X, Gushiken M, Noguchi T, Karatsu T, Kitamura A et al (2014) Supramolecular engineering of oligothiophene nanorods without insulators: hierarchical association of rosettes/photovoltaic properties. *Chem Eur J* 20(49):16128–16137
 75. Zhou Y, Zhang M, Guo Z, Miao L, Han ST, Wang Z, Zhang X, Zhang H, Peng Z (2017) Recent advances in black phosphorus-based photonics, electronics, sensors and energy devices. *Mater Horiz* 4(6):997–1019
 76. Lee IG, Yoon SH, Lee JS, Hong IP (2016) Design of wideband radar absorbing material with improved optical transmittance by using printed metal-mesh. *Electron Lett* 52(7):555–557
 77. Yakovlev AV, Milichko VA, Vinogradov VV, Vinogradov AV (2016) Inkjet color printing by interference nanostructures. *ACS Nano* 10(3):3078–3086
 78. Qu B, Zhu C, Li C, Zhang X, Chen Y (2016) Coupling hollow Fe₃O₄-Fe nanoparticles with graphene sheets for high-performance electromagnetic wave absorbing material. *ACS Appl Mater Interfaces* 8(6):3730–3735. <https://doi.org/10.1021/acsami.5b12789>
 79. Li Y, Li W, Wang Y, Cao J, Guan J (2018) Refractory metamaterial microwave absorber with strong absorption insensitive to temperature. *Adv Opt Mater* 6:1800691. <https://doi.org/10.1002/adom.201800691>
 80. Gao K, Jo SB, Shi X, Nian L, Zhang M, Kan Y, Lin F, Kan B, Xu B, Rong Q, Shui L (2019) Over 12% efficiency nonfullerene all-small-molecule organic solar cells with sequentially evolved multilength scale morphologies. *Adv Mater* 31(12):1807842
 81. Yu Z, Jiao S, Li S, Chen X, Song W-L, Teng T, Jiguo Tu, Chen H-S, Zhang G, Fang D-N (2019) Flexible stable solid-state Al-ion batteries. *Adv Funct Mater* 29(1):1806799
 82. Wang Y, Zhang KL, Zhang BX, Ma CJ, Song WL, Hou ZL, Chen M (2018) Smart mechano-hydro-dielectric coupled hybrid sponges for multifunctional sensors. *Sens Actuators B Chem* 270:239–246
 83. Xu H, Yin X, Li M, Ye F, Han M, Hou Z, Li X, Zhang L, Cheng L (2018) Mesoporous carbon hollow microspheres with red blood cell-like morphology for efficient microwave absorption at elevated temperature. *Carbon* 132:343–351
 84. Chen H, Ma W, Huang Z, Zhang Y, Huang Y, Chen Y (2019) Graphene-based materials toward microwave and terahertz absorbing stealth technologies. *Adv Opt Mater* 7(8):1803333
 85. Xiang Y, Chen D (2007) Preparation of a novel pH-responsive silver nanoparticle/poly(HEMA-PEGMA-MAA) composite hydrogel. *Eur Polym J* 43:4178–4187
 86. McGehee MD, Topinka WA (2006) Solar cells: pictures the blended zone. *Nat Mater* 5(9):675–676
 87. Devaki SJ, Narayana RK, Sarojani S (2014) Electrically conducting silver nanoparticle-polyacrylic acid hydrogel by in situ reduction and polymerization approach. *Mater Lett* 116:135–138
 88. Fantino L, Chiappone A, Toppolo I et al (2016) 3D printing of conductive core-shell structures with in situ generation of silver nanoparticles. *Adv Mater* 28:3712–3717
 89. Hyun DC, Park K, Park C et al (2011) Ordered zigzag stripes of polymer gel/metal nanoparticle composites for highly stretchable conductive electrodes. *Adv Mater* 23:2946–2950
 90. Janina KL, Dékány I (2010) Optical properties and electric conductivity of gold nanoparticle-containing, hydrogel-based thin layer composite films obtained by photopolymerization. *Appl Surf Sci* 256:2809–2817
 91. Pardo-Yissar V, Gabai R, Shipway AN, Bourenko T, Willner I (2001) Gold nanoparticle/hydrogel composites with solvent-switchable electronic properties. *Adv Mater* 13:1320–1323
 92. Zhao X, Ding X, Deng Z, Zheng Z, Peng Y, Long X (2005) Thermoswitchable electronic properties of a gold nanoparticle/hydrogel composite. *Macromol Rapid Commun* 26:1784–1787
 93. Baei P, Jalili-Firoozinezhad S, Rajabi-Zeleti S, Tafazzoli-Shadpour M, Baharvand H, Aghdami N (2016) Electrically conductive gold nanoparticle-chitosan thermosensitive hydrogels for cardiac tissue engineering. *Mater Sci Eng C* 63:131–141
 94. Navaei A, Saini H, Christenson W, Sullivan RT, Ros R, Nikkham M (2016) Gold nanorod-incorporated gelatin-based conductive hydrogels for engineering cardiac tissue constructs. *Acta Biomater* 41:133–146
 95. Wei Q, Luo Y, Zhang C, Fan L, Chen Y (2008) Assembly of Cu nanoparticles in a polyacrylamide grafted poly(vinyl alcohol) copolymer matrix and vapor-induced response. *Sens Actuators B Chem* 134:49–56
 96. Ehsan K, Mafi S (2020) Ionic liquids: properties, application, and synthesis. *Fine Chem Eng* 2:22–31
 97. Faghieh SM, Kianfar E (2018) Modeling of fluid bed reaction of ethylene dichloride production in Abadan Petrochemical based on three-phase hydrodynamic model. *Int J Chem React Eng* 16:1–14
 98. Ehsan K, Mazaheri H (2020) Methanol to gasoline: a sustainable transport fuel. In: Taylor JC (ed) *Advances in chemistry research*, chapter: 4. Nova Science Publishers, Hauppauge, p 66
 99. Han L, Liu K, Wang M et al (2018) Mussel-inspired adhesive and conductive hydrogel with long-lasting moisture and extreme temperature tolerance. *Adv Funct Mater* 28(1):1195
 100. Liang Y, Zhao X, Hu T, Han Y, Guo B (2019) Mussel-inspired, antibacterial, conductive, antioxidant injectable composite hydrogel wound dressing to promote the regeneration of infected skin. *J Colloid Interface Sci* 556:514–528
 101. Cai G, Wang J, Qian C, Chen J, Li J, Lee PS (2017) Extremely stretchable strain sensor based on conductive self-healing dynamic cross-links hydrogels for human motion detection. *Adv Sci* 4:1600190
 102. Motter L, Le Cornec G, Moël JM et al (2018) A conductive hydrogel based on polyimide and carbon nanotubes for probing microbial electroactivity. *Sens Mater* 14:1434–1441
 103. Deng Z, Hu T, Lei Q, He J, Ma PX, Guo B (2019) Stimuli-responsive conductive nanocomposite hydrogels with high stretchability, self-healing, adhesiveness, and 3D printability for human motion sensing. *ACS Appl Mater Interfaces* 11:6796–6808
 104. Xu Y, Lin Z, Huang X, Wang Y, Huang Y, Duan X (2013) Functionalized graphene hydrogel-based high-performance supercapacitors. *Adv Mater* 25:5779–5784
 105. Liu Q, Zhang M, Huang L et al (2015) High-quality graphene ribbons prepared from graphene oxide hydrogels and their application for strain sensors. *ACS Nano* 9:12320–12326
 106. Xiao X, Wu G, Zhou H, Qian K, Hu J (2017) Preparation and property evaluation of conductive hydrogel using poly(vinyl alcohol)/polyethylene glycol/graphene oxide for human electrocardiogram acquisition. *Polymers* 9:259
 107. Alam A, Meng Q, Shi G et al (2016) Electrically conductive, mechanically robust, pH-sensitive graphene/polymer composite hydrogels. *Compos Sci Technol* 127:119–126
 108. Annabi N, Shin SR, Tamayol A et al (2016) Highly elastic and conductive human-based protein hybrid hydrogels. *Adv Mater* 28:40–49
 109. Han L, Lu X, Wang M et al (2017) A mussel-inspired conductive, self-adhesive, and self-healable tough hydrogel as cell stimulators and implantable bioelectronics. *Small* 13:1601916
 110. Liang Y, Zhao X, Hu T et al (2019) Adhesive hemostatic conducting injectable composite hydrogels with sustained drug release and photo-thermal antibacterial activity to promote full-thickness skin regeneration during wound healing. *Small* 15:1900046
 111. Jing X, Mi HY, Napiwocki BN, Peng XF, Turng LS (2017) Mussel-inspired electroactive chitosan/graphene oxide composite hydrogel with rapid self-healing and recovery behavior for tissue engineering. *Carbon* 125:557–570
 112. Qiu L, Liu D, Wang Y et al (2014) Mechanically robust, electrically conductive and stimuli-responsive binary network hydrogels enabled by superelastic graphene aerogels. *Adv Mater* 26:3333–3337
 113. Wang Y, Huang F, Chen X et al (2018) Stretchable, conductive, and self-healing hydrogel with super metal adhesion. *Chem Mater* 30:4289–4297
 114. Mano N, Yoo JE, Tarver J, Loo YL, Heller A (2007) An electron-conducting cross-linked polyaniline-based redox hydrogel, formed in one step at pH 7.2, wires glucose oxidase. *J Am Chem Soc* 129:7006–7007
 115. Guarino V, Alvarez-Perez MA, Borriello A, Napolitano T, Ambrosio L (2013) Conductive PANi/PEGDA macroporous hydrogels for nerve regeneration. *Adv Healthc Mater* 2:218–227
 116. Dong R, Zhao X, Guo B, Ma PX (2016) Self-healing conductive injectable hydrogels with antibacterial activity as cell delivery carrier for cardiac cell therapy. *ACS Appl Mater Interfaces* 8:17138–17150
 117. Zhao X, Wu H, Guo B, Dong R, Qiu Y, Ma PX (2017) Antibacterial anti-oxidant electroactive injectable hydrogel as self-healing wound

- dressing with hemostasis and adhesiveness for cutaneous wound healing. *Biomaterials* 122:34–47
118. Qu J, Zhao X, Ma PX, Guo B (2018) Injectable antibacterial conductive hydrogels with dual response to an electric field and pH for localized “smart” drug release. *Acta Biomater* 72:55–69
 119. Guo B, Qu J, Zhao X, Zhang M (2019) Degradable conductive self-healing hydrogels based on dextran-graft-tetraaniline and N-carboxyethyl chitosan as injectable carriers for myoblast cell therapy and muscle regeneration. *Acta Biomater* 84:180–193
 120. Li W, Gao F, Wang X, Zhang N, Ma M (2016) Strong and robust polyaniline-based supramolecular hydrogels for flexible supercapacitors. *Angew Chem Int Ed* 55:9196–9201
 121. Pan L, Yu G, Zhai D et al (2012) Hierarchical nanostructured conducting polymer hydrogel with high electrochemical activity. *PNAS* 109:9287–9292
 122. Guo H, He W, Lu Y, Zhang X (2015) Self-crosslinked polyaniline hydrogel electrodes for electrochemical energy storage. *Carbon* 92:133–141
 123. Chakraborty P, Guterman T, Adadi N et al (2019) A self-healing, all-organic, conducting, composite peptide hydrogel as pressure sensor and electrogenic cell soft substrate. *ACS Nano* 13:163–175
 124. Shi Y, Ma C, Peng L, Yu G (2015) Conductive, “smart” hybrid hydrogels with PNIPAM and nanostructured conductive polymers. *Adv Funct Mater* 25:1219–1225
 125. Deng Z, Guo Y, Ma PX, Guo B (2018) Rapid thermal responsive conductive hybrid cryogels with shape memory properties, photothermal properties and pressure dependent conductivity. *J Colloid Interface Sci* 526:281–294
 126. Chen J, Peng Q, Thundat T, Zeng H (2019) Stretchable, injectable, and self-healing conductive hydrogel enabled by multiple hydrogen bonding toward wearable electronics. *Chem Mater* 31:4553–4563
 127. Wang Z, Zhou H, Lai J et al (2018) Extremely stretchable and electrically conductive hydrogels with dually synergistic networks for wearable strain sensors. *J Mater Chem C* 6:9200–9207
 128. Hur J, Im K, Kim SW et al (2014) Polypyrrole/agarose-based electrically conductive and reversibly restorable hydrogel. *ACS Nano* 8:10066–10076
 129. Shi Y, Pan L, Liu B et al (2014) Nanostructured conductive polypyrrole hydrogels as high-performance, flexible supercapacitor electrodes. *J Mater Chem A* 2:6086–6091
 130. Han L, Yan L, Wang M et al (2018) Transparent, adhesive, and conductive hydrogel for soft bioelectronics based on light-transmitting polydopamine-doped polypyrrole nanofibrils. *Chem Mater* 30:5561–5572
 131. Gan D, Han L, Wang M et al (2018) Conductive and tough hydrogels based on biopolymer molecular templates for controlling in situ formation of polypyrrole nanofibrils. *ACS Appl Mater Interfaces* 10:36218–36228
 132. Rong Q, Lei W, Chen Y, Yin Y, Zhou J, Liu M (2017) Anti-freezing, conductive self-healing organic hydrogels with stable strain-sensitivity at subzero temperatures. *Angew Chem Int Ed* 56:14159–14163
 133. Gotovitskiy PM, Badrionova GU, Zubavichus YV et al (2019) Electroconductive PEDOT:PSS-based hydrogel prepared by freezing-thawing method. *Helv Chim Acta* 92:2498
 134. Maynard D, Artzy-Schnirman A, Tonkin J et al (2016) Electroconductive hydrogel based on functional poly(ethylenedioxy thiophene). *Chem Mater* 28:6080–6088
 135. Lu B, Yuk H, Lin S et al (2019) Pure PEDOT:PSS hydrogels. *Nat Commun* 10:1043
 136. Kianfar (2020) A comparison and assessment on performance of zeolite catalyst based selective for the process methanol to gasoline: a review. In: *Advances in chemistry research*, chapter 2. Nova Science Publishers, New York, p 63
 137. Kianfar E, Salimi M, Kianfar F et al (2019) CO₂/N₂ separation using polyvinyl chloride iso-phthalic acid/aluminium nitrate nanocomposite membrane. *Macromol Res* 27:83–89. <https://doi.org/10.1007/s13233-019-7009-4>
 138. Ehsan K (2020) Synthesis and characterization Nanoparticles isophthalic acid/aluminum nitrate (CAU-10-H) using method hydrothermal. *Advances in chemistry research*. Nova Science Publishers, New York
 139. Ehsan K (2020) CO₂ capture with ionic liquids: a review. *Advances in chemistry research*, vol 67. Nova Science Publishers, New York
 140. Ehsan K (2020) Enhanced light olefins production via methanol dehydration over promoted SAPO-34. *Advances in chemistry research*, chapter: 4. Nova Science Publishers, New York, p 63
 141. Ehsan K (2020) Gas hydrate: applications, structure, formation, separation processes, thermodynamics. In: Taylor JC (ed) *Advances in Chemistry research*, chapter: 8. Nova Science Publishers, New York, p 63
 142. Kianfar M, Kianfar F, Kianfar E (2016) The effect of nano-composites on the mechanic and morphological characteristics of NBR/PA6. *Iran J Polym Sci Technol* 4(1):29–44
 143. Farshad K, Moghadam SRM, Kianfar E (2015) Energy optimization of ilam gas refinery unit 100 by using HYSYS refinery software. *Indian J Sci Technol* 8(59):431–436
 144. Kianfar E (2015) Production and identification of vanadium oxide nanotubes. *Indian J Sci Technol* 8(59):435–464
 145. Farshad K, Moghadam SRM, Kianfar E (2015) Synthesis of spiro pyran by using silica-bonded N-propyl-diethyl-tri-amine as recyclable basic catalyst. *Indian J Sci Technol* 9(11):68669
 146. Kianfar E (2019) Recent advances in synthesis, properties, and applications of vanadium oxide nanotube. *Microchem J* 145:966–978
 147. Hajimirzaee M, Golmohammadi M, Mehr A, Kianfar E (2020) Modified ZSM-5 zeolite for conversion of LPG to aromatics. *Polycycl Arom Compd*. <https://doi.org/10.1080/10406638.2020.1833048>
 148. Li L, Wang Y, Pan L et al (2015) A nanostructured conductive hydrogels-based biosensing platform for human metabolite detection. *Nano Lett* 15:1146–1151
 149. Das S, Chakraborty P, Mondal S, Shit A, Nandi AK (2016) Enhancement of energy storage and photoresponse properties of folic acid-polyaniline hybrid hydrogel by in situ growth of Ag nanoparticles. *ACS Appl Mater Interfaces* 8:28055–28067
 150. Li P, Jin Z, Peng L et al (2018) Stretchable all-gel-state fiber-shaped supercapacitors enabled by macromolecularly interconnected 3D graphene/nanostructured conductive polymer hydrogels. *Adv Mater* 30:1800124
 151. Guo Y, Zheng K, Wan P (2018) A flexible stretchable hydrogel electrolyte for healable all-in-one configured supercapacitors. *Small* 14:1704497
 152. Rong Q, Han H, Feng F, Ma Z (2015) Network nanostructured polypyrrole hydrogel/Au composites as enhanced electrochemical biosensing platform. *Sci Rep* 5:11440. <https://doi.org/10.1038/srep11440>
 153. Yang J, Wang X, Li B et al (2017) Novel iron/cobalt-containing polypyrrole hydrogel-derived trifunctional electrocatalyst for self-powered overall water splitting. *Adv Funct Mater* 27:1606497
 154. Shi Y, Zhang J, Bruck AM et al (2017) A tunable 3D nanostructured conductive gel framework electrode for high-performance lithium ion batteries. *Adv Mater* 29:1603922
 155. Deng Z, Guo Y, Zhao X, Ma PX, Guo B (2018) Multifunctional stimuli-responsive hydrogels with self-healing, high conductivity, and rapid recovery through host-guest interactions. *Chem Mater* 30:1729–1742
 156. Chen J, Sheng K, Luo P, Li C, Shi G (2012) Graphene hydrogels deposited in nickel foams for high-rate electrochemical capacitors. *Adv Mater* 24:4569–4573
 157. Mao L, Guan C, Huang X, Ke Q, Zhang Y, Wang J (2016) 3D graphene-nickel hydroxide hydrogel electrode for high-performance supercapacitor. *Electrochim Acta* 196:653–660
 158. Wang R, Jayakumar A, Xu C, Lee JM (2016) Ni(OH)₂ nanoflowers/graphene hydrogels: a new assembly for supercapacitors. *ACS Sustain Chem Eng* 4:3736–3742
 159. Javadi M, Gu Q, Naficy S et al (2018) Conductive tough hydrogel for bioapplications. *Macromol Biosci* 18:1700270
 160. De B, Kuila T, Kim NH, Lee JH (2017) Carbon dot stabilized copper sulphide nanoparticles decorated graphene oxide hydrogel for high performance asymmetric supercapacitor. *Carbon* 122:247–257
 161. Kianfar E (2021) Investigation of the effect of crystallization temperature and time in synthesis of SAPO-34 catalyst for the production of light olefins. *Pet Chem* 61:527–537. <https://doi.org/10.1134/S0965544121050030>
 162. Huang X, Zhu Y, Kianfar E (2021) Nano biosensors: properties, applications and electrochemical techniques. *J Mater Res Technol* 12:1649–1672. <https://doi.org/10.1016/j.jmrt.2021.03.048>
 163. Kianfar E (2021) Protein nanoparticles in drug delivery: animal protein, plant proteins and protein cages, albumin nanoparticles. *J Nanobiotechnol* 19:159. <https://doi.org/10.1186/s12951-021-00896-3>

164. Kianfar E (2021) Magnetic nanoparticles in targeted drug delivery: a review. *J Supercond Novel Magn*. <https://doi.org/10.1007/s10948-021-05932-9>
165. Syah R, Zahar M, Kianfar E (2021) Nanoreactors: properties, applications and characterization. *Int J Chem Reactor Eng* 19(10):981–1007. <https://doi.org/10.1515/ijcre-2021-0069>
166. Raya I, Kzar HH, Mahmoud ZH, Al Ayub Ahmed A, Ibatova AZ, Kianfar E (2021) A review of gas sensors based on carbon nanomaterial. *Carbon Lett*. <https://doi.org/10.1007/s42823-021-00276-9>
167. Majdi HS, Latipov ZA, Borisov V et al (2021) Nano and battery anode: a review. *Nanoscale Res Lett* 16:177. <https://doi.org/10.1186/s11671-021-03631-x>
168. Bokov D, Turki Jalil A, Chupradit S, Suksatan W, Javed Ansari M, Shewael IH, Valiev GH, Kianfar E (2021) Nanomaterial by sol–gel method: synthesis and application. *Adv Mater Sci Eng* 2021:21. <https://doi.org/10.1155/2021/5102014>
169. Jasim SA, Kadhim MM, Kn V et al (2022) Molecular junctions: introduction and physical foundations, nanoelectrical conductivity and electronic structure and charge transfer in organic molecular junctions. *Braz J Phys* 52:31. <https://doi.org/10.1007/s13538-021-01033-z>
170. Ansari MJ, Kadhim MM, Hussein BA et al (2022) Synthesis and stability of magnetic nanoparticles. *BioNanoSci*. <https://doi.org/10.1007/s12668-022-00947-5>
171. Krishna Sindhu C, Naga Sowmya A, Haveela B, Kavya Nandini G, Shaik S (2021) Design of frequency reconfigurable microstrip antenna. *Natl J Antennas Propag* 3(1):16–21. <https://doi.org/10.31838/NJAP/03.01.04>
172. Sadulla S (2020) A review on finfets from device to circuit. *J VLSI Circuits Syst* 2(1):11–13. <https://doi.org/10.31838/jvcs/02.01.03>
173. Srilakshmi K, Preethi K, Afsha Md, Pooja Sree N, Venu M (2022) Advanced electricity billing system using arduino uno. *Int J Commun Comput Technol* 10(1):1–3. <https://doi.org/10.31838/ijccts/10.01.01>
174. Enany MA, Farahat MA, Otay MI (2021) Optimal design and operation of fast charging station for electric vehicle via renewable energy in Wadi El-Natrun-El Alamein Road, Egypt. *Int J Sustain Energy Environ Res* 10(1):38–46. <https://doi.org/10.18488/journal.13.2021.01.38>
175. Al-Shawi SG, Andreevna Alekhina N, Aravindhana S, Thangavelu J, Elena A, Viktorovna Kartamysheva N, Rafkatovna Zaleeva R (2021) Synthesis of NiO nanoparticles and sulfur, and nitrogen doped-graphene quantum dots/nio nanocomposites for antibacterial application. *J Nanostruct* 11(1):181–188
176. Wang H, Zhu B, Jiang W et al (2014) A mechanically and electrically self-healing supercapacitor. *Adv Mater* 26:3638–3643
177. Wang K, Zhang X, Li C et al (2015) Chemically crosslinked hydrogel film leads to integrated flexible supercapacitors with superior performance. *Adv Mater* 27:7451–7457
178. Huang Y, Zhong M, Shi F et al (2017) An intrinsically stretchable and compressible supercapacitor containing a polyacrylamide hydrogel electrolyte. *Angew Chem Int Ed* 56:9141–9145
179. Panchal H, Sadasivuni KK, Ahmed AA, Hishan SS, Doranehgard MH, Essa FA, Manmugan S, Khalid M (2021) Graphite powder mixed with black paint on the absorber plate of the solar still to enhance yield: an experimental investigation. *Desalination* 520:115349
180. Ahmed Alian E, Maleki S, Sharifi S, Eftekhari A, Samiei M (2020) Hyaluronic acid hydrogel nanoscaffolds: production and assessment of the physico-chemical properties. *Euras Chem Commun* 2(1):51–58. <https://doi.org/10.33945/sami/ecc.2020.1.6>
181. Shinde R, Adole VA (2021) Anti-microbial evaluation, experimental and theoretical insights into molecular structure, electronic properties, and chemical reactivity of (E)-2-((1H-indol-3-yl)methylene)-2,3-dihydro-1H-inden-1-one. *J Appl Organomet Chem* 1(2):48–58. <https://doi.org/10.22034/jaoc.2021.278742.1011>
182. Sanjeev R, Jagannadham V, Ravi R (2020) Can non-bonded pair of electrons of Sp³ nitrogen with two single σ-bonds on either side still transmit substituent electronic effects to the reaction site? Reversal of attenuation effect by Sp³ nitrogen—a chemical education perspective. *Chem Methodol* 4(1):106–114. <https://doi.org/10.33945/sami/chemm.2020.1.10>
183. Ozkendir OM, Gunaydin S, Mirzaei M (2019) Electronic structure study of the LiBC₃ borocarbide graphene material. *Adv J Chem Sect B* 1(1):37–41. <https://doi.org/10.33945/sami/ajcb.2019.1.7>
184. Chen TC, Rajiman R, Elveny M, Guerrero JW, Lawal AI, Dwijendra NK, Surendar A, Danshina SD, Zhu Y (2021) Engineering of novel Fe-based bulk metallic glasses using a machine learning-based approach. *Arab J Sci Eng* 46(12):12417–12425. <https://doi.org/10.1007/s13369-021-05966-0>
185. Qaderi J (2020) A brief review on the reaction mechanism of CO₂ hydrogenation into methanol. *Int J Innov Res Sci Stud* 2(1):33–38. <https://doi.org/10.53894/ijirss.v3i2.31>
186. Watandost H, Achak J, Haqmal A (2021) Oxidation of hydrogen based of sodium alginate and MnO₂ as catalyst. *Int J Innov Res Sci Stud* 4(4):191–199. <https://doi.org/10.53894/ijirss.v4i4.7>
187. Issa M (2022) Rapid enzymatically reduction of zinc oxide nanocomplex for the biomufacturing of zinc oxide nanoparticles by mycoextracellular filtrate of penicillium digitatum (Pdigi-1) as a soft green technique. *Arch Razi Inst* 77(1):91–100. <https://doi.org/10.1007/ari.2021.356422.1841>
188. Fan FR, Tang W, Wang ZL (2016) Flexible nanogenerators for energy harvesting and self-powered electronics. *Adv Mater* 28:4283–4305
189. Hinchet R, Seung W, Kim SW (2015) Recent progress on flexible triboelectric nanogenerators for self-powered electronics. *Chemsuschem* 8:2327–2344
190. Pu X, Liu M, Chen Y et al (2017) Ultrastretchable, transparent triboelectric nanogenerator for electronic skin for biomechanical energy harvesting and tactile sensing. *Sci Adv* 3:e1700015
191. Bai Y, Jiang H, Chen B et al (2014) Cyclic performance of viscoelastic dielectric elastomers with solid hydrogel electrodes. *Appl Phys Lett* 104:062907
192. Chen B, Bai Y, Xiang F et al (2014) Stretchable and transparent hydrogels as soft conductors for dielectric elastomer actuators. *J Polym Sci B* 52:1055–1060
193. Li T, Li G, Liang Y et al (2017) Fast-moving soft electronic fish. *Sci Adv* 3:e1602045
194. Larson C, Peele B, Li S et al (2016) Highly stretchable electroluminescent skin for optical signaling and tactile sensing. *Science* 351:1071–1074
195. Li S, Peele BN, Larson CM, Zhao H, Shepherd RF (2016) A stretchable multicolor display and touch interface using photopatterning and transfer printing. *Adv Mater* 28:9770–9775
196. Yang CH, Chen B, Zhou J, Chen YM, Suo Z (2016) Electroluminescence of giant stretchability. *Adv Mater* 28:4480–4484
197. Yang CH, Zhou S, Shian S, Clarke DR, Suo Z (2017) Organic liquid-crystal devices based on ionic conductors. *Mater Horiz* 4:1102–1109
198. Kim CC, Lee HH, Oh KH, Sun JY (2016) Highly stretchable, transparent ionic touch panel. *Science* 353:682–687
199. Zhou Y, He B, Yan Z, Shang Y, Wang Q, Wang Z (2018) Touch locating and stretch sensing studies of conductive hydrogels with applications to soft robots. *Sensors* 18:569
200. Bella F, Galliano S, Falco M et al (2017) Approaching truly sustainable solar cells by the use of water and cellulose derivatives. *Green Chem* 19:1043–1051
201. Liu T, Liu M, Dou S et al (2018) Triboelectric-nanogenerator-based soft energy-harvesting skin enabled by toughly bonded elastomer/hydrogel hybrids. *ACS Nano* 12:2818–2826
202. Keplinger C, Sun JY, Foo CC, Rothemund P, Whitesides GM, Suo Z (2013) Stretchable, transparent, ionic conductors. *Science* 341:984–987
203. Kweon OY, Samanta SK, Won Y, Yoo JH, Oh JH (2019) Stretchable and self-healable conductive hydrogels for wearable multimodal touch sensors with thermoresponsive behavior. *ACS Appl Mater Interfaces* 11:26134–26143
204. Sun JY, Keplinger C, Whitesides GM, Suo Z (2014) Ionic skin. *Adv Mater* 26:7608–7614
205. Liu S, Zheng R, Chen S et al (2018) A compliant, self-adhesive and self-healing wearable hydrogel as epidermal strain sensor. *J Mater Chem C* 6:4183–4190
206. Morelle XP, Illeperuma WR, Tian K, Bai R, Suo Z, Vlassak JJ (2018) Highly stretchable and tough hydrogels below water freezing temperature. *Adv Mater* 30:1801541
207. Lei Z, Wang Q, Sun S, Zhu W, Wu P (2017) A bioinspired mineral hydrogel as a self-healable, mechanically adaptable ionic skin for highly sensitive pressure sensing. *Adv Mater* 29:1700321
208. Si Y, Wang L, Wang X, Tang N, Yu J, Ding B (2017) Ultrahigh-water-content, superelastic, and shape-memory nanofiber-assembled hydrogels exhibiting pressure-responsive conductivity. *Adv Mater* 29:1700339

209. Liu YJ, Cao WT, Ma MG, Wan P (2017) Ultrasensitive wearable soft strain sensors of conductive, self-healing, and elastic hydrogels with synergistic “soft and hard” hybrid networks. *ACS Appl Mater Interfaces* 9:25559–25570
210. Deng Y, Hussain I, Kang M et al (2018) Self-recoverable and mechanical-reinforced hydrogel based on hydrophobic interaction with self-healable and conductive properties. *Chem Eng J* 353:900–910
211. Liu S, Li K, Hussain I et al (2018) A conductive self-healing double network hydrogel with toughness and force sensitivity. *Chem A Eur J* 24:6632–6638
212. Liu S, Oderinde O, Hussain I, Yao F, Fu G (2018) Dual ionic cross-linked double network hydrogel with self-healing, conductive, and force sensitive properties. *Polymer* 144:111–120
213. Shao C, Wang M, Meng L et al (2018) Mussel-inspired cellulose nanocomposite tough hydrogels with synergistic self-healing, adhesive, and strain-sensitive properties. *Chem Mater* 30:3110–3121
214. Tran VT, Mredha MTI, Pathak SK, Yoon H, Cui J, Jeon I (2019) Conductive tough hydrogels with a staggered ion-coordinating structure for high self-recovery rate. *ACS Appl Mater Interfaces* 11:24598–24608
215. Lai J, Zhou H, Wang M et al (2018) Recyclable, stretchable and conductive double network hydrogels towards flexible strain sensors. *J Mater Chem C* 6:13316–13324
216. Schroeder TBH, Guha A, Lamoureux A et al (2017) An electric-eel-inspired soft power source from stacked hydrogels. *Nature* 552:214–218
217. Jing X, Mi HY, Lin YJ, Enriquez E, Peng XF, Turgun LS (2018) Highly stretchable and biocompatible strain sensors based on mussel-inspired super-adhesive self-healing hydrogels for human motion monitoring. *ACS Appl Mater Interfaces* 10:20897–20909
218. Wu J, Han S, Yang T et al (2018) Highly stretchable and transparent thermistor based on self-healing double network hydrogel. *ACS Appl Mater Interfaces* 10:19097–19105
219. Wu J, Wu Z, Han S et al (2019) Extremely deformable, transparent, and high-performance gas sensor based on ionic conductive hydrogel. *ACS Appl Mater Interfaces* 11:2364–2373
220. Bai Y, Chen B, Xiang F, Zhou J, Wang H, Suo Z (2014) Transparent hydrogel with enhanced water retention capacity by introducing highly hydratable salt. *Appl Phys Lett* 105:151903
221. Huo Z, Tao L, Wang S et al (2015) A novel polysulfide hydrogel electrolyte based on low molecular mass organogelator for quasi-solid-state quantum dot-sensitized solar cells. *J Power Sources* 284:582–587
222. Liu X, Wu D, Wang H, Wang Q (2014) Self-recovering tough gel electrolyte with adjustable supercapacitor performance. *Adv Mater* 26:4370–4375
223. He X, Zhang C, Wang M, Zhang Y, Liu L, Yang W (2017) An electrically and mechanically autonomous self-healing hybrid hydrogel with tough and thermoplastic properties. *ACS Appl Mater Interfaces* 9:11134–11143
224. Hao GP, Goppauf F, Gschatz M et al (2014) Stretchable and semitransparent conductive hybrid hydrogels for flexible supercapacitors. *ACS Nano* 8:7143–7146
225. Ding H, Zhong M, Kim YJ et al (2014) Biologically derived soft conductive hydrogels using heparin-doped polymer networks. *ACS Nano* 8:4351–4357
226. Liao M, Wan P, Wen J et al (2017) Wearable, healable, and adhesive epidermal sensors assembled from mussel-inspired conductive hybrid hydrogel framework. *Adv Funct Mater* 27:1703852
227. Hutapea S, Ghazi Al-Shawi S, Chen TC, You X, Bokov D, Abdelbasset WK, Suksatan W (2021). Study on food preservation materials based on nano-particle reagents. *Food Sci Technol*
228. Yin G, Alazzawi FJ, Mironov S, Reegu F, El-Shafay AS, Rahman ML, Su CH, Lu YZ, Nguyen HC (2022) Machine learning method for simulation of adsorption separation: comparisons of model's performance in predicting equilibrium concentrations. *Arab J Chem* 15(3):103612
229. Bashar Mahmood H, Obead W, Al-Arubaye N (2022) Anatomical assessments for grey mongoose tongue by scanning electron microscope (*Herpestes edwardsii*) in Iraq. *Arch f Razi Inst* 77(1):118–122. <https://doi.org/10.22092/ari.2021.356480.1851>

Publisher's Note

Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Submit your manuscript to a SpringerOpen® journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at ► [springeropen.com](https://www.springeropen.com)