

To recreate bone's nanostructure in the laboratory, Stupp and his team designed a cone-shaped molecule, a peptide-amphiphile, that is bulkier and hydrophilic on one end (a peptide) and slimmer and hydrophobic on the other (an alkyl group). When in water at low pH, the molecules assemble themselves like spokes on a wheel, with the hydrophobic greasy tail directed to the center, leaving the peptide to face the exterior aqueous environment. This basic structure is repeated so that a long nanofiber is formed, similar to an insulated copper wire where the insulation is the peptide and the wire is the alkyl group. The synthetic fibers orient the growth of the hydroxyapatite crystals so that they mimic the structure found in natural bone.

The researchers engineered their peptide structure to attract bone cells, but the chemistry of the peptide is customizable, said Stupp, and can be changed to attract different cells to the fibrous scaffold, such as neurons, cartilage, muscle, liver, and pancreas cells.

Stupp said, "We've mimicked this for bone, but we have offered a strategy that would work for other tissues of the human body, or to create materials inspired by bone that could be useful in electronics or photonics."

Electrical Conductivity of Single-Molecule Wires Accurately Measured

Researchers from Arizona State University have determined a method for creating through-bond electrical contacts with single molecules, enabling them to achieve reproducible measurements of the molecules' conductivity. ASU chemistry professor Devens Gust said, "Progress in the field has been hampered by two problems. The first has been in making robust, reproducible electrical connections to both ends of molecules. After this has been achieved, the next problem is knowing how many molecules there actually are between the electrical contacts."

As reported in the October 19, 2001, issue of *Science*, the researchers began with a uniform atomic layer of gold atoms and attached octanethiol insulator molecules to it through chemical bonds, forming a coating of aligned molecules. Using a solvent, they removed some of the insulators and replaced them with molecules of 1,8-octanedithiol, a molecule that is similar but capable of bonding with gold at both ends and acting as a molecular "wire."

Gold 2-nm particles were then added to the solvent, where they bonded to the free ends of the 1,8-octanedithiol mole-

cules, thus creating a bonded metallic contact at either end of the conducting molecules. A gold-coated conducting atomic force microscope probe was then run across the surface and conductivity was measured when it made contact with the gold particles.

When electrical measurements were made on over 4000 gold particles, virtually all measurements fell into one of five groups of distinct conductivity curves, according to the researchers. The conductivity curves were distinct whole-number multiples of a single, fundamental curve, they said.

The researchers said that the fundamental curve represents conduction by a single molecule of octanedithiol attached to the two gold contacts. When more than a single molecule was bound, each additional molecule increased the current capacity by the single unit amount of current that could be carried by one molecule. When the probe encountered octanethiol insulator molecules, which could not bond with a gold particle, a much higher electrical resistance was recorded.

Gust said, "The molecule becomes a much better conductor when it is 'soldered' into the circuit by the bonds to gold at each end. This suggests how we can wire single-molecule components into a molecular circuit board, and lays some important groundwork for doing practical molecular electronics."

Cubic ZnMgO Alloys Offer Alternative to III-Nitride Wurtzite Structure

Jagdish Narayan and his associates at North Carolina State University have synthesized ZnMgO alloys that have a cubic sodium chloride structure, which may provide an alternative to III-nitrides of wurtzite hexagonal structure. When ZnO is alloyed with MgO, it can be controlled to produce either a hexagonal (wurtzite) or cubic (sodium-chloride) structure, they said. The cubic structure can be grown epitaxially on Si(100) by domain-matching epitaxy, where four lattice constants of the silicon match with three of the substrate. In addition, ZnO and its alloys have a higher exciton binding energy (60 meV) as compared with III-nitride counterparts (25 meV), which results in less trapping of carriers and luminescent efficiencies, they said.

ZnO, a II-VI semiconductor with a bandgap of 3.27 eV at 300 K, compares very closely with GaN of III-V systems. To vary the bandgap of ZnO, it can be alloyed with MgO (8.2 eV) to increase the bandgap or with CdO (2.0 eV) to decrease it. This is similar to the III-nitride system,

Narayan said, where GaN is alloyed with AlN (6.2 eV) to increase the bandgap or with AlN to decrease it. These III-nitride alloys have a hexagonal (wurtzite) structure, which can be grown epitaxially only on substrates of hexagonal symmetry. These substrates include α -Al₂O₃, (III)Si, 6H-SiC, and ZnO. The epitaxial growth on 6H-SiC and ZnO(0001) substrates occurs by lattice-matching epitaxy due to a small misfit. On the other hand, Narayan said, the epitaxial growth of III-nitride on α -Al₂O₃ and (111)Si occurs by means of domain-matching epitaxy, where an integral multiple of major planes/lattice constants of the film match with the substrate. For example, six (01 $\bar{1}$ 0) planes of the film match with the seven ($\bar{1}$ 2 $\bar{1}$ 0) planes of the substrate after a 30°/90° rotation in the basal plane, he said.

The ZnMgO alloys can be used to produce any color, including the three primary colors needed for white light-emitting devices that would be more durable and consume less power than conventional incandescent bulbs or fluorescent lamps, Narayan said.

"The shorter wavelength can also be focused more tightly, leading to a substantial increase in storage capacity of magnetic and optical disks," he said.

The researchers anticipate further applications for their U.S. patented alloy in the field of spintronics, biosensors, and optical communications.

Nanosphere Converted to Nanoprism, Offering Different Properties

Scientists at Northwestern University have been able to create triangular nanoprisms. They reported the method used to produce triangular nanoprisms in large quantities, using commercially available silver nanospheres, soap, and visible light, in the November 30, 2001, issue of *Science*.

In nanotechnology, most of the bulk preparatory methods are for spheres and rods, said Chad A. Mirkin, director of Northwestern's Institute for Nanotechnology, who led the experimental portion of the study.

In their experiments, the researchers found that when they placed common nanospheres made of silver in a solution containing soap molecules and irradiated the mixture with room light for three days, the spheres were converted into triangular prisms 15 nm thick.

The light induced the nanospheres to break up into silver atoms, which then fed the growth of the nanoprisms, a process called ripening. The conversion process could be arrested at any point by