

face reaction of H₂O on Ru, and for the Pt-CeO₂/CB anode is the diffusion of the active species on the Pt-CeO₂ particles. These findings led the research team to infer that using nanosized CeO₂ particles has the potential to increase the performance of the Pt-CeO₂/CB anode even more, making it possible to reduce the amount of Pt needed in the electrode.

SIARI S. SOSA

Bioactive Glass Scaffolds with Hierarchical Pore Networks Fabricated

Mesoscopic bioactive glasses have been reported to have excellent bone-forming bioactivities, but are ineffective as tissue scaffolds. The pore dimensions are too small to promote cell seeding and migration necessary for tissue regeneration. Researchers from Korea Institute of Machinery & Materials (KIMM) addressed these concerns in the March 16 issue of *Chemical Communications* (DOI: 10.1039/b702103h). H.-S. Yun and co-workers at KIMM reported on the design and fabri-

cation of three-dimensional bioactive glass scaffolds with hierarchical pore networks and bone-tissue regeneration capabilities.

The fabrication protocol is a combination of sol-gel synthesis, polymer templating, and rapid prototyping using a robotic deposition mechanism. A virtual 3D scaffold architecture was generated by computer-aided design and interpreted by the robotic deposition device for fabrication using a gel paste. In addition to inorganic precursors, the gel paste uses a triblock copolymer (EO₁₀₀PO₆₅EO₁₀₀ (F127)) as a mesostructure directing agent and methyl cellulose (MC) as a macrostructure directing agent and binder. Extrusion of the gel paste onto a heated (60–100°C) substrate yields a stable gel structure following quick solvent evaporation and solidification of MC. The size, thickness, pore dimensions, and number of stacking layers in the scaffold can be easily manipulated by computer control. After aging for 24 h at 40°C, calcination of the organic-inorganic hybrid removes

the polymer template. As a result, 3D pore networks with hierarchically giant (>100 μm), macro- (10 μm < d_{pore} < 100 μm), and mesopores are generated in the scaffold. No apparent structural deformation was observed after calcination although there was an ~35% decrease in scaffold size.

In vitro bioactivity of the 3D porous scaffolds were tested in simulated body fluid (SBF) at 37°C. Formation of hydroxyl apatite on the porous surface was monitored by acquiring and comparing scanning electron microscopy images before and after interaction with SBF. Within 24 hours, formation of biomimetic hydroxyl apatite confirmed excellent bone-forming bioactive capabilities *in vitro*.

Although this simple and reproducible synthetic method was directed toward biomimetic applications, the researchers said that it could be very easily adapted for various hierarchical porous structures with potential applications in optics, sensing, and catalysis.

SOMA CHATTOPADHYAY



Recommend
To Your Library
Today!

PROCEEDINGS LIBRARY

Expanded online resources for the materials community
Now available to libraries and institutions!

12-month unlimited access to over 17,500 papers—
proceedings volumes published from our 2000 MRS Spring Meeting
to the present, with more added daily.

www.mrs.org/publications

For more information, contact: Anita B. Miller, Materials Research Society, 506 Keystone Drive, Warrendale, PA 15086
Tel: 724-779-3004, X 551; Fax: 724-779-8313; amiller@mrs.org

Advertisers in This Issue

			Page No.
American Scientific Publishers	www.aspbs.com	order@aspbs.com	530
Bruker AXS, Inc.	www.bruker-axs.com	info@bruker-axs.com	521
Carl Zeiss SMT Inc.	www.smt.zeiss.com/nts	info-usa@smt.zeiss.com	533
Frontiers in Optics 2007	www.FrontiersInOptics.org	info@osa.org	565
Hidden Analytical Inc.	www.HiddenInc.com	info@HiddenInc.com	543
High Voltage Engineering Europa B.V.	www.highvolteng.com	info@highvolteng.com	Inside front cover
Huntington Mechanical Laboratories, Inc.	www.huntvac.com	vacman@huntvac.com	Outside back cover
Janis Research Company, Inc.	www.janis.com	sales@janis.com	543
JEOL USA, Inc.	www.jeolusa.com	salesinfo@jeol.com	522
Kurt J. Lesker Company	www.lesker.com	materialsgroup@lesker.com	Inside back cover

For direct links to the advertisers in this issue, access www.mrs.org/bulletin_ads or use the information provided above.