

be too long for practical use, and those based on birefringence, while small, are too lossy to be practical. To address this, the researchers decided to pursue a hybrid device, which combines a central birefringent section with mode-matching tapered-waveguide input/output couplers to reduce optical loss. The researchers fabricated samples of the devices in an InGaAsP heterostructure consisting of an InP top cladding layer, an InGaAsP waveguide layer, and an InP buffer layer. A silica layer was deposited to form a hard mask. The waveguide was formed by writing the waveguide pattern into a 200-nm thick layer of polymethylmethacrylate (PMMA) using electron-beam lithography, transferring the pattern into a hard-mask layer of silica with reactive ion etching using  $\text{CHF}_3$  chemistry, and finally deep etching into the InP layers using chemically assisted ion beam etching. The final devices were all less than 50  $\mu\text{m}$  long.

The group then tested the devices by launching polarized light at a wavelength of 1.55  $\mu\text{m}$  into them and measuring the rotation of the plane of polarization as a function of the width of the central birefringent section. The rotation angle increased with decreasing width, and ranged from nearly zero for a 1500-nm-wide central section to over 250 degrees for a 500-nm-wide central section. The overall insertion losses were only about 1 dB, dominated by propagation loss rather than back reflections, which can degrade photonic circuit performance. The devices were also found to operate over a 100 nm wavelength range, demonstrating that they could be used in a broadband photonic circuit configuration. Given these results, hybrid polarization-control devices of this nature may form a key component of future integrated microphotonic systems.

COLIN MCCORMICK

### **SnO<sub>2</sub> Nanowires Used to Fabricate Fully Transparent Thin-Film Transistor Devices**

The extraordinary properties of semiconductor nanowires have led many researchers to pursue novel device applications. For example, conventional transparent thin-film transistors (TFTs) that use single-crystal channel materials typically require growth and annealing at high temperature and expensive single-crystalline substrates. In contrast, high-performance, nanowire-based TFTs have been fabricated on glass and plastic substrates. A key advantage to this approach is its capacity to separate the nanowire growth step from the device fabrication, which makes moot the compatibility between the device substrate with nano-

wire growth. High temperatures can therefore be used to obtain nanowires composed of single crystals, which are then transferred to the device substrate, configured into thin-film form, and processed into TFTs using conventional techniques. Heretofore, opaque semiconducting nanowires, (e.g., silicon), were used with electrodes made from normal metals such as Au or Ni but new frontiers such as "invisible electronics" require optical transparency. Recently, W. Lu and co-researchers from the University of Michigan fabricated fully transparent nanowire-based TFT devices that exhibit excellent transistor performance.

As reported in the August issue of *Nano Letters* (p. 2463, DOI: 10.1021/nl0712217), Lu and co-researchers grew single-crystalline, Ta-doped SnO<sub>2</sub> nanowires using a simple, inexpensive method and used them as channel material in field-effect transistor (FET) and TFT devices. The researchers chose SnO<sub>2</sub> nanowires because they have high optical transmittance and easily form Ohmic contacts with conducting oxide films. Scanning electron microscopy (SEM) and transmission electron microscopy (TEM) showed that the nanowires have a mean, uniform diameter of 55 nm with lengths measured in the tens of micrometers. High-resolution TEM showed that each nanowire is a perfect single crystal. FET devices with a channel consisting of a single nanowire, fabricated on Si substrates to investigate the intrinsic electrical properties of Ta-doped SnO<sub>2</sub> nanowires, displayed field-effect mobilities over 100  $\text{cm}^2/\text{V}\cdot\text{s}$ . In contrast, undoped SnO<sub>2</sub>-nanowire devices displayed pronounced Schottky barrier behavior. The researchers then fabricated fully transparent TFTs on glass substrates using arrays of parallel, doped nanowires as the transistor channel and indium tin oxide source and drain electrodes. Techniques, such as sputter deposition, that can be used in large-scale production were employed. Furthermore, the high-temperature limit in the fabrication process was 250°C, making it compatible with many plastic substrates. Even at low nanowire coverage, the TFTs exhibit high mobilities similar to the single-nanowire devices as well as excellent optical transparency and transistor performance, such as transconductance, bias, voltage range, and on/off ratio. The researchers said that "[our] study circumvents the position-registry problem hindering single-nanowire based approaches and may lead to large-scale applications of high performance, transparent, nanowire-based thin-film devices on diverse substrates."

STEVEN TROHALAKI

### **Carbon Nanotubes Endure Heavy Wear and Tear**

The ability of carbon nanotubes to withstand repeated stress yet retain their structural and mechanical integrity is similar to the behavior of soft tissue, according to researchers J. Suhr of the University of Nevada in Reno, V. Pushparaj of Rensselaer Polytechnic Institute, and their colleagues.

When paired with the strong electrical conductivity of carbon nanotubes, this ability to endure wear and tear, or fatigue, suggests the materials could be used to create structures that mimic artificial muscles or electromechanical systems, the researchers said.

"The idea was to show how fatigue affects nanotube structures over the lifetime of a device that incorporates carbon nanotubes," said Pushparaj, a senior research specialist in Rensselaer's department of materials science and engineering. "Even when exposed to high levels of stress, the nanotubes held up extremely well. The behavior is reminiscent of the mechanics of soft tissues, such as a shoulder muscle or stomach wall, which expand and contract millions of times over a human lifetime."

As reported in the July issue of *Nature Nanotechnology* (p. 417; DOI: 10.1038/nnano.2007.186), the research team created a free-standing, macroscopic, 2-mm square block of carbon nanotubes, made up of individual, vertically aligned, multi-walled nanotubes. The researchers then compressed the block between two steel plates in a vice-like machine.

The team repeated this process more than 500,000 times, recording precisely how much force was required to compress the nanotube block down to about 25% percent of its original height. Even after 500,000 compressions, the nanotube block retained its original shape and mechanical properties, the researchers said. Similarly, the nanotube block also retained its original electrical conductance.

In the initial stages of the experiment, the force needed to compress the nanotube block decreased slightly, but soon stabilized to a constant value, said Suhr, an assistant professor of mechanical engineering at the University of Nevada.

As the researchers continued to compress the block, the individual nanotube arrays collectively and gradually adjusted to getting squeezed, showing very little fatigue. This "shape memory," or viscoelastic-like behavior—although the individual nanotubes are not themselves viscoelastic—is often observed in soft-tissue materials.

While more promising than polymers and other engineered materials that exhib-