Synthesis and characterisation of HIP $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ zirconolite and observations of the ceramic–canister interface

Lewis R. Blackburn¹ · Max R. Cole¹ · Laura J. Gardner¹ · Daniel J. Bailey¹ · Merve Kuman¹ · Amber R. Mason¹ · Shi-Kuan Sun¹ · Ewan R. Maddrell² · Martin C. Stennett¹ · Claire L. Corkhill¹ · Neil C. Hyatt¹

Received: 24 December 2020 / Accepted: 2 April 2021 / Published online: 16 April 2021
© The Author(s) 2021

Abstract

A sample of zirconolite with nominal composition $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ was processed via Hot Isostatic Pressing (HIP), with a dwell temperature and pressure of 1320 °C/100 MPa maintained for 4 h. The produced wastefrom was characterised by powder XRD, SEM–EDS, Ce L₃ and Cr K-edge XANES. A significant portion of the Ce inventory did not fully partition within the zirconolite phase, instead remaining as CeO_2 within the microstructure. Inspection of the stainless steel–ceramic interface detailed the presence of an interaction region dominated by a Cr-rich oxide layer. No significant Cr or Fe migration was observed, although a greater concentration of perovskite was observed at the periphery, relative to the bulk ceramic matrix. The X-ray absorption features of Cr remained analogous with Cr^{3+} accommodation within TiO_6 octahedra in the zirconolite matrix. The absorption edge of Ce was comprised of contributions from zirconolite-2M and unincorporated CeO_2 , with an average oxidation state of $\text{Ce}^{3.9+}$. As zirconolite-2M accounted for > 92 wt% of the overall phase assemblage, it is clear that the dominant oxidation state of Ce in this phase was Ce^{4+} .

Introduction

In the United Kingdom, aqueous reprocessing of spent nuclear fuel (SNF) has afforded a significant inventory of PuO_2 , forecast to amount to 140 teHM (tonnes heavy metal equivalent), representing a significant decommissioning effort and a unique challenge with respect materials degradation [1]. Immobilisation of the bulk Pu inventory through a campaign of hot isostatic pressing (HIP), prior to geological disposal, is considered a credible pathway to disposition. Zirconolite ceramics (ideally $\text{CaZrTi}_2\text{O}_7$) are considered a potential host matrix for immobilisation of Pu; the crystal structure may accept a wide variety of tri- and tetravalent rare earth and actinide species in solid solution, with aqueous durability superior to that of closely related pyrochlore

($\text{Gd}_2\text{Ti}_2\text{O}_7$) and brannerite (UTi_2O_6) phases [2]. Zirconolite is considered to be a derivative of the anion-deficient fluorite superstructure, with the parent zirconolite-2M structure crystallising with monoclinic symmetry over the compositional range $\text{CaZr}_x\text{Ti}_{3-x}\text{O}_7$ ($0.8 < x < 1.3$), in the space group C2/c [3]. The aristotype is comprised of alternating layers of Ca^{2+} and Zr^{4+} cation polyhedra, coordinated 8- and sevenfold to oxygen, respectively, interspaced with corner sharing TiO_6 arranged in a topology similar to that of hexagonal tungsten bronze (HTB). Zirconolite may accept actinide cations, such as Pu^{4+} in solid solution via isovalent substitution i.e. $\text{CaZr}_{1-x}\text{Pu}_x\text{Ti}_2\text{O}_7$ or by a coupled substitution by which Pu^{4+} is accommodated in the Ca^{2+} site, facilitated by the incorporation of a lower valence charge balancing species e.g. $\text{Ca}_{1-x}\text{Pu}_x\text{ZrTi}_{2-2x}\text{Cr}_{2x}\text{O}_7$. We recently investigated the feasibility of Cr^{3+} as a charge balancing species, targeting $\text{Ca}_{1-x}\text{Ce}_x\text{ZrTi}_{2-2x}\text{Cr}_{2x}\text{O}_7$, utilising Ce as a Pu surrogate, through two distinct ceramic processing routes: a conventional cold press and sinter method (CPS), and a novel reactive spark plasma sintering (RSPS) methodology [4]. Whilst the CPS route yielded a single phase product in the range $0.05 \leq x \leq 0.15$, further substitution of Ce promoted the formation of a Ce-rich perovskite (CaTiO_3) phase, facilitated by partial Ce^{3+} speciation, and unincorporated CeO_2 and Cr_2O_3 above $x = 0.25$. The formation of an accessory perovskite

✉ Lewis R. Blackburn
lewis.blackburn@sheffield.ac.uk

✉ Neil C. Hyatt
n.c.hyatt@sheffield.ac.uk

¹ Immobilisation Science Laboratory, Department of Materials Science and Engineering, University of Sheffield, Sir Robert Hadfield Building, Mappin Street, Sheffield S13JD, UK

² National Nuclear Laboratory, Workington CA201PJ, Cumbria, UK

phase would reduce the overall wasteform performance, as this phase is known to exhibit reduced aqueous durability relative to zirconolite [5]. Nevertheless, a yield of ~94 wt% zirconolite-2M was obtained when targeting $x=0.35$, corresponding to approximately 25 wt% Pu loading in the corresponding solid solution. All specimens prepared by the CPS method presented a highly porous microstructure. RSPS was therefore applied to achieve complete sintering, since this technique has previously been utilised to produce zirconolite with near theoretical density [6]. Whilst RSPS produced ceramic bodies with no significant porosity, the conditions were sufficient to entirely reduce the Ce inventory to Ce^{3+} , resulting in disruption of the target phase assemblage, favouring Ce-perovskite as an accessory phase. Hot isostatic pressing is the favoured thermal processing route for disposition of the bulk Pu inventory, and has recently been investigated for both zirconolite ceramic and glass–ceramic matrices, using a multitude of Pu surrogates, and indeed Pu validation trials have been performed [7–10]. HIP processing involves the simultaneous application of high temperatures ($> 1300\text{ }^\circ\text{C}$) and isostatic pressure ($> 100\text{ MPa}$) via an inert Ar gas medium, to a loosely packed ceramic precursor material pressed into the walls of a hermetically sealed overpack, typically Ni metal or high grade stainless steel. This offers distinct advantages with respect to conventional sintering and RSPS, as the application of isostatic pressure during processing affords elimination of porosity, whilst producing minimal secondary effluent streams and remaining insensitive to the physical and chemical nature of the feedstock material [11]. In the present work, we investigate the feasibility of Cr^{3+} as a charge compensation species, targeting $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ as to remain analogous to our previous studies of this system. We also provide a characterisation of the ceramic–canister interface.

Experimental methods

Materials synthesis

A zirconolite ceramic with nominal composition $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ was fabricated by hot isostatic pressing, with the view to use Ce^{4+} as a structural surrogate for Pu^{4+} . This composition was selected since it would afford an approximate 15 wt% incorporation rate of Pu. Commercial metal oxide precursors CaTiO_3 (Sigma-Aldrich, $> 99.9\%$), ZrO_2 (Sigma-Aldrich, $> 99.9\%$), CeO_2 (Acros Organics, $> 99.9\%$), TiO_2 (rutile, Sigma-Aldrich, $> 99.9\%$) and Cr_2O_3 (Sigma-Aldrich, $> 99.9\%$) were dried and batched according to desired composition, intimately mixed by planetary milling at 500 rpm for 20 min, using ZrO_2 milling media and isopropanol as a milling agent. Powder slurries were discharged and dried at $80\text{ }^\circ\text{C}$

overnight to evaporate excess solvent, prior to calcination at $600\text{ }^\circ\text{C}$ for 12 h. Compositions were then pressed into the walls of a 316 stainless steel HIP canister under uniaxial pressure, ensuring uniform packing density. The HIP canisters were machined with internal diameter 22 mm and can wall thickness of 2 mm. The canisters were then heated under vacuum at $300\text{ }^\circ\text{C}$ until an internal canister pressure of ~7 Pa was reached, before crimping and welding shut to attain a hermetic seal. The canisters were then placed into a AIP6-30H HIP unit and processed at $1320\text{ }^\circ\text{C}$, with a 100 MPa dwell pressure maintained for 4 h, with inert Ar gas introduced into the pressure vessel as the pressure transfer medium.

Materials characterisation

The processed canister was retrieved and sectioned using a Buehler IsoMet 1000 low speed saw, with material extracted from the bulk and the stainless steel–ceramic interface preserved for analysis. Powder X-ray diffraction (XRD) analysis was performed using a Bruker D2 Phaser fitted with a Lynxeye position sensitive detector and Ni filter. Data were acquired using a Cu $\text{K}\alpha$ source ($\lambda = 1.5418\text{ \AA}$) in the range $5^\circ \leq 2\theta \leq 80^\circ$ with a stepsize of 0.02° . Powder XRD data were refined by the Rietveld method, using the GSAS package with EXPGUI interface [12]. The bottom section of the canister was set in epoxy resin and polished to a $1\text{ }\mu\text{m}$ optical finish, permitting microanalysis of both the bulk ceramic material and the exterior can–ceramic interface. Scanning electron microscopy (SEM) analysis was performed using a FEI Inspect f50 operating at 20 kV accelerating voltage and 10.6 mm working distance. Ce L_3 and Cr K-edge X-ray absorption near edge spectroscopy (XANES) data were collected at beamline BL-27 at the Photon Factory (PF) accelerator light source (Tsukuba, Japan). The optical arrangement consists of a double crystal Si(111) monochromator and slits were used to reduce the size of the beam to 3 mm in the horizontal and 1 mm in the vertical. Spectra were recorded between 5590–5990 eV and 5523–6154 eV in energy steps of 0.25 eV using an acquisition time of 50 ms step^{-1} for Cr K and Ce L_3 edges, respectively. Data were collected alongside a series of reference compounds, representative of Ce and Cr in a variety of valence states and coordination environments.

Results and discussion

Characterisation of bulk zirconolite ceramic matrix by XRD and SEM

The HIP processing cycle produced a high density monolith, visually black in colour, with no evidence of loss of containment. Powder XRD data for material retrieved

from the bulk of the HIP can is displayed in Fig. 1. Intense reflections, corresponding in position and intensity to the target zirconolite-2M phase, were identified. The lattice parameters corresponding to the zirconolite-2M phase were calculated by Rietveld refinement to be: $a = 12.4499(7)$ Å, $b = 7.2457(4)$ Å, $c = 11.3798(6)$ Å, $\beta = 100.591(6)^\circ$ and $V = 1009.06(8)$ Å³. Accessory phases CaTiO_3 (~0.8 wt%), ZrO_2 (~1.1 wt%), CeO_2 (~3.9 wt%) and Cr_2O_3 (~1.9 wt%) were also distinguished (precision ± 0.1 wt%). Whilst the material densified with a comparable quantity of perovskite reported for the corresponding CPS sample (~1.2 wt%) [4], incomplete digestion of the CeO_2 surrogate inventory within the wasteform was observed to an unsatisfactory degree. SEM analysis of the bulk microstructure detailed a dense morphology consistent with those previously characterised for zirconolite produced by HIP [7]. A matrix of zirconolite-2M was observed with medium grey-scale contrast, with accessory phases clearly distinguished from the bulk through backscattered electron contrast, alongside some minor porosity (black regions in Fig. 2). Relics of undigested CeO_2 were clearly evidenced with bright contrast throughout the ceramic matrix, with a clear reaction rim indicating that the reaction did not achieve equilibrium under the imposed HIP conditions. The composition of the reaction rims was consistent with Ce-rich perovskite $(\text{Ca,Ce})\text{TiO}_3$, in agreement with powder XRD data, or potentially $\text{CaCeTi}_2\text{O}_7$, although reflections consistent with this pyrochlore structured phase were not evidenced by diffraction data.

Fig. 1 Powder XRD data for $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ processed via HIP at 1320 °C with a dwell pressure of 100 MPa maintained for 4 h

Examination of ceramic–canister interface

A cross-sectional backscattered electron micrograph, and corresponding elemental mapping of the interface between the stainless steel HIP-canister and the ceramic matrix is shown in Fig. 3, allowing a detailed interpretation of the interaction region. The interior HIP-can region did not evidence any significant diffusion of constituent elements beyond the layer marked ‘interface’ in Fig. 3, as demonstrated by Ni and Fe element maps. The HIP can did contain some discrete Cr_2O_3 oxides scattered adjacent to the interface. The interface region was consistently measured to be 5–8 µm in width across the specimen, and was dominated in composition by a Cr-rich oxide, with minor Fe and trace Ti evidenced by EDS analysis. The formation of the Cr-rich interface layer was considered to be the effect of Cr/Fe diffusion from the HIP canister and subsequent oxidation, as had been previously described for stainless steel–SYNROC interactions under comparable conditions [13]. Nevertheless, the composition of the interface region was not entirely consistent with those described previously for pyrochlore-rich SYNROC and zirconolite-rich wasteforms. For example, Li et al. confirmed that Fe^{2+} was the main element to diffuse from the can material, partitioning within zirconolite and hollandite ($\text{BaAl}_2\text{Ti}_6\text{O}_{16}$), replacing Ca/Ti and Al, respectively, however it was noted that Fe^{2+} preferentially entered the Ti site in zirconolite [13]. Zhang et al. described similar features, with Fe and Cr diffusion into the zirconolite phase [14]. The composition of the interface region is generally more heterogeneous than the data presented in the present work, dominated by Fe diffusion into the wasteform. For example, Zhang et al. described five distinct subsections of the interface, one of which was rich in Fe adjacent to the bulk ceramic matrix, whereas the interface for $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}$ appears to be comprised of just three distinct layers [15]. Close inspection of the Fe EDS data did reveal a thin reaction layer rich in Fe relative to Cr, however Fe diffusion did not appear to influence the local chemistry of the zirconolite phase. The distinct lack of an Fe-rich region in the interaction layer is presumably due to the high concentration of Cr present in the wasteform matrix, with subsequent diffusion into the interface. The primary observation from these data is that the diffusion and subsequent oxidation of Cr and Fe from the canister material did not appear to significantly destabilise the local phase assemblage in the ceramic microstructure, although it is evident that undigested CeO_2 was concentrated towards the bulk of the ceramic matrix, likely the result of local redox chemistry favouring slightly reducing conditions at the periphery, resulting from Cr and Fe oxidation. The reducing environment may have promoted reduction of the local Ce inventory to Ce^{3+} and subsequent partitioning within a perovskite phase. Moreover, clusters of perovskite

Fig. 2 SEM-EDS analysis of HIPed $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ matrix

appeared more readily formed near the Cr-rich oxide layer, with EDS analysis confirming greater Cr concentration (likely substituted for $\text{Ti}^{3+/4+}$ in perovskite) relative to the perovskite reaction rims located around undigested CeO_2 in the bulk material. It is important to note, however, that there is no clear indication that the stainless steel–wasteform interface will lead to the formation of non-durable phases or free actinides.

Cr K- and Ce L_3 -edge XANES

X-ray absorption spectroscopy (XAS) is a fundamental technique in support of nuclear waste management, as an effective means to probe the local structure and valence chemistry of radionuclides in immobilisation matrices, supporting the safety case towards geological disposal through underpinning the underlying crystal chemistry of actinide-containing wasteforms [16–18]. Accordingly, Ce L_3 and Cr K-edge X-ray absorption near edge structure (XANES) data were collected alongside a series of reference compounds

representing Ce and Cr in a variety of oxidation states and coordination environments, allowing the speciation and local environment of Ce and Cr to be inferred. Cr K edge XANES is displayed in Fig. 4, alongside Cr_2O_3 , YCrO_3 and K_2CrO_4 (representing Cr^{3+} , Cr^{3+} and Cr^{6+} , respectively). The XANES region for K_2CrO_4 , in which Cr^{6+} adopts tetrahedral coordination to neighbouring oxygen atoms, was dominated by an intense pre-edge feature, with a centroid position approximately 15 eV from the main absorption edge. This feature was not present in the XANES spectrum for the HIPed zirconolite specimen, inferring the absence of Cr^{6+} . Inspection of the Cr K-edge data revealed white line features comparable with Cr^{3+} reference compounds (YCrO_3 and Cr_2O_3), consistent with a similar edge position and low intensity pre-edge feature [19]. Through modelling of the pre-edge feature, it was previously observed that Cr^{3+} adopts the octahedral coordination in the zirconolite structure, consistent with substitution within TiO_6 polyhedra. The absorption features for HIPed $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ were consistent with those reported previously for the

Fig. 3 Backscattered SEM micrograph and elemental distribution maps for the stainless steel-ceramic interface

Fig. 4 Cr K (left) and Ce L₃-edge (right) XANES data for HIPed $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$, alongside $\text{YCr}^{3+}\text{O}_3$, $\text{K}_2\text{Cr}^{6+}\text{O}_4$, $\text{Cr}_2^{3+}\text{O}_3$, Ce^{4+}O_2 and $\text{Ce}^{3+}\text{PO}_4$ reference compounds

corresponding CPS composition [4], hence by analogy, it can be assumed that the same substitution mechanism occurred for the HIPed sample. Ce L_3 XANES were collected alongside CeO_2 and CePO_4 , representing Ce^{4+} and Ce^{3+} in eight and ninefold coordination to oxygen, respectively [20]. The Ce absorption edge for the HIPed zirconolite composition was comprised of an asymmetric doublet, similar in energy position to that of the CeO_2 reference compound, inferring that the available Ce inventory remained present as Ce^{4+} , analogous to Pu^{4+} . A linear combination fit was performed to determine the average oxidation state of Ce, confirming that $93.3 \pm 2\%$ of the Ce remained present as Ce^{4+} , inferring an average oxidation state of approximately $\text{Ce}^{3.9+}$ (data fit with an R-factor of 0.017). However, powder XRD and SEM data confirmed that considerable unincorporated CeO_2 remained present in the microstructure, hence the XANES signal for the HIPed specimen is comprised of contributions from two distinct Ce chemical environments. Nevertheless, as the zirconolite-2M phase accounted for approximately 92 wt% of the overall phase assemblage, it is clear that the dominant oxidation state of Ce in the zirconolite phase is Ce^{4+} .

Conclusions

A sample of zirconolite with nominal composition $\text{Ca}_{0.80}\text{Ce}_{0.20}\text{ZrTi}_{1.60}\text{Cr}_{0.40}\text{O}_7$ was produced by HIP, with a densification cycle of 1320 °C and 100 MPa maintained for 4 h. The resulting wasteform was characterised by powder XRD, detailing that whilst the target zirconolite-2M phase accounted for 92.3 ± 0.1 wt% of the total phase assemblage, a significant fraction of the available Ce inventory, equivalent to approximately 3.9 wt% (acting as a surrogate for Pu) was unincorporated into the zirconolite matrix. SEM–EDS data also revealed the presence of Ce within an accessory perovskite phase, presumably incorporated as Ce^{3+} , in line with previous observations. Observations of the interface region between the HIP canister and the bulk ceramic matrix revealed the presence of a Cr-rich oxide layer, with a thickness comparable to those previously detailed for SYNROC that was HIPed in stainless steel canisters. Whilst diffusion of Cr and Fe did not appear to significantly destabilise the phase assemblage at the canister-ceramic interface, Cr was observed to partition within the accessory perovskite phase, potentially providing a charge balancing mechanism permitting greater Ce loading. The formation of a Ce-bearing perovskite expected to be detrimental to the overall wasteform performance. Cr K edge XANES data were consistent with our previous observations, in which Cr^{3+} was largely accommodated in TiO_6 octahedra. The Ce L_3 XANES spectrum presented features consistent with the Ce^{4+} reference sample, although as a significant portion of the available

Ce inventory remained present in the microstructure as CeO_2 , we do not consider the XANES spectrum obtained to be entirely representative of Ce speciation in the zirconolite phase.

Acknowledgments We acknowledge financial support from the Nuclear Decommissioning Authority (NDA) and EPSRC under Grant Numbers EP/S01019X/1, EP/P013600/1 and EP/R511754/1. This research utilised the HADES/MIDAS facility at the University of Sheffield established with financial support from EPSRC and BEIS, under grant EP/T011424/1 [21]. Collection of the Ce L_3 and Cr K-edge XAS data was performed under the approval of the Photon Factory Advisory Committee (Proposal No. 2019G586); the support of Yoshihiro Okamoto (Japanese Atomic Energy Agency) and Noriko Usami (The High Energy Accelerator Research Organisation—Kō Enerugi Kasokuki Kenkyū Kikō) during the experiment is gratefully acknowledged.

Data availability The data that support these findings cannot be shared at the present time, as they form part of an ongoing study.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

References

1. N.C. Hyatt, Safe management of the UK separated plutonium inventory: a challenge of materials degradation. *NPJ Mater. Degrad.* (2020). <https://doi.org/10.1038/s41529-020-00132-7>
2. S.K. Roberts, W.L. Bourcier, H.F. Shaw, Aqueous dissolution kinetics of pyrochlore, zirconolite and brannerite at 25, 50, and 75 °C. *Radiochim. Acta* **88**(9–11), 539–543 (2000)
3. B.M. Gatehouse, I.E. Grey, R.J. Hill, H.J. Rossell, Zirconolite, $\text{CaZr}_x\text{Ti}_{3-x}\text{O}_7$; structure refinements for near-end-member compositions with $x = 0.85$ and 1.30 . *Acta Crystallogr.* **B37**(1974), 306–312 (1981)
4. L.R. Blackburn et al., Synthesis and characterisation of $\text{Ca}_{1-x}\text{Ce}_x\text{ZrTi}_{2-2x}\text{Cr}_{2x}\text{O}_7$: analogue zirconolite wasteform for the immobilisation of stockpiled UK plutonium. *J. Eur. Ceram. Soc.* **40**(15), 5909–5919 (2020)
5. G.R. Lumpkin, K.L. Smith, M.G. Blackford, Electron microscope study of Synroc before and after exposure to aqueous solutions. *J. Mater. Res.* **6**(10), 2218–2233 (1991)
6. S.-K. Sun, M.C. Stennett, C.L. Corkhill, N.C. Hyatt, Reactive spark plasma synthesis of $\text{CaZrTi}_2\text{O}_7$ zirconolite ceramics for plutonium disposition. *J. Nucl. Mater.* **500**, 11–14 (2018)
7. L. R. Blackburn et al., Hot isostatically pressed zirconolite wasteforms for actinide immobilization. *IOP Conf. Ser. Mater. Sci. Eng.* **818**(1), 012010 (2020)
8. S. Thornber, M.C. Stennett, N.C. Hyatt, Investigation of Ce incorporation in zirconolite glass-ceramics for UK plutonium disposition, in 2016 MRS Fall Meeting (2016)

9. S.M. Thornber et al., A preliminary validation study of PuO_2 incorporation into zirconolite glass-ceramics. *MRS Adv.* **1**(4), 1–7 (2018)
10. D.J. Bailey et al., A new approach to the immobilisation of technetium and transuranics: co-disposal in a zirconolite ceramic matrix. *J. Nucl. Mater.* **528**, 151885 (2019)
11. E. Maddrell, Hot isostatically pressed wasteforms for future nuclear fuel cycles. *Chem. Eng. Res. Des.* **91**, 735–741 (2013)
12. B.H. Toby, EXPGUI, a graphical user interface for GSAS. *J. Appl. Crystallogr.* **34**, 210–213 (2001)
13. H. Li, Y. Zhang, P.J. McGlinn, S. Moricca, B.D. Begg, E.R. Vance, Characterisation of stainless steel-synroc interactions under hot isostatic pressing (HIPing) conditions. *J. Nucl. Mater.* **355**(1–3), 136–141 (2006)
14. Y. Zhang, M.W.A. Stewart, H. Li, M.L. Carter, E.R. Vance, S. Moricca, Zirconolite-rich titanate ceramics for immobilisation of actinides - Waste form/HIP can interactions and chemical durability. *J. Nucl. Mater.* **395**, 69–74 (2009)
15. Y. Zhang, H. Li, S. Moricca, Pyrochlore-structured titanate ceramics for immobilisation of actinides: Hot isostatic pressing (HIPing) and stainless steel/waste form interactions. *J. Nucl. Mater.* **377**, 470–475 (2008)
16. L.M. Mottram et al., A feasibility investigation of laboratory based X-ray absorption spectroscopy in support of nuclear waste management. *MRS Adv.* **XLIII**, 27–35 (2020)
17. S.M. Thornber, L.M. Mottram, A.R. Mason, P. Thompson, C. Stennett, N.C. Hyatt, Solubility, speciation and local environment of chlorine in zirconolite glass-ceramics for the immobilisation of plutonium residues. *RSC Adv.* **10**, 32497–32510 (2020)
18. D.J. Bailey et al., Ce and U speciation in wasteforms for thermal treatment of plutonium bearing wastes, probed by L3 edge XANES. *IOP Conf. Ser. Mater. Sci. Eng.* **818**(1), 012019 (2020)
19. M. Tromp, J. Moulin, G. Reid, J. Evans, Cr K-edge XANES spectroscopy: Ligand and oxidation state dependence—what is oxidation state? *AIP Conf. Proc.* **882**, 699–701 (2007)
20. L.R. Blackburn, S. Sun, L.J. Gardner, E.R. Maddrell, M.C. Stennett, N.C. Hyatt, A systematic investigation of the phase assemblage and microstructure of the zirconolite $\text{CaZr}_{1-x}\text{Ce}_x\text{Ti}_2\text{O}_7$ system. *J. Nucl. Mater.* **535**, 152137 (2020)
21. N.C. Hyatt, C.L. Corkhill, M.C. Stennett, R.J. Hand, L.J. Gardner, C.L. Thorpe, The HADES facility for high activity decommissioning engineering & science : part of the UK National Nuclear User Facility. *IOP Conf. Ser. Mater. Sci. Eng.* **818**, 1–8 (2020)