Erratum to: "Occurrence of 2-phenylphenol
in food paper packages"

Erratum

Lenka Votavová*, Kristýna Hanušová, Lukáš Vápenka,
Jaroslav Dobiáš, František Kvasnička

Department of Food Preservation, Institute of Chemical Technology,
Prague, 166 28 Prague 6, Czech Republic

Received 21 May 2014; Accepted 27 May 2014

Abstract: The original version of the article was published in Cent. Eur. J. Chem. 12(11) (2014) pp. 1162-1168. Unfortunately, the original version of this article contains some mistakes in the Tables 2 and 3. Corrected versions of the tables are presented below.

© Versita Sp. z o.o.

Table 2. Content of 2-phenylphenol in samples of paper materials used for food packaging in the Czech Republic.

Sample No.	Producer	2-phenylphenol result $\pm U_c^1$ ($\mu\text{g kg}^{-1}$)	Declared content of recycled pulp in paper (% w/w)
1	1	142 ± 5	> 90
2		131 ± 5	< 10
3		349 ± 15	> 90
4		418 ± 15	> 90
5		404 ± 15	> 90
6		< 10	< 10
7		103 ± 5	> 90
8		355 ± 15	> 90
9	2	431 ± 15	100
10		399 ± 15	100
11		12 ± 5	< 10
12		11 ± 5	0
13		80 ± 5	80-90
14		527 ± 15	100
15		10 ± 5	0
16	3	14 ± 5	0
17		98 ± 5	50
18		< 10	0
19		15 ± 5	0
20		55 ± 5	< 10
21		< 10	0
22	4	505 ± 15	> 90
23		236 ± 10	80-90

¹expanded combined uncertainty (coverage factor $k = 2$)

* E-mail: lenka.lenka.votavova@vscht.cz

Table 3. Migration of OPP from paper packaging materials coated with low density polyethylene into 3% acetic acid, 10% and 95% ethanol and olive oil after 10 days at 40°C.

Sample No.	OPP content		Migration ($\mu\text{g dm}^{-2}$)			
	($\mu\text{g kg}^{-1}$)	($\mu\text{g dm}^{-2}$)	10% ethanol	3% acetic acid	95% ethanol	Olive oil
22	505	0.86	<u>n.d.</u>	<u>n.d.</u>	0.18 ± 0.01 ($n=2$)	n.d.
23	236	1.27	<u>n.d.</u>	<u>n.d.</u>	0.15 ± 0.01 ($n=2$)	n.d.

n.d. – not detected